

Ta Khoa Drilling Update

- **Portable XRF records up to 20% Ni at New Massive Sulfide Discovery**
- **Resource drilling at Ban Chang and King Snake continues to deliver impressive results**

Blackstone Minerals Limited ("Blackstone" or the "Company") is pleased to provide an update on drilling at the Company's flagship Ta Khoa Nickel Project (TKNP) in northern Vietnam.

New Massive Nickel Sulfide Targets

Blackstone drilling targeting new opportunities within the Ta Khoa district has identified Massive Sulfide Vein (MSV), Semi-Massive Sulfide Vein (SMSV) and Net-textured Sulfide (NTS) mineralisation.

- At the **Suoi Phang** prospect (refer Figures 2, 3), drill hole SP22-01 has intersected 2.95m of sulfide (including MSV, SMSV and NTS) with Portable XRF readings indicating the presence of **up to 20% Ni** (refer Table 1, Table 3, Table 4 and Appendix 1)
- At the **Suoi Chanh** prospect (refer Figure 4), the second drill hole **SC22-02 has intersected SMSV** consistent with the Blackstone Electromagnetic (EM) targeting.

Resource Drilling

Blackstone has continued to drill its most advanced MSV deposits (Ban Chang & King Snake), primarily focusing on upgrading the current resources (refer ASX announcement 23 December 2021) into a higher confidence category. At King Snake, the most recent drilling indicates potential for the deposit to continue to plunge further west and at depth (refer Image 1, Figure 7, Figure 8 & Table 2).

Highlights from infill drilling at Ban Chang include:

BC21-66	9.6m @ 2.02% Ni, 1.92% Cu, 0.1% Co & 3.04g/t PGE¹ from 60.1m
including	4.8m @ 3.38% Ni, 3.07% Cu, 0.16% Co & 5.29g/t PGE¹ from 63.7m
BC21-104	6.75m @ 1.44% Ni, 2.1% Cu, 0.08% Co & 1.32g/t PGE ¹ from 27.7m
including	3.65m @ 2.58% Ni, 2.1% Cu, 0.15% Co & 1.21g/t PGE¹ from 30.8m
BC21-77	25.55m @ 0.63% Ni, 0.43% Cu, 0.04% Co & 0.33g/t PGE ¹ from 43.65m
including	3.57m @ 2.17% Ni, 0.82% Cu, 0.12% Co & 0.94g/t PGE¹ from 62.43m
BC21-62	3.75m @ 2.16% Ni, 0.82% Cu, 0.13% Co & 1.09g/t PGE¹ from 101.6m
BC21-90	13.95m @ 0.99% Ni, 0.63% Cu, 0.05% Co & 0.99g/t PGE ¹ from 78.75m
including	8.52m @ 1.49% Ni, 0.88% Cu, 0.07% Co & 1.35g/t PGE ¹ from 79.08m
BC21-48	7.75m @ 1.00% Ni, 0.53% Cu, 0.06% Co & 0.84g/t PGE ¹ from 59.25m
including	2.65m @ 1.52% Ni, 0.43% Cu, 0.09% Co & 1.81g/t PGE ¹ from 63m

¹ Platinum (Pt) + Palladium (Pd) + Gold (Au)

For personal use only

Highlights from infill drilling at King Snake include:

KS21-34	15.7m @ 1.25% Ni, 0.69% Cu, 0.05% Co & 1.66g/t PGE¹ from 249.5m
including	6.02m @ 2.18% Ni, 0.62% Cu, 0.08% Co & 2.97g/t PGE¹ from 250.4m
KS21-38	1.92m @ 3.02% Ni, 0.63% Cu, 0.11% Co & 2.13g/t PGE ¹ from 400.5m
KS21-40	1.35m @ 3.67% Ni, 0.54% Cu, 0.15% Co & 2.25g/t PGE ¹ from 154.1m
KS21-32	2.52m @ 1.07% Ni, 0.35% Cu, 0.04% Co & 1.93g/t PGE ¹ from 321.3m

¹ Platinum (Pt) + Palladium (Pd) + Gold (Au)



Image 1 - MSV from drill hole KS22-17

Scott Williamson, Blackstone's Managing Director, said:

"It is an exciting phase of exploration for the Company as we start to look at massive sulfide opportunities in addition to Blackstone's established resources at Ban Chang and King Snake. Suoi Chanh is yet another example of our in-house geophysics teams proven track record, with success being achieved from the second drill hole. We look forward to continuing to systematically assess the massive sulfide potential at Ta Khoa."




Figure 1. Ta Khoa District Geology Map

Suoi Phang

The Suoi Phang prospect is located at the far western end of the Ta Khoa license area and is hosted within Devonian metasediments of the Ban Mong Formation (see Figure 1). Massive sulfide was exposed in a historical adit, and two gossans were exposed in historical trenching (assays up to 5.9% Ni). The northern gossan measures 120m in strike length and the south part of the gossan is 100m long (see Figure 2).

Blackstone’s exploration program at Suoi Phang is following up targets generated from surface EM surveying, with the most recent drillhole (SP22-01) intersecting massive sulfide close to surface, and with Portable XRF readings indicating the presence of up to 20% Ni.

For personal use only

For personal use only




Figure 2. Suoi Phang Plan View

*Historic trench results previously announced to the ASX on 29 May 2020

For personal use only




Figure 3. Suoi Phang Cross Section 3500E



Image 2. Core from drill hole SP22-01

Table 1. Sulfide mineralisation zones in SP22-01*

From (m)	To (m)	Width (m)	Sulfide (type)	Sulfide %
37.05	37.37	0.32	Net Textured Sulfide	30-35
37.37	37.75	0.38	Massive Sulfide Vein	60-65
37.75	38.06	0.31	Disseminated Sulfide	10-12
38.06	38.14	0.08	Massive Sulfide Vein	70
38.14	38.61	0.47	Disseminated Sulfide	5-7
38.61	38.91	0.30	Semi-Massive Sulfide Vein	35-40
38.91	39.70	0.79	Net Textured Sulfide	40
39.70	39.85	0.15	Semi-Massive Sulfide Vein	40-45
39.85	40.00	0.15	Disseminated Sulfide	1-2

*In relation to the disclosure of visual mineralisation, the Company cautions that visual estimates of sulfide mineral abundance should never be considered a proxy or substitute for a laboratory analysis. Assay results are required to determine the widths and grade of the visible mineralisation reported in preliminary geological logging. The Company will update the market when laboratory analytical results become available.

Suoi Chanh

The Suoi Chanh prospect is located at the eastern end of the Ta Khoa license area and is hosted within Devonian metasediments (refer Figure 1). The area is characterised by a high density of mafic - ultramafic dykes. There are some dykes that are strongly differentiated with coarse grained particles in the lower part and grading to fine grains across the dyke. This feature suggests the existence of magma sulfide zones located at the bottom of the dyke. Drillhole SC22-02 has intersected a mafic-ultramafic dyke of 2.55m thickness with 0.1 m semi-massive sulfide. This indicates the potential to find massive sulfide veins common within the Ta Khoa district.




Figure 4. Suoi Chanh Overview Map

Ban Chang

The Ban Chang prospect is located 2.5 km east of the Ban Phuc deposit adjacent to the Chim Van – Co Muong fault system (refer Figure 1). The prospect geology consists of a tremolitic dyke swarm within phyllites, sericite schists and sandstones of the Sap Viet Horizon. The MSV mineralisation consists of two west-east striking, steeply south dipping veins, which are 580m apart along strike. The eastern vein consists of a vein of massive sulfide which has a disseminated ultramafic outer domain encapsulating the MSV. The western vein consists of a single massive sulfide vein. The MSV contains high grade PGEs when compared to the previously mined Ban Phuc MSV deposit which may indicate sulfide segregation in a PGE bearing dyke before formation.

The dyke swarms are located along a zone of approximately 1,500 m long and varies between 5 m and 60 m wide. The dykes and massive sulfides are interpreted to be hosted within a splay (and subsidiary structures) off the major regional Chim Van - Co Muong fault system.




Figure 5. Ban Chang Cross Section 53175E

The current inferred mineral resource for Ban Chang is 0.70 Mt at 1.2% Ni (2.0% NiEQ) and was based on information up to and including drill hole BC21-34 (Oct 2021). The latest round of assays included in this report are from infill drilling programs designed to improve the resource confidence classification.




Figure 6. Ban Chang Cross Section 53275E

King Snake

King Snake is located approximately 1 km north of the Ban Phuc disseminated nickel sulfide deposit (refer Figure 1). The King Snake prospect is a typical magmatic MSV of high-grade brecciated Ni-Cu-Co-PGE minerals associated with tremolite-altered mafic-ultramafic dykes developed along a shear zone within the calcareous sediments and quartz-mica schists of the Ban Phuc Horizon.

Similar to Ban Chang, King Snake contains high grade PGEs compared to the previously mined Ban Phuc MSV deposit which indicates that mineralisation was likely formed by sulfide segregation from PGE bearing magma in an active feed dyke.

Blackstone's drilling at King Snake has been focussed on EM targets which extend down plunge to the west of historic drilling. Assay results indicate greater thicknesses of sulfide mineralisation down plunge of historic drilling. The higher power surface EM targeting has accurately guided the down plunge drilling hundreds of meters from the historic surface showings. In addition, downhole EM (DHEM) has further directed investigations to wider higher-grade zones throughout this consistent, high grade and tabular massive sulfide vein (refer Figure 7).




Figure 7. King Snake Long Section




Figure 8. King Snake Cross Section 50025E

The current mineral resource for King Snake is 0.43 Mt at 1.3% Ni (2.4% NiEQ) and was based on information up to and including drill hole KS21-26 (Oct 2021). Recent drilling by Blackstone at King Snake has primarily been infill, however success at KS22-17 (refer Figure 8), suggests potential for mineralisation at King Snake to continue to plunge at depth to the west. Downhole EM survey is being planned at KS22-17.

For personal use only

Table 2. Sulfide mineralisation zones in KS22-08, KS22-13 & KS22-17*

Drill Hole	From (m)	To (m)	Width (m)	Sulfide (type)	Sulfide %
KS22-08	392.75	396.03	3.28	Stringer	1-6
KS22-08	396.03	396.10	0.07	Massive Sulfide Vein	60
KS22-08	396.10	398.55	2.45	Stringer	1-6
KS22-13	435.40	445.60	10.20	Disseminated Sulfide	1-7
KS22-13	462.90	463.50	0.60	Stringer	1-2
KS22-13	463.50	463.75	0.25	Massive Sulfide Vein	60
KS22-13	463.75	464.00	0.25	Stringer	1-2
KS22-17	488.00	496.72	8.72	Disseminated Sulfide	1-4
KS22-17	496.72	497.28	0.56	Semi-Massive Sulfide Vein	30-35
KS22-17	497.28	501.45	4.17	Disseminated Sulfide	2-3
KS22-17	501.45	501.78	0.33	Massive Sulfide Vein	70
KS22-17	501.78	514.50	12.72	Disseminated Sulfide	1-3
KS22-17	514.50	514.67	0.17	Semi-Massive Sulfide Vein	20-30

*In relation to the disclosure of visual mineralisation, the Company cautions that visual estimates of sulfide mineral abundance should never be considered a proxy or substitute for a laboratory analysis. Assay results are required to determine the widths and grade of the visible mineralisation reported in preliminary geological logging. The Company will update the market when laboratory analytical results become available.

Included in Table 3 and Table 4 of this report are further assays from the Ta Cuong prospect (refer ASX announcement 13 May 2021). Blackstone is also completing an infill drilling program at the Ban Khoa disseminated sulfide deposit. The Company looks forward to providing an update to the market when the program is completed, and assays are available.

Authorised by the Managing Director on behalf of the Board.

For more information, please contact

Scott Williamson

Managing Director
+61 8 9425 5217
scott@blackstoneminerals.com.au

Dhanu Anandarasa

Manager Corporate Development
+61 8 9425 5217
dhanu@blackstoneminerals.com.au

About Blackstone

Blackstone Minerals Ltd (ASX: BSX / OTCQX: BLSTF / FRA: B9S) is focused on building an integrated upstream and downstream battery metals processing business in Vietnam that produces NCM Precursor products for Asia's growing Lithium-ion battery industry.

The Company owns a 90% interest in the TKNP. The TKNP is located 160km west of Hanoi in the Son La Province of Vietnam (refer Figure 9) and includes an existing modern nickel mine built to Australian standards, which is currently being used to process nickel ore delivered by the underground bulk sample program. The Ban Phuc nickel mine successfully operated as a mechanised underground nickel mine from 2013 to 2016.




Figure 9. Ta Khoa Project Location

Blackstone's TKNP and Ta Khoa Refinery (TKR) are the two major cogs in Blackstone's vertically integrated development strategy (together - the Ta Khoa Project). The Company's development strategy is underpinned by Blackstone's ability to secure nickel concentrate and Ta Khoa is emerging as a nickel sulfide district of enviable scale with several exploration targets yet to be tested.

In February 2022, Blackstone completed a Pre-Feasibility Study for the TKNP, and presented this on an integrated basis with the proposed TKR development (refer ASX announcement 28 February 2022). The TKR is being designed to have a refining capacity of 400ktpa, with feedstock provided from a combination of concentrate from the TKNP and third-party feed sources (3PF). Pilot Plant testing and Definitive Feasibility Studies are underway and will continue to technically de-risk the Ta Khoa Project.

At both the mine (upstream) and refinery (downstream) level, Blackstone is focused on a partnership model and is collaborating with groups who are focused on sustainable mining, minimising carbon footprint and implementing a fully vertically integrated supply chain.

Competent Person Statement

Estimation and Reporting of Mineral Resources - Ta Khoa Nickel Project

No new Mineral Resource information is contained in this report. Information in this report which refers to Mineral Resources for the Ban Phuc, Ban Khoa, Ban Chang and King Snake Prospects is taken from the company's initial ASX disclosure dated 23 December 2021 - *Ta Khoa Mineral Resource Update*, found at www.blackstoneminerals.com.au. The December disclosure fairly represents information compiled by Mr. Kahan Mit-hat Cervoj. Mr Cervoj is a full-time employee of Optiro Pty Ltd, consulting to Blackstone Minerals Ltd, and is a Member of Australian Institute of Mining and Metallurgy.

The Company confirms that all material assumptions and technical parameters underpinning the Mineral Resources Estimates referred to within previous ASX announcements remain current and have not materially changed since last reported. The Company is not aware of any new information or data that materially affects the information included in this announcement.

The Company confirms that the form and context in which the Competent Person's findings are or were presented have not been materially modified.

Reporting of Exploration Results

The information in this report that relates to Exploration Results and Exploration Targets is based on information compiled by compiled and reported by Mr Chris Ramsay, Manager of Resource Geology for the Company and a Member of The Australasian Institute of Mining and Metallurgy. Mr Ramsay has sufficient experience which is relevant to the style of mineralisation and type of deposits under consideration and to the activity which he is undertaking to qualify as a Competent Person (as defined in the 2012 Edition of the

'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves').

Mr Chris Ramsay consents to the inclusion in the report of the matters based on his information in the form and context in which it appears.

Forward Looking Statements

This report contains certain forward-looking statements. The words "expect", "forecast", "should", "projected", "could", "may", "predict", "plan", "will" and other similar expressions are intended to identify forward looking statements. Indications of, and guidance on, future earnings, cash flow costs and financial position and performance are also forward-looking statements. Forward looking statements, opinions and estimates included in this announcement are based on assumptions and contingencies which are subject to change without notice, as are statements about market and industry trends, which are based on interpretations of current market conditions. Forward looking statements are provided as a general guide only and should not be relied on as a guarantee of future performance. Forward looking statements may be affected by a range of variables that could cause actual results or trends to differ materially. These variations, if materially adverse, may affect the timing or the feasibility of the development of the Ta Khoa Project.

The project development schedule assumes the completion for the TKNP of a Definitive Feasibility Study (DFS) in 2023. A DFS for the TKR is also assumed to be completed in 2022. Development approvals and investment permits will be sought from the relevant Vietnamese authorities concurrent to studies being completed. Delays in any one of these key activities could result in a delay to the commencement of construction (planned in 2023). This could lead on to a delay to first production, currently planned for 2025. It is expected that the Company's stakeholder and community engagement programs will reduce the risk of project delays. Please note these dates are indicative only.

ASX ANNOUNCEMENT

2 June 2022

ASX: BSX

Table 3

New and historic Blackstone Ban Chang, King Snake, Ta Cuong, Suoi Phang and Suoi Chanh drill hole locations, orientations and mineralised intersections (down hole positions & lengths are shown).

Note: Drill holes marked with “*” relate to new information presented in this report which assay results have been received

Note: Complete assay interval data for drill holes with new assay results is presented in Table 4

Note: Complete assay interval data for historic drill holes by Blackstone at King Snake can be located in previous ASX announcements

Note: Drill holes marked “***” relates to new information presented in this report based on observations of visual mineralisation

Note: PGE = Pt+Pd+Au.

Note: NSI = No Significant Intercept

Note: All coordinates UTM Zone48N WGS84, Surveys by Leica 1203+ total station system.

Project Area	Hole	East UTM 48N WGS84	North UTM 48N WGS84	RLm UTM 48N WGS84	Azimuth UTM (°)	Dip (°)	End of hole (metres)	From m	To m	Interval m	Ni %	Cu %	Co %	Pt+Pd+Au g/t	Pt g/t	Pd g/t	Au g/t	Recovery %								
BC West	BC20-01 including	432265	2341875	631	22	-50	100	58.00	63.20	5.20	0.66	0.73	0.04	0.79	0.17	0.55	0.07	100								
								58.50	60.00	1.50	2.20	2.12	0.13	2.66	0.59	1.86	0.21	100								
BC West	BC20-02 or including	432475	2341790	670	22	-55	133	85.90	90.00	4.10	0.92	0.69	0.05	0.26	0.04	0.19	0.03	100								
								85.90	88.20	2.30	1.60	1.09	0.09	0.43	0.07	0.32	0.04	100								
								86.40	88.20	1.80	2.01	1.27	0.12	0.53	0.09	0.41	0.03	100								
BC East	BC20-03 including and	433321	2341766	816	22	-45	133	57.05	66.85	9.80	1.45	0.90	0.08	0.70	0.23	0.44	0.03	100								
								60.00	65.70	5.70	2.07	1.08	0.12	0.95	0.34	0.57	0.04	100								
								63.35	65.20	1.85	3.59	1.18	0.20	1.97	0.40	1.53	0.04	100								
BC East	BC20-04 including	433545	2341690	881	22	-50	120	71.00	92.25	21.25	0.69	0.66	0.03	0.81	0.46	0.23	0.11	100								
								77.60	79.70	2.10	2.53	1.36	0.11	0.76	0.43	0.30	0.03	100								
BC West	BC20-05	432630	2341765	677	22	-55	92	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-								
								BC West	BC20-06 and including and including	432054	2341975	600	14	-50	150	76.77	77.00	0.23	1.00	0.12	0.07	0.44	0.17	0.25	0.02	100
																89.00	102.00	13.00	0.50	0.71	0.05	0.46	0.23	0.18	0.05	99.00
																92.00	93.75	1.75	0.72	0.49	0.07	0.39	0.24	0.10	0.05	100
																97.80	102.00	4.20	0.52	0.81	0.06	0.82	0.41	0.35	0.06	100
101.00	102.00	1.00	0.24	1.80	0.05	1.30	0.07	1.13	0.10	100																
BC East	BC20-07 including	433372	2341758	840	22	-45	114	34.20	38.00	3.80	0.79	0.45	0.05	0.62	0.27	0.29	0.06	100								
								35.30	36.95	1.65	1.13	0.62	0.06	0.71	0.29	0.37	0.05	100								
BC East	BC20-08 including and	433274	2341783	805	22	-50	105	57.00	66.60	9.60	0.84	0.73	0.05	0.70	0.26	0.34	0.10	100								
								58.20	60.35	2.15	1.16	0.89	0.07	1.00	0.45	0.46	0.09	100								
								61.70	64.13	2.43	1.20	1.29	0.08	0.80	0.10	0.48	0.22	100								
BC West	BC20-09	432316	2341867	629	22	-45	107	41.50	42.05	0.55	2.24	1.11	0.12	0.75	0.30	0.43	0.02	100								
BC East	BC20-10 including	433226	2341789	795	22	-45	107	45.00	59.65	14.65	0.74	0.71	0.04	0.54	0.32	0.18	0.04	100								
								56.78	57.65	0.87	3.32	3.89	0.16	1.65	1.18	0.42	0.05	100								
BC West	BC20-11	432368	2341846	644	22	-50	103	60.65	62.15	1.50	0.87	0.49	0.05	0.23	0.03	0.18	0.02	100								

personal use only

Project Area	Hole	East UTM 48N WGS84	North UTM 48N WGS84	RLm UTM 48N WGS84	Azimuth UTM (°)	Dip (°)	End of hole (metres)	From m	To m	Interval m	NI %	Cu %	Co %	Pt+Pd+Au g/t	Pt g/t	Pd g/t	Au g/t	Recovery %
	including							60.65	61.50	0.85	1.45	0.42	0.08	0.38	0.06	0.31	0.01	100
BC East	BC20-12	433180	2341800	774	22	-50	101	35.50	43.80	8.30	0.50	0.70	0.05	0.46	0.23	0.16	0.07	100
	including							39.00	43.80	4.80	0.71	0.81	0.06	0.46	0.22	0.19	0.05	100
BC West	BC20-13	432418	2341831	663	22	-50	101	67.45	70.75	3.30	0.48	0.48	0.03	0.38	0.16	0.19	0.03	100
	including							67.45	68.27	0.82	1.17	0.40	0.07	0.90	0.45	0.40	0.05	100
	and							70.55	70.75	0.20	1.32	1.57	0.08	0.78	0.29	0.45	0.03	100
BC East	BC20-14	433425	2341750	852	22	-45	108	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC20-15	432535	2341793	678	22	-50	100	68.60	69.85	1.25	0.55	0.52	0.03	0.39	0.22	0.15	0.02	100
	including							68.60	69.00	0.40	1.52	0.42	0.09	1.13	0.66	0.45	0.02	100
BC East	BC20-16	433495	2341705	852	22	-45	90	55.10	60.75	5.65	1.04	1.16	0.05	0.71	0.15	0.52	0.04	100
	including							58.83	60.75	1.92	2.10	2.56	0.11	1.46	0.34	1.06	0.06	100
BC West	BC20-17	432578	2341779	677	22	-50	92	69.70	69.77	0.07	0.58	0.98	0.03	0.80	0.22	0.51	0.06	100
BC East	BC20-18	433384	2341783	850	22	-50	90	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC20-19	432484	2341825	681	22	-50	80	41.75	57.50	15.75	0.47	0.25	0.03	0.21	0.10	0.10	0.01	100
	including							55.60	57.50	1.90	1.21	0.48	0.07	0.70	0.35	0.32	0.02	100
BC East	BC20-20	433286	2341802	812	22	-45	75	46.00	49.85	3.85	0.81	0.57	0.05	0.36	0.13	0.21	0.02	100
	including							48.15	49.85	1.70	1.45	1.08	0.08	0.60	0.20	0.37	0.03	100
BC West	BC20-21	432380	2341879	663	22	-45	80	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC20-22	433533	2341664	864	22	-73	150	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC20-23	433241	2341827	809	22	-45	73	22.10	23.30	1.20	0.34	0.17	0.02	0.15	0.06	0.08	0.01	100
BC West	BC20-24	432325	2341886	643	22	-45	86	0.55	1.50	0.95	0.93	0.34	0.05	0.27	0.08	0.14	0.05	100
	and							32.50	35.05	2.55	0.40	0.32	0.02	na	na	na	na	100
BC East	BC20-25	433188	2341823	791	22	-50	67	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC20-26	433366	2341737	819	22	-50	103	54.00	70.30	16.30	0.58	0.37	0.04	0.30	0.15	0.14	0.01	100
	including							62.87	63.42	0.55	1.49	1.63	0.09	0.49	0.14	0.31	0.04	100
BC West	BC20-27	432270	2341899	640	22	-45	70	42.32	43.00	0.68	2.56	0.65	0.14	0.97	0.39	0.56	0.02	100
BC East	BC20-28	433138	2341844	779	22	-50	84	15.20	17.20	2.00	0.17	0.22	0.01	na	na	na	na	100
BC West	BC20-29	432230	2341883	629	22	-45	83	63.60	64.80	1.20	0.51	0.16	0.03	0.27	0.11	0.15	0.01	100
	including							63.60	63.75	0.15	2.65	0.08	0.14	0.99	0.35	0.63	0.01	100
BC East	BC20-30	433313	2341728	792	15	-50	143	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	100
BC East	BC20-31	433127	2341808	756	22	-50	121	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	100
BC West	BC20-32	432190	2341912	626	22	-45	96	61.59	62.95	1.36	1.11	0.44	0.07	0.46	0.16	0.28	0.02	100

Project Area	Hole	East UTM 48N WGS84	North UTM 48N WGS84	RLm UTM 48N WGS84	Azimuth UTM (°)	Dip (°)	End of hole (metres)	From m	To m	Interval m	NI %	Cu %	Co %	Pt+Pd+Au g/t	Pt g/t	Pd g/t	Au g/t	Recovery %
	including							61.86	62.30	0.44	2.16	0.91	0.14	0.76	0.30	0.43	0.03	100
	and							62.60	62.95	0.35	1.10	0.12	0.07	0.24	0.01	0.22	0.02	100
BC West	BC20-33	432063	2342093	556	227	-45	150	-	-	-	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC20-34	432153	2341939	631	22	-45	122	66.65	68.57	1.92	1.03	0.60	0.06	0.44	0.23	0.19	0.02	100
	including							66.65	67.56	0.91	1.99	0.92	0.12	0.84	0.46	0.36	0.02	100
BC West	BC20-35	432456	2341760	635	22	-50	135	109.70	110.35	0.65	0.99	2.97	0.06	0.90	0.31	0.32	0.27	100
BC West	BC20-36	432115	2341979	626	22	-45	79	52.95	55.10	2.15	0.57	0.35	0.05	0.20	0.08	0.11	0.01	82.47
	including							53.25	53.65	0.40	2.07	0.88	0.17	0.57	0.16	0.40	0.01	100
	and							56.00	63.10	7.10	0.66	0.45	0.06	0.18	0.08	0.07	0.03	100
	including							58.45	59.30	0.85	1.91	0.60	0.13	0.29	0.14	0.11	0.04	100
BC West	BC20-37	432730	2341769	712	22	-45	102	-	-	-	NSI	NSI	NSI	NSI	NSI	NSI	NSI	100
BC East	BC20-38	433355	2341710	799	22	-47	140	89.20	94.60	5.40	0.60	0.47	0.05	0.20	0.07	0.11	0.02	100
	including							91.38	93.60	2.22	0.92	0.53	0.08	0.24	0.09	0.14	0.01	100
BC East	BC20-39	433412	2341722	828	22	-45	130	63.80	66.87	3.07	1.39	0.79	0.08	0.72	0.25	0.50	0.03	100
BC East	BC20-40	433270	2341757	791	22	-50	130	-	-	-	NSI	NSI	NSI	NSI	NSI	NSI	NSI	100
BC East	BC20-41	433482	2341685	843	22	-50	105	73.50	74.40	0.90	0.62	0.40	0.04	0.83	0.38	0.35	0.09	100
BC East	BC20-42	433226	2341765	777	22	-51	106	-	-	-	NSI	NSI	NSI	NSI	NSI	NSI	NSI	100.
BC East	BC20-43	433575	2341670	873	22	-45	120	-	-	-	NSI	NSI	NSI	NSI	NSI	NSI	NSI	100
BC East	BC20-44	433536	2341672	867	22	-51	120	87.70	92.42	4.72	1.78	0.83	0.08	0.82	0.51	0.47	0.16	100
	including							88.30	88.65	0.35	2.57	0.32	0.12	0.95	0.78	0.21	0.04	100
	and							89.26	90.15	0.89	3.72	0.73	0.18	1.46	0.77	0.85	0.16	100
BC East	BC20-45	433188	2341823	791	22	-50	67	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC20-46	433171	2341774	753	22	-50	122	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC20-47	433352	2341698	801	22	-58	164	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC21-01	433521	2341733	869	22	-51	109	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC21-02	433290	2341822	825	22	-50	79	31.00	36.30	5.30	0.22	0.14	0.01	0.12	0.05	0.06	0.01	100
BC East	BC21-03	433452	2341683	846	22	-60	157	106.20	109.73	3.53	0.60	0.40	0.05	0.23	0.09	0.11	0.03	100
BC East	BC21-04	433333	2341801	832	22	-50	93	21.45	25.50	4.05	0.21	0.04	0.01	0.05	0.02	0.02	0.01	100
BC East	BC21-05	433462	2341706	833	22	-50	98	59.60	64.86	5.26	0.74	0.57	0.04	0.71	0.29	0.35	0.07	100
	including							61.52	64.43	2.91	1.12	0.69	0.06	0.80	0.35	0.39	0.06	100
BC East	BC21-06	433400	2341685	818	22	-46	141	95.80	109.00	13.20	0.33	0.39	0.02	0.52	0.28	0.19	0.05	100
	including							99.15	102.53	3.38	0.75	0.57	0.05	0.81	0.44	0.30	0.07	100

Project Area	Hole	East UTM 48N WGS84	North UTM 48N WGS84	RLm UTM 48N WGS84	Azimuth UTM (°)	Dip (°)	End of hole (metres)	From m	To m	Interval m	NI %	Cu %	Co %	Pt+Pd+Au g/t	Pt g/t	Pd g/t	Au g/t	Recovery %
BC East	BC21-07 including and	433323	2341761	814	22	-60	98	72.12	83.93	11.81	0.40	0.40	0.04	0.74	0.17	0.45	0.12	100
								71.12	71.42	0.30	0.95	2.73	0.17	15.99	2.32	13.50	0.17	100
								81.40	83.93	2.53	1.00	0.87	0.08	0.72	0.12	0.25	0.35	100
BC East	BC21-08	433478	2341745	860	22	-45	62	15.60	32.50	16.90	0.20	0.10	0.02	na	na	na	na	95.00
BC East	BC21-09 including	433358	2341724	808	22	-46	107	64.72	83.00	18.28	0.44	0.41	0.03	0.31	0.11	0.16	0.04	100
								68.75	74.40	5.65	1.07	0.53	0.06	0.51	0.21	0.26	0.04	100
BC East	BC21-10 including and	433281	2341794	807	22	-51	66	42.30	57.60	15.30	0.72	0.45	0.04	0.36	0.16	0.18	0.02	100
								50.62	55.63	5.01	1.67	1.01	0.09	0.95	0.42	0.49	0.04	100
								53.63	55.63	2.00	3.31	1.14	0.18	1.93	0.80	1.09	0.04	100
BC East	BC21-11 including	433469	2341726	849	22	-45	70	43.10	55.65	12.55	0.57	0.42	0.03	0.38	0.15	0.18	0.05	100
								46.90	50.00	3.10	1.16	0.95	0.06	0.67	0.27	0.33	0.07	100
BC East	BC21-12 including	433235	2341809	798	22	-45	69	23.73	43.00	19.27	0.35	0.23	0.02	0.16	0.07	0.08	0.01	100
								37.00	40.75	3.75	1.02	0.67	0.06	0.43	0.19	0.22	0.02	100
BC West	BC21-13	432186	2341887	615	22	-49	125	87.75	88.58	0.83	2.37	0.63	0.13	1.19	0.32	0.85	0.02	100
BC West	BC21-14 including	432406	2341801	645	22	-50	125	88.40	89.75	1.35	0.46	0.27	0.03	0.20	0.05	0.14	0.01	100
								89.15	89.45	0.30	1.22	0.38	0.07	0.60	0.18	0.40	0.02	100
BC West	BC21-15	432100	2341944	617	22	-48	126	87.05	89.35	2.30	0.60	0.31	0.04	0.64	0.25	0.38	0.01	100
BC West	BC21-16 including	432138	2341906	619	22	-48	135	92.10	94.50	2.40	0.59	0.28	0.03	0.25	0.06	0.18	0.01	100
								93.00	93.50	0.50	2.73	0.46	0.15	1.12	0.28	0.83	0.01	100
BC West	BC21-17	432301	2341834	607	22	-50	125	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-18 including	432523	2341767	663	22	-55	130	92.50	96.30	3.80	1.13	0.59	0.06	0.52	0.11	0.33	0.08	100
								93.00	94.60	1.60	2.49	0.65	0.14	1.01	0.26	0.73	0.02	100
BC West	BC21-19	432250	2341836	611	22	-50	147	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-20	432429	2341857	673	22	-45	78	25.70	27.40	1.70	0.26	0.13	0.02	0.15	0.06	0.09	<0.01	100
BC West	BC21-21 including	432453	2341739	621	22	-47	164	130.80	133.90	3.10	0.49	1.42	0.04	0.76	0.14	0.61	0.01	100
								132.00	133.15	1.15	0.97	0.96	0.07	1.55	0.30	1.23	0.02	100
BC West	BC21-22	432283	2341926	657	22	-45	52	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-23 including	432355	2341814	627	22	-50	142	82.39	84.22	1.83	1.57	0.32	0.09	0.96	0.69	0.25	0.02	100
								82.39	83.66	1.27	2.01	0.42	0.12	1.13	0.79	0.32	0.02	100
BC West	BC21-24	432239	2341905	639	22	-45	69	51.02	52.54	1.52	1.95	0.42	0.10	0.78	0.28	0.48	0.02	100
BC West	BC21-25 including	432207	2341942	642	22	-45	60	12.80	42.50	29.70	0.43	0.25	0.03	0.25	0.11	0.11	0.03	100
								28.80	31.80	3.00	0.94	0.69	0.06	0.75	0.34	0.34	0.07	100

Project Area	Hole	East UTM 48N WGS84	North UTM 48N WGS84	RLm UTM 48N WGS84	Azimuth UTM (°)	Dip (°)	End of hole (metres)	From m	To m	Interval m	NI %	Cu %	Co %	Pt+Pd+Au g/t	Pt g/t	Pd g/t	Au g/t	Recovery %
	and						40.60	42.50	1.90	0.67	0.77	0.05	1.02	0.49	0.41	0.12	100	
BC West	BC21-26	432167	2341975	637	22	-45	66	27.80	38.50	10.70	0.54	0.45	0.03	0.20	0.06	0.11	0.03	91.00
	including							35.80	38.50	2.70	1.21	0.76	0.07	0.16	0.07	0.08	0.01	63.00
BC West	BC21-27	432221	2341870	622	22	-54	133	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-28	432294	2341886	632	20	-53	63	40.16	40.90	0.74	1.24	0.83	0.07	0.59	0.23	0.32	0.04	100
BC West	BC21-29	432292	2341867	620	21	-60	91	60.00	66.60	6.60	0.44	0.74	0.03	1.35	0.60	0.66	0.09	100
	including							60.85	63.00	2.15	0.69	1.32	0.04	3.47	1.73	1.57	0.17	100
BC West	BC21-30	432478	2341801	668	21	-46	94	63.90	68.40	4.50	0.67	0.49	0.04	0.39	0.14	0.22	0.03	100
	including							65.00	66.61	1.61	1.35	0.73	0.08	0.60	0.24	0.32	0.04	100
	and							71.95	72.25	0.30	2.30	0.50	0.13	2.26	0.72	1.52	0.02	100
BC West	BC21-31	432313	2341857	622	21	-57	80	57.60	58.28	0.68	1.43	0.22	0.08	0.67	0.37	0.29	0.01	100
BC West	BC21-32	432455	2341842	679	22	-45	76	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-33	432338	2341854	633	21	-51	77	50.47	51.15	0.68	3.27	0.37	0.20	0.45	0.01	0.43	0.01	100
BC West	BC21-34	432448	2341823	672	21	-52	98	56.00	69.85	13.85	0.51	0.33	0.03	0.30	0.13	0.15	0.02	100
	including							65.72	69.85	4.13	1.16	0.72	0.07	0.67	0.31	0.33	0.03	100
BC West	BC21-35	432356	2341887	657	21	-64	62	38.30	41.90	3.60	1.15	1.10	0.07	0.70	0.32	0.34	0.04	100
	including							39.60	41.60	2.00	1.85	1.57	0.10	1.10	0.50	0.55	0.05	100
BC West	BC21-36	432491	2341844	685	21	-45	69	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-37	432378	2341869	659	21	-61	79	20.90	25.90	5.00	0.83	0.47	0.04	0.44	0.26	0.11	0.07	100
	including							22.10	24.00	1.90	1.44	0.67	0.06	0.55	0.36	0.13	0.06	100
BC West	BC21-38	432541	2341807	684	21	-48	74	43.90	50.00	6.10	1.07	0.63	0.06	0.94	0.49	0.38	0.07	100
	including							48.63	50.00	1.37	1.63	0.62	0.09	1.41	0.88	0.48	0.05	100
BC East	BC21-39	433482	2341658	862	22	-56	157	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-40	432422	2341845	668	19	-45	82	37.50	44.50	7.00	0.52	0.40	0.03	0.22	0.09	0.11	0.02	100
	including							42.55	43.70	1.15	1.73	0.88	0.08	0.74	0.29	0.42	0.04	100
BC East	BC20-41	433533	2341663	865	22	-55	142	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-42	432415	2341814	655	19	-50	100	78.35	80.00	1.65	1.04	0.23	0.06	0.66	0.18	0.46	0.02	100
	including							79.20	80.00	0.80	2.04	0.25	0.11	1.26	0.31	0.93	0.02	100
BC West	BC21-43*	432438	2341798	654.5	21.86	-54.8	124.7	89.3	91.78	2.48	0.53	0.6	0.03	0.25	0.1	0.13	0.02	100
	including							89.3	90.1	0.8	0.88	1.1	0.05	0.42	0.1	0.27	0.05	100
BC West	BC21-44*	432513	2341825	684.7	21.16	-46.2	73	27.8	49.15	21.35	0.59	0.28	0.04	0.26	0.11	0.13	0.02	100
	including							28.9	32.5	3.6	1.04	0.62	0.06	0.41	0.09	0.29	0.03	100

Project Area	Hole	East UTM 48N WGS84	North UTM 48N WGS84	RLm UTM 48N WGS84	Azimuth UTM (°)	Dip (°)	End of hole (metres)	From m	To m	Interval m	NI %	Cu %	Co %	Pt+Pd+Au g/t	Pt g/t	Pd g/t	Au g/t	Recovery %
	and							42.15	45.75	3.6	1.05	0.38	0.06	0.66	0.4	0.23	0.03	100
BC East	BC21-45*	433443	2341658	853.82	22.26	-61.2	220.8	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC21-46*	433494	2341725	854.86	20.06	-45.2	84.4	36.1	47.1	11	0.3	0.19	0.02	0.2	0.08	0.1	0.02	100
	and							41.2	42.3	1.1	0.7	0.6	0.03	0.54	0.21	0.3	0.03	100
BC West	BC21-47*	432394	2341842	653.86	21.86	-47.8	87.2	52.95	53.75	0.8	0.77	0.34	0.04	0.38	0.22	0.13	0.03	100
	and							60.95	61.6	0.65	1.12	0.33	0.06	0.63	0.32	0.3	0.01	100
BC West	BC21-48*	432503	2341802	679.17	21.16	-45.4	94.7	59.25	67	7.75	1	0.53	0.06	0.84	0.29	0.51	0.04	100
	including							63	65.65	2.65	1.52	0.43	0.09	1.81	0.53	1.2	0.08	100
BC East	BC21-49*	433420	2341731	837.67	19.46	-46.4	87	46.15	66.55	20.4	0.53	0.28	0.03	0.26	0.1	0.14	0.02	100
	including							63.5	66.55	3.05	1.34	0.67	0.07	0.72	0.3	0.39	0.03	100
BC West	BC21-50*	432382	2341821	644.38	21.86	-48	102	73.8	75.2	1.4	1.13	0.58	0.07	0.59	0.2	0.38	0.01	100
BC West	BC21-51*	432503	2341802	679.17	21.16	-68.2	107.1	85.7	90	4.3	0.56	0.42	0.03	0.23	0.02	0.07	0.14	100
	including							86.7	88.63	1.93	1.12	0.38	0.07	0.19	0.05	0.11	0.03	100
BC East	BC21-52*	433329	2341778	821.47	18.46	-42.3	74.1	47.1	55.4	8.3	0.46	0.23	0.03	0.23	0.1	0.11	0.02	100
BC West	BC21-53*	432245	2341923	648.48	22.26	-43.4	61.1	25	41	16	0.44	1.34	0.03	0.98	0.4	0.46	0.12	100
	including							28.2	32	3.8	0.78	0.57	0.05	0.56	0.19	0.33	0.04	100
	and							34.5	37.8	3.3	0.32	4.15	0.02	2.53	0.95	1.14	0.44	100
BC West	BC21-54*	432303	2341901	644.87	22.25	-42.5	50.5	6	31.15	25.15	0.31	0.45	0.02	na	na	na	na	100
	including							26	31.15	5.15	0.59	1.7	0.03	1.09	0.51	0.55	0.03	100
BC East	BC21-55*	433274	2341772	798.44	20.35	-51.5	121.8	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-56*	432201	2341926	633.52	19.95	-42.3	68	50.8	51.8	1	0.33	0.01	0.02	0.01	<0.01	0.01	<0.01	100
BC West	BC21-57*	432145	2341923	625.97	22.25	-44.8	100.4	80.75	81.05	0.3	2.43	0.45	0.15	0.64	0.26	0.36	0.02	100
BC East	BC21-58*	433298	2341770	803.52	19.75	-42.8	99.8	58.5	60.7	2.2	0.36	0.41	0.02	0.72	0.32	0.3	0.1	100
	including							59.6	60.7	1.1	0.55	0.43	0.03	1.01	0.44	0.45	0.12	100
BC West	BC21-59*	432128	2341879	608.83	22.25	-48	151	115.8	116.1	0.3	0.14	1.08	0.01	0.94	0.86	0.07	0.01	100
BC West	BC21-60*	433298	2341769	803.51	19.75	-61.3	117.5	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-61*	432093	2341930	610.73	22.25	-53.3	140.1	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-62*	432174	2341862	601.76	22.25	-46.3	139.1	101.6	105.35	3.75	2.16	0.82	0.13	1.09	0.21	0.86	0.02	100
BC East	BC21-63*	433309	2341794	821.15	19.75	-48.2	68.6	39.2	55.75	16.55	0.31	0.29	0.02	0.19	0.06	0.12	0.01	100
	including							49.36	50.65	1.29	0.86	0.45	0.05	0.46	0.13	0.31	0.02	100
BC West	BC21-64*	432174	2341862	601.69	22.25	-58.8	143.5	116.45	116.9	0.45	2.14	0.41	0.12	1.3	0.62	0.65	0.03	100
BC East	BC21-65*	433149	2341792	758.22	21.35	-53.6	77.8	52	52.35	0.35	0.13	0.17	<0.01	na	na	na	na	100

Project Area	Hole	East UTM 48N WGS84	North UTM 48N WGS84	RLm UTM 48N WGS84	Azimuth UTM (°)	Dip (°)	End of hole (metres)	From m	To m	Interval m	Ni %	Cu %	Co %	Pt+Pd+Au g/t	Pt g/t	Pd g/t	Au g/t	Recovery %
BC East	BC21-66*	433251	2341780	789.63	21.65	-43.6	90.2	60.1	69.7	9.6	2.02	1.92	0.1	3.04	0.47	1.82	0.75	100
	including							63.7	68.5	4.8	3.38	3.07	0.16	5.29	0.87	3.01	1.41	100
BC East	BC21-67*	433208	2341797	779.69	20.45	-47.4	71.1	39	47.7	8.7	0.53	0.44	0.03	0.34	0.18	0.14	0.02	100
	including							44	46.5	2.5	1.09	0.81	0.05	0.79	0.46	0.29	0.04	100
BC East	BC21-68*	433251	2341779	789.8	21.65	-64	144.2	78.65	79.4	0.75	0.11	0.69	<0.01	na	na	na	na	100
BC East	BC21-69*	433437	2341706	823.29	20.15	-45.3	94.6	64.9	67.5	2.6	0.52	0.63	0.03	0.42	0.19	0.19	0.04	100
	including							65.7	67	1.3	0.73	0.53	0.04	0.55	0.26	0.26	0.03	100
BC East	BC21-70*	433208	2341797	779.62	20.45	-71.2	122.6	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC21-71*	433436	2341706	823.3	20.15	-65.8	117.7	87.1	92	4.9	0.26	0.54	0.03	0.13	0.06	0.05	0.02	100
	including							87.1	88.1	1	0.51	1.87	0.05	0.34	0.18	0.09	0.07	100
BC East	BC21-72*	433340	2341737	811.06	19.05	-43.6	98	68	78.3	10.3	0.68	0.6	0.04	0.42	0.17	0.21	0.04	100
	including							73.15	76.3	3.15	1.12	0.96	0.06	0.5	0.16	0.3	0.04	100
BC East	BC21-73*	433215	2341816	790.03	20.45	-43.7	51.6	18	24.3	6.3	0.7	0.28	0.04	0.23	0.09	0.13	0.01	100
	including							20	23.5	3.5	0.88	0.38	0.05	0.31	0.12	0.17	0.02	100
BC East	BC21-74*	433266	2341809	807.58	22.25	-40	72.2	45.2	46.6	1.4	0.66	0.17	0.04	0.27	0.06	0.2	0.01	100
BC East	BC21-75*	433446	2341736	850.27	22.25	-43.1	73	42.7	46.1	3.4	0.31	0.17	0.02	0.18	0.07	0.09	0.02	100
BC East	BC21-76*	433340	2341736	811.26	19.05	-63.5	130	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC21-77*	433354	2341776	835.69	22.25	-67.8	88	43.65	69.2	25.55	0.63	0.43	0.04	0.33	0.13	0.16	0.04	98
	including							62.43	66	3.57	2.17	0.82	0.12	0.94	0.42	0.44	0.08	100
BC East	BC21-78*	433385	2341712	813.31	22.25	-47.8	111.9	67.4	83.35	15.95	0.28	0.35	0.01	0.15	0.07	0.07	0.01	100
	including							67.4	70.15	2.75	0.59	1.43	0.04	0.39	0.19	0.17	0.03	100
BC East	BC21-79*	433277	2341843	833.59	22.25	-53	91.9	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC21-80*	433354	2341777	835.85	22.25	-39.8	65.3	18	42	24	0.4	0.27	0.02	0.18	0.08	0.09	0.01	100
	including							23.9	25.9	2	0.95	0.25	0.04	0.25	0.07	0.05	0.13	100
BC East	BC21-81*	433320	2341816	837.2	22.25	-45.5	74.1	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC21-82*	433380	2341697	803.55	22.25	-58.8	170.6	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC21-83*	433365	2341794	846.77	22.25	-40.3	64.6	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC21-84*	433395	2341738	835.62	22.26	-52	105.6	52.5	70.1	17.6	0.49	0.29	0.03	0.36	0.14	0.19	0.03	100
	including							65.2	70.1	4.9	1.2	0.52	0.06	0.92	0.37	0.47	0.08	100
BC East	BC21-85*	433394	2341670	813.7	22.26	-47.2	170.4	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC21-86*	433504	2341745	861.4	22.26	-43.5	60.8	19.65	22.4	2.75	0.12	0.2	0.01	0.68	0.29	0.24	0.15	85
BC East	BC21-87*	433525	2341703	872.69	22.26	-52	105.5	54.85	67.45	12.6	0.63	0.45	0.03	0.35	0.18	0.15	0.02	100

Project Area	Hole	East UTM 48N WGS84	North UTM 48N WGS84	RLm UTM 48N WGS84	Azimuth UTM (°)	Dip (°)	End of hole (metres)	From m	To m	Interval m	NI %	Cu %	Co %	Pt+Pd+Au g/t	Pt g/t	Pd g/t	Au g/t	Recovery %
	including							64.3	67.45	3.15	1.72	1.28	0.08	1.01	0.55	0.4	0.06	100
BC East	BC21-88*	433404	2341756	847.51	22.26	-47.2	79.9	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC21-89*	433420	2341673	833.53	22.26	-63.2	176.3	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC21-90*	433518	2341685	864.98	22.26	-55.7	120.7	78.75	92.7	13.95	0.99	0.63	0.05	0.99	0.41	0.44	0.14	100
	including							79.08	87.6	8.52	1.49	0.88	0.07	1.35	0.52	0.64	0.19	100
BC West	BC21-91*	432568	2341807	682.8	22.26	-61.8	82.9	41.95	45.17	3.22	0.49	0.4	0.03	0.41	0.2	0.18	0.03	100
	including							43.8	45.17	1.37	0.84	0.76	0.05	0.76	0.37	0.34	0.05	100
BC West	BC21-92*	432125	2341937	625.29	22.26	-55	136.6	87.6	88	0.4	0.4	0.06	0.02	0.18	0.09	0.09	<0.01	100
BC East	BC21-93*	433510	2341666	855.14	22.26	-59.8	158.5			NSI								
BC West	BC21-94*	432557	2341781	678.04	22.26	-61.6	121.4	77.85	78.15	0.3	0.3	0.26	0.02	0.73	0.07	0.65	0.01	100
BC West	BC21-95*	432106	2341898	607.9	22.26	-53.2	159.6	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-96*	432546	2341754	661.11	22.26	-65	150	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-97*	432282	2341850	610.42	22.26	-62.2	120.9	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC21-98*	433242	2341762	779.56	22.26	-64.7	150.8	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-99*	432322	2341826	615.51	22.26	-50.2	108.5	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-100*	432350	2341799	619.32	22.26	-65.1	170.4	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-101*	432523	2341743	647.28	22.26	-58.1	150	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC21-102*	433194	2341777	765.72	22.26	-68.8	122.6	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-103*	432176	2341931	631.41	22.26	-58.2	106.7	68.2	69	0.8	1.94	3.56	0.12	0.62	0.39	0.19	0.04	100
BC East	BC21-104*	433154	2341812	771.23	22.26	-46.2	54.6	27.7	34.45	6.75	1.44	2.1	0.08	1.32	0.07	0.57	0.68	100
	including							30.8	34.45	3.65	2.58	2.1	0.15	1.21	0.12	1.03	0.06	100
BC West	BC21-105*	432372	2341788	626.49	22.26	-44.3	145	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-106*	432497	2341775	662.57	22.26	-67.5	151.4	127.25	132.85	5.6	1.09	1.39	0.06	1.07	0.66	0.34	0.07	100
	including							128	130.15	2.15	1.66	2.83	0.1	1.93	1.2	0.67	0.06	100
BC East	BC21-107*	433141	2341773	739.76	22.26	-55.7	102.3	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-108*	432161	2341901	617.63	22.26	-58	111.7	93.27	94	0.73	1.74	1.69	0.11	1.46	0.83	0.6	0.03	100
BC West	BC21-109*	432114	2341856	597.52	22.26	-50.7	175	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-110*	432406	2341872	670.72	22.26	-45.5	55	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-111*	432208	2341870	617.93	22.26	-63	147.7	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-112*	432146	2341856	597.08	22.26	-55.2	173.7	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-113*	432189	2341956	640.6	22.26	-46.6	82.8	13	41.15	28.15	0.33	0.18	0.02	0.15	0.06	0.08	0.01	98
	including							27.7	28.85	1.15	1.29	0.81	0.06	0.4	0.2	0.19	0.01	100

Project Area	Hole	East UTM 48N WGS84	North UTM 48N WGS84	RLm UTM 48N WGS84	Azimuth UTM (°)	Dip (°)	End of hole (metres)	From m	To m	Interval m	NI %	Cu %	Co %	Pt+Pd+Au g/t	Pt g/t	Pd g/t	Au g/t	Recovery %
BC West	BC21-114*	432428	2341768	633.44	22.26	-54.8	160.8	125.7	127.85	2.15	1.28	0.7	0.07	0.6	0.19	0.37	0.04	100
BC West	BC21-115*	432142	2341982	629.71	22.26	-55.3	79.9	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-116*	432156	2341822	579.76	22.26	-51.8	182.2	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-117*	432095	2342003	618.16	22.26	-55.8	99.9	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC21-118*	432398	2341778	629	22.26	-50.7	152.2	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC East	BC22-01*	432191	2341832	599.2	22.26	-60.9	177.3	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
BC West	BC22-02*	432078	2341969	612.5	22.26	-56.3	118.8	78.4	80	1.6	1.21	0.21	0.08	0.63	0.19	0.43	0.01	100
King Snake	KS20-01A	430865	2343777	170	22	-60	380	193.05	193.65	0.60	2.79	3.81	0.10	4.85	3.52	1.01	0.32	100
King Snake	KS20-02	431082	2343791	209	22	-66	292	131.74	137.62	5.88	1.22	0.49	0.04	4.67	2.64	1.78	0.25	100
	including	-	-	-	-	-	-	131.74	133.55	1.81	0.77	0.44	0.03	12.53	6.88	4.93	0.72	100
	and	-	-	-	-	-	-	135.00	135.25	0.25	1.28	0.32	0.05	2.69	2.22	0.32	0.15	100
	and	-	-	-	-	-	-	135.47	136.65	1.18	3.72	0.84	0.12	2.41	1.51	0.87	0.04	100
	and	-	-	-	-	-	-	137.15	137.62	0.47	1.66	1.23	0.06	2.50	1.53	0.83	0.15	100
King Snake	KS20-03	430818	2343806	213	22	-68	374	204.00	209.55	5.55	1.35	0.45	0.05	1.28	0.44	0.81	0.03	100
	including							205.38	206.57	1.19	3.56	0.98	0.13	3.10	0.13	2.95	0.02	100
King Snake	KS20-04	430949	2343732	236	22	-56	424	229.47	230.00	0.53	0.79	0.83	0.03	1.44	0.53	0.75	0.16	100
King Snake	KS20-05	431089	2343818	191	22	-50	143	63.35	68.00	4.65	0.09	0.33	<0.01	0.28	0.14	0.08	0.06	100
	including							67.50	68.00	0.50	0.46	1.02	0.02	0.35	0.14	0.14	0.07	100
King Snake	KS21-01	431319	2344112	291	202	-60	224	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
King Snake	KS21-02	431064	2343759	231	22	-68	278	206.45	206.75	0.30	0.45	0.79	0.02	0.88	0.34	0.46	0.08	100
King Snake	KS21-03	430869	2343780	170	37	-46	213	151.60	153.00	1.40	0.69	0.77	0.03	0.58	0.16	0.15	0.27	100
	including							151.60	151.90	0.30	2.63	2.80	0.10	1.40	0.73	0.56	0.11	100
King Snake	KS21-04	430950	2343732	237	22	-47	250	194.00	204.45	10.45	0.32	0.22	0.02	0.33	0.16	0.12	0.05	100
	including							202.80	203.43	0.63	3.77	2.11	0.15	2.33	1.01	1.13	0.19	100
King Snake	KS21-05	430871	2343806	179	22	-55	168	121.76	123.50	1.74	0.58	0.45	0.02	0.71	0.45	0.18	0.08	100
	including							121.76	122.55	0.79	1.17	0.69	0.05	1.21	0.87	0.28	0.06	100
King Snake	KS21-06	430869	2343779	170	37	-57	245	184.87	188.00	3.13	1.23	0.75	0.04	2.03	1.15	0.67	0.21	100
	including							185.18	186.30	1.12	2.19	0.93	0.07	2.72	1.54	0.89	0.29	100
King Snake	KS21-07	431044	2343839	173	22	-50	95	45.09	45.39	0.30	1.38	0.52	0.06	0.80	0.39	0.36	0.05	100
King Snake	KS21-08	430950	2343732	237	22	-66	400	265.30	265.70	0.40	1.44	1.14	0.05	1.97	0.85	1.03	0.09	100
King Snake	KS21-09	430869	2343779	170	37	-67	302	232.65	233.30	0.65	1.56	0.35	0.06	2.46	1.77	0.59	0.10	100
King Snake	KS21-10							254.08	256.70	2.62	1.54	2.01	0.06	5.16	3.90	1.16	0.10	100

Project Area	Hole	East UTM 48N WGS84	North UTM 48N WGS84	RLm UTM 48N WGS84	Azimuth UTM (°)	Dip (°)	End of hole (metres)	From m	To m	Interval m	Ni %	Cu %	Co %	Pt+Pd+Au g/t	Pt g/t	Pd g/t	Au g/t	Recovery %
	including							254.08	254.70	0.62	3.00	0.84	0.11	3.36	1.87	1.41	0.09	100
King Snake	KS21-11							267.63	270.55	2.92	0.90	0.54	0.04	1.60	0.95	0.46	0.19	100
	including							267.63	269.30	1.67	1.33	0.67	0.05	1.17	0.74	0.38	0.05	100
King Snake	KS21-12							349.90	351.80	1.90	1.00	0.27	0.04	1.48	1.00	0.35	0.13	100
	including							349.90	350.75	0.85	1.45	0.41	0.05	1.92	1.37	0.42	0.13	100
King Snake	KS21-13	430863	2343774	170	22	-68	300	243.58	244.70	1.12	0.48	0.20	0.02	0.71	0.54	0.14	0.03	100
	including							243.58	243.90	0.32	1.09	0.45	0.04	2.34	1.85	0.41	0.08	100
King Snake	KS21-14	430863	2343773	170	22	-74	383	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
King Snake	KS21-15	430674	2343729	270	22	-55	375	342.30	343.68	1.38	0.65	0.70	0.02	0.44	0.15	0.24	0.05	100
	including							343.05	343.35	0.30	1.98	0.60	0.07	1.03	0.45	0.51	0.07	100
	and							347.90	351.05	3.15	0.60	0.49	0.02	0.36	0.10	0.22	0.04	89
	including							350.22	351.05	0.83	1.56	1.42	0.06	1.11	0.34	0.72	0.05	100
King Snake	KS21-16	430673	2343729	270	22	-69	499	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
King Snake	KS21-17	430625	2343739	243	22	-65	460	426.20	428.00	1.80	0.36	0.23	0.02	0.43	0.26	0.12	0.05	100
King Snake	KS21-18	430994	2343749	241	22	-51	268	178.00	191.80	13.80	0.26	0.18	0.01	0.31	0.18	0.10	0.03	100
	including							190.62	191.80	1.18	1.73	1.09	0.06	1.07	0.56	0.38	0.13	100
King Snake	KS21-19	431169	2343753	237	22	-50	171	133.00	137.90	4.90	1.09	0.97	0.04	0.89	0.59	0.26	0.04	100
	including							134.68	136.56	1.88	2.66	1.92	0.10	2.13	1.45	0.63	0.05	100
King Snake	KS21-20	431169	2343753	237	22	-63	218	167.00	168.30	1.30	0.94	0.96	0.04	1.29	0.82	0.44	0.03	100
	including							167.00	167.50	0.50	2.39	2.00	0.09	3.29	2.13	1.11	0.05	100
King Snake	KS21-21	430912	2343592	237	17	-52	462	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
King Snake	KS21-22	430994	2343748	241	22	-60	329	197.95	211.45	13.50	0.30	0.24	0.01	0.37	0.23	0.12	0.02	100
	including							209.45	210.00	0.55	2.87	1.05	0.10	2.40	1.61	0.72	0.07	100
King Snake	KS21-23	431111	2343737	245	22	-50	266	171.40	175.47	4.07	0.41	1.19	0.01	1.72	1.06	0.42	0.24	100
	including							174.30	175.47	1.17	0.71	1.87	0.03	4.71	0.74	3.47	0.50	100
King Snake	KS21-24	431111	2343737	245	22	-66	284	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
King Snake	KS21-25	430793	2343754	193	22	-70	426	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
King Snake	KS21-26	430701	2343703	244	22	-65	490	421.80	422.10	0.30	0.56	0.22	0.02	1.01	0.82	0.16	0.03	100
King Snake	KS21-27	431448	2343769	248	22	-64	106	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
King Snake	KS21-28	430613	2343718	243	22	-70	642	545.00	545.43	0.43	0.42	0.15	0.02	0.50	0.25	0.24	0.01	100
King Snake	KS21-29	431447	2343768	248	22	-45	91	38.65	44.50	5.85	0.30	0.66	0.01	0.98	0.66	0.19	0.13	100
	including							42.34	43.50	1.16	1.06	2.21	0.04	3.70	2.78	0.66	0.26	100

Project Area	Hole	East UTM 48N WGS84	North UTM 48N WGS84	RLm UTM 48N WGS84	Azimuth UTM (°)	Dip (°)	End of hole (metres)	From m	To m	Interval m	NI %	Cu %	Co %	Pt+Pd+Au g/t	Pt g/t	Pd g/t	Au g/t	Recovery %
King Snake	KS21-30*	430724	2343777	247.28	22.26	-55.6	336.9	246.9	248.1	1.2	0.56	0.12	0.02	0.2	0.09	0.1	0.01	100
King Snake	KS21-31*	430724	2343777	246.67	22.25	-60.3	349.6	264.5	264.8	0.3	0.43	0.29	0.02	0.35	0.16	0.18	0.01	100
King Snake	KS21-32*	430724	2343776	246.81	22.25	-67.5	350	320.95	326.6	5.65	0.63	0.28	0.02	1.53	1	0.41	0.12	100
	including							321.28	323.8	2.52	1.07	0.35	0.04	1.93	1.34	0.51	0.08	100
King Snake	KS21-33*	430779	2343786	226.37	22.25	-59.4	275	211.28	214.35	3.07	0.51	0.32	0.02	1.3	0.7	0.38	0.22	100
	including							211.28	211.58	0.3	1.22	0.67	0.05	1.68	1.21	0.43	0.04	100
King Snake	KS21-34*	430778	2343786	226.49	22.26	-65.3	320.9	249.5	265.2	15.7	1.25	0.69	0.05	1.66	1.16	0.41	0.09	100
	including							250.38	256.4	6.02	2.18	0.62	0.08	2.97	2.23	0.63	0.11	100
King Snake	KS21-35*	430779	2343786	226.35	22.26	-70.3	341.6	302	303.05	1.05	0.59	0.22	0.1	2.26	1.66	0.41	0.19	100
	and							305.33	306.2	0.87	1.04	0.69	0.04	0.69	0.36	0.26	0.07	100
King Snake	KS21-36*	430869	2343779	169.83	22.26	-72.1	340	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
King Snake	KS21-37*	430994	2343748	241.03	22.26	-67.3	302.5	251.16	251.46	0.3	2.01	1.34	0.08	3.19	1.83	1.26	0.1	100
King Snake	KS21-38*	430674	2343729	270.11	22.26	-61.6	435.4	400.45	402.37	1.92	3.02	0.63	0.11	2.13	1.32	0.75	0.06	100
King Snake	KS21-39*	430814	2343805	213.19	22.26	-58.7	224.8	158.65	158.95	0.3	1.4	0.16	0.05	0.79	0.45	0.31	0.03	100
King Snake	KS21-40*	430864	2343773	170.21	12.26	-50.1	199.3	154.1	155.45	1.35	3.67	0.54	0.15	2.25	0.92	1.11	0.22	100
King Snake	KS21-41*	430748	2343774	236.84	22.26	-52.7	272	225.3	225.6	0.3	0.43	0.17	0.02	0.3	0.12	0.16	0.02	100
King Snake	KS21-42*	430688	2343763	259.9	22.26	-52.5	321.5	292.53	292.83	0.3	0.55	0.15	0.02	0.41	0.24	0.15	0.02	100
King Snake	KS21-43*	430704	2343723	245.16	379.26	-61.6	413	393.08	393.38	0.3	1.67	0.93	0.06	1.52	0.96	0.52	0.04	100
King Snake	KS21-44*	430704	2343723	245.32	379.26	-65.5	465	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
King Snake	KS22-01**	430860	2343769	170.09	32.26	-53.4	231			Pending								
King Snake	KS22-02**	430859	2343768	170.16	32.26	-64	270			Pending								
King Snake	KS22-03**	430859	2343768	170.24	32.26	-70.2	340			Pending								
King Snake	KS22-04**	430951	2343733	236.73	367.26	-55.2	244.8			Pending								
King Snake	KS22-05**	431038	2343754	235.39	22.26	-60.8	220			Pending								
King Snake	KS22-06**	430951	2343733	236.64	367.26	-65.5	301.3			Pending								
King Snake	KS22-07**	431038	2343753	235.21	22.26	-71.2	284.9			Pending								
King Snake	KS22-08**	430638	2343701	273.9	22.26	-54.4	420			Pending								
King Snake	KS22-09**	430951	2343732	236.76	367.26	-70.5	327.4			Pending								
King Snake	KS22-10**	431093	2343759	227.9	22.26	-57.6	216.7			Pending								
King Snake	KS22-11**	431093	2343759	227.9	22.26	-69.6	241.1			Pending								
King Snake	KS22-12**	431065	2343757	232.01	22.26	-75.5	285.3			Pending								
King Snake	KS22-13**	430638	2343701	273.72	22.26	-59.7	475			Pending								

Project Area	Hole	East UTM 48N WGS84	North UTM 48N WGS84	RLm UTM 48N WGS84	Azimuth UTM (°)	Dip (°)	End of hole (metres)	From m	To m	Interval m	NI %	Cu %	Co %	Pt+Pd+Au g/t	Pt g/t	Pd g/t	Au g/t	Recovery %	
King Snake	KS22-14**	431205	2343772	227.13	22.26	-78	230												Pending
King Snake	KS22-15**	430748	2343773	236.84	22.26	-66.5	332.6												Pending
King Snake	KS22-16**	430725	2343777	246.68	22.26	-45.5	270												Pending
King Snake	KS22-17**	430638	2343701	273.9	22.26	-63	525												Pending
Ta Cuong	TC20-05	426115	2347811	287	202	-50.3	224	110.9	188	77.1	0.16	0.03	0.01	0.01	<0.01	<0.01	<0.01		99
Ta Cuong	TC20-06	426507	2347398	211	202	-60	158	41	74.4	33.4	0.2	0.08	0.01	0.08	0.04	0.03	0.01		100
Ta Cuong	incl.	-	-	-	-	-	-	59.9	60.4	0.5	0.9	0.64	0.05	0.3	0.15	0.12	0.02		100
Ta Cuong	TC20-07	426599	2347341	152	22	-50	247.9	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI		-
Ta Cuong	TC21-01	426094	2347758	304	202	-49.7	183	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI		-
Ta Cuong	TC21-02	426148	2347853	283	202	-46.5	286.6	217.5	218.77	1.27	0.89	0.28	0.05	0.27	0.1	0.16	0.01		100
Ta Cuong	incl.	-	-	-	-	-	-	218.12	218.77	0.65	1.54	0.42	0.08	0.43	0.14	0.28	0.01		100
Ta Cuong	TC21-03	426432	2347465	259	202	-54.3	122	18.35	53.6	35.25	0.9	0.6	0.05	0.5	0.22	0.24	0.04		100
Ta Cuong	incl.	-	-	-	-	-	-	27	47.4	20.4	1.35	0.8	0.07	0.72	0.32	0.35	0.05		100
Ta Cuong	TC21-04*	426447	2347499	230	202	-45	166.2	86.38	100.15	13.77	0.5	0.31	0.03	0.35	0.16	0.16	0.03		100
	including							86.38	89.25	2.87	1.48	0.9	0.09	1.12	0.52	0.5	0.1		100
	and							114	116.95	2.95	0.92	0.65	0.06	1.03	0.2	0.76	0.07		100
	including							115.3	116.95	1.65	1.38	0.74	0.08	0.76	0.3	0.44	0.02		100
Ta Cuong	TC21-05*	426404	2347504	220	202	-46	151.9	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI		-
Ta Cuong	TC21-06*	426474	2347472	259	212	-45	122.1	76.5	77.7	1.2	0.17	0.49	0.01	0.2	0.14	0.05	0.01		100
	and							115.3	116.65	1.35	0.37	0.25	0.02	0.16	0.05	0.1	0.01		100
	including							115.3	115.65	0.35	1.04	0.49	0.12	0.52	0.19	0.31	0.02		100
Ta Cuong	TC21-07*	426502	2347504	237	212	-45	186.3	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI		-
Ta Cuong	TC21-08*	426494	2347435	232	202	-55	163.7	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI		-
Ta Cuong	TC21-09*	426542	2347278	188	22	-65	88.2	44	46	2	0.24	0.18	0.02	0.19	0.08	0.09	0.02		100
Ta Cuong	TC21-10*	426593	2347202	205	22	-54	124	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI		-
Ta Cuong	TC21-11*	426562	2347235	217	22	-63	115.3	57	60.4	3.4	0.26	0.17	0.02	0.6	0.45	0.12	0.03		100
	including							57	57.8	0.8	0.38	0.12	0.03	1.26	1.08	0.14	0.04		100
Ta Cuong	TC21-12*	426509	2347291	201	22	-54	146.8	66.95	67.25	0.3	0.84	0.14	0.05	0.18	0.03	0.15	<0.01		100
Ta Cuong	TC21-13*	426497	2347264	210	22	-63	156.4	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI		-
Ta Cuong	TC21-14*	426526	2347441	205	202	-54	171.5	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI		-
Ta Cuong	TC21-15*	426120	2347816	289	202	-62	291.4	215.45	237.4	21.95	0.46	0.41	0.03	0.29	0.15	0.12	0.03		100
	including							222.55	228.25	5.7	0.74	0.53	0.05	0.38	0.21	0.14	0.03		100

Project Area	Hole	East UTM 48N WGS84	North UTM 48N WGS84	RLm UTM 48N WGS84	Azimuth UTM (°)	Dip (°)	End of hole (metres)	From m	To m	Interval m	Ni %	Cu %	Co %	Pt+Pd+Au g/t	Pt g/t	Pd g/t	Au g/t	Recovery %
	including							227.15	228.25	1.1	1.31	0.44	0.08	0.65	0.4	0.19	0.06	100
	and							231.1	232.5	1.4	1.41	0.57	0.09	0.63	0.46	0.16	0.01	100
Ta Cuong	TC21-16*	426080	2347597	291.85	22.25	-50	211.7	148.3	156.5	8.2	0.86	0.55	0.06	0.72	0.33	0.31	0.08	100
Ta Cuong	TC21-17*	426104	2347589	271.76	22.25	-61.5	254	181.3	182.38	1.08	1.12	1.3	0.07	0.58	0.27	0.3	0.01	100
Ta Cuong	TC21-18*	426080	2347597	291.46	22.25	-61.4	249.4	189.05	191.7	2.65	0.76	0.75	0.05	0.64	0.27	0.32	0.05	100
	including							190.67	191.7	1.03	1.45	1.34	0.09	1.07	0.42	0.6	0.05	100
Ta Cuong	TC21-19*	426094	2347646	305.96	22.25	-50.8	160.9	50.5	54.6	4.1	0.32	0.18	0.02	0.24	0.11	0.1	0.03	100
	and							73.9	85.4	11.5	0.38	0.13	0.02	0.2	0.11	0.08	0.01	100
Ta Cuong	TC21-20*	426116	2347557	262.68	22.25	-49.5	244	159.3	162.5	3.2	0.37	0.41	0.02	0.35	0.12	0.2	0.03	100
	including							159.96	161.5	1.54	0.45	0.49	0.03	0.5	0.19	0.27	0.04	100
Ta Cuong	TC21-21*	426080	2347597	291.66	22.25	-69.8	300.2	230.45	231.38	0.93	1.08	0.6	0.07	1.34	0.68	0.62	0.04	100
Ta Cuong	TC21-22*	426152	2347579	234.81	22.25	-63.7	250.2	132.63	133	0.37	0.65	0.24	0.04	0.17	0.06	0.1	0.01	100
Ta Cuong	TC21-23*	426116	2347557	262.82	22.25	-56.8	247.7	184.02	184.45	0.43	0.91	0.57	0.06	0.57	0.27	0.29	0.01	100
Ta Cuong	TC21-24*	426116	2347557	262.81	22.25	-64.8	295.6	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
Ta Cuong	TC21-25*	426176	2347569	219.77	22.25	-54.8	197.9	98.65	98.95	0.3	0.51	0.38	0.03	0.34	0.08	0.25	0.01	100
Ta Cuong	TC21-26*	426041	2347576	326.85	22.25	-65.9	321.8	282	286.74	4.74	0.73	1.1	0.05	1.13	0.57	0.49	0.07	100
	including							283.4	286	2.6	1.04	1.08	0.07	1.45	0.95	0.44	0.06	100
Ta Cuong	TC21-27*	426088	2347880	236.27	202.25	-49.4	250.8	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
Ta Cuong	TC21-28*	425999	2347931	266.22	202.25	-49.7	257.4	185	189.2	4.2	0.36	0.06	0.02	0.08	0.03	0.03	0.02	100
Ta Cuong	TC21-29*	425816	2348006	363.68	202.26	-60	150	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
Ta Cuong	TC21-30*	425908	2347968	310.69	202.26	-49.7	250	169	169.3	0.3	0.66	0.11	0.04	0.08	<0.01	0.04	0.04	100
Ta Cuong	TC21-31*	425796	2347960	374.99	202.26	-49.6	104	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
Ta Cuong	TC21-32*	425908	2347968	310.55	202.26	-65.8	292	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
Ta Cuong	TC21-33*	426389	2347432	282.11	22.26	-64.2	128.7	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
Ta Cuong	TC21-34*	426380	2347414	280.61	22.26	-68	163	125.1	125.7	0.6	0.54	0.51	0.03	1.53	0.69	0.64	0.2	100
Ta Cuong	TC21-35*	425875	2347892	311.38	202.26	-54.1	186.8	81.5	84.1	2.6	0.24	0.05	0.01	0.14	0.08	0.05	0.01	100
Ta Cuong	TC21-36*	426471	2347443	255.13	202.26	-39.5	120	29.3	30.45	1.15	0.36	0.55	0.02	0.44	0.15	0.24	0.05	100
Ta Cuong	TC21-37*	426490	2347484	249.89	202.26	-46	169.4	117.75	118.3	0.55	0.34	0.04	0.03	0.15	0.09	0.05	0.01	100
Ta Cuong	TC21-38*	426451	2347511	221.1	202.26	-47.8	260.3	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
Ta Cuong	TC21-39*	426500	2347376	217.03	202.26	-57.7	127.4	66	67	1	0.38	0.08	0.02	0.3	0.14	0.15	0.01	100
Ta Cuong	TC21-40*	426494	2347346	220.01	202.26	-57.4	88.6	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
Ta Cuong	TC21-41*	426387	2347488	230.23	202.26	-41.7	120.4	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-

Project Area	Hole	East UTM 48N WGS84	North UTM 48N WGS84	RLm UTM 48N WGS84	Azimuth UTM (°)	Dip (°)	End of hole (metres)	From m	To m	Interval m	NI %	Cu %	Co %	Pt+Pd+Au g/t	Pt g/t	Pd g/t	Au g/t	Recovery %
Ta Cuong	TC21-42*	426487	2347415	232.57	202.26	-45.8	125.5	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
Ta Cuong	TC21-43*	426335	2347628	165.2	202.26	-50.1	250	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
Suoi Phang	SP21-01	419788	2349481	239.33	226.25	-45	133	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
Suoi Phang	SP21-02	419730	2349373	272.16	46.25	-60	115.2	50.28	51.3	1.02	0.41	0.15	0.03	0.26	<0.01	0.25	0.01	100
	including							51	51.3	0.3	0.86	0.14	0.07	0.87	0.01	0.84	0.02	100
Suoi Phang	SP22-01	419789	2349392	278.3	226	-58	60			pending								
Suoi Chanh	SC22-01**	439784	2343006	657.1	27.26	-65	140.9	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	NSI	-
Suoi Chanh	SC22-02**	439079	234307	401.9	202.26	-71	343			pending								

Table 4

Drill hole assays, preparation by SGS, Hai Phong, assays by ALS Geochemistry, Perth (see Appendix One for assay methods). Note: na denotes assay result not available (element was not determined), < - below the detection of the test performed.

Complete assay interval data is provided below for drill holes marked with "*" in Table 3.

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-43	39.25	40.25	1	100	732	100	75	na	na	na
BC21-43	40.25	41.1	0.85	100	755	87	78	na	na	na
BC21-43	80.1	81.6	1.5	100	443	74	65	na	na	na
BC21-43	83	84	1	100	283	65	63	na	na	na
BC21-43	88.3	89.3	1	100	211	286	20	<0.005	0.002	0.001
BC21-43	89.3	89.7	0.4	100	14450	5640	822	0.196	0.292	0.016
BC21-43	89.7	90.1	0.4	100	3100	16300	227	<0.005	0.241	0.086
BC21-43	90.1	90.9	0.8	100	854	1250	60	<0.005	0.016	0.008
BC21-43	90.9	91.35	0.45	100	2380	1000	163	0.01	0.009	0.003
BC21-43	91.35	91.78	0.43	100	10300	10900	612	0.36	0.194	0.011
BC21-43	91.78	92.2	0.42	100	1025	2930	80	<0.005	0.02	0.015
BC21-43	92.2	93.2	1	100	309	1205	26	<0.005	0.006	0.031
BC21-43	93.2	94.3	1.1	100	289	1085	22	<0.005	0.005	0.007
BC21-43	94.3	95.2	0.9	100	38	45	38	<0.005	<0.001	<0.001
BC21-43	95.2	96.05	0.85	100	52	36	34	<0.005	<0.001	0.001
BC21-43	96.05	97.2	1.15	100	290	404	28	<0.005	0.003	0.003
BC21-43	97.2	98.2	1	100	71	157	48	<0.005	<0.001	0.001
BC21-43	98.2	99.2	1	100	41	62	43	<0.005	0.001	<0.001
BC21-43	99.2	100.1	0.9	100	32	66	30	<0.005	<0.001	<0.001
BC21-44	5.4	6.6	1.2	100	20	35	6	<0.005	<0.001	0.001
BC21-44	7	8	1	100	286	25	48	<0.005	0.001	<0.001
BC21-44	8	9	1	100	592	110	61	<0.005	0.005	0.001
BC21-44	9	10	1	100	915	229	103	0.006	0.007	0.001
BC21-44	10	11	1	100	1030	273	107	0.012	0.008	0.001
BC21-44	11	12	1	100	1125	312	109	0.015	0.011	0.002
BC21-44	12	12.6	0.6	100	1035	298	98	0.011	0.013	0.002
BC21-44	12.6	13.6	1	100	1045	275	107	0.017	0.012	0.002
BC21-44	13.6	14.4	0.8	100	1030	243	108	0.016	0.012	0.002
BC21-44	14.4	15	0.6	100	990	228	95	0.018	0.012	0.002
BC21-44	15.3	16.5	1.2	100	1595	505	127	0.025	0.022	0.003
BC21-44	16.5	17.5	1	100	1545	347	118	0.022	0.026	0.003
BC21-44	17.5	18.5	1	100	1415	189	110	0.014	0.015	0.006
BC21-44	18.5	19.5	1	100	2270	730	150	0.029	0.034	0.019
BC21-44	19.5	20.7	1.2	100	2460	862	156	0.047	0.038	0.018
BC21-44	20.7	21.7	1	100	1655	313	109	0.006	0.015	0.005
BC21-44	21.7	22.7	1	70	1760	577	111	0.016	0.026	0.005
BC21-44	22.7	23.7	1	100	1985	867	139	0.03	0.031	0.005
BC21-44	23.7	24.5	0.8	100	1950	820	140	0.026	0.03	0.006
BC21-44	24.5	25.7	1.2	100	2120	1020	166	0.033	0.038	0.012
BC21-44	25.7	26.7	1	100	1400	492	106	0.018	0.023	0.005
BC21-44	26.7	27.8	1.1	100	1240	420	106	0.019	0.017	0.003
BC21-44	27.8	28.9	1.1	100	2910	1965	202	0.041	0.057	0.009
BC21-44	28.9	29.9	1	100	8260	3630	462	0.054	0.194	0.028
BC21-44	29.9	30.9	1	100	7890	6750	358	0.073	0.298	0.028
BC21-44	30.9	31.65	0.75	100	12200	4810	652	0.1	0.34	0.026
BC21-44	31.65	32.5	0.85	100	14450	9950	883	0.153	0.34	0.041
BC21-44	32.5	33.5	1	100	4870	3450	320	0.117	0.136	0.014
BC21-44	33.5	34.5	1	100	1535	868	130	0.156	0.079	0.008
BC21-44	34.5	35.5	1	100	2820	1120	154	0.038	0.054	0.006
BC21-44	35.5	36.85	1.35	100	2080	1015	134	0.046	0.062	0.007
BC21-44	36.85	37.7	0.85	100	4450	1340	472	0.02	0.1	0.015
BC21-44	37.7	38.7	1	100	1330	539	99	0.016	0.024	0.007
BC21-44	38.7	39.7	1	100	1230	473	94	0.015	0.024	0.008
BC21-44	39.7	40.7	1	100	1365	645	106	0.02	0.029	0.014
BC21-44	40.7	41.6	0.9	100	1790	804	126	0.03	0.036	0.015
BC21-44	41.6	42.15	0.55	100	3230	2310	207	0.075	0.113	0.018
BC21-44	42.15	43	0.85	100	7280	2940	437	0.18	0.195	0.028
BC21-44	43	43.7	0.7	100	8660	4040	526	0.196	0.255	0.029
BC21-44	43.7	44.4	0.7	100	9690	5580	447	0.342	0.225	0.052
BC21-44	44.4	45.4	1	100	10850	3720	570	0.69	0.283	0.033
BC21-44	45.4	45.75	0.35	100	22200	2000	1150	0.594	0.143	0.012

For personal use only

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-44	45.75	46.5	0.75	100	2050	1270	125	0.03	0.04	0.012
BC21-44	46.5	47.2	0.7	100	2230	951	125	0.117	0.041	0.008
BC21-44	47.2	48.35	1.15	100	7410	5780	372	<0.005	0.173	0.012
BC21-44	48.35	49.15	0.8	100	15550	2400	724	<0.005	0.001	0.001
BC21-44	49.15	50.15	1	100	259	589	32	<0.005	0.003	0.002
BC21-44	65.7	66.6	0.9	100	104	32	28	<0.005	<0.001	0.001
BC21-45	35.2	36.5	1.3	100	291	110	60	na	na	na
BC21-45	42.4	44	1.6	100	252	57	26	na	na	na
BC21-45	46	47.4	1.4	100	635	119	86	na	na	na
BC21-45	73.2	74.2	1	100	409	109	62	na	na	na
BC21-45	74.2	75.2	1	100	418	72	42	na	na	na
BC21-45	110	111	1	100	423	107	60	na	na	na
BC21-45	111	112	1	100	292	82	48	na	na	na
BC21-45	112	113.2	1.2	100	426	48	67	na	na	na
BC21-45	114.15	115.55	1.4	100	658	175	71	na	na	na
BC21-45	144.9	146.15	1.25	100	82	32	40	na	na	na
BC21-45	151.4	152.85	1.45	100	411	55	54	na	na	na
BC21-45	182.2	182.8	0.6	100	64	45	15	na	na	na
BC21-45	187.5	188.5	1	100	497	43	62	na	na	na
BC21-45	188.5	189.5	1	100	231	132	47	na	na	na
BC21-45	189.5	190.5	1	100	335	21	53	na	na	na
BC21-45	190.5	191.7	1.2	100	295	27	49	na	na	na
BC21-45	191.7	192.9	1.2	100	235	165	59	na	na	na
BC21-46	31.3	32.6	1.3	100	91	174	13	<0.005	0.001	0.002
BC21-46	32.6	33.8	1.2	100	63	326	42	<0.005	0.001	0.001
BC21-46	33.8	35	1.2	100	848	117	74	0.021	0.027	0.003
BC21-46	35	36.1	1.1	100	1330	364	88	0.016	0.021	0.006
BC21-46	36.1	37.1	1	100	2620	1300	144	0.051	0.065	0.043
BC21-46	37.1	38	0.9	100	2780	1740	166	0.051	0.073	0.023
BC21-46	38	38.55	0.55	100	3480	2640	198	0.068	0.09	0.024
BC21-46	38.55	39.55	1	100	1220	944	100	0.024	0.033	0.031
BC21-46	39.55	40.55	1	100	1780	795	124	0.037	0.053	0.005
BC21-46	40.55	41.2	0.65	100	1565	1460	107	0.029	0.04	0.025
BC21-46	41.2	42.3	1.1	100	7030	5960	342	0.212	0.3	0.033
BC21-46	42.3	43.3	1	100	1640	626	109	0.032	0.049	0.021
BC21-46	43.3	44.3	1	100	1650	954	108	0.035	0.05	0.013
BC21-46	44.3	45.2	0.9	100	2820	1920	185	0.096	0.113	0.019
BC21-46	45.2	46	0.8	100	3310	2250	218	0.137	0.128	0.016
BC21-46	46	47.1	1.1	100	4870	2380	307	0.194	0.126	0.015
BC21-46	47.1	48	0.9	100	602	1720	41	<0.005	0.026	0.008
BC21-46	48	49	1	100	359	611	24	<0.005	0.005	0.002
BC21-47	37.8	38.8	1	100	94	156	19	na	na	na
BC21-47	38.8	39.6	0.8	100	305	335	39	na	na	na
BC21-47	39.6	40.6	1	100	182	76	41	na	na	na
BC21-47	40.6	41.6	1	100	126	47	36	na	na	na
BC21-47	41.6	42.65	1.05	100	123	34	38	na	na	na
BC21-47	42.65	43.6	0.95	100	302	121	57	na	na	na
BC21-47	43.6	44.6	1	100	71	72	32	na	na	na
BC21-47	44.6	45.8	1.2	100	69	228	14	<0.005	0.001	<0.001
BC21-47	45.8	46.8	1	100	201	193	22	<0.005	0.002	<0.001
BC21-47	46.8	47.8	1	100	153	186	17	<0.005	0.002	0.001
BC21-47	47.8	48.8	1	100	227	571	18	<0.005	0.003	0.002
BC21-47	48.8	49.8	1	100	491	411	27	<0.005	0.006	0.001
BC21-47	49.8	50.8	1	100	1070	755	38	<0.005	0.018	0.001
BC21-47	50.8	51.45	0.65	100	951	858	38	<0.005	0.009	0.004
BC21-47	51.45	52.45	1	100	1030	1630	61	0.031	0.052	0.041
BC21-47	52.45	52.95	0.5	100	1450	2590	69	<0.005	0.018	0.028
BC21-47	52.95	53.34	0.39	100	8780	4710	435	0.169	0.12	0.011
BC21-47	53.34	53.75	0.41	100	6680	2230	330	0.266	0.138	0.041
BC21-47	53.75	54.5	0.75	100	922	1230	71	0.005	0.016	0.011
BC21-47	54.5	55.2	0.7	100	1000	1960	36	<0.005	0.01	0.006
BC21-47	55.2	56.15	0.95	100	136	242	21	<0.005	0.001	0.001
BC21-47	60	60.95	0.95	100	602	707	52	<0.005	0.004	0.006
BC21-47	60.95	61.6	0.65	100	11200	3300	608	0.317	0.296	0.013
BC21-47	61.6	62.5	0.9	100	1060	1350	73	<0.005	0.082	0.006
BC21-47	62.5	63.25	0.75	100	184	197	23	<0.005	0.006	0.002
BC21-48	42.75	43.75	1	100	149	106	25	<0.005	0.001	0.005
BC21-48	43.75	45.4	1.65	100	752	214	68	0.01	0.011	0.002
BC21-48	45.4	46.4	1	100	1065	183	84	0.005	0.007	0.001

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-48	46.4	47.4	1	100	1190	169	85	0.005	0.005	0.007
BC21-48	47.4	48.4	1	100	1715	348	107	0.011	0.041	0.016
BC21-48	48.4	49.75	1.35	100	2090	711	136	0.017	0.023	0.009
BC21-48	49.75	50.8	1.05	100	472	153	76	<0.005	0.01	0.003
BC21-48	50.8	51.8	1	100	1125	319	86	0.017	0.012	0.004
BC21-48	51.8	52.8	1	100	2540	1890	164	0.026	0.043	0.007
BC21-48	52.8	53.8	1	100	1880	850	121	0.027	0.028	0.077
BC21-48	53.8	54.6	0.8	100	720	392	71	<0.005	0.009	0.003
BC21-48	54.6	55.7	1.1	100	2150	1260	129	0.031	0.038	0.012
BC21-48	55.7	56.8	1.1	100	1675	1610	112	0.035	0.032	0.094
BC21-48	56.8	58.25	1.45	100	547	526	89	<0.005	0.008	0.01
BC21-48	58.25	59.25	1	100	1745	1020	116	0.033	0.036	0.008
BC21-48	59.25	60	0.75	100	5750	3020	367	0.124	0.14	0.016
BC21-48	60	61.1	1.1	100	10250	3710	615	0.317	0.198	0.027
BC21-48	61.1	62.2	1.1	100	11650	8540	664	0.206	0.335	0.042
BC21-48	62.2	63	0.8	100	10750	4460	635	0.235	0.111	0.021
BC21-48	63	63.9	0.9	100	15600	5830	897	0.453	0.578	0.084
BC21-48	63.9	64.8	0.9	100	5090	2820	308	0.776	0.544	0.114
BC21-48	64.8	65.65	0.85	100	25600	4130	1430	0.362	2.55	0.028
BC21-48	65.65	67	1.35	100	388	7920	38	<0.005	0.003	0.018
BC21-48	67	68.05	1.05	100	52	300	10	<0.005	0.002	0.115
BC21-48	75.45	76.8	1.35	100	18	18	21	na	na	na
BC21-49	23.3	24.6	1.3	100	194	76	16	<0.005	<0.001	0.001
BC21-49	24.6	26	1.4	100	384	119	54	<0.005	0.003	0.001
BC21-49	26.4	27.4	1	100	776	135	79	0.007	0.009	0.002
BC21-49	27.4	28.4	1	100	1065	293	92	0.008	0.011	0.001
BC21-49	28.4	29	0.6	100	991	153	85	0.005	0.006	0.001
BC21-49	29	30	1	100	1140	102	88	0.005	0.008	0.002
BC21-49	30	31	1	100	865	146	75	0.005	0.005	<0.001
BC21-49	31	32	1	100	801	160	70	0.009	0.006	0.001
BC21-49	32	32.7	0.7	100	690	188	72	0.006	0.006	0.005
BC21-49	32.7	33.7	1	100	1370	370	94	0.025	0.022	0.002
BC21-49	33.7	34.3	0.6	100	1380	350	104	0.013	0.019	0.001
BC21-49	34.3	35.1	0.8	100	1595	541	106	0.018	0.021	0.001
BC21-49	35.1	36	0.9	100	486	38	70	<0.005	0.005	0.001
BC21-49	36	37	1	100	496	80	72	<0.005	0.001	0.001
BC21-49	37	38	1	100	592	80	77	<0.005	0.001	0.001
BC21-49	38	38.7	0.7	100	492	71	69	<0.005	0.001	<0.001
BC21-49	38.7	39.6	0.9	100	237	137	46	<0.005	0.002	0.001
BC21-49	39.6	40.6	1	100	89	452	23	<0.005	0.003	0.006
BC21-49	40.6	41.75	1.15	100	152	581	32	<0.005	0.003	0.004
BC21-49	41.75	42.7	0.95	100	332	221	40	<0.005	0.002	0.001
BC21-49	42.7	43.7	1	100	151	54	36	<0.005	0.001	0.001
BC21-49	43.7	44.5	0.8	100	148	121	30	<0.005	0.002	0.002
BC21-49	44.5	45.1	0.6	100	87	64	34	<0.005	0.002	0.001
BC21-49	45.1	46.15	1.05	100	1750	524	107	0.022	0.028	0.004
BC21-49	46.15	47	0.85	100	2350	1150	165	0.033	0.043	0.008
BC21-49	47	48	1	100	2940	1170	183	0.046	0.063	0.01
BC21-49	48	49	1	100	2640	803	163	0.04	0.058	0.008
BC21-49	49	50	1	100	2380	382	136	0.021	0.034	0.008
BC21-49	50	51	1	100	1890	790	124	0.026	0.039	0.011
BC21-49	51	51.8	0.8	100	1720	376	112	0.031	0.032	0.005
BC21-49	51.8	52.6	0.8	100	1570	470	92	0.02	0.023	0.004
BC21-49	52.6	53.6	1	100	9390	3870	487	0.127	0.234	0.022
BC21-49	53.6	54.6	1	100	9530	3410	477	0.171	0.241	0.024
BC21-49	54.6	55.5	0.9	100	12100	9870	616	0.197	0.285	0.04
BC21-49	55.5	56.5	1	100	2240	2820	148	0.094	0.1	0.029
BC21-49	56.5	57.5	1	100	1880	813	129	0.048	0.065	0.02
BC21-49	57.5	58.5	1	100	1780	2200	121	0.041	0.059	0.031
BC21-49	58.5	59.5	1	100	2250	1435	153	0.047	0.072	0.025
BC21-49	59.5	60.5	1	100	2300	1675	158	0.051	0.07	0.041
BC21-49	60.5	61.5	1	100	2760	834	147	0.052	0.068	0.029
BC21-49	61.5	62.5	1	100	2440	841	140	0.045	0.055	0.013
BC21-49	62.5	63.5	1	100	6810	4400	406	0.138	0.241	0.042
BC21-49	63.5	64.5	1	100	12400	6060	718	0.214	0.358	0.034
BC21-49	64.5	65.5	1	100	12100	10950	673	0.337	0.349	0.037
BC21-49	65.5	66.25	0.75	100	13200	3290	691	0.323	0.351	0.018
BC21-49	66.25	66.55	0.3	100	21700	2910	1050	0.375	0.732	0.051
BC21-49	66.55	67.8	1.25	100	409	3270	42	<0.005	0.004	0.01
BC21-49	67.8	68.7	0.9	100	544	74	55	0.007	0.005	0.001
BC21-49	70.75	71.75	1	100	1010	113	78	na	na	na
BC21-50	73.4	73.8	0.4	100	366	181	55	<0.005	0.002	<0.001

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-50	73.8	74.3	0.5	100	459	2230	35	<0.005	0.01	0.006
BC21-50	74.3	75.2	0.9	100	17300	7840	994	0.316	0.58	0.015
BC21-50	75.2	76.4	1.2	100	632	1910	38	0.013	0.017	0.013
BC21-50	76.4	77.4	1	100	39	27	12	<0.005	<0.001	0.001
BC21-50	81.2	82.2	1	100	251	69	41	<0.005	0.001	0.001
BC21-51	24.7	25.9	1.2	100	725	73	74	na	na	na
BC21-51	25.9	27.1	1.2	100	704	90	72	na	na	na
BC21-51	27.1	28.4	1.3	100	414	76	56	na	na	na
BC21-51	42.3	43.65	1.35	100	95	64	50	na	na	na
BC21-51	71.6	73.2	1.6	100	198	97	57	na	na	na
BC21-51	80	81.5	1.5	100	244	91	49	na	na	na
BC21-51	84.7	85.7	1	100	128	176	14	<0.005	0.001	0.002
BC21-51	85.7	86.7	1	100	748	5050	41	<0.005	0.005	0.017
BC21-51	86.7	87.25	0.55	100	21200	4310	1260	0.015	0.242	0.029
BC21-51	87.25	88.3	1.05	100	414	2000	47	0.009	0.005	0.043
BC21-51	88.3	88.63	0.33	100	28900	8680	1690	0.212	0.218	0.01
BC21-51	88.63	89	0.37	100	1860	6880	100	0.018	0.138	0.14
BC21-51	89	90	1	100	1100	2990	39	<0.005	0.013	0.09
BC21-51	90	91.2	1.2	100	1190	787	28	0.034	0.037	0.011
BC21-51	91.2	92.4	1.2	100	979	867	33	<0.005	0.011	0.002
BC21-51	95.8	97.1	1.3	100	76	52	40	na	na	na
BC21-51	97.1	98.4	1.3	100	147	57	51	na	na	na
BC21-52	24.6	25.3	0.7	100	113	128	13	<0.005	<0.001	0.001
BC21-52	25.3	26.1	0.8	100	286	205	50	<0.005	<0.001	<0.001
BC21-52	26.8	27.8	1	100	1410	443	94	0.017	0.031	0.001
BC21-52	27.8	28.8	1	100	1760	713	123	0.049	0.041	0.002
BC21-52	28.8	29.9	1.1	100	1780	734	120	0.035	0.047	0.003
BC21-52	29.9	31	1.1	100	2830	1380	183	0.064	0.073	0.005
BC21-52	31	31.3	0.3	100	4120	2090	270	0.045	0.062	0.005
BC21-52	31.3	32.3	1	100	730	447	54	0.007	0.018	0.004
BC21-52	32.3	32.9	0.6	100	872	905	62	<0.005	0.022	0.009
BC21-52	32.9	33.9	1	100	1900	763	120	0.046	0.046	0.01
BC21-52	33.9	34.9	1	100	2070	914	134	0.04	0.05	0.01
BC21-52	34.9	35.9	1	100	1960	781	131	0.053	0.048	0.009
BC21-52	35.9	36.9	1	100	1510	512	102	0.036	0.03	0.005
BC21-52	36.9	37.85	0.95	100	2100	1150	140	0.064	0.067	0.008
BC21-52	37.85	38.7	0.85	100	1430	527	111	0.037	0.045	0.005
BC21-52	38.7	39.7	1	100	1290	372	93	0.018	0.027	0.002
BC21-52	39.7	40.7	1	100	302	166	55	<0.005	0.002	0.003
BC21-52	40.7	41.7	1	100	2050	1160	130	0.033	0.06	0.014
BC21-52	41.7	42.7	1	100	2280	752	136	0.038	0.053	0.02
BC21-52	42.7	43.4	0.7	100	1470	439	88	0.02	0.024	0.005
BC21-52	43.4	44.4	1	100	2630	1060	154	0.049	0.068	0.011
BC21-52	44.4	45.4	1	100	2520	1030	151	0.064	0.074	0.014
BC21-52	45.4	46.4	1	100	2730	1270	166	0.057	0.079	0.013
BC21-52	46.4	47.1	0.7	100	2440	929	143	0.063	0.063	0.009
BC21-52	47.1	47.6	0.5	100	9230	3520	558	0.182	0.225	0.016
BC21-52	47.6	48.7	1.1	100	2970	1960	181	0.039	0.058	0.012
BC21-52	48.7	49.9	1.2	100	3130	1160	169	0.101	0.087	0.009
BC21-52	49.9	51.05	1.15	100	2220	1050	136	0.054	0.064	0.01
BC21-52	51.05	52.2	1.15	100	3380	1880	203	0.075	0.091	0.013
BC21-52	52.2	52.68	0.48	100	18000	5680	983	0.199	0.206	0.015
BC21-52	52.68	53.55	0.87	100	2230	7980	159	0.043	0.075	0.045
BC21-52	53.55	54.4	0.85	100	615	147	72	0.048	0.079	0.006
BC21-52	54.4	55.1	0.7	100	1370	217	107	0.1	0.064	0.021
BC21-52	55.1	55.4	0.3	100	26400	1130	1190	0.515	0.53	0.013
BC21-52	55.4	56.45	1.05	100	933	2800	57	0.005	0.028	0.01
BC21-53	13	14	1	100	1300	359	114	na	na	na
BC21-53	14	15	1	100	1320	208	93	na	na	na
BC21-53	15	16	1	100	2640	929	161	na	na	na
BC21-53	16	17	1	100	1610	578	117	na	na	na
BC21-53	17	18	1	100	1550	477	108	na	na	na
BC21-53	18	19	1	100	1620	736	111	na	na	na
BC21-53	19	20	1	100	2080	998	168	na	na	na
BC21-53	20	21	1	100	2560	1490	285	na	na	na
BC21-53	21	22	1	100	1560	1230	195	na	na	na
BC21-53	22	23	1	100	1860	1110	169	na	na	na
BC21-53	23	24	1	100	1620	1150	145	na	na	na
BC21-53	24	25	1	100	3440	1690	235	na	na	na
BC21-53	25	26	1	100	3750	3230	217	0.071	0.136	0.032
BC21-53	26	27	1	100	3130	7030	278	0.046	0.065	0.01
BC21-53	27	28.2	1.2	100	4940	4780	329	0.081	0.222	0.037

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-53	28.2	29	0.8	100	6960	4850	477	0.08	0.443	0.024
BC21-53	29	30	1	100	8340	3570	564	0.078	0.465	0.044
BC21-53	30	31	1	100	9210	6980	462	0.316	0.283	0.054
BC21-53	31	32	1	100	6360	7110	540	0.246	0.144	0.024
BC21-53	32	33	1	100	3470	2530	259	0.679	0.151	0.047
BC21-53	33	34.5	1.5	100	2630	9820	151	0.46	0.347	0.104
BC21-53	34.5	35	0.5	100	2940	232000	147	0.253	0.397	0.888
BC21-53	35	35.8	0.8	100	3530	13150	166	0.943	2.96	1.17
BC21-53	35.8	36.8	1	100	3110	5450	269	0.992	0.772	0.026
BC21-53	36.8	37.8	1	100	3020	4970	235	1.255	0.409	0.03
BC21-53	37.8	38.8	1	100	2110	6140	85	0.286	0.431	0.036
BC21-53	38.8	39.8	1	100	5330	12300	115	0.077	0.183	0.014
BC21-53	39.8	40.7	0.9	100	1780	3660	176	0.532	0.505	0.022
BC21-53	40.7	41	0.3	100	5180	4430	402	0.268	0.563	0.109
BC21-53	41	42.2	1.2	100	158	1050	23	<0.005	0.008	0.008
BC21-53	42.2	43.2	1	100	231	325	48	na	na	na
BC21-53	43.2	44.2	1	100	102	235	50	na	na	na
BC21-53	44.2	45.2	1	100	122	184	44	na	na	na
BC21-53	45.2	46.3	1.1	100	161	79	35	na	na	na
BC21-54	3	4	1	100	1510	577	115	na	na	na
BC21-54	4	5	1	100	1365	891	85	na	na	na
BC21-54	5	6	1	100	1505	2290	80	na	na	na
BC21-54	6	7	1	100	2060	7820	128	na	na	na
BC21-54	7	8	1	100	1935	2250	143	na	na	na
BC21-54	8	9	1	100	2620	3460	197	na	na	na
BC21-54	9	10	1	100	1675	1715	121	na	na	na
BC21-54	10	11	1	100	1690	1325	117	na	na	na
BC21-54	11	12	1	100	1570	624	106	na	na	na
BC21-54	12	13	1	100	3020	787	134	na	na	na
BC21-54	13	14	1	100	4540	370	150	na	na	na
BC21-54	14	15.2	1.2	100	3470	551	145	na	na	na
BC21-54	15.2	16.5	1.3	100	4030	552	137	na	na	na
BC21-54	16.5	18	1.5	100	3500	741	206	0.014	0.023	0.005
BC21-54	18	19	1	100	1315	701	143	0.013	0.015	0.003
BC21-54	19	20	1	100	1415	499	107	0.015	0.021	0.003
BC21-54	20.5	22	1.5	100	1380	684	115	0.014	0.022	0.005
BC21-54	22	23	1	100	2150	1200	201	0.034	0.056	0.007
BC21-54	23	24	1	100	2240	1475	159	0.05	0.076	0.01
BC21-54	24	25	1	100	1795	525	135	0.011	0.017	0.004
BC21-54	25	26	1	100	3400	1725	174	0.028	0.044	0.007
BC21-54	26	26.4	0.4	100	16650	6940	606	0.275	0.072	0.007
BC21-54	26.4	27	0.6	100	4230	12450	236	0.19	0.112	0.013
BC21-54	27	27.55	0.55	100	6970	5080	471	0.268	0.134	0.02
BC21-54	27.55	29	1.45	100	3080	36100	210	0.842	1.07	0.028
BC21-54	29	29.6	0.6	100	6880	8590	321	0.519	0.657	0.017
BC21-54	30	31.15	1.15	100	5670	8840	376	0.449	0.413	0.047
BC21-54	31.15	32.15	1	100	1330	2130	66	<0.005	0.025	0.015
BC21-54	32.15	33.2	1	100	37	193	20	na	na	na
BC21-54	33.2	38.2	1.1	100	193	139	44	na	na	na
BC21-55	61	61.85	0.85	100	617	83	65	na	na	na
BC21-55	64.5	65.85	1.35	100	436	84	53	na	na	na
BC21-55	68	69.3	1.3	100	387	291	58	<0.005	0.002	0.002
BC21-55	69.3	70.2	0.9	100	399	4240	21	<0.005	0.02	0.041
BC21-55	70.2	70.7	0.5	100	676	3170	40	<0.005	0.013	0.036
BC21-55	70.7	72	1.3	100	748	1430	29	<0.005	0.011	0.014
BC21-55	72	73	1	100	1090	2100	44	<0.005	0.09	0.043
BC21-55	73	74	1	100	792	2070	42	<0.005	0.015	0.027
BC21-55	74	75	1	100	864	2850	33	<0.005	0.02	0.018
BC21-55	75	76	1	100	818	1410	30	<0.005	0.02	0.007
BC21-55	76	77	1	100	811	1010	36	<0.005	0.024	0.006
BC21-55	77	78	1	100	638	889	31	<0.005	0.017	0.004
BC21-55	78	79.2	1.2	100	258	550	21	<0.005	0.004	0.004
BC21-55	79.2	80.5	1.3	100	234	614	13	<0.005	0.008	0.006
BC21-55	80.5	81.5	1	100	141	81	22	<0.005	0.002	0.002
BC21-56	47.5	48	0.5	100	1490	114	116	<0.005	0.007	0.002
BC21-56	48	49.3	1.3	100	318	91	24	<0.005	0.002	0.003
BC21-56	49.3	50.2	0.9	100	2740	125	219	<0.005	0.007	0.002
BC21-56	50.2	50.8	0.6	100	248	284	26	<0.005	0.008	0.004
BC21-56	50.8	51.8	1	100	3340	146	174	<0.005	0.006	0.002
BC21-56	51.8	52.1	0.3	66	2930	876	338	<0.005	0.022	0.004
BC21-57	79	79.8	0.8	100	535	507	34	<0.005	0.009	0.002
BC21-57	79.8	80.75	0.95	100	646	653	52	<0.005	0.006	0.004

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-57	80.75	81.05	0.3	100	24300	4530	1510	0.255	0.359	0.018
BC21-57	81.05	82.1	1.05	100	356	1720	30	<0.005	0.014	0.009
BC21-57	82.1	83.05	0.95	100	448	361	52	0.008	0.008	0.004
BC21-58	54.7	55.75	1.05	100	536	525	50	<0.005	0.005	0.005
BC21-58	55.75	56.4	0.65	100	131	345	11	<0.005	0.003	0.002
BC21-58	56.4	57.5	1.1	100	563	600	30	<0.005	0.008	0.004
BC21-58	57.5	58.5	1	100	1260	3540	74	0.019	0.019	0.06
BC21-58	58.5	59.6	1.1	100	1650	3790	113	0.204	0.145	0.081
BC21-58	59.6	59.92	0.32	100	7150	2580	383	0.286	0.234	0.073
BC21-58	59.92	60.7	0.78	100	4830	5070	266	0.509	0.543	0.137
BC21-58	60.7	61.7	1	100	420	1200	78	<0.005	0.017	0.022
BC21-58	61.7	62.7	1	100	224	852	66	<0.005	0.005	0.156
BC21-58	62.7	63.7	1	100	223	34	75	<0.005	0.001	0.001
BC21-58	63.7	64.6	0.9	100	445	557	76	<0.005	0.011	0.007
BC21-58	64.6	65.25	0.65	100	1910	4220	130	0.015	0.032	0.012
BC21-58	65.25	66.8	1.55	100	795	1470	59	<0.005	0.045	0.006
BC21-58	66.8	67.7	0.9	100	96	238	16	<0.005	0.001	0.002
BC21-59	92.6	93.5	0.9	100	622	128	66	na	na	na
BC21-59	93.5	94.35	0.85	100	594	71	64	na	na	na
BC21-59	113	113.55	0.55	100	39	143	10	<0.005	0.001	0.001
BC21-59	113.55	113.85	0.3	100	256	496	48	<0.005	0.002	0.001
BC21-59	113.85	114.25	0.4	100	200	102	21	<0.005	0.002	<0.001
BC21-59	114.25	114.9	0.65	100	668	133	60	<0.005	0.004	0.003
BC21-59	114.9	115.83	0.93	100	37	154	10	<0.005	0.001	0.005
BC21-59	115.83	116.13	0.3	100	1360	10750	107	0.861	0.066	0.009
BC21-59	116.13	117.4	1.27	100	351	570	36	0.015	0.015	0.004
BC21-59	117.4	118.8	1.4	100	1230	855	111	<0.005	0.012	0.004
BC21-59	118.8	119.6	0.8	100	161	241	22	<0.005	0.002	0.001
BC21-59	125.65	126.7	1.05	100	103	35	44	na	na	na
BC21-59	126.7	127.8	1.1	100	173	77	45	na	na	na
BC21-59	127.8	128.9	1.1	100	56	40	29	na	na	na
BC21-60	68.15	69.2	1.05	100	542	48	57	na	na	na
BC21-60	74.7	75.3	0.6	100	156	44	52	na	na	na
BC21-60	75.3	76	0.7	100	50	76	13	na	na	na
BC21-60	76	77	1	100	37	63	12	na	na	na
BC21-60	77	77.6	0.6	100	524	92	60	na	na	na
BC21-60	77.6	78.4	0.8	100	42	46	13	na	na	na
BC21-61	84.85	85.7	0.85	100	389	81	58	na	na	na
BC21-61	91.8	92.7	0.9	100	562	71	64	na	na	na
BC21-61	102.2	103	0.8	100	180	197	19	<0.005	0.003	0.001
BC21-61	103	103.36	0.36	100	1780	2540	135	0.295	0.021	0.001
BC21-61	103.36	103.85	0.49	100	448	454	53	0.009	0.008	0.001
BC21-61	103.85	104.65	0.8	100	69	193	15	<0.005	0.001	0.001
BC21-61	104.65	106	1.35	100	280	86	54	0.01	0.012	0.002
BC21-61	106	107.3	1.3	100	377	66	56	0.012	0.011	0.002
BC21-61	110.5	111.8	1.3	100	106	182	43	na	na	na
BC21-61	111.8	113	1.2	100	261	39	61	na	na	na
BC21-61	121.6	123.25	1.65	100	285	54	48	na	na	na
BC21-62	100.1	100.9	0.8	100	90	557	11	<0.005	0.002	0.007
BC21-62	100.9	101.6	0.7	100	536	351	73	0.015	0.013	0.002
BC21-62	101.6	102.05	0.45	100	1820	9050	124	0.159	0.112	0.031
BC21-62	102.05	103	0.95	100	29500	1500	1845	0.035	0.683	0.01
BC21-62	103	104	1	100	28100	4140	1750	0.272	1.95	0.032
BC21-62	104	104.7	0.7	100	21800	22900	1300	0.409	0.717	0.029
BC21-62	104.7	105.05	0.35	100	1350	2370	103	0.011	0.046	0.01
BC21-62	105.05	105.35	0.3	100	27200	14600	1710	0.359	0.221	0.021
BC21-62	105.35	106	0.65	100	407	115	52	0.008	0.007	0.001
BC21-62	106	107	1	100	311	2140	57	0.009	0.008	0.002
BC21-62	107	108	1	100	294	101	49	0.008	0.005	0.002
BC21-63	29.3	30	0.7	100	256	132	42	<0.005	0.001	0.001
BC21-63	30	30.6	0.6	100	171	73	50	<0.005	0.001	0.001
BC21-63	30.6	31.8	1.2	100	1350	402	87	0.018	0.022	0.005
BC21-63	31.8	33	1.2	100	1700	365	100	0.021	0.038	0.002
BC21-63	33	34	1	100	1610	505	102	0.047	0.062	0.009
BC21-63	34	35.3	1.3	100	1090	72	76	<0.005	0.003	0.034
BC21-63	35.3	36.65	1.35	100	1230	124	87	<0.005	0.003	0.001
BC21-63	36.65	37.5	0.85	100	1680	247	101	0.026	0.03	0.007
BC21-63	37.5	38.3	0.8	100	1440	426	99	0.008	0.012	0.004
BC21-63	38.3	39.2	0.9	100	1320	466	92	0.009	0.012	0.003
BC21-63	39.2	40.1	0.9	100	2470	1230	160	0.046	0.057	0.009
BC21-63	40.1	41	0.9	100	2560	1090	159	0.044	0.077	0.006
BC21-63	41	42	1	100	3070	2210	208	0.065	0.073	0.004

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-63	42	42.65	0.65	100	2350	1490	158	0.039	0.052	0.008
BC21-63	42.65	43.05	0.4	100	13800	2530	721	0.102	0.164	0.006
BC21-63	43.05	44	0.95	100	2060	4210	137	0.062	0.079	0.009
BC21-63	44	44.97	0.97	100	813	5770	66	0.008	0.041	0.025
BC21-63	44.97	45.35	0.38	100	9180	6920	653	0.021	0.852	0.021
BC21-63	45.35	45.8	0.45	100	3910	3080	233	0.171	0.077	0.007
BC21-63	45.8	46.1	0.3	100	5590	2190	321	0.111	0.133	0.015
BC21-63	46.1	47.25	1.15	100	2120	1340	141	0.097	0.1	0.005
BC21-63	47.25	48.25	1	100	1920	1500	112	0.081	0.096	0.011
BC21-63	48.25	49.36	1.11	100	2180	1070	133	0.09	0.087	0.011
BC21-63	49.36	49.82	0.46	100	18200	5650	952	0.201	0.732	0.024
BC21-63	49.82	50.35	0.53	100	2180	1230	122	0.064	0.076	0.007
BC21-63	50.35	50.65	0.3	100	5110	8640	299	0.131	0.061	0.024
BC21-63	50.65	51.6	0.95	100	2400	2110	147	0.051	0.065	0.004
BC21-63	51.6	52.65	1.05	100	2200	3670	179	0.005	0.448	0.01
BC21-63	52.65	53.65	1	100	1440	3410	74	0.01	0.01	0.006
BC21-63	53.65	54.75	1.1	100	1810	4010	79	0.008	0.006	0.001
BC21-63	54.75	55.75	1	100	1130	3200	52	<0.005	0.009	0.007
BC21-63	55.75	56.8	1.05	100	315	284	15	<0.005	0.009	0.002
BC21-64	115.45	116.45	1	100	319	1550	25	<0.005	0.011	0.005
BC21-64	116.45	116.9	0.45	100	21400	4050	1165	0.622	0.647	0.029
BC21-64	116.9	117.8	0.9	100	1620	3300	135	0.039	0.339	0.006
BC21-64	117.8	118.6	0.8	100	499	665	32	<0.005	0.017	0.005
BC21-64	121.5	122.8	1.3	100	405	100	60	na	na	na
BC21-64	122.8	124.15	1.35	100	312	81	47	na	na	na
BC21-64	129.2	130.5	1.3	100	353	87	56	na	na	na
BC21-64	132	133	1	100	321	61	49	na	na	na
BC21-64	133	134	1	100	178	109	46	na	na	na
BC21-64	134	135	1	100	451	65	60	na	na	na
BC21-64	135	136	1	100	372	80	55	na	na	na
BC21-64	136	137	1	100	134	30	60	na	na	na
BC21-64	137	138	1	100	112	5	52	na	na	na
BC21-64	138	139	1	100	249	118	62	na	na	na
BC21-64	139	140.1	1.1	100	268	108	53	na	na	na
BC21-64	140.1	141.35	1.25	100	295	76	52	na	na	na
BC21-65	47.7	49.2	1.5	100	581	65	49	na	na	na
BC21-65	49.2	50	0.8	100	77	56	15	na	na	na
BC21-65	50	51	1	100	1370	933	52	na	na	na
BC21-65	51	52	1	100	1100	911	44	na	na	na
BC21-65	52	52.35	0.35	100	1310	1680	55	na	na	na
BC21-65	52.35	53.1	0.75	100	214	408	16	na	na	na
BC21-65	53.1	53.65	0.55	100	557	62	63	na	na	na
BC21-65	53.65	54.1	0.45	100	45	53	17	na	na	na
BC21-65	54.1	55.1	1	100	290	35	63	na	na	na
BC21-65	55.1	56.2	1.1	100	185	102	62	na	na	na
BC21-65	56.2	57.2	1	100	349	83	50	na	na	na
BC21-66	58.2	59.3	1.1	100	326	1050	22	<0.005	0.006	0.007
BC21-66	59.3	60.1	0.8	100	683	2900	54	<0.005	0.035	0.053
BC21-66	60.1	61.1	1	100	1330	5730	62	<0.005	0.015	0.038
BC21-66	61.1	61.8	0.7	100	1900	4220	131	0.009	0.21	0.063
BC21-66	61.8	62.4	0.6	100	34200	7300	1455	0.287	0.699	0.035
BC21-66	62.4	63.7	1.3	100	5060	13800	285	0.119	0.349	0.111
BC21-66	63.7	65	1.3	100	38600	11250	1640	1.01	0.834	0.018
BC21-66	65	66	1	100	38100	22300	1725	0.737	2.43	0.066
BC21-66	66	67	1	100	33300	24300	1430	0.938	1.59	0.042
BC21-66	67	68.5	1.5	100	27100	57400	1570	0.806	6.22	4.42
BC21-66	68.5	69.7	1.2	100	1880	4660	272	<0.005	1.685	0.16
BC21-66	69.7	71	1.3	100	312	907	26	<0.005	0.012	0.01
BC21-67	34	35.2	1.2	100	562	1380	48	<0.005	0.088	0.007
BC21-67	35.2	36	0.8	100	1180	704	81	0.043	0.026	0.002
BC21-67	36	37	1	100	1450	647	110	0.064	0.042	0.002
BC21-67	37	38	1	100	1220	884	99	0.03	0.029	0.003
BC21-67	38	39	1	100	1520	778	117	0.032	0.037	0.003
BC21-67	39	39.55	0.55	100	2830	2450	218	0.069	0.093	0.008
BC21-67	39.55	41	1.45	100	1930	1470	149	0.026	0.053	0.009
BC21-67	41	42	1	100	2110	1260	156	0.06	0.064	0.012
BC21-67	42	43.3	1.3	100	2060	1510	141	0.052	0.069	0.014
BC21-67	43.3	44	0.7	100	4830	2920	257	0.092	0.148	0.022
BC21-67	44	45	1	100	10500	7300	492	0.341	0.317	0.017
BC21-67	45	46.1	1.1	100	8330	5040	409	0.594	0.235	0.025
BC21-67	46.1	46.5	0.4	100	18700	18550	891	0.401	0.348	0.12
BC21-67	46.5	47.4	0.9	100	6060	7320	324	0.121	0.114	0.029

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-67	47.4	47.7	0.3	100	2740	8990	164	0.008	0.031	0.033
BC21-67	47.7	48.6	0.9	100	758	1575	73	<0.005	0.019	0.01
BC21-67	48.6	49.6	1	100	123	167	41	<0.005	0.001	0.003
BC21-67	49.6	50.75	1.15	100	227	67	50	<0.005	<0.001	0.001
BC21-68	72.4	73.4	1	100	57	194	12	na	na	na
BC21-68	73.4	74.4	1	100	467	1210	19	na	na	na
BC21-68	74.4	75.4	1	100	771	1255	17	na	na	na
BC21-68	75.4	76.4	1	100	580	6070	14	na	na	na
BC21-68	76.4	77.4	1	100	743	4340	23	na	na	na
BC21-68	77.4	78.3	0.9	100	600	4370	19	na	na	na
BC21-68	78.3	78.65	0.35	100	544	6540	20	na	na	na
BC21-68	78.65	79.4	0.75	100	1130	6930	33	na	na	na
BC21-68	79.4	80.4	1	100	42	211	13	na	na	na
BC21-69	61.6	62.75	1.15	100	60	185	10	<0.005	0.001	0.004
BC21-69	62.75	63.45	0.7	100	434	1470	30	0.009	0.01	0.041
BC21-69	63.45	64.9	1.45	100	887	523	84	0.081	0.049	0.045
BC21-69	64.9	65.23	0.33	100	8100	3980	470	0.239	0.248	0.038
BC21-69	65.23	65.7	0.47	100	1905	4030	131	0.125	0.084	0.011
BC21-69	65.7	66.1	0.4	100	10650	9690	602	0.326	0.216	0.017
BC21-69	66.1	66.7	0.6	100	4570	3840	281	0.349	0.376	0.046
BC21-69	66.7	67	0.3	100	8470	2520	477	0.012	0.074	0.008
BC21-69	67	67.5	0.5	100	1060	12350	75	<0.005	0.08	0.085
BC21-69	67.5	68.35	0.85	100	156	685	29	<0.005	0.004	0.007
BC21-69	68.35	69.5	1.15	100	115	223	15	<0.005	0.002	0.004
BC21-70	58.25	58.55	0.3	100	563	62	57	na	na	na
BC21-70	58.55	59.6	1.05	100	771	585	35	na	na	na
BC21-70	59.6	60.6	1	100	897	907	33	na	na	na
BC21-70	60.6	61.6	1	100	876	2550	29	na	na	na
BC21-70	61.6	62.6	1	100	867	3420	28	na	na	na
BC21-70	62.6	63.4	0.8	100	139	487	19	na	na	na
BC21-70	63.4	64.4	1	100	99	169	23	na	na	na
BC21-71	81.5	82.4	0.9	100	552	288	93	0.007	0.007	0.003
BC21-71	82.4	83.4	1	100	708	241	98	0.006	0.008	0.002
BC21-71	83.4	84.4	1	100	729	181	91	0.006	0.007	0.003
BC21-71	84.4	85.3	0.9	100	708	481	86	0.009	0.009	0.005
BC21-71	85.3	86.1	0.8	100	132	146	55	<0.005	0.001	0.019
BC21-71	86.1	87.1	1	100	1240	900	129	0.012	0.014	0.007
BC21-71	87.1	87.42	0.32	100	7060	49500	692	0.302	0.099	0.179
BC21-71	87.42	88.1	0.68	100	4110	4140	399	0.127	0.087	0.021
BC21-71	88.1	89.38	1.28	100	492	620	81	<0.005	0.002	0.004
BC21-71	89.38	90	0.62	100	5700	2400	533	0.065	0.075	0.016
BC21-71	90	90.9	0.9	100	601	1080	90	<0.005	<0.001	0.004
BC21-71	90.9	91.55	0.65	100	3150	3420	291	0.056	0.038	0.013
BC21-71	91.55	92	0.45	100	2480	5550	250	0.012	0.127	0.011
BC21-71	92	93.2	1.2	100	1320	2190	102	<0.005	0.015	0.006
BC21-71	93.2	93.7	0.5	100	738	128	74	<0.005	0.001	0.001
BC21-71	93.7	95.2	1.5	100	1340	1410	82	<0.005	0.006	0.006
BC21-71	95.2	96.2	1	100	73	48	13	<0.005	0.001	0.003
BC21-72	65	66.1	1.1	100	1700	781	86	<0.005	0.021	0.005
BC21-72	66.1	67	0.9	100	1630	3180	111	0.014	0.035	0.008
BC21-72	67	68	1	100	868	675	91	0.011	0.006	0.004
BC21-72	68	68.3	0.3	100	4050	578	282	0.024	0.069	0.008
BC21-72	68.3	68.8	0.5	100	189	279	70	<0.005	<0.001	0.006
BC21-72	68.8	69.6	0.8	100	3290	3770	204	0.115	0.142	0.155
BC21-72	69.6	70.7	1.1	100	9930	4660	572	0.113	0.247	0.022
BC21-72	70.7	71	0.3	100	6640	3320	388	0.527	0.245	0.071
BC21-72	71	72	1	100	7440	5640	429	0.51	0.419	0.088
BC21-72	72	73.15	1.15	100	6910	9770	407	0.195	0.208	0.029
BC21-72	73.15	74	0.85	100	12050	10900	684	0.119	0.358	0.036
BC21-72	74	75	1	100	13500	8620	782	0.084	0.41	0.044
BC21-72	75	75.93	0.93	100	8040	5840	447	0.178	0.134	0.034
BC21-72	75.93	76.3	0.37	100	10850	18950	589	0.417	0.325	0.048
BC21-72	76.3	77.2	0.9	100	1660	1790	107	0.063	0.044	0.013
BC21-72	77.2	78.3	1.1	100	1120	3410	53	0.102	0.04	0.015
BC21-73	11.4	13	1.6	100	2280	396	140	0.014	0.018	0.009
BC21-73	13	14	1	100	1900	438	120	0.009	0.013	0.027
BC21-73	14	15	1	100	1560	302	103	0.009	0.013	0.003
BC21-73	15	16	1	100	1850	294	121	0.013	0.018	0.003
BC21-73	16	16.8	0.8	100	1320	175	104	0.009	0.013	0.003
BC21-73	16.8	18	1.2	100	1870	477	120	0.025	0.02	0.004
BC21-73	18	19	1	100	4760	1500	295	0.076	0.097	0.013
BC21-73	19	20	1	100	6740	2030	407	0.062	0.103	0.012

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-73	20	21	1	100	9380	3420	522	0.074	0.132	0.017
BC21-73	21	22	1	100	9110	4570	511	0.084	0.167	0.019
BC21-73	22	23	1	100	8130	4160	435	0.171	0.171	0.023
BC21-73	23	23.5	0.5	100	8690	2290	455	0.199	0.244	0.009
BC21-73	23.5	24.3	0.8	100	2120	718	124	0.035	0.035	0.006
BC21-73	24.3	25.5	1.2	100	871	334	78	<0.005	0.004	0.003
BC21-73	25.5	27	1.5	100	85	283	23	<0.005	0.002	0.002
BC21-73	32.2	33.55	1.35	100	648	2460	53	<0.005	0.015	0.039
BC21-73	33.55	33.85	0.3	100	4040	3390	194	0.036	0.097	0.009
BC21-73	33.85	35	1.15	100	1880	1350	86	0.005	0.023	0.005
BC21-74	20.75	22	1.25	100	1780	380	117	0.01	0.021	0.007
BC21-74	22	23.5	1.5	100	1860	397	114	0.01	0.023	0.008
BC21-74	23.5	24.7	1.2	100	2850	1720	198	0.066	0.094	0.012
BC21-74	24.7	25.6	0.9	100	2050	772	140	0.026	0.038	0.007
BC21-74	25.6	26.8	1.2	100	2060	745	135	0.034	0.041	0.007
BC21-74	26.8	27.65	0.85	100	2890	1210	180	0.05	0.07	0.014
BC21-74	27.65	28.5	0.85	100	1585	406	108	0.017	0.018	0.006
BC21-74	28.5	29.5	1	100	1280	333	90	0.017	0.012	0.006
BC21-74	29.5	30.4	0.9	100	1435	470	135	0.02	0.026	0.002
BC21-74	30.4	32	1.6	100	1270	355	95	0.008	0.008	0.004
BC21-74	32	33	1	100	1100	211	84	<0.005	0.003	0.002
BC21-74	33	34.55	1.55	100	1010	198	82	0.019	0.017	0.002
BC21-74	43.7	45.2	1.5	100	1535	631	116	0.03	0.041	0.005
BC21-74	45.2	46.3	1.1	100	2500	1240	164	0.039	0.063	0.005
BC21-74	46.3	46.6	0.3	100	21500	3500	1205	0.12	0.725	0.012
BC21-74	46.6	47.55	0.95	100	536	493	48	<0.005	0.003	0.001
BC21-75	3.85	5	1.15	100	581	158	102	na	na	na
BC21-75	5	6	1	100	781	211	136	na	na	na
BC21-75	6	7	1	100	946	260	146	na	na	na
BC21-75	7	8	1	100	622	179	135	na	na	na
BC21-75	8	9	1	100	666	120	64	na	na	na
BC21-75	9	10.2	1.2	100	979	245	100	na	na	na
BC21-75	10.2	11.5	1.3	100	747	271	119	na	na	na
BC21-75	11.5	13	1.5	100	376	322	54	na	na	na
BC21-75	13	14	1	100	639	327	59	na	na	na
BC21-75	14	15	1	100	646	312	68	na	na	na
BC21-75	15	16	1	100	970	293	96	na	na	na
BC21-75	16	17	1	100	1040	355	92	na	na	na
BC21-75	17	18	1	100	965	399	86	na	na	na
BC21-75	18	19	1	100	1470	366	90	na	na	na
BC21-75	19	20	1	100	1200	358	72	na	na	na
BC21-75	20	21	1	100	1450	259	112	na	na	na
BC21-75	21	21.9	0.9	100	1130	283	93	na	na	na
BC21-75	21.9	23	1.1	100	1710	447	129	na	na	na
BC21-75	23	23.8	0.8	100	1150	250	92	na	na	na
BC21-75	23.8	24.7	0.9	100	1790	96	102	na	na	na
BC21-75	24.7	26	1.3	100	1440	390	113	0.021	0.021	0.003
BC21-75	26	27	1	100	1640	113	97	0.015	0.011	0.013
BC21-75	27	28	1	100	1680	317	119	0.018	0.021	0.007
BC21-75	28	29.2	1.2	100	1410	316	100	0.013	0.015	0.005
BC21-75	29.2	29.85	0.65	100	1860	115	92	0.005	0.004	0.002
BC21-75	29.85	30.6	0.75	100	1580	407	112	0.015	0.017	0.004
BC21-75	30.6	31.65	1.05	100	1870	658	123	0.039	0.029	0.006
BC21-75	31.65	32.5	0.85	100	2950	265	128	0.008	0.011	<0.001
BC21-75	32.5	33.4	0.9	100	1280	255	84	0.013	0.013	0.003
BC21-75	33.4	34.6	1.2	100	226	143	53	<0.005	0.003	0.004
BC21-75	34.6	35.8	1.2	100	287	119	56	<0.005	0.001	0.001
BC21-75	35.8	37.1	1.3	100	321	24	64	<0.005	0.001	0.001
BC21-75	37.1	38	0.9	100	1430	394	84	0.012	0.016	0.019
BC21-75	38	38.5	0.5	100	518	126	69	<0.005	0.003	0.002
BC21-75	38.5	39.5	1	100	877	486	88	0.006	0.006	0.003
BC21-75	39.5	40.5	1	100	1460	306	97	0.011	0.015	0.005
BC21-75	40.5	41.5	1	100	1360	301	85	0.014	0.018	0.005
BC21-75	41.5	42.7	1.2	100	1870	1090	129	0.015	0.031	0.008
BC21-75	42.7	43.75	1.05	100	2980	1360	173	0.042	0.089	0.016
BC21-75	43.75	44.9	1.15	100	3630	1680	220	0.084	0.1	0.018
BC21-75	44.9	46.1	1.2	100	2690	1890	173	0.071	0.075	0.015
BC21-75	46.1	47.2	1.1	100	1770	1320	127	0.036	0.051	0.009
BC21-75	47.2	48.3	1.1	100	1530	575	105	0.041	0.039	0.005
BC21-75	48.3	49.1	0.8	100	1750	931	121	0.037	0.046	0.006
BC21-75	49.1	50.3	1.2	100	2710	1060	146	0.057	0.08	0.009
BC21-75	50.3	51.25	0.95	100	1445	353	101	0.025	0.032	0.006

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-75	51.25	52.45	1.2	100	1730	582	115	0.043	0.052	0.006
BC21-75	52.45	53	0.55	100	1550	510	108	0.041	0.075	0.003
BC21-75	53	54	1	100	301	264	20	<0.005	0.004	0.003
BC21-75	54	55	1	100	537	367	32	<0.005	0.008	0.004
BC21-75	55	56	1	100	1205	649	59	<0.005	0.035	0.006
BC21-75	56	56.8	0.8	100	149	245	16	<0.005	0.003	0.002
BC21-76	37.9	39.1	1.2	100	523	71	61	<0.005	0.004	0.001
BC21-76	40.25	41.3	1.05	100	287	58	56	<0.005	0.002	0.001
BC21-76	41.3	42.5	1.2	100	226	75	54	<0.005	<0.001	0.002
BC21-76	53.5	54.65	1.15	100	218	74	51	<0.005	0.001	0.001
BC21-76	95.75	96.55	0.8	100	375	114	53	<0.005	0.003	0.002
BC21-76	96.55	97.2	0.65	100	88	536	15	<0.005	0.002	0.002
BC21-76	97.2	97.9	0.7	100	632	1620	30	<0.005	0.009	0.008
BC21-76	97.9	98.9	1	100	309	594	24	<0.005	0.005	0.013
BC21-76	98.9	99.9	1	100	279	1410	20	<0.005	0.007	0.006
BC21-77	24.6	25.9	1.3	100	320	132	44	<0.005	0.004	0.002
BC21-77	25.9	27	1.1	100	240	107	43	<0.005	0.005	0.002
BC21-77	27	28	1	100	245	98	36	0.005	0.005	0.002
BC21-77	28	29	1	100	284	117	41	0.005	0.006	0.001
BC21-77	29	30	1	100	250	140	40	<0.005	0.005	0.002
BC21-77	30	31	1	100	309	195	45	0.007	0.006	0.002
BC21-77	31	32	1	100	243	127	37	0.006	0.006	0.016
BC21-77	32	33	1	100	400	129	48	0.008	0.007	0.002
BC21-77	33	34	1	100	267	137	43	0.006	0.005	0.002
BC21-77	34	35.15	1.15	100	280	177	47	0.006	0.005	0.002
BC21-77	35.15	36.1	0.95	100	1175	240	84	0.011	0.017	0.001
BC21-77	36.1	37.1	1	100	1565	394	104	0.023	0.032	0.002
BC21-77	37.1	38.1	1	100	1500	351	98	0.022	0.027	0.002
BC21-77	38.1	38.85	0.75	100	304	88	43	<0.005	0.003	0.002
BC21-77	38.85	39.85	1	100	133	199	26	<0.005	0.003	0.002
BC21-77	39.85	40.8	0.95	100	187	122	32	<0.005	0.003	0.001
BC21-77	40.8	41.8	1	100	406	151	51	<0.005	0.007	<0.001
BC21-77	41.8	42.8	1	100	367	940	46	0.007	0.011	0.006
BC21-77	42.8	43.65	0.85	100	466	1920	83	<0.005	0.005	0.006
BC21-77	43.65	44.5	0.85	100	2170	1380	127	0.046	0.067	0.009
BC21-77	44.5	45.5	1	100	2210	973	131	0.041	0.051	0.008
BC21-77	45.5	46.5	1	100	2850	1330	168	0.045	0.068	0.018
BC21-77	46.5	47.5	1	100	2320	1510	146	0.039	0.054	0.043
BC21-77	47.5	48.3	0.8	100	2870	2850	180	0.067	0.106	0.051
BC21-77	48.3	49.3	1	100	3340	2650	208	0.091	0.123	0.053
BC21-77	49.3	50.3	1	100	2640	1970	181	0.071	0.098	0.034
BC21-77	50.3	51.3	1	100	1670	1080	129	0.06	0.06	0.022
BC21-77	51.3	52	0.7	100	1630	1010	124	0.048	0.051	0.022
BC21-77	52.5	53.5	1	100	2600	2090	177	0.086	0.104	0.039
BC21-77	53.5	54.5	1	100	2850	1720	183	0.096	0.114	0.024
BC21-77	54.5	55.7	1.2	100	2050	1520	178	0.007	0.257	0.051
BC21-77	55.7	56.4	0.7	100	10050	3650	551	0.108	0.188	0.012
BC21-77	56.4	57.4	1	100	12200	5270	628	0.12	0.234	0.025
BC21-77	57.4	58.4	1	100	8820	4390	466	0.127	0.179	0.016
BC21-77	58.4	59.65	1.25	100	7400	2360	403	0.128	0.202	0.021
BC21-77	59.65	60.5	0.85	100	877	972	110	0.02	0.013	0.008
BC21-77	60.5	61.5	1	100	4870	16400	323	0.219	0.07	0.029
BC21-77	61.5	62.43	0.93	100	4980	13650	322	0.349	0.087	0.019
BC21-77	62.43	63.15	0.72	100	40800	8280	2250	0.405	0.312	0.228
BC21-77	63.15	63.45	0.3	100	7680	17250	403	0.249	0.316	0.052
BC21-77	63.45	64.5	1.05	100	11500	5250	616	0.438	0.268	0.023
BC21-77	64.5	65.57	1.07	100	16500	6440	872	0.469	0.591	0.058
BC21-77	65.57	66	0.43	100	37100	13650	1980	0.422	0.768	0.081
BC21-77	66	66.55	0.55	100	1400	2800	94	<0.005	0.011	0.02
BC21-77	66.55	67.4	0.85	100	618	3110	54	<0.005	0.019	0.046
BC21-77	67.4	68.2	0.8	100	1500	2340	162	0.009	0.153	0.024
BC21-77	68.2	69.65	1.25	100	7400	2360	403	0.128	0.202	0.021
BC21-77	69.65	70.5	0.85	100	877	972	110	0.02	0.013	0.008
BC21-77	70.5	71.5	1	100	4870	16400	323	0.219	0.07	0.029
BC21-77	71.5	72.43	0.93	100	4980	13650	322	0.349	0.087	0.019
BC21-77	72.43	73.15	0.72	100	40800	8280	2250	0.405	0.312	0.228
BC21-77	73.15	73.45	0.3	100	7680	17250	403	0.249	0.316	0.052
BC21-77	73.45	74.5	1.05	100	11500	5250	616	0.438	0.268	0.023
BC21-77	74.5	75.57	1.07	100	16500	6440	872	0.469	0.591	0.058
BC21-77	75.57	76	0.43	100	37100	13650	1980	0.422	0.768	0.081
BC21-77	76	76.55	0.55	100	1400	2800	94	<0.005	0.011	0.02
BC21-77	76.55	77.4	0.85	100	618	3110	54	<0.005	0.019	0.046

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-77	67.4	68.2	0.8	100	1500	2340	162	0.009	0.153	0.024
BC21-77	68.2	69.2	1	100	2530	8930	137	0.006	0.099	0.042
BC21-77	69.2	70.1	0.9	100	376	319	24	<0.005	0.004	0.002
BC21-77	70.1	70.75	0.65	100	162	67	25	<0.005	0.002	0.002
BC21-77	70.75	71.7	0.95	100	266	115	61	0.005	0.003	0.002
BC21-78	60.3	61.3	1	100	457	865	34	0.005	0.025	0.001
BC21-78	61.3	62.3	1	100	832	636	48	<0.005	0.022	0.001
BC21-78	62.3	63.4	1.1	100	920	778	52	<0.005	0.021	0.001
BC21-78	63.4	63.7	0.3	100	913	3060	76	0.135	0.01	0.002
BC21-78	63.7	64.9	1.2	100	1350	872	76	<0.005	0.025	0.002
BC21-78	64.9	66.1	1.2	100	914	662	48	<0.005	0.011	0.002
BC21-78	66.1	67.4	1.3	100	616	1390	36	<0.005	0.01	0.005
BC21-78	67.4	67.7	0.3	100	3560	20900	338	0.395	0.329	0.009
BC21-78	67.7	68.38	0.68	100	1740	2490	140	0.165	0.145	0.023
BC21-78	68.38	68.95	0.57	100	11650	29000	678	0.405	0.316	0.097
BC21-78	68.95	69.75	0.8	100	907	2180	82	0.03	0.022	0.003
BC21-78	69.75	70.15	0.4	100	16450	32500	848	0.104	0.176	0.021
BC21-78	70.15	70.45	0.3	100	1330	3900	85	0.006	0.017	0.004
BC21-78	70.45	71.25	0.8	100	484	561	58	<0.005	0.007	0.001
BC21-78	71.25	72.4	1.15	100	433	1470	29	0.005	0.017	0.005
BC21-78	72.4	73.6	1.2	100	388	522	24	<0.005	0.005	0.002
BC21-78	73.6	73.9	0.3	100	327	429	15	<0.005	0.003	0.003
BC21-78	73.9	74.7	0.8	100	779	1360	33	0.051	0.018	0.006
BC21-78	74.7	75.5	0.8	100	854	3340	42	<0.005	0.157	0.01
BC21-78	75.5	76.5	1	100	651	346	54	<0.005	0.005	0.004
BC21-78	76.5	77.5	1	100	1120	989	59	<0.005	0.023	0.008
BC21-78	77.5	78.5	1	100	1125	1330	67	<0.005	0.017	0.029
BC21-78	78.5	79.5	1	100	1330	721	114	0.096	0.073	0.02
BC21-78	79.5	79.9	0.4	100	1245	2740	110	0.139	0.172	0.028
BC21-78	79.9	80.2	0.3	100	9520	2010	555	0.078	0.201	0.016
BC21-78	80.2	81	0.8	100	506	410	66	<0.005	0.017	0.005
BC21-78	81	81.7	0.7	100	1060	1775	91	0.022	0.037	0.02
BC21-78	81.7	82.7	1	100	5870	1530	244	0.24	0.148	0.021
BC21-78	82.7	83	0.3	100	1240	2480	101	0.104	0.1	0.03
BC21-78	83	83.35	0.35	100	28500	412	845	0.006	0.007	0.01
BC21-78	83.35	84.2	0.85	100	581	372	62	<0.005	0.004	0.004
BC21-78	84.2	85	0.8	100	542	168	66	<0.005	0.003	0.003
BC21-78	85	86.2	1.2	100	815	837	57	<0.005	0.007	0.007
BC21-78	86.2	87.25	1.05	100	617	290	65	0.008	0.005	<0.001
BC21-78	91.75	92.6	0.85	100	147	308	34	<0.005	<0.001	<0.001
BC21-78	92.6	93.6	1	100	480	210	84	<0.005	0.001	0.002
BC21-78	93.6	94.6	1	100	346	197	85	<0.005	0.001	0.002
BC21-78	94.6	95.4	0.8	100	483	258	76	<0.005	0.001	0.002
BC21-78	95.4	96.2	0.8	100	398	600	46	<0.005	0.003	0.001
BC21-78	96.2	96.9	0.7	100	145	285	26	<0.005	<0.001	<0.001
BC21-79	66.8	67.35	0.55	100	189	76	31	na	na	na
BC21-79	84.8	85.8	1	100	385	51	46	na	na	na
BC21-79	85.8	86.8	1	100	29	58	23	na	na	na
BC21-79	86.8	87.75	0.95	100	60	39	41	na	na	na
BC21-80	11.8	13	1.2	100	552	88	54	0.006	0.004	0.002
BC21-80	13	14	1	100	451	112	48	0.005	0.004	0.002
BC21-80	14	15	1	100	812	254	60	0.005	0.008	0.003
BC21-80	15	16.5	1.5	100	1330	525	97	0.012	0.012	0.003
BC21-80	16.5	18	1.5	100	1000	1195	69	0.035	0.049	0.003
BC21-80	18	19	1	100	7120	3380	427	0.078	0.07	0.006
BC21-80	19	20	1	100	3640	1570	223	0.016	0.055	0.007
BC21-80	20	20.9	0.9	100	1830	8180	102	0.112	0.194	0.018
BC21-80	20.9	21.9	1	100	1600	10800	189	0.303	0.215	0.03
BC21-80	21.9	22.8	0.9	100	4470	2450	173	0.181	0.161	0.037
BC21-80	23.9	24.9	1	100	11700	4010	488	0.086	0.048	0.008
BC21-80	24.9	25.9	1	100	7220	1070	301	0.054	0.049	0.017
BC21-80	25.9	27.2	1.3	100	2330	1415	168	0.047	0.062	0.007
BC21-80	27.2	28.1	0.9	100	1510	1205	118	0.054	0.048	0.008
BC21-80	28.7	30	1.3	100	1685	408	115	0.024	0.029	0.008
BC21-80	31	32.2	1.2	100	1900	558	137	0.016	0.021	0.008
BC21-80	32.2	33.2	1	100	1455	209	86	0.006	0.009	0.006
BC21-80	33.2	34.2	1	100	2680	731	146	0.028	0.04	0.007
BC21-80	34.2	35.3	1.1	100	5250	2230	265	0.077	0.131	0.019
BC21-80	35.3	36.4	1.1	100	2820	1925	163	0.055	0.077	0.031
BC21-80	36.4	37.6	1.2	100	4820	2770	235	0.112	0.074	0.018
BC21-80	37.6	38.4	0.8	100	11750	6460	650	0.133	0.266	0.032
BC21-80	38.4	39.4	1	100	2780	1810	158	0.061	0.102	0.007

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-80	39.4	40.3	0.9	100	2580	961	149	0.035	0.046	0.003
BC21-80	40.3	41.1	0.8	100	2260	632	124	0.06	0.05	0.012
BC21-80	41.1	41.5	0.4	100	5370	12550	318	0.163	0.148	0.015
BC21-80	41.5	42	0.5	100	2430	2860	147	0.131	0.129	0.03
BC21-80	42.8	43.3	0.5	100	1685	379	109	0.012	0.021	0.006
BC21-80	44	45.1	1.1	100	1315	276	93	0.015	0.016	0.005
BC21-80	45.1	46.2	1.1	100	155	142	17	<0.005	0.001	<0.001
BC21-80	46.2	46.9	0.7	100	49	54	41	<0.005	<0.001	0.001
BC21-81	38.7	39.4	0.7	100	600	71	72	na	na	na
BC21-81	42.7	43.2	0.5	100	632	100	67	na	na	na
BC21-81	47.4	47.95	0.55	100	1100	182	98	na	na	na
BC21-81	67.5	68.1	0.6	100	121	59	41	na	na	na
BC21-81	69.1	70.15	1.05	100	174	49	58	na	na	na
BC21-82	96	96.9	0.9	100	492	553	18	na	na	na
BC21-82	106.3	106.9	0.6	100	624	71	63	0.01	0.007	0.001
BC21-82	106.9	107.35	0.45	100	169	265	18	<0.005	0.001	0.001
BC21-82	107.35	107.65	0.3	100	2570	582	143	<0.005	0.005	0.005
BC21-82	107.65	108.2	0.55	100	418	368	22	<0.005	0.006	0.001
BC21-82	108.2	108.6	0.4	100	241	167	14	<0.005	0.002	0.001
BC21-82	143.45	144.5	1.05	100	282	69	53	na	na	na
BC21-82	144.5	145.5	1	100	216	127	52	na	na	na
BC21-82	145.5	146.5	1	100	367	77	63	na	na	na
BC21-82	146.5	147.5	1	100	313	54	51	na	na	na
BC21-82	147.5	148.15	0.65	100	337	88	50	na	na	na
BC21-82	151.7	152.7	1	100	70	196	18	<0.005	<0.001	0.002
BC21-82	152.7	153	0.3	100	867	112	199	0.006	0.003	<0.001
BC21-82	153	154	1	100	215	61	61	<0.005	0.001	0.001
BC21-82	154	155.25	1.25	100	352	511	63	na	na	na
BC21-84	33.3	34.5	1.2	100	284	101	40	0.012	0.003	0.004
BC21-84	34.5	35.7	1.2	100	418	81	48	0.006	0.004	0.002
BC21-84	35.7	36.9	1.2	100	280	56	56	<0.005	0.002	<0.001
BC21-84	36.9	38.1	1.2	100	459	37	70	<0.005	0.002	<0.001
BC21-84	38.1	39.6	1.5	100	241	100	49	<0.005	0.004	<0.001
BC21-84	39.6	41	1.4	100	322	121	52	0.005	0.01	<0.001
BC21-84	41	42.5	1.5	100	231	136	41	<0.005	0.005	0.001
BC21-84	42.5	44	1.5	100	266	104	37	0.007	0.008	0.002
BC21-84	44	45.5	1.5	100	184	97	27	0.006	0.006	0.003
BC21-84	45.5	46.8	1.3	100	184	148	35	0.005	0.004	0.002
BC21-84	46.8	48	1.2	100	242	131	35	0.005	0.005	0.002
BC21-84	48	49.1	1.1	100	126	152	20	<0.005	0.003	0.003
BC21-84	49.1	50.3	1.2	100	175	92	53	<0.005	0.001	<0.001
BC21-84	50.3	51.6	1.3	100	146	134	17	<0.005	<0.001	0.002
BC21-84	51.6	52.5	0.9	100	1980	715	72	<0.005	0.024	0.003
BC21-84	52.5	54	1.5	100	2050	1190	132	0.05	0.069	0.006
BC21-84	54	55.33	1.33	100	1370	1580	99	0.025	0.046	0.007
BC21-84	55.33	55.63	0.3	100	8400	3830	496	0.129	0.289	0.015
BC21-84	55.63	56.4	0.77	100	1770	3010	111	0.08	0.061	0.024
BC21-84	56.4	57.6	1.2	100	1460	6910	99	0.013	0.097	0.013
BC21-84	57.6	58.6	1	100	1940	1100	125	0.072	0.096	0.011
BC21-84	58.6	59.6	1	100	1900	818	115	0.034	0.052	0.008
BC21-84	59.6	60.6	1	100	1790	727	116	0.036	0.053	0.008
BC21-84	60.6	61.6	1	100	1910	1130	127	0.038	0.076	0.012
BC21-84	61.6	62.6	1	100	1780	860	139	0.036	0.045	0.009
BC21-84	62.6	63.8	1.2	100	2010	924	143	0.058	0.071	0.018
BC21-84	63.8	65.2	1.4	100	3400	2550	231	0.1	0.128	0.029
BC21-84	65.2	66.3	1.1	100	8520	7710	551	0.323	0.368	0.206
BC21-84	66.3	67.4	1.1	100	8440	5690	534	0.509	1.125	0.097
BC21-84	67.4	68.7	1.3	100	10500	5470	557	0.687	0.336	0.02
BC21-84	68.7	69.2	0.5	100	2490	1470	209	<0.005	0.393	0.004
BC21-84	69.2	70.1	0.9	100	28100	3400	1090	<0.005	0.023	0.01
BC21-84	70.1	70.75	0.65	100	601	286	60	0.008	0.006	<0.001
BC21-84	70.75	71.75	1	100	89	51	18	<0.005	<0.001	0.003
BC21-84	76.7	77.7	1	100	694	80	70	<0.005	0.002	<0.001
BC21-84	82	83.25	1.25	100	379	77	51	na	na	na
BC21-84	83.25	84.6	1.35	100	159	51	37	na	na	na
BC21-84	96.4	97.4	1	100	589	71	67	na	na	na
BC21-85	81.5	82.5	1	100	235	79	38	na	na	na
BC21-85	86.7	87.85	1.15	100	173	98	51	na	na	na
BC21-85	97.2	98.15	0.95	100	388	126	60	na	na	na
BC21-85	99.3	100.4	1.1	100	275	336	16	<0.005	0.004	0.002
BC21-85	100.4	101.55	1.15	100	453	613	16	<0.005	0.002	0.006
BC21-85	106.8	107.8	1	100	590	98	66	<0.005	0.005	<0.001

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-85	116.2	117.25	1.05	100	374	81	54	<0.005	0.004	<0.001
BC21-85	118	119.1	1.1	100	115	165	21	<0.005	0.001	0.003
BC21-85	119.1	120.3	1.2	100	752	850	38	<0.005	0.008	0.005
BC21-85	120.3	120.6	0.3	100	473	272	47	<0.005	0.011	<0.001
BC21-85	120.6	121.6	1	100	913	1250	56	<0.005	0.01	0.004
BC21-85	121.6	122.5	0.9	100	582	881	52	<0.005	0.003	0.002
BC21-85	122.5	122.95	0.45	100	636	468	81	<0.005	0.003	0.002
BC21-85	122.95	123.55	0.6	100	948	1170	98	<0.005	0.007	0.004
BC21-86	12.7	13.6	0.9	100	976	249	73	0.019	0.018	0.01
BC21-86	13.6	14.55	0.95	100	2590	443	162	0.027	0.033	0.014
BC21-86	14.55	15.8	1.25	100	531	141	74	0.005	0.004	0.001
BC21-86	15.8	17	1.2	100	734	167	97	0.007	0.009	0.007
BC21-86	17	18.3	1.3	100	1720	279	110	0.013	0.016	0.018
BC21-86	18.3	19.65	1.35	100	1430	1020	162	0.064	0.054	0.039
BC21-86	19.65	21	1.35	100	1310	2110	112	0.36	0.293	0.211
BC21-86	21.4	22.4	1	100	1050	1840	179	0.205	0.171	0.078
BC21-86	22.4	23.4	1	100	639	897	63	0.048	0.068	0.006
BC21-86	23.4	24.3	0.9	100	413	528	55	0.03	0.035	0.003
BC21-87	53.65	54.85	1.2	100	817	218	72	0.005	0.008	0.001
BC21-87	54.85	56	1.15	100	2690	1840	167	0.051	0.067	0.006
BC21-87	56	57.4	1.4	100	2120	1300	125	0.058	0.052	0.008
BC21-87	57.4	58.4	1	100	2220	1300	128	0.047	0.055	0.013
BC21-87	58.4	58.75	0.35	100	689	283	67	<0.005	0.004	0.004
BC21-87	58.75	59.5	0.75	100	2750	1770	162	0.056	0.076	0.022
BC21-87	59.5	60.6	1.1	100	5480	3710	316	0.16	0.163	0.017
BC21-87	60.6	61.8	1.2	100	2930	2450	193	0.068	0.079	0.008
BC21-87	61.8	62.6	0.8	100	1420	513	103	0.017	0.043	0.007
BC21-87	62.6	63.5	0.9	100	1210	915	82	0.008	0.017	0.001
BC21-87	63.5	64.3	0.8	100	3260	2550	163	0.08	0.067	0.01
BC21-87	64.3	65.3	1	100	14200	9230	605	0.441	0.32	0.025
BC21-87	65.3	66.3	1	100	15850	20700	700	0.473	0.587	0.127
BC21-87	66.3	67.15	0.85	100	17300	5840	756	0.717	0.283	0.023
BC21-87	67.15	67.45	0.3	100	31100	18200	1420	0.693	0.383	0.109
BC21-87	67.45	67.75	0.3	100	965	927	89	0.006	0.005	<0.001
BC21-87	67.75	69.2	1.45	100	411	129	63	<0.005	0.002	0.001
BC21-87	69.2	70.3	1.1	100	752	3430	36	<0.005	0.018	0.089
BC21-87	70.3	71.4	1.1	100	578	5310	19	<0.005	0.007	0.103
BC21-87	71.4	72.6	1.2	100	287	2710	13	<0.005	0.016	0.018
BC21-87	72.6	73.8	1.2	100	123	725	15	<0.005	0.009	0.011
BC21-87	73.8	75	1.2	100	183	809	16	<0.005	0.001	0.001
BC21-87	75	75.8	0.8	100	347	117	57	<0.005	0.002	<0.001
BC21-88	12.8	14.1	1.3	100	300	111	46	na	na	na
BC21-88	14.1	15.4	1.3	100	326	106	40	na	na	na
BC21-88	15.8	16.9	1.1	100	439	63	54	na	na	na
BC21-88	16.9	18	1.1	100	449	112	69	na	na	na
BC21-88	18	19.2	1.2	100	346	90	46	na	na	na
BC21-88	19.2	20.3	1.1	100	159	53	26	na	na	na
BC21-88	20.3	21.4	1.1	100	396	94	56	na	na	na
BC21-88	21.4	22.5	1.1	100	308	129	75	na	na	na
BC21-88	22.5	23.6	1.1	100	299	150	52	na	na	na
BC21-88	23.6	24.7	1.1	100	379	182	55	na	na	na
BC21-88	24.7	25.8	1.1	100	331	206	38	na	na	na
BC21-88	25.8	26.9	1.1	100	316	102	77	na	na	na
BC21-88	26.9	28	1.1	100	421	139	60	na	na	na
BC21-88	28	29	1	100	427	155	62	na	na	na
BC21-88	29	30	1	100	341	118	63	na	na	na
BC21-88	30	31	1	100	334	87	54	na	na	na
BC21-88	31	32	1	100	278	182	38	na	na	na
BC21-88	32	33.4	1.4	100	223	262	32	na	na	na
BC21-88	33.4	35	1.6	100	1500	318	100	na	na	na
BC21-88	71.2	71.5	0.3	100	147	72	32	<0.005	0.001	<0.001
BC21-88	71.5	72	0.5	100	12	10	2	<0.005	<0.001	<0.001
BC21-88	72	72.3	0.3	100	550	232	89	<0.005	<0.001	0.006
BC21-88	72.3	73.5	1.2	100	40	26	8	<0.005	<0.001	<0.001
BC21-89	42.5	44.1	1.6	100	235	67	43	na	na	na
BC21-89	60	61.25	1.25	100	1560	267	110	na	na	na
BC21-89	87.2	88.9	1.7	100	420	207	58	na	na	na
BC21-89	92.7	93.7	1	100	391	90	69	na	na	na
BC21-89	93.7	94.95	1.25	100	1640	169	107	na	na	na
BC21-89	104.8	106	1.2	100	374	95	61	na	na	na
BC21-89	106	107.2	1.2	100	380	116	64	na	na	na
BC21-89	107.2	108.4	1.2	100	462	134	66	na	na	na

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-89	108.4	109.75	1.35	100	497	66	63	na	na	na
BC21-89	129.1	129.85	0.75	100	72	24	46	na	na	na
BC21-89	144.05	145.45	1.4	100	623	94	68	na	na	na
BC21-89	154.2	155.95	1.75	100	485	103	63	na	na	na
BC21-89	174.6	176.2	1.6	100	427	31	58	na	na	na
BC21-90	59.1	60.2	1.1	100	539	89	66	na	na	na
BC21-90	60.2	61.3	1.1	100	512	177	54	na	na	na
BC21-90	61.3	62.4	1.1	100	368	82	65	na	na	na
BC21-90	78.75	79.08	0.33	100	1630	13550	119	<0.005	0.472	0.03
BC21-90	79.08	80.05	0.97	100	34900	13100	1700	0.29	1.16	0.101
BC21-90	80.05	81.1	1.05	100	13450	17550	612	0.332	0.577	0.127
BC21-90	81.1	82.2	1.1	100	11600	9340	610	0.442	0.32	0.292
BC21-90	82.2	83.3	1.1	100	9450	7650	505	0.32	0.441	0.3
BC21-90	83.3	84.4	1.1	100	10200	3250	536	0.465	0.445	0.223
BC21-90	84.4	85.5	1.1	100	13500	10450	674	0.735	0.399	0.141
BC21-90	85.5	86.6	1.1	100	14950	6090	768	0.481	1.03	0.191
BC21-90	86.6	87.6	1	100	13150	3770	691	1.125	0.828	0.13
BC21-90	87.6	88.5	0.9	100	4100	3200	247	0.56	0.343	0.086
BC21-90	88.5	89.5	1	100	2700	1720	181	0.028	0.102	0.023
BC21-90	89.5	90.6	1.1	100	1100	884	94	0.035	0.022	0.033
BC21-90	90.6	91.7	1.1	100	1170	1200	123	0.014	0.055	0.065
BC21-90	91.7	92.7	1	100	1450	792	155	0.73	0.062	0.062
BC21-90	92.7	93.7	1	100	316	236	87	<0.005	<0.001	<0.001
BC21-90	93.7	94.7	1	100	479	1420	85	<0.005	0.003	0.024
BC21-90	94.7	95.6	0.9	100	631	670	90	<0.005	0.01	0.001
BC21-90	95.6	96.8	1.2	100	595	1070	52	<0.005	0.007	<0.001
BC21-90	96.8	98	1.2	100	1190	484	85	<0.005	0.002	<0.001
BC21-90	98	99	1	100	319	323	29	<0.005	0.004	<0.001
BC21-90	99	99.7	0.7	100	104	85	20	<0.005	<0.001	<0.001
BC21-90	104.6	105.7	1.1	100	220	53	56	<0.005	0.001	<0.001
BC21-90	105.7	106.85	1.15	100	112	94	50	<0.005	<0.001	<0.001
BC21-91	39.8	40.8	1	100	72	81	19	<0.005	<0.001	0.001
BC21-91	40.8	41.95	1.15	100	940	228	86	0.007	0.01	0.003
BC21-91	41.95	42.9	0.95	100	2430	1140	157	0.032	0.043	0.009
BC21-91	42.9	43.8	0.9	100	2160	1430	138	0.141	0.069	0.019
BC21-91	43.8	44.7	0.9	100	9140	8930	552	0.403	0.288	0.044
BC21-91	44.7	45.17	0.47	100	7080	4930	439	0.297	0.454	0.064
BC21-91	45.17	45.7	0.53	100	866	4330	62	0.013	0.057	0.013
BC21-92	67.7	68.6	0.9	100	365	104	76	na	na	na
BC21-92	75.9	77	1.1	100	163	74	40	<0.005	<0.001	0.002
BC21-92	83.1	83.9	0.8	100	667	68	69	0.005	0.006	0.001
BC21-92	83.9	84.7	0.8	100	737	105	60	0.005	0.003	<0.001
BC21-92	86.6	87.6	1	100	100	95	14	<0.005	0.004	0.001
BC21-92	87.6	88	0.4	100	3990	606	230	0.088	0.091	0.002
BC21-92	88	88.7	0.7	100	907	532	69	0.011	0.042	0.002
BC21-92	88.7	89.6	0.9	100	277	404	30	<0.005	0.007	0.005
BC21-92	89.6	90.8	1.2	100	360	256	61	0.009	0.009	0.002
BC21-92	90.8	92	1.2	100	112	181	43	<0.005	<0.001	0.001
BC21-93	102.7	103.6	0.9	100	130	126	50	na	na	na
BC21-93	116.8	117.35	0.55	100	1290	112	103	na	na	na
BC21-93	117.8	118.5	0.7	100	341	74	63	na	na	na
BC21-93	119.4	120	0.6	100	70	29	43	na	na	na
BC21-93	120.3	121.1	0.8	100	282	117	49	na	na	na
BC21-93	123.05	124.1	1.05	100	319	103	62	na	na	na
BC21-93	125.8	126.6	0.8	100	648	78	67	na	na	na
BC21-93	127.45	128.05	0.6	100	487	60	56	na	na	na
BC21-93	136.1	136.6	0.5	100	461	74	50	na	na	na
BC21-94	72.1	73.2	1.1	100	258	55	59	na	na	na
BC21-94	76.45	77.85	1.4	100	103	237	15	<0.005	0.002	0.003
BC21-94	77.85	78.15	0.3	100	3020	2550	199	0.065	0.653	0.012
BC21-94	78.15	79.45	1.3	100	636	872	27	<0.005	0.015	0.005
BC21-95	101.4	102	0.6	100	550	158	89	na	na	na
BC21-95	103.6	104.4	0.8	100	329	97	49	na	na	na
BC21-95	108.2	108.7	0.5	100	244	74	54	na	na	na
BC21-95	112.2	113	0.8	100	523	84	61	na	na	na
BC21-95	115.3	116.8	1.5	100	346	95	52	na	na	na
BC21-95	123.05	124.3	1.25	100	410	52	57	na	na	na
BC21-95	125.95	126.95	1	100	414	63	57	na	na	na
BC21-95	126.95	127.95	1	100	338	78	54	na	na	na
BC21-95	127.95	128.95	1	100	410	94	61	na	na	na
BC21-96	47.1	48.2	1.1	100	698	83	72	na	na	na
BC21-96	60	61	1	100	347	59	54	na	na	na

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-96	61	62	1	100	377	79	52	na	na	na
BC21-96	62	63	1	100	406	47	45	na	na	na
BC21-96	63	63.7	0.7	100	580	50	61	na	na	na
BC21-96	91.25	92.25	1	100	223	87	64	na	na	na
BC21-96	102.3	103.3	1	100	440	78	57	na	na	na
BC21-96	111.1	111.95	0.85	100	220	92	54	na	na	na
BC21-96	144.7	145.7	1	100	35	65	37	na	na	na
BC21-96	145.7	146.7	1	100	49	31	38	na	na	na
BC21-96	146.7	147.7	1	100	32	42	38	na	na	na
BC21-96	147.7	148.25	0.55	100	93	24	33	na	na	na
BC21-97	70	70.7	0.7	100	333	119	74	na	na	na
BC21-97	74	74.75	0.75	100	186	81	54	na	na	na
BC21-97	76.8	77.55	0.75	100	319	68	57	na	na	na
BC21-97	78.45	79.35	0.9	100	258	88	52	na	na	na
BC21-97	81.5	81.8	0.3	100	21	17	6	na	na	na
BC21-97	86.15	86.6	0.45	100	582	47	65	na	na	na
BC21-97	89.4	90.5	1.1	100	229	109	51	na	na	na
BC21-97	90.5	91.6	1.1	100	259	100	51	na	na	na
BC21-97	91.6	92.7	1.1	100	289	53	54	na	na	na
BC21-97	92.7	93.9	1.2	100	213	58	50	na	na	na
BC21-98	64.8	66	1.2	100	169	80	33	na	na	na
BC21-98	66	67	1	100	539	97	70	na	na	na
BC21-98	67	68.1	1.1	100	434	103	53	na	na	na
BC21-98	89.55	90	0.45	100	592	67	68	na	na	na
BC21-99	67	67.75	0.75	100	299	68	54	0.014	0.012	0.002
BC21-99	80.8	81.8	1	100	227	103	48	0.013	0.011	0.003
BC21-99	81.8	82.8	1	100	329	65	54	na	na	na
BC21-99	82.8	83.8	1	100	332	77	56	na	na	na
BC21-89	144.05	145.45	1.4	100	623	94	68	na	na	na
BC21-89	154.2	155.95	1.75	100	485	103	63	na	na	na
BC21-89	174.6	176.2	1.6	100	427	31	58	na	na	na
BC21-90	59.1	60.2	1.1	100	539	89	66	na	na	na
BC21-90	60.2	61.3	1.1	100	512	177	54	na	na	na
BC21-90	61.3	62.4	1.1	100	368	82	65	na	na	na
BC21-90	78.75	79.08	0.33	100	1630	13550	119	<0.005	0.472	0.03
BC21-90	79.08	80.05	0.97	100	34900	13100	1700	0.29	1.16	0.101
BC21-90	80.05	81.1	1.05	100	13450	17550	612	0.332	0.577	0.127
BC21-90	81.1	82.2	1.1	100	11600	9340	610	0.442	0.32	0.292
BC21-90	82.2	83.3	1.1	100	9450	7650	505	0.32	0.441	0.3
BC21-90	83.3	84.4	1.1	100	10200	3250	536	0.465	0.445	0.223
BC21-90	84.4	85.5	1.1	100	13500	10450	674	0.735	0.399	0.141
BC21-90	85.5	86.6	1.1	100	14950	6090	768	0.481	1.03	0.191
BC21-90	86.6	87.6	1	100	13150	3770	691	1.125	0.828	0.13
BC21-90	87.6	88.5	0.9	100	4100	3200	247	0.56	0.343	0.086
BC21-90	88.5	89.5	1	100	2700	1720	181	0.028	0.102	0.023
BC21-90	89.5	90.6	1.1	100	1100	884	94	0.035	0.022	0.033
BC21-90	90.6	91.7	1.1	100	1170	1200	123	0.014	0.055	0.065
BC21-90	91.7	92.7	1	100	1450	792	155	0.73	0.062	0.062
BC21-90	92.7	93.7	1	100	316	236	87	<0.005	<0.001	<0.001
BC21-90	93.7	94.7	1	100	479	1420	85	<0.005	0.003	0.024
BC21-90	94.7	95.6	0.9	100	631	670	90	<0.005	0.01	0.001
BC21-90	95.6	96.8	1.2	100	595	1070	52	<0.005	0.007	<0.001
BC21-90	96.8	98	1.2	100	1190	484	85	<0.005	0.002	<0.001
BC21-90	98	99	1	100	319	323	29	<0.005	0.004	<0.001
BC21-90	99	99.7	0.7	100	104	85	20	<0.005	<0.001	<0.001
BC21-90	104.6	105.7	1.1	100	220	53	56	<0.005	0.001	<0.001
BC21-90	105.7	106.85	1.15	100	112	94	50	<0.005	<0.001	<0.001
BC21-91	39.8	40.8	1	100	72	81	19	<0.005	<0.001	0.001
BC21-91	40.8	41.95	1.15	100	940	228	86	0.007	0.01	0.003
BC21-91	41.95	42.9	0.95	100	2430	1140	157	0.032	0.043	0.009
BC21-91	42.9	43.8	0.9	100	2160	1430	138	0.141	0.069	0.019
BC21-91	43.8	44.7	0.9	100	9140	8930	552	0.403	0.288	0.044
BC21-91	44.7	45.17	0.47	100	7080	4930	439	0.297	0.454	0.064
BC21-91	45.17	45.7	0.53	100	866	4330	62	0.013	0.057	0.013
BC21-92	67.7	68.6	0.9	100	365	104	76	na	na	na
BC21-92	75.9	77	1.1	100	163	74	40	<0.005	<0.001	0.002
BC21-92	83.1	83.9	0.8	100	667	68	69	0.005	0.006	0.001
BC21-92	83.9	84.7	0.8	100	737	105	60	0.005	0.003	<0.001
BC21-92	86.6	87.6	1	100	100	95	14	<0.005	0.004	0.001
BC21-92	87.6	88	0.4	100	3990	606	230	0.088	0.091	0.002
BC21-92	88	88.7	0.7	100	907	532	69	0.011	0.042	0.002
BC21-92	88.7	89.6	0.9	100	277	404	30	<0.005	0.007	0.005

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-92	89.6	90.8	1.2	100	360	256	61	0.009	0.009	0.002
BC21-92	90.8	92	1.2	100	112	181	43	<0.005	<0.001	0.001
BC21-93	102.7	103.6	0.9	100	130	126	50	na	na	na
BC21-93	116.8	117.35	0.55	100	1290	112	103	na	na	na
BC21-93	117.8	118.5	0.7	100	341	74	63	na	na	na
BC21-93	119.4	120	0.6	100	70	29	43	na	na	na
BC21-93	120.3	121.1	0.8	100	282	117	49	na	na	na
BC21-93	123.05	124.1	1.05	100	319	103	62	na	na	na
BC21-93	125.8	126.6	0.8	100	648	78	67	na	na	na
BC21-93	127.45	128.05	0.6	100	487	60	56	na	na	na
BC21-93	136.1	136.6	0.5	100	461	74	50	na	na	na
BC21-94	72.1	73.2	1.1	100	258	55	59	na	na	na
BC21-94	76.45	77.85	1.4	100	103	237	15	<0.005	0.002	0.003
BC21-94	77.85	78.15	0.3	100	3020	2550	199	0.065	0.653	0.012
BC21-94	78.15	79.45	1.3	100	636	872	27	<0.005	0.015	0.005
BC21-95	101.4	102	0.6	100	550	158	89	na	na	na
BC21-95	103.6	104.4	0.8	100	329	97	49	na	na	na
BC21-95	108.2	108.7	0.5	100	244	74	54	na	na	na
BC21-95	112.2	113	0.8	100	523	84	61	na	na	na
BC21-95	115.3	116.8	1.5	100	346	95	52	na	na	na
BC21-95	123.05	124.3	1.25	100	410	52	57	na	na	na
BC21-95	125.95	126.95	1	100	414	63	57	na	na	na
BC21-95	126.95	127.95	1	100	338	78	54	na	na	na
BC21-95	127.95	128.95	1	100	410	94	61	na	na	na
BC21-96	47.1	48.2	1.1	100	698	83	72	na	na	na
BC21-96	60	61	1	100	347	59	54	na	na	na
BC21-96	61	62	1	100	377	79	52	na	na	na
BC21-96	62	63	1	100	406	47	45	na	na	na
BC21-96	63	63.7	0.7	100	580	50	61	na	na	na
BC21-96	91.25	92.25	1	100	223	87	64	na	na	na
BC21-96	102.3	103.3	1	100	440	78	57	na	na	na
BC21-96	111.1	111.95	0.85	100	220	92	54	na	na	na
BC21-96	144.7	145.7	1	100	35	65	37	na	na	na
BC21-96	145.7	146.7	1	100	49	31	38	na	na	na
BC21-96	146.7	147.7	1	100	32	42	38	na	na	na
BC21-96	147.7	148.25	0.55	100	93	24	33	na	na	na
BC21-97	70	70.7	0.7	100	333	119	74	na	na	na
BC21-97	74	74.75	0.75	100	186	81	54	na	na	na
BC21-97	76.8	77.55	0.75	100	319	68	57	na	na	na
BC21-97	78.45	79.35	0.9	100	258	88	52	na	na	na
BC21-97	81.5	81.8	0.3	100	21	17	6	na	na	na
BC21-97	86.15	86.6	0.45	100	582	47	65	na	na	na
BC21-97	89.4	90.5	1.1	100	229	109	51	na	na	na
BC21-97	90.5	91.6	1.1	100	259	100	51	na	na	na
BC21-97	91.6	92.7	1.1	100	289	53	54	na	na	na
BC21-97	92.7	93.9	1.2	100	213	58	50	na	na	na
BC21-98	64.8	66	1.2	100	169	80	33	na	na	na
BC21-98	66	67	1	100	539	97	70	na	na	na
BC21-98	67	68.1	1.1	100	434	103	53	na	na	na
BC21-98	89.55	90	0.45	100	592	67	68	na	na	na
BC21-99	67	67.75	0.75	100	299	68	54	0.014	0.012	0.002
BC21-99	80.8	81.8	1	100	227	103	48	0.013	0.011	0.003
BC21-99	81.8	82.8	1	100	329	65	54	na	na	na
BC21-99	82.8	83.8	1	100	332	77	56	na	na	na
BC21-100	103	104.35	1.35	100	318	173	69	na	na	na
BC21-100	137.8	138.15	0.35	100	166	155	38	na	na	na
BC21-100	138.4	138.7	0.3	100	170	664	27	na	na	na
BC21-100	147.4	147.8	0.4	100	39	39	17	na	na	na
BC21-101	41.3	42.5	1.2	100	331	110	52	na	na	na
BC21-101	46.15	47.15	1	100	257	52	56	na	na	na
BC21-101	47.15	48.25	1.1	100	517	100	73	na	na	na
BC21-101	56.2	57.3	1.1	100	449	74	64	na	na	na
BC21-101	60.3	61.6	1.3	100	550	71	66	na	na	na
BC21-101	77	78.35	1.35	100	213	79	46	na	na	na
BC21-101	84.4	85.5	1.1	100	433	65	60	na	na	na
BC21-101	85.5	86.7	1.2	100	691	98	72	na	na	na
BC21-101	100.25	101.3	1.05	100	584	75	69	na	na	na
BC21-101	130.75	131.75	1	100	112	63	53	na	na	na
BC21-101	131.75	132.75	1	100	128	34	53	na	na	na
BC21-101	132.75	134	1.25	100	58	34	43	na	na	na
BC21-102	16.4	17.9	1.5	100	655	70	62	na	na	na
BC21-102	26.7	27.6	0.9	100	267	59	53	na	na	na

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-102	52.25	53.5	1.25	100	308	76	65	na	na	na
BC21-102	95.35	96.75	1.4	100	401	74	67	na	na	na
BC21-102	97.45	98.7	1.25	100	255	85	49	na	na	na
BC21-102	98.7	100.1	1.4	100	287	103	54	na	na	na
BC21-103	18.95	21	2.05	100	307	65	86	na	na	na
BC21-103	21	23	2	100	268	66	51	na	na	na
BC21-103	23	25	2	100	408	100	47	na	na	na
BC21-103	25	26.5	1.5	100	400	94	49	na	na	na
BC21-103	26.5	28	1.5	100	306	89	56	na	na	na
BC21-103	67.2	68.2	1	100	409	1705	34	<0.005	0.003	0.026
BC21-103	68.2	69	0.8	100	19350	35600	1235	0.388	0.186	0.04
BC21-103	69	70.45	1.45	100	463	1190	48	<0.005	0.007	0.009
BC21-104	4.4	5.6	1.2	100	332	65	26	na	na	na
BC21-104	5.6	6.8	1.2	100	430	67	46	na	na	na
BC21-104	6.8	8	1.2	100	732	112	64	na	na	na
BC21-104	8	9	1	100	713	116	67	na	na	na
BC21-104	9	10	1	100	726	119	69	na	na	na
BC21-104	24	25.15	1.15	100	784	186	67	0.007	0.006	0.003
BC21-104	25.15	26.5	1.35	100	135	134	17	<0.005	0.002	0.003
BC21-104	26.5	27.7	1.2	100	90	670	25	<0.005	<0.001	0.005
BC21-104	27.7	28.9	1.2	100	534	22900	80	<0.005	0.006	0.021
BC21-104	28.9	30	1.1	100	1150	32300	112	0.01	0.036	0.027
BC21-104	30	30.8	0.8	100	841	2440	119	<0.005	0.017	0.017
BC21-104	30.8	31.5	0.7	190	37100	16200	2220	0.016	2.33	0.022
BC21-104	31.5	32.13	0.63	100	24600	8500	1410	0.013	0.761	0.147
BC21-104	32.13	32.6	0.47	100	2660	4070	192	0.005	0.162	0.072
BC21-104	32.6	33.5	0.9	100	30600	10050	1735	0.027	0.675	0.021
BC21-104	33.5	34.45	0.95	100	25300	51500	1315	0.417	1.01	0.057
BC21-104	34.45	35.45	1	100	235	233	55	<0.005	0.001	0.004
BC21-104	35.45	36.4	0.95	100	367	2380	63	<0.005	0.008	0.01
BC21-104	36.4	37.8	1.4	100	782	4680	71	<0.005	0.019	0.02
BC21-105	83	84	1	100	372	203	54	0.009	0.009	0.002
BC21-105	84	84.95	0.95	100	583	111	73	<0.005	0.003	0.002
BC21-105	99	100.1	1.1	100	54	73	13	<0.005	0.001	0.003
BC21-105	100.1	100.95	0.85	100	1370	2120	51	<0.005	0.035	0.006
BC21-105	100.95	102	1.05	100	90	109	12	<0.005	0.001	0.001
BC21-105	109	109.9	0.9	100	40	39	12	na	na	na
BC21-105	109.9	110.25	0.35	100	25	74	33	na	na	na
BC21-105	110.25	110.65	0.4	100	24	46	16	na	na	na
BC21-106	97.3	98.05	0.75	100	496	190	60	na	na	na
BC21-106	103.05	103.5	0.45	100	109	141	25	na	na	na
BC21-106	106.7	107.9	1.2	100	370	50	62	na	na	na
BC21-106	111.35	112.7	1.35	100	238	81	58	na	na	na
BC21-106	124.35	124.9	0.55	100	455	73	57	na	na	na
BC21-106	126.25	127.25	1	100	291	2200	25	0.012	0.006	0.008
BC21-106	127.25	128	0.75	100	1920	11050	123	0.01	0.056	0.037
BC21-106	128	128.45	0.45	100	9270	103000	632	1.885	1.1	0.212
BC21-106	128.45	128.75	0.3	100	17350	6850	1015	1.05	0.458	0.011
BC21-106	128.75	129.35	0.6	100	20500	5280	1190	1.2	0.936	0.025
BC21-106	129.35	130.15	0.8	100	17550	11650	1010	0.864	0.295	0.023
BC21-106	130.15	131	0.85	100	9900	3400	599	0.377	0.175	0.025
BC21-106	131	131.7	0.7	100	11850	3890	700	0.978	0.088	0.085
BC21-106	131.7	132	0.3	100	21500	3730	1260	0.374	0.651	0.013
BC21-106	132	132.85	0.85	100	920	2590	47	<0.005	0.022	0.172
BC21-106	132.85	134	1.15	100	357	260	18	0.005	0.012	0.002
BC21-107	39.85	40.35	0.5	100	639	135	58	0.027	0.017	<0.001
BC21-107	42.7	43	0.3	100	126	33	34	<0.005	0.001	<0.001
BC21-107	43	43.4	0.4	100	92	34	56	<0.005	<0.001	<0.001
BC21-107	43.4	44	0.6	100	39	14	9	<0.005	0.001	0.002
BC21-107	56	57	1	100	643	135	70	na	na	na
BC21-107	57	58	1	100	531	97	57	na	na	na
BC21-107	62.45	63.5	1.05	100	275	86	60	na	na	na
BC21-107	63.5	64.25	0.75	100	355	56	67	na	na	na
BC21-107	64.65	65.5	0.85	69	307	50	61	na	na	na
BC21-108	81.1	82.2	1.1	100	489	89	81	na	na	na
BC21-108	82.2	83.5	1.3	100	422	88	63	na	na	na
BC21-108	87.25	87.9	0.65	100	131	45	51	na	na	na
BC21-108	90.2	91.4	1.2	100	397	782	19	<0.005	0.014	0.007
BC21-108	91.4	92.4	1	100	1385	2640	83	0.016	0.016	0.037
BC21-108	92.4	93.27	0.87	100	973	4330	67	<0.005	0.009	0.065
BC21-108	93.27	94	0.73	100	17400	16900	1105	0.831	0.598	0.03
BC21-108	94	94.6	0.6	100	434	829	55	0.028	0.035	0.01

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-108	94.6	95.7	1.1	100	1035	2620	55	<0.005	0.02	0.023
BC21-108	95.7	96.6	0.9	100	131	299	17	<0.005	<0.001	0.005
BC21-108	96.6	97.6	1	100	196	79	46	na	na	na
BC21-108	97.6	98.6	1	100	149	143	57	na	na	na
BC21-108	98.6	99.7	1.1	100	161	88	61	na	na	na
BC21-108	99.7	100.7	1	100	84	57	47	na	na	na
BC21-108	100.7	101.9	1.2	100	88	92	50	na	na	na
BC21-109	111.9	112.65	0.75	100	621	83	67	na	na	na
BC21-109	134.5	135.2	0.7	100	617	157	92	na	na	na
BC21-109	148.5	149.7	1.2	100	416	130	59	na	na	na
BC21-109	149.7	150.8	1.1	100	406	90	44	na	na	na
BC21-109	160.3	161.4	1.1	100	294	154	52	na	na	na
BC21-109	161.4	162.5	1.1	100	183	178	34	na	na	na
BC21-110	3	4.1	1.1	100	267	74	54	na	na	na
BC21-110	4.1	5.2	1.1	100	313	86	54	na	na	na
BC21-110	5.2	6.3	1.1	100	339	85	55	na	na	na
BC21-110	6.3	7.45	1.15	100	332	79	48	na	na	na
BC21-110	9.4	10.6	1.2	100	374	101	43	0.005	0.006	<0.001
BC21-110	10.6	11.8	1.2	100	693	114	71	0.008	0.008	<0.001
BC21-110	11.8	13	1.2	100	724	103	81	0.01	0.006	<0.001
BC21-110	13	14.3	1.3	100	1075	132	77	<0.005	0.003	<0.001
BC21-110	14.3	15.5	1.2	100	1085	144	82	<0.005	0.003	0.001
BC21-110	15.5	17.15	1.65	100	544	77	68	<0.005	0.002	<0.001
BC21-110	39	40.4	1.4	100	405	32	44	<0.005	0.002	<0.001
BC21-110	40.4	41.7	1.3	100	31	57	25	<0.005	<0.001	0.004
BC21-111	4.2	5.4	1.2	100	503	146	68	na	na	na
BC21-111	5.4	6.6	1.2	100	568	128	58	na	na	na
BC21-111	6.6	7.8	1.2	100	470	128	68	na	na	na
BC21-111	7.8	9	1.2	100	257	70	34	na	na	na
BC21-111	9	10	1	100	241	66	34	na	na	na
BC21-111	18.2	19.4	1.2	100	349	52	54	na	na	na
BC21-111	57.3	58.2	0.9	100	564	97	61	na	na	na
BC21-111	58.2	59.15	0.95	100	301	81	59	na	na	na
BC21-111	78.7	79.7	1	100	358	84	53	<0.005	0.005	<0.001
BC21-111	79.7	80.7	1	100	444	63	63	<0.005	0.003	<0.001
BC21-111	80.7	81.9	1.2	100	470	75	56	<0.005	0.001	<0.001
BC21-111	82.7	84	1.3	100	377	69	49	<0.005	0.002	0.001
BC21-111	115.7	116.15	0.45	100	2120	3800	117	0.03	0.063	0.003
BC21-111	116.15	117	0.85	100	558	2210	37	<0.005	0.011	0.002
BC21-111	139.45	140.45	1	100	687	99	74	na	na	na
BC21-112	32.2	33.2	1	100	296	66	48	na	na	na
BC21-112	33.2	34.2	1	100	477	88	55	na	na	na
BC21-112	38	39.7	1.7	100	453	77	60	na	na	na
BC21-112	53.9	55	1.1	100	462	125	55	na	na	na
BC21-112	55	56.15	1.15	100	373	78	50	na	na	na
BC21-112	96.35	98	1.65	100	490	50	54	na	na	na
BC21-112	99.8	100.85	1.05	100	379	98	58	na	na	na
BC21-112	134.05	135.2	1.15	100	595	76	59	na	na	na
BC21-112	135.2	136.3	1.1	100	341	133	60	na	na	na
BC21-112	136.3	137.4	1.1	100	293	67	50	na	na	na
BC21-112	137.4	138.5	1.1	100	851	88	72	na	na	na
BC21-113	1	2	1	100	1640	638	247	0.022	0.025	0.004
BC21-113	2	3	1	100	1455	477	137	0.018	0.02	0.029
BC21-113	3	4	1	100	1290	198	109	0.01	0.011	0.001
BC21-113	4	5	1	100	1520	371	121	0.018	0.017	0.003
BC21-113	5	6	1	100	1935	749	140	0.036	0.043	0.002
BC21-113	6	7	1	100	1860	490	127	0.015	0.018	0.001
BC21-113	7	8	1	100	1450	381	107	0.021	0.016	0.067
BC21-113	8	9	1	100	1400	322	83	0.014	0.016	0.008
BC21-113	9	10	1	100	1850	490	123	0.015	0.016	0.003
BC21-113	10	11	1	100	1220	346	107	0.009	0.011	0.001
BC21-113	11	12	1	100	1850	554	143	0.016	0.016	0.002
BC21-113	12	13	1	100	2300	584	143	0.016	0.018	0.002
BC21-113	13	14	1	100	2320	1045	204	0.049	0.049	0.006
BC21-113	14	15	1	100	2930	1580	362	0.066	0.066	0.007
BC21-113	15	16	1	100	2210	1275	200	0.067	0.075	0.007
BC21-113	16	17	1	100	1765	595	150	0.015	0.019	0.008
BC21-113	17	18	1	100	1915	448	179	0.01	0.015	0.001
BC21-113	18	19	1	100	1090	159	70	<0.005	0.006	0.002
BC21-113	19	20	1	100	2440	1705	180	0.069	0.083	0.015
BC21-113	20	21	1	100	2140	1120	116	0.05	0.063	0.007
BC21-113	21	22	1	100	2250	1205	140	0.055	0.059	0.015

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC21-113	22	23	1	100	2240	597	118	0.019	0.028	0.005
BC21-113	23	24	1	100	2270	455	125	<0.005	0.014	0.003
BC21-113	24	25	1	100	2710	971	157	0.023	0.03	0.004
BC21-113	25	26.3	1.3	100	2120	917	173	0.013	0.021	0.003
BC21-113	26.3	27.7	1.4	100	2340	2070	221	0.078	0.047	0.004
BC21-113	27.7	28.5	0.8	100	7680	5330	334	0.157	0.102	0.01
BC21-113	28.5	28.85	0.35	100	24900	14450	1170	0.288	0.378	0.014
BC21-113	28.85	30.3	1.45	70	2740	3310	168	0.062	0.1	0.011
BC21-113	30.3	31.55	1.25	100	3910	1790	283	0.03	0.287	0.013
BC21-113	31.55	33	1.45	100	1165	992	121	0.053	0.067	0.012
BC21-113	33	34	1	100	1610	1385	216	0.068	0.062	0.01
BC21-113	34	35	1	100	1680	1830	198	0.135	0.13	0.105
BC21-113	35	36	1	100	2070	1800	118	0.149	0.139	0.043
BC21-113	36	37	1	100	4860	1635	272	0.1	0.117	0.035
BC21-113	37	38	1	100	2620	1220	194	0.007	0.039	0.009
BC21-113	38.7	39.9	1.2	100	8400	3400	436	0.087	0.106	0.016
BC21-113	39.9	41.15	1.25	100	8070	3470	305	0.061	0.069	0.016
BC21-113	70.85	71.95	1.1	100	154	87	29	<0.005	0.002	0.001
BC21-114	123.6	124.6	1	100	594	695	26	<0.005	0.031	0.003
BC21-114	124.6	125.7	1.1	100	1395	1160	84	<0.005	0.014	0.011
BC21-114	125.7	126	0.3	100	2250	3140	199	<0.005	0.273	0.031
BC21-114	126	126.42	0.42	100	23500	10650	1410	0.196	0.705	0.02
BC21-114	126.42	127.2	0.78	100	15800	9740	876	0.223	0.271	0.071
BC21-114	127.2	127.85	0.65	100	7160	3060	416	0.243	0.304	0.019
BC21-114	127.85	128.85	1	100	1505	1230	94	<0.005	0.029	0.004
BC21-114	128.85	129.85	1	100	955	810	51	<0.005	0.011	0.004
BC21-114	129.85	130.85	1	100	1250	1230	63	<0.005	0.041	0.006
BC21-114	130.85	131.8	0.95	100	1100	2210	52	<0.005	0.026	0.003
BC21-115	7.1	8.1	1	100	771	115	130	na	na	na
BC21-115	8.1	9.1	1	100	547	78	69	na	na	na
BC21-115	9.1	10.1	1	100	497	134	75	na	na	na
BC21-115	10.1	11.3	1.2	100	430	116	56	na	na	na
BC21-115	32.3	33.8	1.5	100	599	101	45	na	na	na
BC21-115	40.1	41	0.9	100	921	1375	122	na	na	na
BC21-115	41	42.3	1.3	100	743	390	99	na	na	na
BC21-116	77.5	78.75	1.25	100	461	91	58	na	na	na
BC21-116	131.7	132.6	0.9	100	710	88	66	na	na	na
BC21-116	132.6	133.4	0.8	100	825	72	75	na	na	na
BC21-116	142.7	144	1.3	100	403	85	72	na	na	na
BC21-116	154.4	155.3	0.9	100	166	84	61	na	na	na
BC21-116	162.95	164.5	1.55	100	544	104	64	na	na	na
BC21-116	167.6	168.6	1	100	416	168	62	na	na	na
BC21-116	168.6	169.5	0.9	100	336	47	49	na	na	na
BC21-116	171.2	172.7	1.5	100	160	48	43	na	na	na
BC21-116	174.6	176	1.4	100	155	23	30	na	na	na
BC21-117	42	42.85	0.85	75	944	169	79	<0.005	0.005	0.004
BC21-117	42.85	43.6	0.75	100	2280	1020	199	0.023	0.03	0.004
BC21-117	43.6	44.45	0.85	100	2490	1495	203	0.036	0.061	0.006
BC21-117	44.45	45.3	0.85	100	7750	10100	569	0.408	0.136	0.057
BC21-117	45.3	45.6	0.3	100	2140	9100	156	0.112	0.069	0.066
BC21-117	45.6	45.9	0.3	100	12450	8290	806	0.311	0.281	0.032
BC21-117	45.9	46.7	0.8	100	128	272	15	<0.005	0.002	0.002
BC21-117	46.7	47.5	0.8	100	87	382	21	<0.005	0.001	0.002
BC21-117	47.5	48.5	1	100	730	364	87	0.007	0.007	0.001
BC21-117	48.5	49.5	1	100	1025	507	125	na	na	na
BC21-117	49.5	50.5	1	100	1120	834	145	na	na	na
BC21-117	50.5	51.5	1	100	720	657	114	na	na	na
BC21-117	51.5	52.5	1	100	538	290	114	na	na	na
BC21-117	52.5	53.5	1	100	447	221	104	na	na	na
BC21-117	53.5	54.5	1	100	417	153	88	na	na	na
BC21-117	54.5	55.5	1	100	559	315	102	na	na	na
BC21-117	55.5	56.5	1	100	713	236	91	na	na	na
BC21-117	56.5	57.5	1	100	624	219	84	na	na	na
BC21-117	57.5	58.5	1	100	908	338	107	na	na	na
BC21-117	58.5	59.5	1	100	409	347	46	na	na	na
BC21-118	106.4	107.4	1	100	550	73	66	na	na	na
BC21-118	107.4	108.8	1.4	100	126	43	19	na	na	na
BC21-118	108.8	110.15	1.35	100	327	121	57	na	na	na
BC22-02	77.5	78.4	0.9	100	173	563	17	<0.005	0.001	0.002
BC22-02	78.4	78.74	0.34	100	3090	1660	229	<0.005	0.019	0.004
BC22-02	78.74	79.4	0.66	100	15500	2430	1075	0.227	0.491	0.01
BC22-02	79.4	80	0.6	100	13550	2000	938	0.256	0.596	0.006

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
BC22-02	80	81.1	1.1	100	573	470	43	<0.005	0.011	0.002
BC22-02	95.4	96.45	1.05	100	419	310	54	0.01	0.01	0.002
BC22-02	96.45	97.6	1.15	100	982	452	73	<0.005	<0.001	0.004
KS21-30	138.6	139.3	0.7	100	1840	366	113	na	na	na
KS21-30	139.3	140.3	1	100	1120	178	83	na	na	na
KS21-30	140.3	141.3	1	100	1350	164	92	na	na	na
KS21-30	141.3	142.3	1	100	1190	225	92	na	na	na
KS21-30	142.3	143.3	1	100	1040	209	87	na	na	na
KS21-30	143.3	144.3	1	100	1110	116	88	na	na	na
KS21-30	144.3	145.3	1	100	1150	104	88	na	na	na
KS21-30	145.3	146.3	1	100	807	166	75	na	na	na
KS21-30	146.3	147.3	1	100	1210	131	90	na	na	na
KS21-30	147.3	148.3	1	100	1170	106	91	na	na	na
KS21-30	148.3	149.2	0.9	100	726	143	69	na	na	na
KS21-30	244.3	245.35	1.05	100	178	491	20	<0.005	0.003	0.007
KS21-30	245.35	245.65	0.3	100	3580	1720	182	0.122	0.161	0.025
KS21-30	245.65	246.9	1.25	100	971	843	46	0.009	0.017	0.068
KS21-30	246.9	247.22	0.32	100	10750	971	425	0.298	0.241	0.012
KS21-30	247.22	248.1	0.88	100	3670	1220	125	0.01	0.05	0.006
KS21-30	248.1	248.9	0.8	100	2220	1760	66	<0.005	0.036	0.005
KS21-30	248.9	250.05	1.15	100	237	232	15	<0.005	0.003	0.002
KS21-30	250.05	251.6	1.55	100	395	75	61	0.01	0.008	<0.001
KS21-30	296.3	296.65	0.35	100	450	101	53	na	na	na
KS21-31	146.75	147.15	0.4	100	178	54	11	na	na	na
KS21-31	147.15	148.45	1.3	100	384	222	50	na	na	na
KS21-31	148.45	149.6	1.15	100	1680	599	108	na	na	na
KS21-31	149.6	150.8	1.2	100	1280	275	80	na	na	na
KS21-31	150.8	152	1.2	100	1410	430	98	na	na	na
KS21-31	152	153	1	100	1270	164	90	na	na	na
KS21-31	153	154	1	100	1610	188	92	na	na	na
KS21-31	154	155	1	100	1050	184	85	na	na	na
KS21-31	155	156	1	100	35	49	13	na	na	na
KS21-31	213.2	214.8	1.6	100	132	30	40	na	na	na
KS21-31	230.1	231	0.9	100	99	82	46	na	na	na
KS21-31	261.2	262.65	1.45	100	82	43	17	<0.005	0.001	<0.001
KS21-31	262.65	263.1	0.45	100	37	16	11	<0.005	0.001	<0.001
KS21-31	263.1	264.5	1.4	100	56	85	11	<0.005	0.001	<0.001
KS21-31	264.5	264.8	0.3	100	4320	2870	175	0.158	0.178	0.011
KS21-31	264.8	265.8	1	100	946	1435	39	<0.005	0.023	0.024
KS21-31	325.3	326.3	1	100	103	37	22	na	na	na
KS21-31	326.3	326.9	0.6	100	661	101	90	na	na	na
KS21-31	326.9	328	1.1	100	57	36	12	na	na	na
KS21-31	339.65	340.45	0.8	100	400	99	41	na	na	na
KS21-31	340.45	341.7	1.25	100	62	47	11	na	na	na
KS21-31	344.98	345.5	0.52	100	173	63	37	na	na	na
KS21-32	168.7	170.2	1.5	100	962	228	82	na	na	na
KS21-32	269.9	270.2	0.3	100	542	288	126	na	na	na
KS21-32	270.2	271.2	1	100	78	50	19	na	na	na
KS21-32	271.2	272.2	1	100	51	31	16	na	na	na
KS21-32	272.2	273.2	1	100	67	32	18	na	na	na
KS21-32	273.2	274.3	1.1	100	39	51	18	na	na	na
KS21-32	274.3	274.95	0.65	100	111	67	41	na	na	na
KS21-32	274.95	276.1	1.15	100	37	55	13	na	na	na
KS21-32	276.1	277.2	1.1	100	35	38	10	na	na	na
KS21-32	277.2	278.35	1.15	100	40	42	13	na	na	na
KS21-32	278.35	278.9	0.55	100	104	184	80	na	na	na
KS21-32	319.8	320.95	1.15	100	129	174	15	<0.005	0.007	0.001
KS21-32	320.95	321.28	0.33	100	3620	3150	142	0.47	0.104	0.02
KS21-32	321.28	321.63	0.35	100	26500	5760	1000	1.08	0.641	0.044
KS21-32	321.63	321.93	0.3	100	14500	8600	534	1.005	0.423	0.041
KS21-32	321.93	322.9	0.97	100	5300	2100	212	1.45	0.61	0.155
KS21-32	322.9	323.8	0.9	100	9090	2480	358	1.425	0.393	0.038
KS21-32	323.8	324.82	1.02	100	1560	1330	88	0.169	0.14	0.027
KS21-32	324.82	325.25	0.43	100	5110	3400	181	0.555	0.288	0.141
KS21-32	325.25	326.6	1.35	100	2720	2430	74	1.28	0.529	0.273
KS21-32	326.6	327.6	1	100	455	637	15	<0.005	0.014	0.004
KS21-33	158.65	160.4	1.75	100	39	43	23	na	na	na
KS21-33	166	167.25	1.25	100	165	31	48	na	na	na
KS21-33	208.6	209.9	1.3	100	50	37	17	<0.005	0.001	0.001
KS21-33	209.9	211.28	1.38	100	163	150	16	<0.005	0.004	0.001
KS21-33	211.28	211.58	0.3	100	12200	9670	510	1.21	0.43	0.039
KS21-33	211.58	212.55	0.97	100	8190	2510	357	0.832	0.313	0.029

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
KS21-33	212.55	213.4	0.85	100	1900	3180	108	1.08	0.746	0.707
KS21-33	213.4	214.35	0.95	100	2690	1740	134	0.079	0.089	0.027
KS21-33	214.35	215.4	1.05	100	79	259	15	<0.005	0.001	0.005
KS21-33	245.5	246.5	1	100	136	130	38	na	na	na
KS21-33	246.5	247.5	1	100	161	146	44	na	na	na
KS21-33	247.5	248.7	1.2	100	113	108	34	na	na	na
KS21-33	248.7	249.7	1	100	72	63	15	na	na	na
KS21-33	249.7	250.7	1	100	110	85	9	0.007	0.007	0.001
KS21-33	250.7	251	0.3	100	397	648	41	0.012	0.018	0.008
KS21-33	251	252	1	100	241	80	26	0.007	0.004	0.001
KS21-33	254.65	255.75	1.1	100	187	136	43	na	na	na
KS21-34	202.6	203.2	0.6	100	134	28	41	na	na	na
KS21-34	217.3	218.65	1.35	100	140	275	32	na	na	na
KS21-34	222.55	222.85	0.3	100	1280	158	76	0.007	0.017	0.003
KS21-34	228	228.6	0.6	100	40	271	59	<0.005	<0.001	0.001
KS21-34	234.2	234.7	0.5	100	47	328	80	<0.005	0.001	0.001
KS21-34	248.6	249.5	0.9	100	559	1690	27	<0.005	0.014	0.029
KS21-34	249.5	250.38	0.88	100	476	11700	27	<0.005	0.554	0.141
KS21-34	250.38	251.3	0.92	100	32400	5150	1250	1.03	1.21	0.047
KS21-34	251.3	252.45	1.15	100	20200	7150	750	1.62	0.518	0.071
KS21-34	252.45	253	0.55	100	39400	1320	1440	0.804	1.015	0.098
KS21-34	253	254	1	100	19200	7500	739	2.19	0.405	0.244
KS21-34	254	255.2	1.2	100	18000	4230	695	3.37	0.413	0.054
KS21-34	255.2	256.4	1.2	100	13350	8980	546	3.28	0.516	0.125
KS21-34	256.4	257.3	0.9	100	11750	7240	461	1.285	0.468	0.077
KS21-34	257.3	258.18	0.88	100	7630	8360	288	1.055	0.245	0.096
KS21-34	258.18	259.4	1.22	100	18650	4910	736	1.42	0.622	0.03
KS21-34	259.4	260.65	1.25	100	13800	19650	546	0.669	0.375	0.135
KS21-34	260.65	261.75	1.1	100	1870	8040	91	0.158	0.079	0.124
KS21-34	261.75	262.85	1.1	100	1940	2660	55	<0.005	0.031	0.072
KS21-34	262.85	263.95	1.1	100	863	2330	28	<0.005	0.019	0.071
KS21-34	263.95	265.2	1.25	100	884	1900	25	0.006	0.085	0.048
KS21-34	265.2	266.2	1	100	289	324	14	<0.005	0.016	0.007
KS21-35	254.9	256.3	1.4	100	41	195	33	na	na	na
KS21-35	273.2	273.5	0.3	100	59	86	71	na	na	na
KS21-35	280.1	280.4	0.3	100	514	852	292	<0.005	0.002	0.005
KS21-35	301	302	1	100	86	258	9	<0.005	<0.001	0.001
KS21-35	302	302.35	0.35	100	3760	3240	164	0.14	0.074	0.015
KS21-35	302.35	303.05	0.7	100	6920	1680	249	2.42	0.571	0.27
KS21-35	303.05	304.15	1.1	100	1085	449	70	0.031	0.027	0.033
KS21-35	304.15	305.33	1.18	100	1770	1455	101	0.098	0.102	0.057
KS21-35	305.33	305.86	0.53	100	15350	6190	531	0.497	0.334	0.028
KS21-35	305.86	306.2	0.34	100	2670	7880	107	0.146	0.156	0.13
KS21-35	306.2	307.2	1	100	1550	2430	49	0.138	0.065	0.03
KS21-35	307.2	308.2	1	100	1200	959	26	<0.005	0.035	0.002
KS21-35	308.2	309.2	1	100	1050	905	29	0.018	0.034	0.006
KS21-35	309.2	310.2	1	100	277	311	16	<0.005	0.004	0.001
KS21-36	78.7	79.9	1.2	100	241	65	50	na	na	na
KS21-36	243	244	1	100	275	69	37	na	na	na
KS21-36	244	245	1	100	424	39	56	na	na	na
KS21-36	245	246	1	100	382	61	59	na	na	na
KS21-36	246	247	1	100	307	106	57	na	na	na
KS21-36	247	248	1	100	550	55	64	na	na	na
KS21-36	248	249	1	100	597	65	63	na	na	na
KS21-36	249	250	1	100	200	88	48	na	na	na
KS21-36	250	251	1	100	594	73	63	na	na	na
KS21-36	251	252	1	100	279	68	47	na	na	na
KS21-36	252	253	1	100	252	65	46	na	na	na
KS21-36	253	254	1	100	341	37	46	na	na	na
KS21-36	254	254.9	0.9	100	333	58	49	na	na	na
KS21-36	275.8	276.8	1	100	607	75	68	0.012	0.011	0.002
KS21-36	276.8	277.8	1	100	859	156	85	0.016	0.019	0.001
KS21-36	277.8	278.8	1	100	1190	265	92	0.023	0.032	0.001
KS21-36	278.8	279.6	0.8	100	842	201	78	0.017	0.019	<0.001
KS21-36	279.6	280.45	0.85	100	114	140	18	<0.005	0.004	0.001
KS21-36	280.45	280.75	0.3	100	324	484	34	<0.005	0.023	0.001
KS21-36	280.75	281.7	0.95	100	796	48	62	0.018	0.019	0.001
KS21-36	281.7	283	1.3	100	90	69	17	<0.005	0.004	0.001
KS21-36	283	284	1	100	61	44	12	<0.005	0.003	0.001
KS21-36	318	318.75	0.75	100	59	38	7	<0.005	0.004	0.002
KS21-36	318.75	319.35	0.6	100	369	116	62	<0.005	0.004	0.002
KS21-36	319.35	320.5	1.15	100	84	36	8	<0.005	0.004	0.002

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
KS21-37	196.1	196.5	0.4	100	57	174	32	na	na	na
KS21-37	202	203.3	1.3	100	97	102	42	na	na	na
KS21-37	217	217.3	0.3	100	57	100	35	na	na	na
KS21-37	234.6	235.35	0.75	100	107	240	31	<0.005	0.003	0.003
KS21-37	235.35	236.45	1.1	100	612	238	65	0.013	0.01	0.002
KS21-37	236.45	237.6	1.15	100	1015	390	84	0.015	0.02	0.004
KS21-37	237.6	238.6	1	100	458	4540	19	<0.005	0.027	0.082
KS21-37	238.6	239.7	1.1	100	1250	6730	28	<0.005	0.033	0.037
KS21-37	239.7	240.8	1.1	100	1000	3600	25	<0.005	0.023	0.043
KS21-37	240.8	241.9	1.1	100	669	3970	22	0.006	0.036	0.042
KS21-37	241.9	243	1.1	100	602	3810	23	<0.005	0.015	0.065
KS21-37	243	244.2	1.2	100	384	3780	19	<0.005	0.027	0.05
KS21-37	244.2	245.2	1	100	1475	2470	64	<0.005	0.019	0.02
KS21-37	245.2	246.2	1	100	633	1925	31	<0.005	0.033	0.008
KS21-37	246.2	247.2	1	100	658	1515	38	0.006	0.032	0.006
KS21-37	247.2	248.2	1	100	56	321	12	<0.005	0.003	0.004
KS21-37	248.2	249.2	1	100	43	131	12	<0.005	0.002	0.005
KS21-37	249.2	250.2	1	100	164	265	19	<0.005	0.009	0.002
KS21-37	250.2	251.16	0.96	100	303	780	21	<0.005	0.012	0.005
KS21-37	251.16	251.46	0.3	100	20100	13400	756	1.825	1.255	0.099
KS21-37	251.46	252.5	1.04	100	575	1045	24	<0.005	0.018	0.015
KS21-38	218.7	219.4	0.7	100	845	52	65	na	na	na
KS21-38	293.4	294.8	1.4	100	768	124	81	na	na	na
KS21-38	323.7	324.85	1.15	100	114	48	46	na	na	na
KS21-38	348.35	349.3	0.95	100	127	38	37	na	na	na
KS21-38	349.3	350.2	0.9	100	200	75	50	na	na	na
KS21-38	356	357.2	1.2	100	42	61	16	na	na	na
KS21-38	357.2	358.3	1.1	100	83	84	28	na	na	na
KS21-38	360.15	360.5	0.35	100	73	101	34	na	na	na
KS21-38	362.95	363.35	0.4	100	44	160	43	na	na	na
KS21-38	363.35	363.65	0.3	100	125	200	77	na	na	na
KS21-38	381.2	381.5	0.3	100	1600	165	252	0.113	0.035	0.004
KS21-38	386.6	387.6	1	100	488	66	74	0.009	0.007	0.001
KS21-38	397.45	397.95	0.5	100	528	100	67	<0.005	0.004	0.002
KS21-38	397.95	399.1	1.15	100	103	56	11	<0.005	0.004	0.001
KS21-38	399.1	400.45	1.35	100	693	974	41	<0.005	0.006	0.003
KS21-38	400.45	401.45	1	100	29000	9210	1090	1.71	0.971	0.069
KS21-38	401.45	402.37	0.92	100	31600	3120	1180	0.904	0.509	0.044
KS21-38	402.37	403.4	1.03	100	244	1310	15	<0.005	0.007	0.015
KS21-39	133.7	135.5	1.8	100	32	78	24	na	na	na
KS21-39	141	142.4	1.4	100	70	156	25	na	na	na
KS21-39	142.4	143.85	1.45	100	213	138	20	na	na	na
KS21-39	154.05	155.05	1	100	751	91	70	na	na	na
KS21-39	157	158.65	1.65	100	379	276	22	na	na	na
KS21-39	158.65	158.95	0.3	100	13950	1610	537	0.451	0.313	0.03
KS21-39	158.95	159.6	0.65	100	2270	1460	87	0.027	0.053	0.028
KS21-39	159.6	159.9	0.3	100	1450	1515	61	<0.005	0.039	0.039
KS21-39	159.9	160.8	0.9	100	465	278	27	<0.005	0.008	0.004
KS21-39	187.9	188.6	0.7	100	410	175	55	na	na	na
KS21-39	198.7	199.5	0.8	100	407	91	53	na	na	na
KS21-40	117.85	118.5	0.65	100	107	76	19	<0.005	0.003	0.001
KS21-40	118.5	118.8	0.3	100	83	198	32	<0.005	0.002	0.001
KS21-40	118.8	119.8	1	100	99	418	44	<0.005	0.003	0.002
KS21-40	119.8	120.8	1	100	47	124	20	<0.005	0.001	0.001
KS21-40	120.8	121.8	1	100	38	42	15	<0.005	0.001	0.002
KS21-40	121.8	122.1	0.3	100	252	107	56	<0.005	<0.001	0.001
KS21-40	144.2	145.3	1.1	100	223	80	48	<0.005	0.005	0.002
KS21-40	145.3	146.55	1.25	100	367	86	46	0.006	0.004	0.003
KS21-40	153	154.1	1.1	100	221	340	20	<0.005	0.006	0.003
KS21-40	154.1	154.75	0.65	100	37500	5380	1530	0.894	1.215	0.024
KS21-40	154.75	155.45	0.7	100	36000	5470	1435	0.944	1.015	0.4
KS21-40	155.45	156.45	1	100	871	1120	33	<0.005	0.025	0.025
KS21-40	176.1	176.45	0.35	100	304	208	36	0.012	0.009	0.003
KS21-40	176.45	176.75	0.3	100	277	457	57	0.007	0.005	0.003
KS21-40	190.55	191.5	0.95	100	1445	302	97	na	na	na
KS21-40	191.5	192.4	0.9	100	425	161	72	na	na	na
KS21-40	192.4	193.4	1	100	783	146	112	na	na	na
KS21-40	193.4	194.4	1	100	908	687	84	na	na	na
KS21-40	194.4	195.4	1	100	540	105	66	na	na	na
KS21-40	195.4	196.45	1.05	100	478	181	62	na	na	na
KS21-41	224	225.3	1.3	100	143	154	17	<0.005	0.005	0.004
KS21-41	225.3	225.6	0.3	100	4300	1715	178	0.124	0.162	0.018

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
KS21-41	225.6	226.2	0.6	100	1040	986	36	<0.005	0.022	0.008
KS21-41	226.2	227.2	1	100	288	384	21	<0.005	0.005	0.002
KS21-41	261.4	262.35	0.95	100	129	124	39	0.006	0.005	0.002
KS21-41	271.5	271.8	0.3	100	110	109	16	<0.005	<0.001	0.006
KS21-42	282.55	282.9	0.35	100	647	54	55	0.015	0.018	<0.001
KS21-42	282.9	284	1.1	100	92	53	19	<0.005	0.002	0.001
KS21-42	284	285	1	100	311	372	26	0.005	0.014	0.006
KS21-42	285	285.3	0.3	100	2450	1490	121	0.007	0.055	0.043
KS21-42	285.3	286.3	1	100	577	958	29	<0.005	0.012	0.012
KS21-42	286.3	287.3	1	100	118	163	13	<0.005	0.003	0.001
KS21-42	287.3	288.3	1	100	1040	481	47	<0.005	0.013	0.002
KS21-42	288.3	288.6	0.3	100	4990	6420	213	0.042	0.188	0.051
KS21-42	288.6	289.8	1.2	100	1160	1605	52	<0.005	0.019	0.012
KS21-42	289.8	290.9	1.1	100	329	57	45	0.011	0.009	0.002
KS21-42	290.9	291.8	0.9	100	1120	1005	53	0.009	0.018	0.01
KS21-42	291.8	292.53	0.73	100	391	518	26	<0.005	0.009	0.006
KS21-42	292.53	292.83	0.3	100	5540	1535	242	0.239	0.147	0.019
KS21-42	292.83	293.7	0.87	100	1945	2390	85	0.014	0.053	0.033
KS21-42	293.7	295	1.3	100	301	242	21	0.013	0.006	0.005
KS21-42	295	296.4	1.4	100	147	226	14	<0.005	0.004	0.001
KS21-42	296.4	297.5	1.1	100	363	308	22	<0.005	0.007	0.002
KS21-43	372	372.5	0.5	100	1005	403	125	0.043	0.019	0.003
KS21-43	372.5	373.5	1	100	1060	422	100	0.021	0.009	0.002
KS21-43	373.5	374.5	1	100	894	206	93	0.006	0.003	0.001
KS21-43	374.5	375.55	1.05	100	862	152	83	0.009	0.006	0.001
KS21-43	375.55	376.6	1.05	100	2530	1300	164	0.026	0.042	0.011
KS21-43	376.6	377.6	1	100	1955	1340	182	0.035	0.044	0.009
KS21-43	377.6	378.35	0.75	100	1050	330	95	<0.005	0.012	0.004
KS21-43	391.7	393.08	1.38	100	43	68	12	<0.005	0.001	0.001
KS21-43	393.08	393.38	0.3	100	16700	9300	571	0.961	0.521	0.038
KS21-43	393.38	394.7	1.32	100	604	1740	26	<0.005	0.032	0.027
KS21-44	283.15	284.55	1.4	100	126	60	43	na	na	na
KS21-44	301.1	302.1	1	100	902	79	74	na	na	na
KS21-44	302.1	303.3	1.2	100	854	96	76	na	na	na
KS21-44	347.7	348	0.3	100	444	223	162	na	na	na
KS21-44	348	348.6	0.6	100	118	23	30	na	na	na
KS21-44	380.25	381	0.75	100	98	113	19	na	na	na
KS21-44	398.4	399	0.6	100	145	45	33	na	na	na
KS21-44	399	399.55	0.55	100	252	18	33	na	na	na
KS21-44	399.55	401.1	1.55	100	45	55	20	na	na	na
KS21-44	401.1	401.7	0.6	100	87	84	36	na	na	na
KS21-44	401.7	402.5	0.8	100	680	94	74	na	na	na
KS21-44	402.5	403.7	1.2	100	229	8	41	na	na	na
KS21-44	403.7	405	1.3	100	440	50	59	na	na	na
KS21-44	405	406	1	100	766	34	83	na	na	na
KS21-44	406	407	1	100	1030	62	103	na	na	na
KS21-44	407	408	1	100	926	40	93	na	na	na
KS21-44	408	409	1	100	596	89	71	na	na	na
KS21-44	409	410	1	100	772	118	79	na	na	na
KS21-44	410	410.8	0.8	100	1100	284	92	na	na	na
KS21-44	410.8	412	1.2	100	172	113	42	na	na	na
KS21-44	412	413.05	1.05	100	31	152	36	na	na	na
KS21-44	413.05	413.45	0.4	100	861	258	77	na	na	na
KS21-44	413.45	415	1.55	100	357	314	43	na	na	na
KS21-44	448.9	450.4	1.5	100	173	251	32	na	na	na
TC21-04	85.35	86.38	1.03	100	163	879	14	<0.005	0.004	0.002
TC21-04	86.38	87.34	0.96	100	9900	9020	581	0.533	0.404	0.091
TC21-04	87.34	88.64	1.3	100	20200	3410	1160	0.61	0.604	0.131
TC21-04	88.64	89.25	0.61	100	10800	20700	656	0.312	0.417	0.052
TC21-04	89.25	90.15	0.9	100	3270	3720	203	0.141	0.162	0.025
TC21-04	90.15	91.15	1	100	3090	1990	194	0.109	0.124	0.028
TC21-04	91.15	92.1	0.95	100	3380	1800	205	0.112	0.13	0.029
TC21-04	92.1	93.1	1	100	2820	1740	158	0.08	0.078	0.024
TC21-04	93.1	94.35	1.25	100	2790	1340	161	0.047	0.052	0.011
TC21-04	94.35	95.3	0.95	100	1580	592	98	0.014	0.031	0.008
TC21-04	95.3	96.1	0.8	100	1610	737	97	0.02	0.036	0.01
TC21-04	96.1	97.15	1.05	100	2010	1280	143	0.042	0.051	0.009
TC21-04	97.15	98.25	1.1	100	2250	800	136	0.057	0.051	0.014
TC21-04	98.25	99.55	1.3	100	1315	744	84	0.017	0.032	0.005
TC21-04	99.55	100.15	0.6	100	3810	4280	220	<0.005	0.059	0.007
TC21-04	100.15	101.15	1	100	643	697	41	<0.005	0.008	0.02
TC21-04	113	114	1	100	247	492	18	<0.005	0.005	0.002

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
TC21-04	114	115.3	1.3	100	3350	5290	300	0.062	1.17	0.139
TC21-04	115.3	116.2	0.9	100	14100	2490	805	0.356	0.441	0.026
TC21-04	116.2	116.95	0.75	100	13500	13300	791	0.241	0.433	0.02
TC21-04	116.95	118	1.05	100	207	1290	17	<0.005	0.006	0.006
TC21-04	122.2	123.23	1.03	100	18	27	35	na	na	na
TC21-04	124.8	126.2	1.4	100	95	36	41	na	na	na
TC21-04	126.2	127.6	1.4	100	38	55	42	na	na	na
TC21-04	129	130	1	100	16	13	21	na	na	na
TC21-04	130	131	1	100	13	12	31	na	na	na
TC21-04	150.55	151.7	1.15	100	151	93	46	na	na	na
TC21-04	151.7	152.8	1.1	100	54	52	30	na	na	na
TC21-04	152.8	154.05	1.25	100	523	97	60	na	na	na
TC21-05	53.9	55.2	1.3	100	64	137	39	na	na	na
TC21-05	55.2	56	0.8	100	109	56	16	na	na	na
TC21-05	59.7	60.8	1.1	100	187	65	41	na	na	na
TC21-05	60.8	61.9	1.1	100	64	76	35	na	na	na
TC21-05	61.9	63	1.1	100	549	78	58	na	na	na
TC21-05	63	64	1	100	438	115	52	na	na	na
TC21-05	64	65	1	100	80	141	40	na	na	na
TC21-05	65	66	1	100	64	70	31	na	na	na
TC21-05	66	67	1	100	18	88	35	na	na	na
TC21-05	67	68.2	1.2	100	8	29	32	na	na	na
TC21-05	68.2	69.4	1.2	100	18	48	35	na	na	na
TC21-05	69.4	70.6	1.2	100	57	71	38	na	na	na
TC21-05	88.75	89.75	1	100	50	54	39	na	na	na
TC21-05	89.75	90.75	1	100	73	57	51	na	na	na
TC21-05	90.75	91.75	1	100	187	79	47	na	na	na
TC21-05	91.75	92.75	1	100	281	82	48	na	na	na
TC21-05	92.75	93.75	1	100	1340	64	99	na	na	na
TC21-05	93.75	94.75	1	100	359	44	46	na	na	na
TC21-05	94.75	95.75	1	100	16	321	66	na	na	na
TC21-05	95.75	96.75	1	100	12	30	35	na	na	na
TC21-05	96.75	97.75	1	100	442	66	55	na	na	na
TC21-05	97.75	98.75	1	100	662	124	74	na	na	na
TC21-05	98.75	100	1.25	100	697	38	58	na	na	na
TC21-05	100	101.25	1.25	100	512	59	53	na	na	na
TC21-06	70.35	71.65	1.3	100	1420	170	65	0.027	0.038	0.019
TC21-06	71.65	73.05	1.4	100	1740	219	79	0.022	0.021	0.015
TC21-06	73.05	73.6	0.55	100	1410	621	110	0.056	0.081	0.036
TC21-06	73.6	74.6	1	100	1980	1070	128	0.026	0.03	0.004
TC21-06	74.6	75.6	1	100	2140	1050	117	0.053	0.052	0.01
TC21-06	75.6	76.5	0.9	100	1680	710	97	0.026	0.021	0.004
TC21-06	76.5	77.4	0.9	100	1600	2230	119	0.155	0.056	0.012
TC21-06	77.4	77.7	0.3	100	2050	13000	166	0.089	0.036	0.02
TC21-06	77.7	78.5	0.8	100	1450	1140	85	<0.005	0.035	0.006
TC21-06	78.5	79.4	0.9	100	740	1680	70	na	na	na
TC21-06	79.4	80.5	1.1	100	1330	1280	84	na	na	na
TC21-06	80.5	81.7	1.2	100	177	253	37	na	na	na
TC21-06	81.7	82.9	1.2	100	247	219	42	na	na	na
TC21-06	82.9	84.1	1.2	100	187	128	26	na	na	na
TC21-06	84.1	85.4	1.3	100	1050	244	84	na	na	na
TC21-06	85.4	86.4	1	100	930	133	83	na	na	na
TC21-06	86.4	87.3	0.9	100	778	964	74	na	na	na
TC21-06	103.6	105.65	2.05	100	53	70	40	na	na	na
TC21-06	115.3	115.65	0.35	100	10350	4910	615	0.192	0.31	0.018
TC21-06	115.65	116.65	1	100	1425	1605	43	<0.005	0.02	0.006
TC21-07	18.9	20.9	2	100	36	19	37	na	na	na
TC21-07	20.9	22.9	2	100	49	27	39	na	na	na
TC21-07	25.3	27.5	2.2	100	32	16	22	na	na	na
TC21-07	27.5	29.7	2.2	100	42	38	43	na	na	na
TC21-07	29.7	31.9	2.2	100	47	23	40	na	na	na
TC21-07	31.9	34	2.1	100	40	19	34	na	na	na
TC21-07	94.2	95.6	1.4	100	46	25	37	na	na	na
TC21-07	116.4	117.8	1.4	100	564	124	63	na	na	na
TC21-07	149.5	151.5	2	100	146	36	48	<0.005	0.001	0.003
TC21-07	151.5	152.4	0.9	100	189	92	93	<0.005	0.001	0.003
TC21-07	157.7	158.5	0.8	100	199	68	41	na	na	na
TC21-07	172.25	174.3	2.05	100	17	22	35	na	na	na
TC21-07	174.3	176.3	2	100	15	24	37	na	na	na
TC21-07	176.3	177.5	1.2	100	14	15	26	na	na	na
TC21-08	69.75	72.4	2.65	100	126	107	35	na	na	na
TC21-08	73.35	73.75	0.4	100	665	412	76	na	na	na

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
TC21-08	73.75	75.4	1.65	100	69	44	31	na	na	na
TC21-08	109.2	110.2	1	100	647	333	73	na	na	na
TC21-08	110.2	111.2	1	100	375	206	42	na	na	na
TC21-08	111.2	112.2	1	100	815	256	70	na	na	na
TC21-08	112.2	113.2	1	100	997	546	92	na	na	na
TC21-08	113.2	114.1	0.9	100	627	421	64	na	na	na
TC21-08	114.1	115.1	1	100	469	350	50	na	na	na
TC21-08	135.95	136.9	0.95	100	128	122	40	na	na	na
TC21-09	34.3	35.3	1	100	134	363	22	<0.005	0.004	0.001
TC21-09	35.3	36.3	1	100	133	154	47	<0.005	<0.001	<0.001
TC21-09	36.3	37.3	1	100	78	180	44	<0.005	<0.001	<0.001
TC21-09	37.3	38.3	1	100	460	180	52	<0.005	0.005	0.001
TC21-09	38.3	39	0.7	100	374	1050	51	<0.005	0.005	0.001
TC21-09	39	40	1	100	576	835	69	0.014	0.015	0.004
TC21-09	40	41	1	100	614	257	67	0.006	0.004	0.001
TC21-09	41	42	1	100	1010	483	86	0.018	0.017	0.003
TC21-09	42	43	1	100	1230	416	95	0.026	0.022	0.003
TC21-09	43	44	1	100	1470	567	121	0.037	0.04	0.005
TC21-09	44	45	1	100	2220	891	182	0.073	0.071	0.015
TC21-09	45	46	1	100	2590	2630	201	0.081	0.102	0.022
TC21-09	46	47	1	100	1685	1230	140	0.032	0.041	0.007
TC21-09	47	48	1	100	1005	628	99	0.016	0.019	0.003
TC21-09	48	48.8	0.8	100	1330	901	127	0.039	0.04	0.012
TC21-09	48.8	49.3	0.5	100	738	513	78	0.011	0.017	0.003
TC21-09	49.3	50.4	1.1	100	399	484	26	<0.005	0.008	0.002
TC21-09	50.4	50.8	0.4	100	1735	1200	124	<0.005	0.008	0.001
TC21-09	56.8	59.1	2.3	100	118	48	35	<0.005	0.001	0.001
TC21-09	59.1	60.6	1.5	100	187	95	42	<0.005	0.002	0.001
TC21-10	42.9	44.25	1.35	100	14	24	36	na	na	na
TC21-10	44.25	45.25	1	100	10	27	35	na	na	na
TC21-10	63.2	64.25	1.05	100	209	50	45	<0.005	0.003	0.001
TC21-11	56	57	1	100	297	408	35	<0.005	0.01	0.001
TC21-11	57	57.8	0.8	100	3830	1200	266	1.08	0.137	0.044
TC21-11	57.8	59.1	1.3	100	2160	1330	162	0.298	0.095	0.031
TC21-11	59.1	60.4	1.3	100	2220	2390	175	0.206	0.14	0.025
TC21-11	60.4	61.5	1.1	100	574	1270	70	<0.005	0.023	0.004
TC21-11	61.5	62.6	1.1	100	460	1010	57	<0.005	0.015	0.002
TC21-11	62.6	63.7	1.1	100	295	494	47	<0.005	0.006	0.002
TC21-11	63.7	65	1.3	100	734	276	75	0.019	0.016	0.001
TC21-11	65	66.15	1.15	100	2280	3630	182	0.008	0.143	0.007
TC21-11	66.15	68.2	2.05	100	108	279	19	<0.005	0.003	0.002
TC21-12	23.45	23.75	0.3	100	3340	248	230	<0.005	0.045	0.005
TC21-12	23.75	24.5	0.75	100	433	1120	37	<0.005	0.009	0.005
TC21-12	54	55	1	100	79	104	42	<0.005	0.001	<0.001
TC21-12	55	56	1	100	146	263	50	<0.005	0.005	0.001
TC21-12	56	57	1	100	66	186	40	<0.005	<0.001	0.001
TC21-12	57	58	1	100	523	1470	72	0.006	0.017	0.004
TC21-12	58	59.2	1.2	100	1515	593	133	0.101	0.027	0.003
TC21-12	59.2	60.2	1	100	932	109	71	0.007	0.006	0.005
TC21-12	60.2	61.3	1.1	100	1050	131	69	0.02	0.012	0.003
TC21-12	61.3	62.3	1	100	2620	1040	168	0.039	0.079	0.02
TC21-12	62.3	63.3	1	100	2340	1330	168	0.043	0.037	0.008
TC21-12	63.3	64.3	1	100	2320	696	151	0.052	0.04	0.012
TC21-12	64.3	65.8	1.5	100	1240	462	105	<0.005	0.029	0.001
TC21-12	65.8	66.95	1.15	100	1100	571	80	0.006	0.011	0.004
TC21-12	66.95	67.25	0.3	100	8410	1370	488	0.026	0.146	0.002
TC21-12	67.25	68	0.75	100	258	385	37	<0.005	0.001	0.001
TC21-12	73	73.85	0.85	100	420	68	48	<0.005	0.003	<0.001
TC21-13	20.2	21.2	1	100	23	14	37	na	na	na
TC21-13	21.2	22.2	1	100	41	16	39	na	na	na
TC21-13	22.2	23.2	1	100	40	15	35	na	na	na
TC21-13	23.2	24.2	1	100	21	15	35	na	na	na
TC21-13	24.2	25.2	1	100	10	8	24	na	na	na
TC21-13	54.2	55.4	1.2	100	23	17	36	na	na	na
TC21-13	55.4	56.6	1.2	100	22	15	39	na	na	na
TC21-13	56.6	57.8	1.2	100	34	18	42	na	na	na
TC21-13	57.8	59	1.2	100	29	13	43	na	na	na
TC21-13	59	60.2	1.2	100	22	49	46	na	na	na
TC21-13	60.2	61.4	1.2	100	23	54	44	na	na	na
TC21-13	61.4	62.6	1.2	100	21	29	35	na	na	na
TC21-13	62.6	63.7	1.1	100	19	19	35	na	na	na
TC21-13	66	67	1	100	39	29	15	na	na	na

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
TC21-13	67	68	1	100	35	24	14	na	na	na
TC21-13	68	69.3	1.3	100	50	33	13	na	na	na
TC21-13	74.95	76.5	1.55	100	586	99	63	na	na	na
TC21-13	85.2	86.65	1.45	100	12	86	23	na	na	na
TC21-13	94.2	95.2	1	100	21	33	37	na	na	na
TC21-13	95.2	96.2	1	100	31	32	38	na	na	na
TC21-13	96.2	97.2	1	100	26	39	39	na	na	na
TC21-13	97.2	98.2	1	100	32	44	39	na	na	na
TC21-13	98.2	99.2	1	100	24	25	32	na	na	na
TC21-13	99.2	100.5	1.3	100	18	55	34	na	na	na
TC21-13	100.5	101.7	1.2	100	26	34	35	na	na	na
TC21-13	107.8	108.8	1	100	291	198	31	<0.005	0.003	0.003
TC21-13	108.8	110	1.2	100	1460	492	118	0.014	0.039	0.009
TC21-13	110	111.2	1.2	100	737	89	74	<0.005	0.003	0.002
TC21-13	111.2	112.45	1.25	100	443	318	73	0.007	0.002	0.001
TC21-13	112.45	114.15	1.7	100	329	510	70	<0.005	0.002	0.005
TC21-14	127.8	128.8	1	100	520	69	64	na	na	na
TC21-14	152.8	153.8	1	100	18	22	35	na	na	na
TC21-14	153.8	154.7	0.9	100	15	14	32	na	na	na
TC21-14	161.8	163	1.2	100	17	13	44	na	na	na
TC21-14	163	164.25	1.25	100	21	17	42	na	na	na
TC21-15	183.4	184.4	1	100	175	73	36	na	na	na
TC21-15	184.4	185.4	1	100	281	133	47	na	na	na
TC21-15	185.4	186.4	1	100	1100	83	68	na	na	na
TC21-15	186.4	187.4	1	100	1280	68	75	na	na	na
TC21-15	187.4	188.5	1.1	100	499	103	51	na	na	na
TC21-15	188.5	189.6	1.1	100	461	47	51	na	na	na
TC21-15	208.05	209.1	1.05	100	28	33	33	na	na	na
TC21-15	209.1	210.2	1.1	100	20	52	42	na	na	na
TC21-15	210.2	211.3	1.1	100	15	15	33	na	na	na
TC21-15	211.3	212.55	1.25	100	24	25	34	na	na	na
TC21-15	214.45	215.45	1	100	488	607	28	<0.005	0.009	0.002
TC21-15	215.45	216	0.55	100	2440	2250	126	0.107	0.104	0.025
TC21-15	216	216.9	0.9	100	3640	1930	215	0.177	0.157	0.027
TC21-15	216.9	217.8	0.9	100	4250	2100	281	0.163	0.155	0.036
TC21-15	217.8	218.8	1	100	3910	2750	249	0.12	0.287	0.038
TC21-15	218.8	219.8	1	100	3660	3250	237	0.117	0.095	0.042
TC21-15	219.8	220.8	1	100	3310	3440	211	0.122	0.108	0.035
TC21-15	220.8	221.7	0.9	100	2310	2790	165	0.14	0.109	0.03
TC21-15	221.7	222.55	0.85	100	3350	3610	234	0.139	0.114	0.031
TC21-15	222.55	222.88	0.33	100	13650	6940	900	0.107	0.072	0.014
TC21-15	222.88	223.6	0.72	100	2800	2210	207	0.097	0.086	0.035
TC21-15	223.6	224.25	0.65	100	1900	1020	130	0.114	0.054	0.008
TC21-15	224.25	225.1	0.85	100	4860	1800	312	0.155	0.118	0.016
TC21-15	225.1	226.1	1	100	8890	2000	555	0.288	0.199	0.034
TC21-15	226.1	227.15	1.05	100	6390	16600	427	0.146	0.158	0.035
TC21-15	227.15	228.25	1.1	100	13100	4380	844	0.399	0.194	0.057
TC21-15	228.25	229.2	0.95	100	989	9010	85	0.126	0.252	0.032
TC21-15	229.2	230.2	1	100	1520	1870	96	0.039	0.038	0.016
TC21-15	230.2	231.1	0.9	100	1590	2590	102	0.011	0.033	0.014
TC21-15	231.1	231.98	0.88	100	17900	3170	1075	0.516	0.124	0.017
TC21-15	231.98	232.5	0.52	100	7610	9870	493	0.364	0.216	0.01
TC21-15	232.5	233.5	1	100	3070	3060	193	0.057	0.11	0.009
TC21-15	233.5	234.4	0.9	100	1595	1590	119	0.028	0.036	0.005
TC21-15	234.4	235.4	1	100	1560	1170	109	0.042	0.036	0.006
TC21-15	235.4	235.85	0.45	100	6040	1970	391	0.137	0.134	0.021
TC21-15	235.85	236.6	0.75	100	2920	2420	211	0.09	0.07	0.016
TC21-15	236.6	237.4	0.8	100	1025	14400	100	<0.005	0.053	0.012
TC21-15	237.4	238.7	1.3	100	562	842	38	<0.005	0.043	0.004
TC21-15	238.7	240	1.3	100	129	321	7	<0.005	0.002	0.001
TC21-15	240	241.05	1.05	100	494	1080	18	<0.005	0.01	0.003
TC21-16	123.8	124.8	1	100	97	41	43	na	na	na
TC21-16	124.8	125.8	1	100	147	50	46	na	na	na
TC21-16	125.8	126.5	0.7	100	170	54	50	na	na	na
TC21-16	138.85	139.95	1.1	100	21	18	37	na	na	na
TC21-16	145.25	146.25	1	100	173	475	6	<0.005	0.005	0.001
TC21-16	146.25	147.3	1.05	100	1610	1700	124	0.124	0.071	0.03
TC21-16	147.3	148.3	1	100	1840	3750	128	0.263	0.151	0.067
TC21-16	148.3	149.5	1.2	100	6280	2370	406	0.312	0.24	0.071
TC21-16	149.5	150.5	1	100	9150	6050	587	0.605	0.325	0.087
TC21-16	150.5	151.5	1	100	8620	5080	570	0.253	0.287	0.074
TC21-16	151.5	152.5	1	100	9880	5760	658	0.327	0.398	0.108

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
TC21-16	152.5	153.5	1	100	9680	9070	656	0.32	0.342	0.099
TC21-16	153.5	154.5	1	100	8800	6810	587	0.348	0.284	0.075
TC21-16	154.5	155.5	1	100	8910	4850	592	0.319	0.274	0.082
TC21-16	155.5	156.5	1	100	8310	4740	543	0.185	0.321	0.076
TC21-16	156.5	157.5	1	100	1190	416	94	0.035	0.025	0.011
TC21-16	157.5	158.5	1	100	1110	276	81	0.012	0.017	0.012
TC21-16	158.5	159.5	1	100	1290	487	96	0.057	0.065	0.029
TC21-16	159.5	160.4	0.9	100	955	508	75	0.079	0.046	0.016
TC21-16	160.4	161.4	1	100	495	1340	44	<0.005	0.015	0.001
TC21-16	161.4	162.4	1	100	162	310	15	<0.005	0.006	0.002
TC21-16	170.1	171.3	1.2	100	102	42	35	na	na	na
TC21-16	171.3	172.5	1.2	100	12	21	38	na	na	na
TC21-16	172.5	173.55	1.05	100	13	24	35	na	na	na
TC21-16	175.05	176.05	1	100	20	32	37	na	na	na
TC21-16	176.05	177.05	1	100	14	32	38	na	na	na
TC21-17	180.3	181.3	1	100	356	655	32	<0.005	0.01	0.001
TC21-17	181.3	182.38	1.08	100	11150	13000	659	0.271	0.302	0.009
TC21-17	182.38	183	0.62	100	1980	4240	141	0.013	0.037	0.017
TC21-17	183	184	1	100	268	386	17	<0.005	0.007	0.001
TC21-17	188.1	189.55	1.45	100	363	92	64	na	na	na
TC21-17	201.2	202.2	1	100	149	102	54	na	na	na
TC21-17	206	207.2	1.2	100	18	20	28	na	na	na
TC21-17	207.2	208.4	1.2	100	143	40	44	na	na	na
TC21-17	208.4	209.6	1.2	100	154	114	58	na	na	na
TC21-17	209.6	210.8	1.2	100	91	49	35	na	na	na
TC21-17	210.8	211.9	1.1	100	89	54	44	na	na	na
TC21-18	151.05	152.2	1.15	100	13	32	39	na	na	na
TC21-18	152.2	153.4	1.2	100	15	23	35	na	na	na
TC21-18	153.4	154.6	1.2	100	56	45	44	na	na	na
TC21-18	154.6	155.8	1.2	100	104	59	48	na	na	na
TC21-18	155.8	157	1.2	100	146	66	47	na	na	na
TC21-18	157	158	1	100	125	117	32	na	na	na
TC21-18	188	189.05	1.05	100	541	1050	25	<0.005	0.013	0.003
TC21-18	189.05	189.65	0.6	100	2970	5140	250	0.128	0.176	0.059
TC21-18	189.65	190.67	1.02	100	3280	3050	224	0.203	0.128	0.05
TC21-18	190.67	191.7	1.03	100	14450	13400	883	0.426	0.601	0.054
TC21-18	191.7	192.7	1	100	1640	1300	112	0.065	0.049	0.007
TC21-18	192.7	193.7	1	100	958	1050	85	0.038	0.03	0.006
TC21-18	193.7	194.45	0.75	100	767	1220	75	0.017	0.014	0.005
TC21-18	194.45	195.45	1	100	553	1010	39	0.03	0.037	0.007
TC21-18	195.45	196.5	1.05	100	169	182	12	<0.005	0.005	0.003
TC21-18	196.5	197.8	1.3	100	437	141	55	0.008	0.01	0.002
TC21-18	209.5	210.4	0.9	100	94	26	41	na	na	na
TC21-18	220.6	221.8	1.2	100	31	32	36	na	na	na
TC21-18	221.8	223	1.2	100	23	21	28	na	na	na
TC21-18	223	224.3	1.3	100	150	66	51	na	na	na
TC21-19	45.5	46.15	0.65	100	910	1970	52	na	na	na
TC21-19	49	49.9	0.9	100	1350	1450	70	<0.005	0.024	0.003
TC21-19	49.9	50.5	0.6	100	1850	1660	103	<0.005	0.03	0.01
TC21-19	50.5	51.25	0.75	100	4390	2650	261	0.052	0.078	0.02
TC21-19	51.25	52.6	1.35	100	1960	935	112	0.034	0.034	0.011
TC21-19	52.6	53.6	1	100	3580	2090	223	0.191	0.143	0.038
TC21-19	53.6	54.6	1	100	3800	1990	238	0.188	0.167	0.04
TC21-19	54.6	55.6	1	100	1520	1440	97	0.02	0.032	0.008
TC21-19	55.6	56.5	0.9	100	1350	1410	78	<0.005	0.002	0.001
TC21-19	56.5	57.25	0.75	100	1660	720	95	0.05	0.043	0.007
TC21-19	57.25	58.5	1.25	100	1210	171	91	<0.005	0.001	0.002
TC21-19	58.5	59.5	1	100	1120	243	87	<0.005	0.002	0.001
TC21-19	59.5	60.55	1.05	100	1030	185	79	<0.005	0.003	0.002
TC21-19	60.55	61.5	0.95	100	465	113	34	<0.005	0.003	0.002
TC21-19	61.5	62.5	1	100	214	20	20	<0.005	0.003	0.001
TC21-19	62.5	63.5	1	100	843	275	60	0.005	0.003	0.002
TC21-19	63.5	64.4	0.9	100	1120	337	89	0.008	0.007	0.001
TC21-19	64.4	65.5	1.1	100	633	129	46	<0.005	0.005	0.003
TC21-19	65.5	66.5	1	100	776	211	55	<0.005	0.004	0.002
TC21-19	66.5	67.6	1.1	100	1280	449	92	0.039	0.023	0.002
TC21-19	67.6	68.4	0.8	100	1540	2780	100	0.013	0.017	0.003
TC21-19	68.4	69.3	0.9	100	927	366	64	0.007	0.01	0.003
TC21-19	69.3	70	0.7	100	322	46	26	<0.005	0.006	<0.001
TC21-19	70	71	1	100	285	85	24	<0.005	0.005	0.001
TC21-19	71	72	1	100	708	185	45	<0.005	0.005	0.001
TC21-19	72	73	1	100	761	239	45	<0.005	0.006	0.002

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
TC21-19	73	73.9	0.9	100	1010	453	60	0.026	0.019	0.001
TC21-19	73.9	75	1.1	100	4230	2010	240	0.172	0.114	0.009
TC21-19	75	76	1	100	3060	1420	178	0.122	0.081	0.013
TC21-19	76	77	1	100	3430	1430	200	0.111	0.077	0.008
TC21-19	77	78	1	100	4180	1640	245	0.141	0.105	0.011
TC21-19	78	79	1	100	3120	917	186	0.106	0.086	0.01
TC21-19	79	80	1	100	3690	997	196	0.114	0.077	0.006
TC21-19	80	81	1	100	4350	1070	237	0.12	0.071	0.004
TC21-19	81	82	1	100	3510	1830	189	0.049	0.061	0.004
TC21-19	82	83	1	100	4050	875	217	0.105	0.056	0.004
TC21-19	83	84	1	100	4470	1160	238	0.083	0.082	0.006
TC21-19	84	85.4	1.4	100	3510	981	175	0.094	0.078	0.007
TC21-19	85.4	86	0.6	100	929	357	69	<0.005	0.011	0.001
TC21-19	86	87	1	100	1240	463	100	0.006	0.007	0.001
TC21-19	87	88	1	100	2030	722	128	0.016	0.022	0.002
TC21-19	88	89	1	100	1490	464	98	0.013	0.015	0.002
TC21-19	89	90.5	1.5	100	1010	283	62	0.012	0.013	0.002
TC21-19	90.5	92	1.5	100	1200	316	81	0.008	0.013	0.002
TC21-19	92	94	2	100	1370	557	104	0.006	0.01	0.002
TC21-19	94	96	2	100	1280	445	94	<0.005	0.005	0.001
TC21-19	96	98	2	100	1220	306	76	0.007	0.011	0.003
TC21-19	98	99	1	100	2050	585	134	0.07	0.053	0.01
TC21-19	99	101	2	100	2030	617	133	0.07	0.046	0.006
TC21-19	101	102.5	1.5	100	1850	717	120	0.122	0.07	0.025
TC21-19	102.5	103.65	1.15	100	2970	1150	199	0.075	0.033	0.006
TC21-19	103.65	104.65	1	100	1030	3620	71	<0.005	0.032	0.003
TC21-19	104.65	105.4	0.75	100	2070	1980	145	0.131	0.024	0.003
TC21-20	72.4	74.4	2	100	1120	44	84	na	na	na
TC21-20	74.4	76	1.6	100	1270	63	84	na	na	na
TC21-20	76	77.4	1.4	100	861	58	77	na	na	na
TC21-20	96.1	98.1	2	100	269	49	43	na	na	na
TC21-20	98.1	100.1	2	100	215	57	46	na	na	na
TC21-20	100.1	102.1	2	100	1180	125	88	na	na	na
TC21-20	102.1	104.4	2.3	100	1160	97	86	na	na	na
TC21-20	109.5	111.5	2	100	908	86	73	na	na	na
TC21-20	111.5	113.5	2	100	1020	76	78	na	na	na
TC21-20	113.5	115	1.5	100	25	67	42	na	na	na
TC21-20	115	116.55	1.55	100	18	27	34	na	na	na
TC21-20	117.25	119.2	1.95	100	13	29	33	na	na	na
TC21-20	119.2	120.8	1.6	100	23	24	30	na	na	na
TC21-20	137.45	139	1.55	100	19	27	40	na	na	na
TC21-20	139	140.5	1.5	100	16	21	36	na	na	na
TC21-20	158.65	159.3	0.65	100	726	1490	35	<0.005	0.017	0.007
TC21-20	159.3	159.96	0.66	100	2820	4230	186	0.105	0.116	0.012
TC21-20	159.96	160.3	0.34	100	9240	13300	525	0.113	0.62	0.093
TC21-20	160.3	161.5	1.2	100	3180	2580	195	0.216	0.177	0.025
TC21-20	161.5	162.1	0.6	100	1810	1820	119	<0.005	0.147	0.015
TC21-20	162.1	162.5	0.4	100	4660	3750	244	<0.005	0.101	0.018
TC21-20	162.5	163.4	0.9	100	591	965	31	<0.005	0.017	0.005
TC21-20	163.4	164.4	1	100	638	589	29	<0.005	0.018	0.005
TC21-20	174.85	175.4	0.55	100	569	92	59	na	na	na
TC21-20	176.2	178	1.8	100	545	71	55	na	na	na
TC21-20	185.6	187.2	1.6	100	102	129	52	na	na	na
TC21-20	194.6	196.05	1.45	100	20	17	35	na	na	na
TC21-20	204.6	206	1.4	100	39	14	27	na	na	na
TC21-20	206	207.2	1.2	100	24	13	19	na	na	na
TC21-21	42.3	42.6	0.3	100	132	141	12	<0.005	0.006	<0.001
TC21-21	229	230	1	100	74	52	9	<0.005	0.003	<0.001
TC21-21	230	230.45	0.45	100	1005	4430	57	<0.005	0.16	0.025
TC21-21	230.45	230.95	0.5	100	9190	8180	550	0.58	0.402	0.05
TC21-21	230.95	231.38	0.43	100	12700	3530	783	0.788	0.869	0.027
TC21-21	231.38	232.4	1.02	100	1195	3060	65	<0.005	0.107	0.008
TC21-21	232.4	233.4	1	100	152	351	10	<0.005	0.003	0.001
TC21-21	233.4	234.5	1.1	100	88	59	9	<0.005	0.003	<0.001
TC21-22	41	42.3	1.3	100	1200	114	78	na	na	na
TC21-22	56.7	57.7	1	100	120	38	46	na	na	na
TC21-22	57.7	58.7	1	100	97	59	47	na	na	na
TC21-22	58.7	59.7	1	100	136	132	52	na	na	na
TC21-22	59.7	60.7	1	100	148	61	49	na	na	na
TC21-22	60.7	61.7	1	100	149	51	47	na	na	na
TC21-22	61.7	62.6	0.9	100	129	92	42	na	na	na
TC21-22	83.85	84.85	1	100	10	34	34	na	na	na

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
TC21-22	84.85	85.8	0.95	100	31	37	37	na	na	na
TC21-22	86.2	87.5	1.3	100	20	31	33	na	na	na
TC21-22	87.5	88.8	1.3	100	67	24	37	na	na	na
TC21-22	131.3	132.3	1	100	120	214	9	<0.005	0.005	<0.001
TC21-22	132.3	132.63	0.33	100	962	1160	45	<0.005	0.03	0.002
TC21-22	132.63	133	0.37	100	6520	2370	403	0.061	0.098	0.008
TC21-22	133	134	1	100	1165	1500	55	<0.005	0.033	0.001
TC21-23	149.55	150	0.45	100	42	87	44	<0.005	<0.001	0.002
TC21-23	150	150.3	0.3	100	211	354	321	<0.005	0.004	0.009
TC21-23	150.3	151.2	0.9	100	16	40	37	<0.005	<0.001	0.001
TC21-23	151.2	152.1	0.9	100	13	15	32	<0.005	<0.001	<0.001
TC21-23	152.1	153	0.9	100	177	36	44	<0.005	0.001	<0.001
TC21-23	173.1	174.1	1	100	373	109	56	0.012	0.007	<0.001
TC21-23	183	184.02	1.02	100	447	1260	25	<0.005	0.015	0.013
TC21-23	184.02	184.45	0.43	100	9070	5680	581	0.27	0.288	0.014
TC21-23	184.45	185.02	0.57	100	1305	1450	101	0.016	0.041	0.004
TC21-23	185.02	186	0.98	100	77	90	4	<0.005	0.004	<0.001
TC21-24	192.4	193.5	1.1	100	406	89	63	na	na	na
TC21-24	216	217.2	1.2	100	125	52	18	na	na	na
TC21-24	217.2	217.93	0.73	100	336	78	49	na	na	na
TC21-24	217.93	219	1.07	100	85	36	12	na	na	na
TC21-24	234.4	235.7	1.3	100	134	78	51	na	na	na
TC21-24	235.7	236.95	1.25	100	45	30	39	na	na	na
TC21-24	237.4	238.85	1.45	100	97	60	47	na	na	na
TC21-25	85.8	86.8	1	100	330	158	53	na	na	na
TC21-25	86.8	87.8	1	100	290	145	71	na	na	na
TC21-25	87.8	88.8	1	100	391	59	61	na	na	na
TC21-25	88.8	89.65	0.85	100	558	70	66	na	na	na
TC21-25	97.5	98.65	1.15	100	137	296	14	<0.005	0.003	<0.001
TC21-25	98.65	98.95	0.3	100	5100	3750	336	0.075	0.25	0.007
TC21-25	98.95	100.5	1.55	100	566	761	29	<0.005	0.015	0.006
TC21-26	279.7	281	1.3	100	369	230	58	0.008	0.007	<0.001
TC21-26	282	283.1	1.1	100	1670	7590	141	<0.005	0.239	0.021
TC21-26	283.1	283.4	0.3	100	4510	46100	466	0.246	2.67	0.257
TC21-26	283.4	284.6	1.2	100	13200	6500	804	1.14	0.535	0.04
TC21-26	284.6	286	1.4	100	8040	14400	536	0.787	0.351	0.08
TC21-26	286	286.44	0.44	100	2930	2630	213	0.025	0.149	0.167
TC21-26	286.44	286.74	0.3	100	9790	2860	627	0.546	0.205	0.031
TC21-26	286.74	288	1.26	100	144	191	14	0.006	0.002	0.006
TC21-26	288	289.5	1.5	100	101	56	13	<0.005	0.002	0.004
TC21-26	289.5	290	0.5	100	370	93	61	0.012	0.007	<0.001
TC21-26	292.1	293.05	0.95	100	60	43	42	na	na	na
TC21-26	299	300	1	100	504	52	58	na	na	na
TC21-26	300	301	1	100	1380	73	83	na	na	na
TC21-26	301	302	1	100	531	91	49	na	na	na
TC21-26	306.78	308	1.22	100	58	43	34	na	na	na
TC21-26	308	309.2	1.2	100	173	50	53	na	na	na
TC21-26	309.2	310.55	1.35	100	95	35	42	na	na	na
TC21-27	72.15	73.3	1.15	100	1250	105	88	na	na	na
TC21-27	73.3	74.5	1.2	100	1205	71	108	na	na	na
TC21-27	74.5	75.7	1.2	100	1120	99	98	na	na	na
TC21-27	75.7	76.9	1.2	100	1145	54	86	na	na	na
TC21-27	79.8	80.7	0.9	100	782	155	76	na	na	na
TC21-27	83.6	84.9	1.3	100	59	111	31	na	na	na
TC21-27	90.5	91.8	1.3	100	47	26	43	na	na	na
TC21-27	91.8	93.2	1.4	100	47	33	45	na	na	na
TC21-27	198.8	200.2	1.4	100	133	190	18	na	na	na
TC21-27	200.2	201.6	1.4	100	286	148	23	na	na	na
TC21-27	201.6	202.6	1	100	229	169	24	na	na	na
TC21-28	168.65	169.65	1	100	123	296	19	<0.005	0.002	0.001
TC21-28	169.65	170.65	1	100	745	798	77	0.005	0.007	0.004
TC21-28	170.65	171.65	1	100	878	567	98	<0.005	0.016	<0.001
TC21-28	171.65	172.6	0.95	100	2060	2000	203	0.03	0.005	<0.001
TC21-28	172.6	173.85	1.25	100	1385	651	108	0.008	0.015	0.005
TC21-28	173.85	175.1	1.25	100	2140	823	175	0.013	0.014	0.004
TC21-28	175.1	176	0.9	100	1830	934	146	0.016	0.013	0.006
TC21-28	176	177	1	100	2240	860	158	0.04	0.032	0.002
TC21-28	177	178	1	100	1440	477	119	0.018	0.015	0.003
TC21-28	178	179	1	100	1680	324	122	0.014	0.014	0.004
TC21-28	179	180	1	100	1545	355	118	0.006	0.008	0.003
TC21-28	180	181	1	100	1620	373	118	0.022	0.012	0.005
TC21-28	181	182	1	100	1300	322	112	0.01	0.012	0.005

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
TC21-28	182	183	1	100	1460	290	108	0.01	0.009	0.003
TC21-28	183	184	1	100	1205	299	92	0.006	0.006	0.002
TC21-28	184	185	1	100	1280	199	106	0.006	0.009	0.003
TC21-28	185	186	1	100	3390	498	165	0.028	0.024	0.029
TC21-28	186	187.2	1.2	100	2990	544	142	0.009	0.021	0.029
TC21-28	187.2	188.45	1.25	100	3550	630	174	0.051	0.045	0.013
TC21-28	188.45	189.2	0.75	100	4810	926	212	0.056	0.031	0.016
TC21-28	189.2	190.2	1	100	1490	317	105	0.006	0.006	0.002
TC21-28	190.2	191.2	1	100	1600	479	109	0.019	0.017	0.002
TC21-28	191.2	193.4	2.2	100	2400	577	132	0.053	0.04	0.005
TC21-28	193.4	194.2	0.8	100	4150	899	183	0.016	0.009	0.006
TC21-28	194.2	195.1	0.9	100	2730	568	144	0.023	0.018	0.004
TC21-28	195.1	196.1	1	100	1280	231	99	0.025	0.017	0.003
TC21-28	196.1	197.1	1	100	1610	334	112	0.03	0.03	0.002
TC21-28	197.1	198.1	1	100	1270	229	109	0.008	0.006	0.002
TC21-28	198.1	199.1	1	100	1200	250	104	0.005	0.004	0.001
TC21-28	199.1	200.1	1	100	1170	376	108	0.005	0.008	0.002
TC21-28	200.1	201.1	1	100	1320	243	107	0.009	0.013	0.002
TC21-28	201.1	202.3	1.2	100	1520	178	123	0.006	0.009	0.002
TC21-28	202.3	203.6	1.3	100	1780	236	112	0.02	0.024	0.004
TC21-28	203.6	204.6	1	100	904	805	78	0.007	0.011	0.001
TC21-29	87.5	88.7	1.2	100	25	31	36	na	na	na
TC21-29	88.7	90	1.3	100	30	26	24	na	na	na
TC21-29	90	91.05	1.05	100	22	21	37	na	na	na
TC21-29	117	118.5	1.5	100	11	16	33	na	na	na
TC21-29	118.5	120	1.5	100	17	14	36	na	na	na
TC21-29	120	121.5	1.5	100	13	15	34	na	na	na
TC21-29	121.5	123	1.5	100	14	11	35	na	na	na
TC21-29	123	124.5	1.5	100	16	18	30	na	na	na
TC21-29	124.5	126	1.5	100	118	19	40	na	na	na
TC21-29	126	127.5	1.5	100	64	24	43	na	na	na
TC21-29	127.5	129	1.5	100	60	57	39	na	na	na
TC21-29	129	130.5	1.5	100	65	37	37	na	na	na
TC21-29	130.5	131.5	1	100	81	35	40	na	na	na
TC21-30	164.1	164.45	0.35	100	609	199	126	<0.005	0.003	0.003
TC21-30	164.45	165.4	0.95	100	66	103	11	<0.005	0.005	0.001
TC21-30	165.4	165.7	0.3	100	707	239	70	0.007	0.006	0.001
TC21-30	165.7	166.9	1.2	100	1185	505	102	<0.005	0.004	<0.001
TC21-30	166.9	167.7	0.8	100	1850	657	129	0.008	0.017	0.007
TC21-30	167.7	168.7	1	100	1635	407	115	0.008	0.009	0.007
TC21-30	168.7	169	0.3	100	109	20	10	<0.005	0.001	0.002
TC21-30	169	169.3	0.3	100	6610	1050	424	<0.005	0.043	0.044
TC21-30	169.3	170.3	1	100	1510	272	91	0.03	0.024	0.011
TC21-30	170.3	171.3	1	100	1340	192	73	<0.005	0.016	0.002
TC21-30	171.3	172.3	1	100	1575	385	107	<0.005	0.02	0.003
TC21-30	172.3	173.3	1	100	1240	293	94	0.006	0.013	<0.001
TC21-30	173.3	174.4	1.1	100	1120	200	79	0.008	0.016	0.001
TC21-30	174.4	175.4	1	100	1740	347	117	0.03	0.026	0.003
TC21-30	175.4	176	0.6	100	1500	268	106	0.03	0.032	0.005
TC21-30	176	177	1	100	1120	164	73	0.025	0.018	0.002
TC21-30	177	178	1	100	1150	353	97	0.007	0.006	0.001
TC21-30	178	179	1	100	663	132	63	<0.005	0.005	<0.001
TC21-30	179	180	1	100	1165	824	121	<0.005	0.004	0.006
TC21-30	180	181	1	100	951	284	106	<0.005	0.005	0.002
TC21-30	181	182	1	100	1000	302	97	<0.005	0.005	0.003
TC21-30	182	183	1	100	921	432	97	0.007	0.008	0.001
TC21-30	183	184	1	100	848	461	86	0.018	0.012	0.002
TC21-30	184	185	1	100	95	93	11	0.006	0.003	0.002
TC21-30	188.2	189.2	1	100	535	84	64	na	na	na
TC21-30	189.2	190.2	1	100	558	90	66	na	na	na
TC21-30	190.2	191.2	1	100	554	98	64	na	na	na
TC21-30	191.2	192.2	1	100	659	124	70	na	na	na
TC21-30	192.2	193.5	1.3	100	568	54	67	na	na	na
TC21-30	193.5	194.5	1	100	597	95	69	na	na	na
TC21-30	194.5	195.5	1	100	605	89	70	na	na	na
TC21-30	247.3	248.2	0.9	100	32	120	29	na	na	na
TC21-31	44	45	1	100	73	33	43	na	na	na
TC21-31	45	46.2	1.2	100	80	65	41	na	na	na
TC21-31	46.2	46.8	0.6	100	57	191	38	na	na	na
TC21-31	46.8	48	1.2	100	64	28	43	na	na	na
TC21-31	48	49	1	100	71	27	44	na	na	na
TC21-31	49	50	1	100	70	49	49	na	na	na

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
TC21-31	50	51	1	100	73	39	38	na	na	na
TC21-31	51	52	1	100	34	20	30	na	na	na
TC21-31	52	53	1	100	14	19	28	na	na	na
TC21-31	53	54	1	100	13	26	31	na	na	na
TC21-31	54	55	1	100	15	17	29	na	na	na
TC21-31	55	56	1	100	11	12	32	na	na	na
TC21-31	56	57	1	100	13	23	29	na	na	na
TC21-31	57	58.3	1.3	100	39	27	36	na	na	na
TC21-31	58.3	59.6	1.3	100	18	30	31	na	na	na
TC21-32	189.15	191	1.85	100	119	56	32	na	na	na
TC21-32	191	192.8	1.8	100	95	60	39	na	na	na
TC21-32	192.8	194.5	1.7	100	144	60	36	na	na	na
TC21-32	194.5	196	1.5	100	115	103	49	na	na	na
TC21-32	196	197.9	1.9	100	104	85	43	na	na	na
TC21-32	198.8	200.7	1.9	100	112	77	42	na	na	na
TC21-32	200.7	202.5	1.8	100	111	49	31	na	na	na
TC21-32	203	204	1	100	114	78	40	na	na	na
TC21-32	204.5	206.3	1.8	100	196	89	42	na	na	na
TC21-32	206.3	208	1.7	100	49	26	39	na	na	na
TC21-32	211.4	213	1.6	100	58	56	44	na	na	na
TC21-32	213	214.2	1.2	100	59	36	41	na	na	na
TC21-33	71.2	72.2	1	100	791	130	66	na	na	na
TC21-33	72.2	73.2	1	100	429	96	56	na	na	na
TC21-33	73.2	74.2	1	100	831	81	64	na	na	na
TC21-33	74.2	75.2	1	100	495	52	52	na	na	na
TC21-33	75.2	76.2	1	100	35	56	36	na	na	na
TC21-33	76.2	77.2	1	100	40	94	34	na	na	na
TC21-33	77.2	78.2	1	100	37	72	26	na	na	na
TC21-33	78.2	79.2	1	100	192	166	47	na	na	na
TC21-33	79.2	80.45	1.25	100	86	82	34	na	na	na
TC21-33	83.25	84.4	1.15	100	758	337	68	na	na	na
TC21-34	124	125.1	1.1	100	392	1700	14	0.005	0.017	0.01
TC21-34	125.1	125.4	0.3	100	7270	3950	414	1.115	0.824	0.241
TC21-34	125.4	125.7	0.3	100	3450	6250	201	0.268	0.449	0.16
TC21-34	125.7	126.7	1	100	677	2340	50	0.005	0.013	0.007
TC21-34	126.7	127.7	1	100	87	143	12	<0.005	0.001	0.002
TC21-34	127.7	128.45	0.75	100	78	32	8	0.005	0.003	0.002
TC21-34	128.45	129.5	1.05	100	17	30	24	<0.005	<0.001	0.001
TC21-35	74.6	75.2	0.6	100	188	210	23	0.029	0.007	0.001
TC21-35	75.45	77	1.55	100	1310	513	81	0.024	0.025	0.004
TC21-35	77	78.5	1.5	100	1270	689	90	0.02	0.021	0.005
TC21-35	78.5	80	1.5	100	1555	499	113	0.015	0.016	0.004
TC21-35	80	81.5	1.5	100	1645	436	107	0.026	0.019	0.007
TC21-35	81.5	83	1.5	100	2670	576	127	0.112	0.061	0.015
TC21-35	83	84.1	1.1	100	2080	342	91	0.038	0.031	0.007
TC21-35	84.1	85.1	1	100	136	265	16	<0.005	0.005	0.002
TC21-36	27	28	1	100	237	325	36	<0.005	0.004	0.002
TC21-36	28	29.3	1.3	100	543	537	25	0.005	0.007	0.001
TC21-36	29.3	29.65	0.35	100	3300	2170	166	0.163	0.092	0.01
TC21-36	29.65	30.45	0.8	100	3770	6990	205	0.148	0.304	0.064
TC21-36	30.45	31.45	1	100	297	472	15	0.005	0.012	<0.001
TC21-36	66.7	68.2	1.5	100	105	70	32	na	na	na
TC21-36	68.2	69.7	1.5	100	76	109	35	na	na	na
TC21-36	69.7	71.3	1.6	100	144	140	40	na	na	na
TC21-37	114.7	115.75	1.05	100	137	196	24	<0.005	<0.001	0.001
TC21-37	115.75	116.75	1	100	449	289	68	0.011	0.006	0.001
TC21-37	116.75	117.75	1	100	1095	385	100	0.025	0.018	0.003
TC21-37	117.75	118.3	0.55	100	3420	427	257	0.087	0.051	0.014
TC21-37	118.3	119.3	1	100	508	272	26	<0.005	0.007	<0.001
TC21-37	122.4	123.4	1	100	12	51	21	na	na	na
TC21-37	123.4	124.4	1	100	17	54	30	na	na	na
TC21-37	137.8	138.7	0.9	100	58	64	37	na	na	na
TC21-38	148.35	149.8	1.45	100	5	17	29	na	na	na
TC21-38	149.8	151	1.2	100	11	23	46	na	na	na
TC21-38	151	152	1	100	6	8	32	na	na	na
TC21-38	152	153	1	100	6	8	38	na	na	na
TC21-38	153	154.2	1.2	100	53	31	14	na	na	na
TC21-38	154.2	154.6	0.4	100	126	82	33	na	na	na
TC21-38	156	157.5	1.5	100	10	24	33	na	na	na
TC21-38	157.5	159	1.5	100	5	10	33	na	na	na
TC21-38	159	160.5	1.5	167	11	36	50	na	na	na
TC21-38	160.5	162.5	2	50	8	28	37	na	na	na

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
TC21-38	162.5	163.2	0.7	100	10	26	30	na	na	na
TC21-38	163.2	164.2	1	100	18	20	11	na	na	na
TC21-38	207.35	208.4	1.05	100	153	110	48	na	na	na
TC21-38	208.4	209.5	1.1	100	253	38	40	na	na	na
TC21-39	11	12	1	100	844	229	69	na	na	na
TC21-39	12	13.3	1.3	100	520	277	75	na	na	na
TC21-39	13.3	14.65	1.35	100	323	651	77	na	na	na
TC21-39	14.65	15.6	0.95	100	451	507	99	na	na	na
TC21-39	15.6	16.65	1.05	100	280	253	56	na	na	na
TC21-39	16.65	17.65	1	100	119	204	22	na	na	na
TC21-39	17.65	18.65	1	100	143	188	27	na	na	na
TC21-39	18.65	19.85	1.2	100	100	250	17	na	na	na
TC21-39	19.85	20.85	1	100	166	183	45	na	na	na
TC21-39	20.85	21.85	1	100	141	179	43	na	na	na
TC21-39	21.85	23	1.15	100	101	294	24	na	na	na
TC21-39	23	24.4	1.4	100	228	522	53	na	na	na
TC21-39	24.4	25.7	1.3	100	155	211	29	na	na	na
TC21-39	25.7	27	1.3	100	191	321	30	na	na	na
TC21-39	27	27.6	0.6	100	205	335	41	<0.005	0.005	0.001
TC21-39	27.6	28.95	1.35	100	142	143	32	<0.005	0.002	0.002
TC21-39	28.95	30.15	1.2	100	652	210	72	0.006	0.007	0.003
TC21-39	30.15	31.5	1.35	100	864	119	74	0.01	0.011	0.006
TC21-39	31.5	32.5	1	100	664	175	72	0.01	0.009	0.002
TC21-39	32.5	33.6	1.1	100	705	448	77	0.014	0.012	0.008
TC21-39	33.6	34.7	1.1	100	202	115	32	0.006	0.004	0.002
TC21-39	34.7	35.8	1.1	100	428	402	55	<0.005	0.011	0.002
TC21-39	35.8	36.8	1	100	812	1730	116	0.02	0.018	0.002
TC21-39	36.8	37.75	0.95	100	789	1525	123	0.014	0.026	0.004
TC21-39	37.75	39	1.25	100	536	1005	112	0.005	0.013	0.002
TC21-39	39	40	1	100	651	127	58	0.005	0.004	0.002
TC21-39	40	41	1	100	903	249	79	0.01	0.007	0.003
TC21-39	41	42	1	100	1165	172	102	0.007	0.007	0.003
TC21-39	42	43	1	100	1790	540	108	0.023	0.03	0.015
TC21-39	43	44.2	1.2	100	1075	551	112	0.006	0.006	0.003
TC21-39	44.2	45.2	1	100	715	115	90	<0.005	0.003	0.002
TC21-39	45.2	46.2	1	100	928	161	106	0.009	0.009	0.003
TC21-39	46.2	47.2	1	100	999	135	103	0.011	0.008	0.003
TC21-39	47.2	48.2	1	100	925	154	97	0.006	0.007	0.002
TC21-39	48.2	49.2	1	100	991	119	97	0.005	0.008	0.003
TC21-39	49.2	50.4	1.2	100	978	59	93	0.005	0.004	0.002
TC21-39	50.4	51.4	1	100	2090	772	133	0.08	0.105	0.046
TC21-39	51.4	52.4	1	100	1015	199	71	0.009	0.013	0.007
TC21-39	52.4	53.5	1.1	100	846	276	60	<0.005	0.006	0.003
TC21-39	53.5	54	0.5	100	539	1610	56	<0.005	0.009	0.005
TC21-39	54	55.3	1.3	100	202	873	61	<0.005	0.001	<0.001
TC21-39	55.3	56.55	1.25	100	48	274	40	<0.005	0.001	<0.001
TC21-39	56.55	57.55	1	100	118	521	31	<0.005	0.005	0.002
TC21-39	57.55	58.8	1.25	100	783	125	78	<0.005	0.003	0.002
TC21-39	58.8	60	1.2	100	976	122	97	<0.005	0.007	0.001
TC21-39	60	60.5	0.5	100	1815	433	154	0.069	0.044	0.007
TC21-39	60.5	61.55	1.05	100	1305	324	96	0.013	0.014	0.004
TC21-39	61.55	63	1.45	100	701	1475	66	<0.005	0.009	0.001
TC21-39	63	64	1	100	1075	340	83	0.013	0.021	0.007
TC21-39	64	65	1	100	1460	499	99	0.044	0.051	0.008
TC21-39	65	66	1	100	1935	2120	127	0.051	0.078	0.01
TC21-39	66	67	1	100	3770	773	224	0.143	0.151	0.013
TC21-39	67	68.2	1.2	100	1810	994	121	0.045	0.059	0.008
TC21-39	68.2	69.45	1.25	100	2830	1425	173	0.038	0.135	0.017
TC21-39	69.45	70.5	1.05	100	1470	1145	104	0.011	0.046	0.008
TC21-39	70.5	71.5	1	100	969	728	80	0.011	0.018	0.004
TC21-39	71.5	72.55	1.05	100	2390	954	165	0.057	0.119	0.02
TC21-39	72.55	73.9	1.35	100	481	2770	34	<0.005	0.016	0.003
TC21-39	73.9	75	1.1	100	993	3400	74	na	na	na
TC21-39	75	76	1	100	139	943	20	na	na	na
TC21-39	76	77	1	100	95	356	24	na	na	na
TC21-39	77	78	1	100	431	347	33	na	na	na
TC21-40	8	9	1	100	30	59	27	na	na	na
TC21-40	9	10	1	100	21	70	28	na	na	na
TC21-40	10	11	1	100	23	60	32	na	na	na
TC21-40	11	11.9	0.9	100	30	63	30	na	na	na
TC21-40	18.1	19.3	1.2	100	314	72	36	0.006	0.01	<0.001
TC21-40	19.3	20.5	1.2	100	564	89	51	0.007	0.009	<0.001

Hole	From (m)	To (m)	Interval (m)	Recovery (%)	Ni (ppm)	Cu (ppm)	Co (ppm)	Pt (g/t)	Pd (g/t)	Au (g/t)
TC21-40	20.5	21.65	1.15	100	210	130	48	0.007	0.005	<0.001
TC21-40	22.1	23	0.9	100	70	131	41	<0.005	0.001	<0.001
TC21-40	23	23.8	0.8	100	122	118	33	<0.005	0.003	<0.001
TC21-40	23.8	24.8	1	100	168	79	42	na	na	na
TC21-40	24.8	25.8	1	100	83	108	37	na	na	na
TC21-40	25.8	26.8	1	100	125	150	43	na	na	na
TC21-40	26.8	27.8	1	100	146	63	39	na	na	na
TC21-40	27.8	28.8	1	100	177	74	41	na	na	na
TC21-40	28.8	29.85	1.05	100	370	112	64	na	na	na
TC21-40	32	33.2	1.2	100	52	29	32	na	na	na
TC21-40	33.2	34.4	1.2	100	21	28	38	na	na	na
TC21-40	34.4	35.6	1.2	100	21	14	38	na	na	na
TC21-41	76.6	77.4	0.8	100	22	23	36	na	na	na
TC21-41	85.6	85.9	0.3	100	61	217	45	na	na	na
TC21-42	67.55	68.3	0.75	100	81	38	20	na	na	na
TC21-42	68.3	69.3	1	100	117	116	40	na	na	na
TC21-42	69.3	70.3	1	100	103	112	43	na	na	na
TC21-42	70.3	71.3	1	100	128	81	39	na	na	na
TC21-42	71.3	72.5	1.2	100	21	26	22	na	na	na
TC21-42	72.5	72.9	0.4	100	56	84	67	na	na	na
TC21-42	72.9	73.9	1	100	20	9	21	na	na	na
TC21-42	73.9	74.9	1	100	31	86	34	na	na	na
TC21-42	74.9	75.2	0.3	100	94	393	114	na	na	na
TC21-42	75.2	75.5	0.3	100	24	48	25	na	na	na
TC21-42	75.5	76.9	1.4	100	43	25	13	na	na	na
TC21-43	35.4	36.4	1	100	44	18	6	na	na	na
TC21-43	36.4	38.5	2.1	100	16	16	34	na	na	na
TC21-43	38.5	40.6	2.1	100	15	21	34	na	na	na
TC21-43	40.6	42.75	2.15	100	15	12	34	na	na	na
TC21-43	42.75	43.75	1	100	78	43	15	na	na	na
TC21-43	90.8	92.8	2	100	35	19	35	na	na	na
TC21-43	92.8	94.35	1.55	100	46	50	43	na	na	na
TC21-43	94.35	95.35	1	100	59	43	10	na	na	na
TC21-43	168.5	170.9	2.4	100	63	59	37	na	na	na
TC21-43	217.7	220	2.3	100	60	69	39	na	na	na
SP21-01	82.7	83	0.3	100	122	447	37	<0.005	0.006	0.035
SP21-01	116.2	117.5	1.3	100	173	90	46	<0.005	0.001	0.001
SP21-01	117.5	118.5	1	100	239	59	37	<0.005	0.002	<0.001
SP21-01	118.5	119.6	1.1	100	299	82	47	<0.005	0.002	<0.001
SP21-02	50.28	50.58	0.3	100	2310	2250	80	0.006	0.004	0.003
SP21-02	50.58	51	0.42	100	2050	952	88	<0.005	0.003	0.005
SP21-02	51	51.3	0.3	100	8620	1360	654	0.006	0.844	0.023
SP21-02	51.3	52.45	1.15	100	20	11	7	<0.005	<0.001	<0.001
SP21-02	68.5	69	0.5	100	519	6	58	<0.005	0.002	<0.001
SP21-02	78.35	78.9	0.55	100	363	55	60	<0.005	0.003	<0.001
SP21-02	81.3	81.75	0.45	100	242	68	45	<0.005	0.002	<0.001
SP21-02	107.05	107.7	0.65	100	308	26	49	<0.005	0.001	<0.001
SP21-02	110.05	110.8	0.75	100	154	84	42	<0.005	0.001	<0.001

Appendix One

JORC Code, 2012 Edition | 'Table 1' Report

Section 1 Sampling Techniques and Data

The notes compiled here specifically relate to the new (previously unannounced) drill holes and assays, namely BC21-43 to BC22-02, KS21-30 to KS21-44, TC21-04 to TC21-43 and SP21-01 to SP21-02, and drill holes KS22-01 to KS21-17, SP22-01 and SC22-02 for which assays are not yet available and visual sulfide abundances are presented in the above report. Previous drilling results are explained in previous ASX announcements.

Criteria	JORC Code explanation	Commentary
Sampling techniques	<ul style="list-style-type: none"> Nature and quality of sampling (e.g. cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling. Measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used. Aspects of the determination of mineralisation that are Material to the Public Report. In cases where 'industry standard' work has been done this would be relatively simple (e.g. 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases, more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (e.g. submarine nodules) may warrant disclosure of detailed information. 	<ul style="list-style-type: none"> Assays are reported for 155 diamond core drill holes for a total of 27,470 m of drilling. The drill core was cut by diamond core saw and continuous quarter (NQ & HQ) core sample taken for assay according to lithological criteria in intervals ranging from 0.3 m to 2.65 m with a mean of 1 m. Sample weights for assay ranged from approx. 0.3 to 4.7 kg with a mean of c. 1.3 kg. Drilling and sampling were both supervised by a suitably qualified geologist. Visual sulfide abundances were estimated by suitably qualified Ban Phuc Nickel Mines geologist and the presence of Ni and Cu confirmed using a Niton portable XRF device. For the Company's best understanding of previous owner's drilling please refer to previous Blackstone Minerals' announcements to the ASX and additionally available from http://blackstoneminerals.com.au.
Drilling techniques	<ul style="list-style-type: none"> Drill type (e.g. core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (e.g. core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc). 	<ul style="list-style-type: none"> The drilling was of HQ (64mm) and NQ (48mm) diameter and was conducted by drilling contractor Intergeo using Longyear diamond coring rigs and Ban Phuc Nickel Mines using GX-1TD and GK300 diamond coring rigs. Selected core runs were orientated with REFLEX ACTIII tools.
Drill sample recovery	<ul style="list-style-type: none"> Method of recording and assessing core and chip sample recoveries and results assessed. Measures taken to maximise sample recovery and ensure representative nature of the samples. Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material. 	<ul style="list-style-type: none"> Recoveries were calculated by Ban Phuc Nickel Mines personnel by measuring recovered core length vs downhole interval length. Drill core recovery through the reported mineralised zones ranged from 85 to 100 % with a mean of 99% (see Table 4). There is no discernible correlation between grades and core recovery.
Logging	<ul style="list-style-type: none"> Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies. Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc.) photography. 	<ul style="list-style-type: none"> All of the drill core was qualitatively geologically logged by a suitably qualified Ban Phuc Nickel Mines geologist. Sulfide mineral abundances were visually estimated. The detail of geological logging is considered sufficient for mineral exploration.

For personal use only

Criteria	JORC Code explanation	Commentary
	<ul style="list-style-type: none"> The total length and percentage of the relevant intersections logged. 	<ul style="list-style-type: none"> 155 holes for 27,470 m were logged and 2,313 m assayed on the basis of the visual presence of sulfides. Visually estimated sulfide abundances are presented for five (5) diamond core drill holes from the King Snake, Suoi Phang and Suoi Chanh Prospects. The drill core was logged and visual abundances estimated by suitably qualified Ban Phuc Nickel Mines geologists. The presence of Ni and Cu has been confirmed using a Niton portable XRF device
Sub-sampling techniques and sample preparation	<ul style="list-style-type: none"> If core, whether cut or sawn and whether quarter, half or all core taken. If non-core, whether riffled, tube sampled, rotary split, etc. and whether sampled wet or dry. For all sample types, the nature, quality and appropriateness of the sample preparation technique. Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples. Measures taken to ensure that the sampling is representative of the in-situ material collected, including for instance results for field duplicate/second-half sampling. Whether sample sizes are appropriate to the grain size of the material being sampled. 	<ul style="list-style-type: none"> The drill core was cut lengthwise by diamond core saw and continuous half or quarter core sample bagged for assay in intervals according to lithological criteria determined by a Ban Phuc Nickel Mines geologist. Sampling intervals ranged from 0.3 m to 2.65 m with a mean of 1 m. Continuous remnant core has been retained in the trays for future reference or sampling as necessary. Duplicate quarter core samples were collected. Sample weights for assay ranged from approx. 0.3 to 4.7 kg with a mean of c. 1.3 kg. The bagged core samples were submitted to SGS Hai Phong, Vietnam ('SGS') where the quarter core samples were dried and crushed to -5 mm, then a 250 g was split from each and pulverised to 85 % passing 75 microns to produce the analytical pulps which were then dispatched to ALS Geochemistry, Perth WA ('ALS') for assay. The presence of Ni and Cu in the logged sulfide zones was confirmed by non-destructive spot analyses using a Niton portable XRF device. Factory calibration settings were used
Quality of assay data and laboratory tests	<ul style="list-style-type: none"> The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total. For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc. Nature of quality control procedures adopted (e.g. standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (i.e. lack of bias) and precision have been established. 	<ul style="list-style-type: none"> Ni, Cu and Co were determined at ALS by industry standard nitric + perchloric + hydrofluoric + hydrochloric acid digest with ICP-AES finish. Pt, Pd and Au were determined at ALS by industry standard 50 g fire assay and ICP-AES finish. Approx. one commercially certified assay standard per 25 core samples was inserted by Blackstone Minerals in each sample submission. >99% of standards reported within 13 % of the Ni, Cu, Co reference values (mean difference 1%) and 97% of standards reported within 20 % of the Pt, Pd and Au reference values (mean difference 2%) for the grade ranges of interest. Approximately one crushed rock blank per 25 samples was included in the submission and reported below 30 ppm for Ni, Cu and

Criteria	JORC Code explanation	Commentary
		<p>Co, less than 17 ppb for A and less than 8 ppb for Pt and Pd.</p> <ul style="list-style-type: none"> Quarter core duplicates were included at a rate of approx. 1 per 25 samples and sampling error is considered acceptable.
Verification of sampling and assaying	<ul style="list-style-type: none"> The verification of significant intersections by either independent or alternative company personnel. The use of twinned holes. Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols. Discuss any adjustment to assay data. 	<ul style="list-style-type: none"> The assay results are compatible with the observed mineralogy, historic mining and exploration results (please refer to previous Blackstone Minerals' announcements to the ASX and additionally available from http://blackstoneminerals.com.au). Twinned holes were not used. Primary data is stored and documented in industry standard ways. Assay data is as reported by ALS and has not been adjusted in any way. Remnant assay pulps are currently held in storage by the assay laboratory.
Location of data points	<ul style="list-style-type: none"> Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation. Specification of the grid system used. Quality and adequacy of topographic control. 	<ul style="list-style-type: none"> Drill hole collar location was determined by Leica 1203+ total station survey to centimetre accuracy. The holes were down hole orientation surveyed using a Deviflex non-magnetic survey tool. Co-ordinates were recorded in Ban Phuc Mine Grid and UTM Zone 48N WGS84 grid and coordinate system. Topographic control is provided by a precision Ban Phuc Nickel Mines Digital Terrain Model.
Data spacing and distribution	<ul style="list-style-type: none"> Data spacing for reporting of Exploration Results. Whether the data-spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied. Whether sample compositing has been applied. 	<ul style="list-style-type: none"> The drilling at Ban Chang, King Snake and Ta Cuong was largely 50 x 50 m and 25 x 25 m infill, drilling at Suoi Phang 50 x 50 m and greater, and reconnaissance nature at Suoi Chanh. Drilling was conducted on local grids tie to UTM VN2000 and WGS84 systems. All visibly altered or mineralised zones in the drill core were sampled and assayed (see above). Non-composited data is reported. The reported drill results will be used to upgrade confidence in the Ban Chang and King Snake resources. Ta Cuong, Suoi Phang and Suoi Chanh are at pre-resource exploration status
Orientation of data in relation to geological structure	<ul style="list-style-type: none"> Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type. If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material. 	<ul style="list-style-type: none"> Previous drilling and interpretation indicate the reported drill holes are suitably orientated to test the target zones. Structural orientations determined from drill core suggest the reported sulfide intervals are close to true thickness for Ban Chang and at Ta Cuong. At King Snake true thicknesses may be 60-80% of the down hole thickness due to terrain constraints and consequent oblique intersection angles. Relevant cross sections are included in the announcement.
Sample security	<ul style="list-style-type: none"> The measures taken to ensure sample security. 	<ul style="list-style-type: none"> The chain of custody for the drill core samples from collection to dispatch to the

Criteria	JORC Code explanation	Commentary
		assay laboratory was managed by Ban Phuc Nickel Mines personnel. Sample numbers were unique and did not include any locational information useful to non-Ban Phuc Nickel Mines and non-Blackstone Minerals personnel. The level of security is considered appropriate.
Audits or reviews	<ul style="list-style-type: none"> The results of any audits or reviews of sampling techniques and data. 	<ul style="list-style-type: none"> The assay results agree well with the observed mineralogy, historic mining and exploration results. The presence of Ni and Cu in pre-assay logged sulfide zones were also confirmed by Niton portable XRF device (refer to previous Blackstone Minerals announcements to the ASX and additionally available from http://blackstoneminerals.com.au). Further drilling is planned to refine the shape and extents of mineralised zones as necessary.

Section 2 Reporting of Exploration Results

(Criteria listed in the preceding section also apply to this section)

Criteria	Explanation	Commentary
Mineral tenement and land tenure status	<ul style="list-style-type: none"> Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings. The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area. 	<ul style="list-style-type: none"> The drilling was located within the Ta Khoa Concession and is covered by the Foreign Investment Licence, 522 G/P, which Ban Phuc Nickel Mines Joint Venture Enterprise (BPNMJVE) was granted on January 29th, 1993. An Exploration Licence issued by the Ministry of Natural Resources and Environment covering 34.8 km² within the Ta Khoa Concession is currently in force. Blackstone Minerals Limited owns 90% of Ban Phuc Nickel Mines.
Exploration done by other parties	<ul style="list-style-type: none"> Acknowledgment and appraisal of exploration by other parties. 	<ul style="list-style-type: none"> The first significant work on the Ban Phuc nickel deposit and various adjacent prospects including Ban Chang was by the Vietnamese Geological Survey in the 1959-1963 period. The next significant phase of exploration and mining activity was by Asian Mineral Resources from 1996 to 2018, including mining of the Ban Phuc massive sulfide vein mining during the 2013 to 2016 period. The project, plant and infrastructure has been on care and maintenance since 2016.
Geology	<ul style="list-style-type: none"> Deposit type, geological setting and style of mineralisation. 	<ul style="list-style-type: none"> The late Permian Ta Khoa nickel-copper-sulfide deposits and prospects are excellent examples of the globally well-known and economically exploited magmatic nickel - copper sulfide deposits. The identified nickel and copper sulfide mineralisation within the project include disseminated, net texture and massive sulfide types. The disseminated and net textured mineralisation occurs within dunite accumulate intrusions, while the massive sulfide veins typically occur in the

Criteria	Explanation	Commentary
		adjacent metasedimentary wall-rocks and usually associated with narrow ultramafic dykes. For more detail of the deposit and regional geology see Mapleson and Grguric N43-101 Technical Report on the Ta Khoa (Ni Cu Co PGE) Prospects Son La Province, Vietnam available from System for Electronic Document Analysis and Retrieval (www.sedar.com) for Asian Minerals Resources Limited. A recent summary of the geology of the Ban Phuc intrusion can be found in Wang et al 2018, A synthesis of magmatic Ni-Cu-(PGE) sulfide deposits in the ~260 Ma Emeishan large igneous province, SW China and northern Vietnam, Journal of Asian Earth Sciences 154.
Drill hole Information	<ul style="list-style-type: none"> A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes: <ul style="list-style-type: none"> easting and northing of the drill hole collar; elevation or RL (Reduced Level - elevation above sea level in metres) of the drill hole collar; dip and azimuth of the hole down hole length and interception depth; hole length. If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case. 	<ul style="list-style-type: none"> Drill hole coordinates, depth, orientation, hole length and assay results are given in Tables 3 and 4. For the Company's best understanding of previous owners drilling please refer to previous Blackstone Minerals announcements to the ASX and additionally available from http://blackstoneminerals.com.au
Data aggregation methods	<ul style="list-style-type: none"> In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g. cutting of high grades) and cut-off grades are usually Material and should be stated. Where aggregate intercepts incorporate short lengths of high-grade results and longer lengths of low-grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail. The assumptions used for any reporting of metal equivalent values should be clearly stated. 	<ul style="list-style-type: none"> Assay results given in Table 4 represent the drill core intervals as sampled and assayed. Upper cuts have not been applied. Metal equivalent values are not used.
Relationship between mineralisation widths and intercept lengths	<ul style="list-style-type: none"> These relationships are particularly important in the reporting of Exploration Results. If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported. If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (e.g. 'down hole length, true width not known'). 	<ul style="list-style-type: none"> All intervals reported in Table 3 are down hole. Structural orientations determined from orientated drill core suggest that the reported intersections and intervals are >80% of the true thicknesses for Ban Chang and Ta Cuong. The King Snake intersections range from c. 60 to >80% of true thickness. Appropriate drill sections are included in the body of this release.

Criteria	Explanation	Commentary
Diagrams	<ul style="list-style-type: none"> Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported. These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views. 	<ul style="list-style-type: none"> Appropriate exploration plan and sections are included in the body of this release.
Balanced reporting	<ul style="list-style-type: none"> Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced, to avoid misleading reporting of Exploration Results. 	<ul style="list-style-type: none"> All drill results given in Table 4 represent the intervals as sampled and assayed.
Other substantive exploration data	<ul style="list-style-type: none"> Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples - size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances. 	<ul style="list-style-type: none"> Appropriate exploration plan and sections are included in the body of this release. For the Company's best understanding of previous owners drilling please refer to previous Blackstone Minerals announcements to the ASX and additionally available from http://blackstoneminerals.com.au
Further work	<ul style="list-style-type: none"> The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large-scale step-out drilling). Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive. 	<ul style="list-style-type: none"> Blackstone Minerals proposes to conduct further drilling and associated activities to better define and extend the identified mineralised zones. An appropriate exploration plan is included in the body of this release.