

ASX Release



7 March 2024

SIGNIFICANT EXPANSION OF STATED RESOURCES AT LAKE WAY AND CENTIPEDE-MILLIPEDE DEPOSITS BOOSTS VALUE OF WILUNA URANIUM PROJECT

Rapidly improving market leads Toro to lower the cut-off grade and expand the stated uranium (U_3O_8) and vanadium (V_2O_5) resources at the Lake Way and Centipede-Millipede Deposits by up to 25% U_3O_8 .

- Rapidly improving uranium market is driving significantly improved economics at the Wiluna Uranium-Vanadium (U-V) Deposits.
- As a result Toro has lowered the U₃O₈ and V₂O₅ cut-off grade for the stated resources at the Lake Way and Centipede-Millipede U-V Deposits from 200ppm to 100ppm, which effectively expands the stated resource and lowers the average grade.
- The stated Centipede-Millipede U₃O₈ resource expands by <u>25% or 5.98Mlbs to 29.95Mlbs contained U₃O₈</u>, with a reduction in average grade to 351ppm U₃O₈.
- The stated Lake Way U₃O₈ resource expands by 15% or 1.79Mlbs to 14.12Mlbs contained U₃O₈, with a reduction in average grade to 406ppm U₃O₈.
- The stated Centipede-Millipede V_2O_5 resource expands by <u>17% or 6.6Mlbs to 45.2Mlbs contained V_2O_5 , with a reduction in average grade to 281ppm V_2O_5 .</u>
- The stated Lake Way V₂O₅ resource expands by <u>9.5% or 1.1Mlbs to 12.7Mlbs contained V₂O₅</u>, with a reduction in average grade to 307ppm V₂O₅.
- The Lake Maitland deposit will be re-estimated to better define the resource at the new cut-off grade before restating the resource and re-calculating the total Wiluna Project resources at the new cut-off grades.
- The lower cut-off grade will also allow for better comparison with Toro's industry peers, many of whom also state uranium resources at a 100ppm U₃O₈ cut-off.



Management Commentary

Commenting on this excellent news Toro's Executive Chairman, Richard Homsany, said:

"Toro's commitment to fast-track the development of the Wiluna Uranium Project towards production, amongst the backdrop of a rapidly strengthening uranium market, continues to unlock considerable value. The stated resource expansion and ongoing pilot plant work are important pillars of our refreshed feasibility study and will further demonstrate the significant returns on offer at Wiluna.

It is becoming more evident that the environmental permits at Wiluna require augmentation to cater for the paradigm shift in the potential economics and enhanced environmental values of the Project that have resulted from our vastly improved metallurgical flowsheet. As a product of our focused and cost effective work since Wiluna was permitted in 2017, the potential feasibility of Wiluna has been transformational and grown in value through our R&D efforts.

Importantly, Toro remains on track to align the finalisation of our optimal development strategy at Wiluna with the potential shift on government policy regarding uranium development in WA.

It may be the case that the uranium-vanadium deposits at Wiluna are developed at one single processing operation or via multiple simultaneous processing operations. A potential stand-alone Lake Maitland operation presently differs from the permitted greater Wiluna Uranium Project in that it contemplates a different processing flow sheet with major changes to the processing plant and reagent volumes, and a simpler more conventional mining method.

The outcome of Toro's evaluation of this optionality, which is to identify the most financially feasible development for its shareholders, will drive our approach to seeking any revision to the regulatory conditions under which we are permitted to operate.

Toro looks forward to providing further updates on our development and value creation within its asset portfolio. Toro is strongly funded and well positioned to deliver on its stated milestones."

Toro Energy Limited (ASX: TOE) ('the **Company'** or '**Toro**') is pleased to announce that the Company has decided to expand the stated uranium (as U_3O_8) and vanadium (as V_2O_5) resources at both the Centipede-Millipede and Lake Way uranium-vanadium (U-V) deposits (Figure 1) by reducing the stated U_3O_8 and V_2O_5 resource cut-off grades at these two deposits to 100ppm from 200ppm.

The decision to reduce the cut-off grade is in response to a rapidly changing uranium market towards positive economics for Toro's uranium resources, potential mining scenarios with pit boundaries beyond current stated resource cut-off grades and to allow for better comparison of Toro's total resource base to that of its uranium peers, many of whom also report stated resources at a $100ppm\ U_3O_8\ cut-off$.



Before restating the Lake Maitland U-V Deposit resource, and therefore the total Wiluna U-V Project U_3O_8 and V_2O_5 resources, the Lake Maitland resource will be re-estimated with a U_3O_8 resource envelope that better matches the design criteria used for the other Wiluna U-V deposits (see below for further details). Toro will now also audit the Nowthanna and Dawson Hinkler U-V resources for potential stated resource expansions at a lower cut-off grade.

The new expanded resources are as follows:

Centipede-Millipede

URANIUM

Contained U_3O_8 increases by 25% or 5.98Mlbs to **38.7Mt at 351ppm for 29.95Mlbs at a 100ppm U_3O_8 cut-off.** Average grade decreased from the previous 553ppm U_3O_8 .

VANADIUM

Contained V_2O_5 increases by 17% or 6.6Mlbs to **73.1Mt at 281ppm for 45.2Mlbs at a 100ppm** V_2O_5 **cut-off**. Average grade decreased from the previous 327ppm V_2O_5 .

Lake Way

URANIUM

Contained U₃O₈ increases by 15% or 1.79Mlbs to **15.78Mt at 406ppm for 14.12Mlbs at a 100ppm U₃O₈ cut-off.** Average grade decreased from the previous 545ppm U₃O₈.

VANADIUM

Contained V_2O_5 increases by 9.5% or 1.1Mlbs to **18.7Mt at 307ppm for 12.7Mlbs at a 100ppm** V_2O_5 **cut-off**. Average grade decreased from the previous 335ppm V_2O_5 .

The tables of resources are presented in Appendix 1 and the JORC Table 1 for the resources is presented in Appendix 2.

Toro decided to audit its stated uranium resources and their associated cut-off grades when it became apparent that the improved economics of the stand-alone Lake Maitland operation had allowed the associated pit re-optimisation to expand the proposed Lake Maitland mining pit into resource grades below the stated 200ppm U_3O_8 cut-off grade (refer to ASX announcement of 24 October 2022). Rapidly changing market conditions towards the positive for uranium since this re-optimisation have sent the U_3O_8 spot price over US\$100/lb (see end of month Cameco Corp UxC and Trade Tech average U_3O_8 spot price calculation for January 2024 https://www.cameco.com/invest/markets/uranium-price) which is some US\$30/lb or 43% more than the base case U_3O_8 price used in that pit re-optimisation. This further highlighted the need to revisit the stated U_3O_8 resource cut-offs for all of Toro's uranium resources. As stated above, stating the uranium resources at a 100ppm U_3O_8 cut-off will also allow the market to better compare Toro's total resource base with its industry peers, many of whom have also moved to or already state uranium resources at a 100ppm U_3O_8 cut-off.



Toro will now re-estimate the Lake Maitland resource to better define the resources at the lower cut-off grade in order to expand the stated resources for Lake Maitland and the entire Wiluna U-V Project at a 100ppm U₃O₈ cut-off. Toro will also proceed to audit the Nowthanna and Dawson Hinkler U-V resources for potential resource expansion at a lower cut-off grade.




Figure 1: Wiluna Uranium Project



This announcement was authorised for release to the ASX by the Board of Toro Energy Limited.

Katherine Garvey Legal Counsel and Company Secretary, Toro Energy Limited 60 Havelock Street, West Perth WA 6005

For further information contact

Richard Homsany Greg Shirtliff +61 8 9214 2100

About Toro

Toro Energy Limited (ASX:TOE) is an ASX listed uranium development and exploration company with projects in Western Australia. Toro's tenure in Western Australia is also prospective for gold and base metals. Toro is committed to building an energy metals business with the flagship Wiluna Uranium Project as the centrepiece. The Wiluna Uranium Project consists of the Centipede-Millipede, Lake Maitland, Lake Way uranium deposits 30km to the south of the town of Wiluna in Western Australia's northern goldfields.

Please visit <u>www.toroenergy.com.au</u> for further information.

Competent Persons' Statement

Wiluna Project Mineral Resources – 2012 JORC Code Compliant Resource Estimates – U₃O₃ and V₂O₅ for Centipede-Millipede, Lake Way and Lake Maitland.

The information presented here that relates to U_3O_8 and V_2O_5 Mineral Resources of the Centipede-Millipede, Lake Way and Lake Maitland deposits is based on information compiled by Dr Greg Shirtliff of Toro Energy Limited and Mr Daniel Guibal of Condor Geostats Services Pty Ltd. Mr Guibal takes overall responsibility for the Resource Estimate, and Dr Shirtliff takes responsibility for the integrity of the data supplied for the estimation. Dr Shirtliff is a Member of the Australasian Institute of Mining and Metallurgy (AusIMM) and Mr Guibal is a Fellow of the AusIMM and they have sufficient experience which is relevant to the style of mineralisation and type of deposit under consideration and to the activity they are undertaking to qualify as Competent Persons as defined in the 2012 Edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves (JORC Code 2012)'. The Competent Persons consent to the inclusion in this release of the matters based on the information in the form and context in which it appears.



Appendix 1 : Tables of Resources for the Wiluna Uranium-Vanadium Project at 100ppm (Table A) and 200ppm (Table B) grade cut-offs.

	A - Wiluna Uranium Project Resources Table (JORC 2012)								
At 100	At 100ppm cut-offs inside U ₃ O ₈ resource envelopes for each deposit - Proposed Mine Only								
		Meas	sured	Indicated		Inferred		Total	
		U_3O_8	V_2O_5	U_3O_8	V_2O_5	U ₃ O ₈	V_2O_5	U_3O_8	V_2O_5
O antima da 1	Ore Mt	7.49	-	21.26	-	9.96	73.1	38.7	73.1
Centipede / Millipede	Grade ppm	428	-	392	-	206	281	351	281
wimpede	Oxide Mlb	7.07	-	18.36	-	4.52	45.2	29.95	45.2
	Ore Mt	-	-	TBA	-	-	TBA	TBA	TBA
Lake Maitland	Grade ppm	-	-	TBA	-	-	TBA	TBA	TBA
	Oxide Mlb	-	-	TBA	-	-	TBA	TBA	TBA
	Ore Mt	-	-	15.78	-	-	18,7	10.3	18.7
Lake Way	Grade ppm	-	-	406	-	-	307	545	307
	Oxide Mlb	-	-	14.12	-	-	12.7	12.3	12.7
	Ore Mt	7.49	-	TBA	-	9.96	TBA	TBA	TBA
Total	Grade ppm	428	-	TBA	-	206	TBA	TBA	TBA
	Mlb	7.07	-	TBA	-	4.52	TBA	TBA	TBA

At 200	B ppm cut-o					able (JORC		d Mine Onl	v
At 200	ppm out o		sured	Indicated		Inferred		Total	
		U ₃ O ₈	U ₃ O ₈ V ₂ O ₅		V_2O_5	U ₃ O ₈	V_2O_5	U ₃ O ₈	V_2O_5
0	Ore Mt	4.9	-	12.1	-	2.7	53.6	19.7	53.6
Centipede / Millipede	Grade ppm	579	-	582	-	382	327	553	327
wiinipede	Oxide Mlb	6.2	-	15.5	-	2.3	38.6	24	38.6
	Ore Mt	-	-	22	-	-	27	22	27
Lake Maitland	Grade ppm	-	-	545	-	-	303	545	303
	Oxide Mlb	-	-	26.4	-	-	18	26.4	18
	Ore Mt	-	-	10.3	-	-	15.7	10.3	15.7
Lake Way	Grade ppm	-	-	545	-	-	335	545	335
	Oxide Mlb	-	-	12.3	-	-	11.6	12.3	11.6
	Ore Mt	4.9	-	44.3	-	2.7	96.3	52	96.3
Total	Grade ppm	579	-	555	-	382	322	548	322
	Mlb	6.2	-	54.2	-	2.3	68.3	62.7	68.3



Appendix 2

JORC Code, 2012 Edition – Table 1 report – Wiluna Uranium Project – Toro Energy Limited Section 1 Sampling Techniques and Data

Section 1 Sampling Techniques and Data

(Criteria in this section apply to all succeeding sections.)

Criteria

Sampling techniques

JORC Code explanation

- Nature and quality of sampling (eg cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling.
- Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.
- Aspects of the determination of mineralisation that are Material to the Public Report.
- In cases where 'industry standard' work has been done this would be relatively simple (eg 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information.

Commentary

- V₂O₅ values are calculated from the direct geochemical analysis of vanadium (V) in drill samples. The geochemical analysis results used in the estimation are from a combination of Toro Energy and historical drilling.
- U₃O₈ values are calculated from a combination of the direct geochemical analysis of uranium (U) in drill samples and gamma radiation readings from a gamma probe (see below for details of method), which are comparatively reviewed with geochemistry where geochemistry is available in the same drill hole. The gamma data used in the estimation are from a combination of Toro Energy and historical drilling, whilst the geochemistry is from Toro only drilling, except for Lake Maitland (see below).

Geochemistry (Lake Maitland excluded)

- Toro's geochemical samples on all of the Wiluna deposits except Lake Maitland (most of the geochemistry at Lake Maitland is from sampling by Mega Uranium, only 2014 and geochemical samples are represent 0.5m half core lengths (prior to 2013) or full core lengths (2013 and planned into the future) of 100mm sonic drill core. Full core samples provide an 8-10kg sample to the lab, half core samples are half this weight approximately. After crushing the lab splits a 2.5 kg sub-sample for milling (pulverizing) to 90% passing 75micron, before taking an aliquot for V analysis by 4 acid digest ICPMS (prior to 2013) or fusion-ICPMS (2013 and into the future).
- In the case of half core samples field duplicates of the core are taken to ensure sample representativity, these field duplicates are the other half of the core that has been sampled. In the case of full core samples, duplicates are taken at the first sample split at the lab, directly



JORC Code explanation Commentary after the initial crush, these duplicates are taken with a rotary splitter after pushing the sample back through the crusher after the initial split. It should be noted that due to the size of the sample supplied to the lab, the initial crushing is a two-step process, a primary crush to 10mm and a secondary crush to 3mm. Both these duplicates are taken at a rate of 1 in 20 or 5% of all non-standard samples. Differences in V concentrations between the duplicates and their corresponding samples are used to produce a mean standard sampling error. Lab duplicates are taken at every stage of the sub-sampling process prior to analysis at the rate of 1 in 20. Geochemical samples are taken through the uranium (U) resource ore zones as determined by hand-held scintillometers and if available at the time of sampling, down-hole gamma measurements. This is considered sufficient since the V resource is a by-product of the uranium resource. The half metre intervals are determined from marking up half metre intervals down the full length of the core from the surface. This is completed at the rig so that any drilling issues can be observed and the geologist can have direct communication 'on the spot' with the driller. To gain geochemical and mineralogical information of waste material or for metallurgical purposes etc., often the entire hole is sampled for geochemistry and a larger suite of elements are analysed for, some having to employ different analytical techniques. Depth corrections are made to geochemistry samples where appropriate, these are based on comparing the down-hole geochemistry to the down-hole gamma U values and assuming the down-hole depth as measured by the gamma probe during probing is correct. Winch cable stretch is not considered an issue in the Wiluna drilling due to the shallow depth of almost all drilling (maximum depth of approximately 25m but mostly no deeper than 10m). Toro uses Auslog natural gamma probes, either in-house or from external contractors. Measurements are made every 2 cm with a logging speed of 3.5m per minute. Prior to the drilling program all gamma probes are calibrated at the Adelaide Calibration Model pits in Adelaide, South Australia. During probing operations every 10th hole is logged twice as a duplicate log. Selected holes across the deposits are used as reference holes for relogging to detect drift in the instrument during each program. Gamma measurements are converted to equivalent U₃O₈ values (eU₃O₈) by an algorithm that takes into account the probe



JORC Code explanation Commentary and crystal used, density, hole diameter, ground water where applicable and PVC pipe thickness. Down-hole gamma probe data is also de-convolved to more accurately reflect what would be expected in nature for down-hole response (gamma curves). **Geochemistry (Lake Maitland only)** Apart from 47 sonic holes drilled in 2014 and 2015, all of the geochemistry in the Lake Maitland estimations is derived from Mega drilling. For the Toro Energy geochemistry related approach and systems see above under "Lake Maitland excluded". Mega Uranium's geochemical samples on the Lake Maitland deposits represent 0.25 m full core lengths of 83 mm diamond drill core (PQ3). Weights of the geochemical samples ranged from 2-5 kg approximately. Intervals were determined during core mark-up and identified with plastic core blocks. Samples were dried at 110 °C before weighing and then crushing. After crushing a sub-sample was split using a rotary splitter for milling (pulverizing) to 90% passing 75 micron, before taking an aliquot for V analysis by 4 acid digest ICPMS. Due to full core sampling no duplicates were needed to measure in-field sampling error. Duplicates were instead taken at the first sample split at the lab, directly after the initial crush, these duplicates were taken with a rotary splitter after pushing the sample back through the crusher after the initial split at a rate of approximately 1 in 20 or 5% of all non-standard Lab duplicates were taken at every stage of the sub-sampling process prior to analysis at the rate of approximately 1 in 20. Geochemical samples were taken through the entire length of each drill hole. The 0.25 m intervals were determined from marking up 0.25 m intervals down the full length of the core from the surface. Other elements analysed include Ba, Th, Al, Ca, Fe, K, Mg, Mn, S, Sr, Ti and U. Depth corrections were made to geochemistry samples where appropriate, these were based on comparing the down-hole geochemistry to the down-hole gamma U values and assuming the down-hole depth as measured by the gamma probe during probing was correct. Winch cable stretch is not considered an issue at Lake Maitland drilling due to the shallow depth of drill holes (3-9 m on average). No depth corrections were deemed necessary. Mega used a 33 mm Auslog natural gamma Criteria



JORC Code explanation Commentary probe (S691) 'in-house', to measure down-hole gamma radiation. Measurements were made every 1 or 2 cm with a logging speed of approximately 2 m per minute. The gamma probes were used on all drill holes, diamond. sonic and aircore. Prior to the drilling program all gamma probes are calibrated at the Adelaide Calibration Model pits in Adelaide, South Australia. During probing operations selected holes are logged twice as a duplicate log. Some selected holes across the deposits are used as reference holes for re-logging to detect drift in the instrument during each program. Gamma measurements are converted to equivalent U₃O₈ values (eU₃O₈) by an algorithm that takes into account the probe and crystal used, density, hole diameter, ground water where

> Historical Aircore - Centipede-Millipede and Lake Way only

curves).

applicable and PVC pipe thickness. Down-hole gamma probe data is also de-convolved to more accurately reflect what would be expected in nature for down-hole response (gamma

There is limited information on the historical aircore drilling. Geochemical samples were collected from historical aircore in 1m intervals from piles of drill chips on the ground that represented 1m intervals of drilling direct from the cyclone. Geochemical analysis was achieved by XRF according to previous resource estimation reports on the uranium mineralisation.

Drilling techniques Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc).

All Wiluna deposits excluding Lake Maitland

- Both sonic and aircore drilling techniques have been utilized on the Wiluna Project.
- The sonic drilling utilizes a 100mm core barrel (inside diameter) with outside casing where needed, producing a 150mm hole diameter and 100mm core. Depending on the ground conditions and thus quality of core being produced, core is retrieved from the 3m barrel in either 1 to 3m length, 1m at a time. Upon exiting the barrel, core is transferred into tubular plastic bags that fit the core before being placed in core trays.
- Aircore drilling is conventional with a 72mm bit producing an approximate 100mm diameter hole.

Lake Maitland only



Criteria JORC Code explanation	Co	ommentary
	•	Diamond, sonic, auger core and air core drilling techniques have all been utilized on the Lake Maitland deposit, however, only diamond and sonic drilling techniques have been utilised to derive the geochemistry used in the V_2O_5 resource estimation. The sonic drilling utilizes a 100mm core barrel (inside diameter) with outside casing where
		needed, producing a 150mm hole diameter and 100mm core. Depending on the ground conditions and thus quality of core being produced, core is retrieved from the 3m barrel in either 1 to 3m length, 1m at a time. Upon
		exiting the barrel, core is transferred into tubular plastic bags that fit the core before being placed in core trays. On occasions where the sonic core was being used for density measurements a hard plastic (clear) cylinder that fits the core
	•	was used instead to ensure lasting core integrity. Diamond drilling is PQ3, which utilizes an 83.18
		mm core barrel (inside diameter) and produces an 83 mm diameter core with an approximate 123 mm diameter hole.
Drill sample • Method of recording and assessing core		All Wiluna deposits excluding Lake Maitland
recovery and chip sample recoveries and results assessed.	•	Chip sample recoveries have not been
	•	recorded. Sonic core recoveries are estimated based on a
		combination of measurement, observation of drilling, the driller's direction, observations made on quality of sample during geological
		logging and sample weight comparisons to average weights and rock type. It should be noted that precise core recovery estimation on
Measures taken to maximise sample		sonic drill core in the Wiluna deposits is inherently difficult due to expansion and contraction of soft sediments during drilling and
recovery and ensure representative nature of the samples.	•	during recovery of core from the barrel. Core loss is minimized by 'casing as we drill'
Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse	•	through all ore zones or any zone where the geological information is critical such as for geotechnical purposes. There is no correlation between estimated core loss and grade
material.		Lake Maitland only
	•	Sonic core recoveries are estimated based on a combination of measurement, observation of drilling, the driller's direction, observations made on quality of sample during geological logging and sample weight comparisons to average weights and rock type. It should be noted that precise core recovery estimation on sonic drill core at Lake Maitland is inherently difficult due to expansion and contraction of soft



Criteria	JORC Code explanation	Commentary
		 sediments during drilling and during recovery of core from the barrel. Diamond core recoveries have been determined by conventional techniques of identification of lost core by driller and geologist at the rig and during core mark up and measure. Core trays are also weighed without and then with core to estimate core recovery based on assumed SG for particular lithology. During sonic core drilling core loss is minimized by 'casing as we drill' through all ore zones or any zone where the geological information is critical such as for geotechnical purposes. There is no correlation between estimated core loss and grade in the Lake Maitland data.
		Historical Aircore – Centipede-Millipede and Lake Way only
3		 Historically, chip sample recoveries have not been recorded in the database.
Logging	 Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies. Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography. The total length and percentage of the relevant intersections logged. 	 It is important to understand that as V is considered a by-product of the U processing, the relationship between geology and V concentrations are not considered essential in the estimation process, it is the relationship between uranium and geology that is important. Geology is not used in the resource estimation process for U, the reasons for this are explained in more detail below, however, basically the deposit has been found to be correlated more to groundwater and depth from the surface than to any geological unit. Thus the geological logging is adequate for resource estimation. Current geological logging (all Toro) is considered to be adequate for the stage of mine planning that Toro is currently at, on the Wiluna Project. Further work is considered necessary to amalgamate or align historical geology logs and geology to current across all deposits.
		 Current logging is both qualitative (subjective geological opinion of rock type and colour and in the case of Lake Maitland, also by limited mineral identification by spectral analysis) and quantitative (recording specific depth intervals and percentages of grain sizes, or in the case of Lake Maitland inclusive of limited quantification of mineralogy by spectral analysis via Hylogger). Core photographs are taken for each individual metre (prior to 2013) and half metre (2013) after core has been split down the middle for logging and so as to see sedimentological features for logging (avoiding clay smear on



	Criteria	JORC Code explanation	Commentary
			 outer surface of core made by drill rods). In the case of Lake Maitland, core photographs have been taken for the entire 2011 drilling program, which consists of a total of 201 holes and is spread across the entirety of the deposit. All drilling intersections have been logged geologically
)	Sub-sampling techniques and sample preparation	 If core, whether cut or sawn and whether quarter, half or all core taken. If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry. For all sample types, the nature, quality and appropriateness of the sample preparation technique. 	 As described above, geochemical samples represent 0.5m half core lengths (prior to 2013) or full core lengths (2013 and planned into the future) of 100mm sonic drill core. At Lake Maitland geochemical samples represent 0.25m full core lengths of 100mm sonic drill core or 83mm diamond core. In historical aircore the samples are representations of each metre drilled as drill chip flow from the cyclone on the drill rig.
)) 1		Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.	 Sample preparation has been described above under 'sampling techniques, it is considered that all sub-sampling and lab preparations are consistent with other laboratories in Australia and overseas and are satisfactory for the intended purpose.
)		Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling.	• In the case of half core samples field duplicates of the core are taken to ensure sample representation, these field duplicates are the other half of the core that has been sampled. In the case of full core samples, duplicates are taken at the first sample split at the lab, directly after the initial crush, these duplicates are taken with a rotary splitter after pushing the sample back through the crusher after the initial split. It should be noted that due to the size of the sample supplied to the lab, the initial crushing is a two-step process, a primary crush to 10mm and a secondary crush to 3mm.
)		Whether sample sizes are appropriate to the grain size of the material being sampled.	 Total sampling errors calculated from half core field duplicates typically range from ±10-20%. Total sampling errors for the first split at the lab in case of full core sampling typically range from ±1-10%.
			 The laboratory used for Toro's geochemical analysis bases all crushing grain sizes and subsequent sub-sampling weights on being inside accepted Gy safety lines for sample representation. These grains sizes and sub- sample weights have been described above under 'sampling techniques'.



Criteria J	IORC Code explanation	Commentary
Quality of assay data and	of the assaying and laboratory procedures used and whether the	All Wiluna deposits (pre-2014) Prior to 2013 a four acid digest followed by
laboratory tests	Ear goonbusies! tools, appetrometers	ICPMS (4-ICPMS) was employed for analysis for geochemistry— this was assumed to be an almost total rock digest technique although with recognition that highly resistant minerals are sometimes not entirely digested. In 2012 a test was done to compare 4-ICPMS with sodium peroxide fusion followed by ICPMS (F-ICPMS) with fused glass XRF (XRF) for the analysis of U. Analysis of a number of standards suggested that the F-ICPMS was the most accurate. So since 2013, F-ICPMS has been used as the basis for all geochemistry. However, on a number of samples 4-ICPMS and fused glass XRF are still used for comparative purposes (U only). In 2014 and 2015 approximately 1 in 50 samples was analysed by fused glass XRF as an intra-lab technique check. Both F-ICPMS and fused glass XRF are considered total rock
•	handheld XRF instruments, etc, the	analytical techniques.
	parameters used in determining the analysis including instrument make and model, reading times, calibrations factors	 Historical geochemistry, mostly at the Lake Way deposit, is almost entirely XRF.
•	applied and their derivation, etc. Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been established.	 Certified matrix matched standards for U only are used to check analyses at the lab at a rate of approximately 5% or 1 in 20 samples. Toro energy has 3 matrix matched U standards from the Centipede ore zone representing a spread through the represented ore grades at Wiluna. Standards are checked against 2 standard deviations (2SD) and 3 standard deviations (3SD) from the mean (the registered value for each particular standard). No standard is allowed to be returned outside 3SD from the mean, an allowance of 5% (95% confidence interval) is made for standards returned between 2SD and 3SD outside the mean. Results analyses of standards are checked against the historical record for inter-program drift. To date, there has been no issue with analyses of standards at the lab. This includes the analysis of V.
		 Since this is primarily a U project, blanks have all been prepared on the basis of U checks. Coarse quartz sand is used as blanks and these are used at a rate of approximately 5% or 1 in 20 samples as well as being strategically placed in front of and behind samples expected to have high concentrations of U so that thresholds for potential cross-contamination within preparations can be obtained. To date there has been no contamination or cross-contamination of significance for ore grades or even the 70-



Criteria JORC Code explanation	Commentary
	100ppm U₃O ₈ mineralised envelopes.
	 Duplicates are used as already explained in detail above.
	 Limited laboratory checks have been made – approximately 3% of all geochemistry samples were represented in 2013 and the lab has remained the same.
	Lake Maitland only – pre-2014
	 In the extensive 2011 diamond drilling program a four acid digest followed by ICPMS was employed for geochemical analysis (ALS laboratories, Perth) – this was assumed to be an
	almost total rock digest technique although with recognition that highly resistant minerals are sometimes not entirely digested. Due to these
	potential issue and the fact that ICPMS has in earlier times had issues dealing with high U concentrations due to dilution factors (etc.), the
	Mega geologists decided to re-analyse all samples with ICPMS results for U of greater than 500 ppm utilizing the XRF technique at the same laboratory
	(ALS, Perth), regarded by Mega geologists as a better whole rock technique.
	 Historical geochemistry data is almost entirely XRF.
	 Since this is primarily a U project, standards were prepared on the basis of U checks. This
	is deemed sufficient for an Inferred V resource assessment (JORC 2012) "Off the shelf" OREAS U standards were used to check
	analyses at the lab at a rate of 2% or 1 in 50 samples.
	 Coarse quartz sand was used as blanks and these were used at a rate of 2% or 1 in 50 samples.
	 Since this is primarily a U project, all lab duplicates were prepared for checks on U. This is deemed sufficient for an Inferred V resource assessment (JORC 2012) Lab duplicates were used as already explained in detail above, from the primary crush stage and every other sub- sampling stage. Limited laboratory checks



	Criteria JORC Code explanation	Commentary
		have been made – from the most recent drilling (2011) a total of 138 samples were re-analysed for U by 4 acid digest ICPMS by a different commercial laboratory (Genalysis, Perth). The samples were chosen as representative of the following U ₃ O ₈ concentrations – 10% between 100 and 200 ppm U ₃ O ₈ , 40% from between 200 and 500 ppm U ₃ O ₈ , and 50% from above 500 ppm U ₃ O ₈ . Differences between the labs were satisfactory, the largest being approximately 5% on average higher values from the XRF derived U ₃ O ₈ by ALS over the ICPMS U ₃ O ₈ by Genalysis, this was taken into consideration during estimations.
	Verification of sampling and assaying • The verification of significant intersections by either independent or alternative company personnel.	 Limited interlab geochemistry analytical checks are completed for each drilling campaign for U, the last interlab check represented 3% of all the geochemical samples. Toro has a calibrated (at the Adelaide Calibration Model pits in Adelaide, South Australia) Auslog gamma probe to check the probing results achieved by external contractors. During probing operations every 10th hole is logged twice as a duplicate log. Selected holes across the deposits are used as reference holes for re-logging to detect drift in the instrument during each program. In 2013 over 50% of all holes drilled at Dawson Hinkler were re-logged with a different probe (from the same contractor) over 3 months after they were drilled to confirm results (results were confirmed). In 2015, a different contractor with a larger probe (larger crystal) was employed along with the normal contractor, again to check
	The use of twinned holes.	the accuracy of the gamma data collected against different probes and at the same moment in time. No significant differences in calculated U ₃ O ₈ values were observed between the two different contractors, once again confirming the validity of the gamma data used in the resource estimations.
)	Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.	At Lake Maitland, a limited number of holes have been twinned - these include twinned holes drilled by both sonic and diamond core methods. A large proportion (approximately 10%) of the holes at Lake Way have been twinned to compare historical data on the U resource.
		 All primary data (gamma log las files, geochemical sample lists, final collar files, geological logs, core photographs, electronic geochemical results, drillers plods, probing



Criteria	JORC Code explanation	Commentary
	Discuss any adjustment to assay data.	plods, de-convolved gamma files, gamma gamma density logs, disequilibrium analysis results etc) are stored on the company server in the appropriate drive and folders. Any hardcopy data, such as official geochemistry results or any paper copy geological logs, are kept in hardcopy in folders and archives as well as being scanned and kept on the company server in the appropriate drives and folders.
		 Data entry procedures are described in some detail below in section 3 under 'data integrity'.
		 To date, there has been no significant adjustments made to geochemical assay U₃O₈ data (or to any other elements). Slight adjustments are made to some geochemical assay data to account for depth corrections if an interval error is discovered, this is rare and always restricted to the near surface above mineralized zones.
		Adjustments to gamma derived eU ₃ O ₈
		 During the estimation process, a factor is applied to all gamma data inside the mineralised envelope at Lake Maitland of 1.25 and at Centipede, Millipede and Dawson Hinkler of 1.2. It is important to note that these factors have not been applied to the eU₃O₈ data within the database, it has only been applied to data during the estimation process.
		Details as to why for each factor follow:
		• Centipede and Millipede - Significant differences between gamma derived eU ₃ O ₈ and geochemical U ₃ O ₈ have been noted since 2012 across Centipede and Millipede. After the 2015 drilling and significant research into the consistently observed difference using all available comparative data back to 2011, it was concluded that the difference was real and resulted from the gamma probe underestimating true grade by at least 20% at Centipede and Millipede, probably more. Performing linear regression on U ₃ O ₈ v eU ₃ O ₈ for all sonic holes since 2012 (where both U ₃ O ₈ and eU ₃ O ₈ is available together to compare) shows a slope of 1.5, so a 50% difference between geochemistry and gamma derived U ₃ O ₈ towards geochemistry. Spatial analysis of the difference bethe description of the difference bethe description of the difference bethe derived bethe derived bethe difference bethe derived bethe difference bethe derived between general

the difference both laterally and vertically by



Commentary Criteria **JORC Code explanation** both Toro geologists and SRK consultants using various averaging techniques and some kriging with investigative test block models in Surpac and Isatis showed that whilst there was some variation, it was surprisingly consistent and definitively positive towards geochemistry always being higher than gamma derived U₃O₈. Successive analysis of geochemical samples for secular disequilibrium by the Australian Nuclear Science and Technology Organisation (ANSTO), first from 2011 drilling and second from 2013 drilling (see ASX release of September 1st 2014) showed that whilst positive disequilibrium was contributing underestimation in parts of the deposits, it was by no means accounting for all of it. After the 2015 research and investigations by both Toro geologists and SRK consulting, it was agreed to apply a factor of 1.2 to all gamma data inside the mineralisation envelope for estimations (see further below) to better represent the 'true' uranium grade as defined by geochemistry. Given that the research shows that the real difference could be as much as 1.5 x, Toro and SRK believe the factor of 1.2 applied is conservative. Lake Maitland - A factor of 1.25 has been applied to the Lake Maitland resource in the same way the 1.2 factor was applied to the Centipede and Millipede resources (see above for details). Similarly high 'real differences' were observed of over 1.5 and in fact Toro believe that the probe is underestimating by as much as 50%. However, to be conservative it was agreed between the Toro geologists and SRK to limit the factor to 1.25. It should be noted that some of this factor is due to a deposit wide consistent positive disequilibrium; Mega have previously found that the average positive disequilibrium, via closed can analysis for secular disequilibrium on samples across the entire deposit by On Site Technologies Pty Ltd in 2011, was 1.18. Location of Accuracy and quality of surveys used to All drill hole collars are pegged to the planned data points locate drill holes (collar and down-hole collar location using a differential GPS (DGPS) with base station (currently an Austech surveys), trenches, mine workings and other locations used in Mineral Resource ProMark500 and ProFlex500). At the end of the estimation. drilling campaigns all collars a picked up using the same DGPS equipment for the final collar locations that are entered into the database. Accuracy of the DGPS is approximately to

100mm in the vertical and 50mm on the

horizontal.



	Criteria	J	ORC Code explanation	C	ommentary
1		•	Specification of the grid system used.	•	Due to all drill holes being shallow (maximum depth of 25m) and vertical no down-hole surveying is required.
		•	Quality and adequacy of topographic control.	•	The grid system used on the Wiluna Project is Geocentric Datum of Australia (GDA) 94, zone 51.
				•	Topographic control is largely achieved by the DGPS with base station. As stated above, all Toro drill holes are accurate to approximately 100mm on the vertical. The vertical control at Millipede and Centipede is checked with a light detection and ranging (LIDAR) survey after drilling. Dawson Hinkler and Lake Maitland all drill holes have been 'pinned' to a topographic surface created from current drill hole collars surveyed with a DGPS and base station.
	Data spacing	•	=,	•	No exploration results, resource drilling only
	and distribution	•	Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.	•	The data spacing and distribution has been considered appropriate for the Mineral Resource estimation procedures and classifications applied (in this case Inferred only for all resources) by the external consultant doing the resource and is based mainly on variography and continuity shown in the statistical analysis of the data. See below in resource section for further information.
				•	In determining the U_3O_8 grade shells (note also that the V_2O_5 resource is estimated within the U_3O_8 mineralisation envelopes for each deposit, at the Wiluna deposits (excluding Lake Maitland) sample compositing to 0.5m composites has been applied to the 2cm interval eU_3O_8 data to match the 0.5m geochemical core samples. At Lake Maitland, compositing to 0.25 m composites has been applied to the 1 and 2 cm interval eU_3O_8 data to match the 0.25 m geochemical core samples.
		•	Whether sample compositing has been applied.		
	Orientation of data in relation to geological structure	•	Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.	•	Sampling is non-subjective (non-biased) downhole sampling from the surface. Historical geochemistry represents a similar non-bias down-hole process. The sampling orientation employed provides no bias to the groundwater related distribution of mineralization.
		•	If the relationship between the drilling orientation and the orientation of key	•	No bias suspected, ore lenses are horizontal and drilling is vertical, cutting mineralization at an approximate right angle (90 degrees).



Criteria	JORC Code explanation	Commentary
	mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.	
Sample security	The measures taken to ensure sample security.	All Wiluna deposits excluding Lake Maitland (pre-2014)
		Sampling of drill core for geochemistry is achieved in the field directly after drilling at the drill site. All samples are bagged firstly in plastic and then again in calico (double bagged). A unique non-descript identifier number is used to number each sample that bares no relation to the deposit or the drill hole. All sample details are entered into a fixed format file ready for later import into the database. Samples are immediately transported by utility to the field camp where they are weighed before being packed into steal 44 gallon drums with lockdown lids and tested for radiation for transport classification. The drums are then fitted on timber pallets and transported to the local transport dock at Wiluna for delivery to Perth. Approximate time between sampling and transport to the laboratory is 4 weeks.
		 Sampling of gamma derived measurements is achieved by a single contractor using a gamma probe (see sampling techniques above). Raw gamma probe data is converted into a las file and sent to a Perth based office on a daily basis by email. This data is then packaged and sent to the Toro Energy Database Manager, who sends it to the analyst (consultant) for calculation of U concentrations and deconvolution.
		Lake Maitland Deposit only
		 Prior to 2014 core length was measured by drillers and blocks were put in at the end of runs. The core was then picked up by the geologist at the end of hole and taken to the core shed where it was divided into 25cm whole samples and allocated a sample ID tag, this was done by the geologist and field assistant. The core was then logged and core loss recorded. Core, in the core trays, is then stacked on to pallets (approximately 3 holes per pallet). For sample security, steel lids were used on the top row of trays before the entire pallet was plastic wrapped and steel strapped.

to ALS Perth, where it underwent spectral

· Additionally, upon transfer of the database from

logging, weighing and assay.



Criteria	JORC Code explanation	Commentary
		Mega to Toro for estimation, all data was converted to raw text files and delivered directly to SRK for the data review prior to estimation so as to avoid any loss of information by converting files into different database formats (Toro and Mega use different databases and database structures).
Audits or reviews	The results of any audits or reviews of sampling techniques and data.	 An internal review of geochemical sampling techniques in 2012 lead to a change in practice from non-selective half-core sampling to full core sampling so as to reduce total sampling error. This recommendation was followed in 2013 and has satisfactorily reduced sampling error. A review by Toro geologists of the Mega drill core sampling techniques (both for geochemistry and gamma measurements [gamma gamma for density and gamma for eU₃O₈ calculations) for the 2011 drilling program found no errors that would affect the resource estimate in any significant way. The spectral analysis based geological model, which has been used to assign density in the block model was found to be highly predictive across the deposit with a limited amount of drill holes, however given the nature of the deposit as shown in a review of multi-element geochemistry (by Toro geologists) and Toro's experience with all of the similar style Wiluna deposits, the model is considered by Toro to be a reasonable interpretation of Lake Maitland geology and in fact in most circumstances a more accurate representation of the geology and geological relationships. SRK reviewed the database that was to be used for the resource estimation and excluded any errors from the estimation. The number of exclusions was considered too small to have affected the estimation.

Section 2 Reporting of Exploration Results

NOT APPLICABLE TO THIS RESOURCE UPDATE

Criteria	JORC Code explanation	Commentary
Mineral tenement and land tenure status	 Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings. The security of the tenure held at the time of reporting along with any known 	• The Yandal Gold Project is located approximately 770km km NE of Perth and less than 35km NE of the Bronzewing Gold Mine operations. The project includes the tenements M53/1089, E53/1211, E53/1060, E53/1210 and E37/1146 which are 100% owned by Redport Exploration Pty Ltd (subject to the agreements referred to below), as well as E53/1858, E53/1929 and E53/1909, which are 100%



Criteria	JORC Code explanation	(Commentary
	impediments to obtaining a licent operate in the area.	ce to	owned by Toro Exploration Pty Ltd. Redport Exploration Pty Ltd and Toro Exploration Pty Ltd are both wholly owned subsidiaries of Toro Energy Ltd.
		•	All tenements are granted.
		•	A heritage agreement has been entered into with the traditional owners of the land the subject of the Yandal Gold Project.
		•	M53/1089 is subject to agreements with JAURD International Lake Maitland Project Pty Ltd (JAURD) and ITOCHU Minerals and Energy of Australia Pty Ltd (IMEA) under which JAURD and IMEA can acquire a 35% interest inM53/1089 and certain associated assets.
		•	The agreements with JAURD and ITOCHU may also be extended, at JAURD and IMEA's election, to uranium rights only on E53/1211, E53/1060, E53/1210 and E37/1146.
		•	Toro Exploration Pty Ltd has rights to all minerals on E53/1858, E53/1909 and E53/1929.
			Toro has agreed to pay JAURD and IMEA net smelter return royalty on non-uranium minerals produced from E53/1211, E53/1060, E53/1210 and E37/1146. The exact percentage of that royalty will depend on Toro's interest in the non-uranium rights at the time and will range from 2% to 6.67%.
		•	E53/1060 is subject to a 1% gross royalty on all minerals produced and sold from that tenement. M53/1089 is subject to a 1% net smelter return royalty on gold and on all other metals derived from that tenement, in addition to a 1% gross royalty on all minerals produced and sold from a discrete area within that tenement.
Exploration done by other parties	 Acknowledgment and appraisal o exploration by other parties. 	•	The Centipede and Millipede deposits were discovered by Esso Exploration and Production Australia and its various joint venture partners in 1977, through a regional RAB drilling over a radiometric anomaly. Exploration occurred between this time and 1982 with evaluation of the Centipede deposit with approximately 500 drill holes. This drilling was mainly by RC drilling but some auger and diamond drilling was also completed. The mineralised areas were drilled out on 100m centres and the surrounding areas on 200m centres. The grade and thickness of the uranium mineralisation was determined from radiometric logging of all holes. Some chemical assays were also completed and disequilibrium studies carried out.



Criteria JORC C	Code explanation Commentary
	Since that initial exploration and definition of a uranium resource various companies have had ownership of the Centipede resource but little further work was completed until 1999 when Acclaim Uranium NL undertook further work by gamma logging over 300 of the previous holes as well as drilling a further 120 aircore drill holes. Nova Energy gained ownership of the Centipede project and undertook various work programmes in 2006 and 2007 including: Compilation of historical data into a database Drilling of over 400 aircore drill holes with associated downhole gamma logging and sample assaying Gamma logging of approximately 100 historical holes where data had been lost Two large exploration costeans completed with a Wirtgen 2200 continuous miner Various baseline studies including groundwater, environmental and radiological studies Acquisition of satellite imagery Metallurgical studies
	 Project scoping study Significant work completed by Toro Energy alone on the deposits has included: Detailed airborne magnetic, radiometric and digital terrain model surveys over the project area in 2010 A resource estimation update of all of the Wiluna uranium deposits by SRK consulting in 2011 Resource estimation update of the Centipede and Millipede resources by SRK Consulting in 2012 taking into account new density information First phase 3-D geological modelling of all of the Wiluna Project's deposits in 2012 First phase 3-D ore shell modelling of all of the Wiluna Project's deposits in 2012 Aircore and sonic core resource drilling in 2013



Criteria	JORC Code explanation	Commentary
		 A resource estimation update on all Wiluna deposits in 2013, inclusive of Lake Maitland. Testing of grade and resource continuity over the short scale on all deposits – reconciling mine blocks to resource estimations in 2014. Sonic core drilling in 2015 A resource estimation update Centipede-Millipede and Lake Maitland in 2015-2016 A resource update based on a change in density on the Nowthanna deposit in 2016. A resource estimation for V₂O₅ for Lake Maitland, Lake Way and Centipede-Millipede inside the U₃O₈ mineralisation envelope for all deposits but using V₂O₅ cut-offs.
Geology	Deposit type, geological setting and style of mineralisation.	• The deposits are shallow groundwater carbonate associated uranium deposits. The Wiluna Uranium Project is situated in the northeast of the Archean Yilgarn Block close to the Capricorn Orogen, the structural zone formed when the Yilgarn Block and the Pilbara Block joined some 1830-1780 million years ago. The basement rocks at Wiluna are part of the Eastern Goldfields Terrane (2.74 - 2.63 Ga), a succession of greenstone belts geographically enclosed by younger granitoid (gneiss-migmatite-granite, banded gneiss, sinuous gneiss and granitic plutons) that makes up the entire eastern Yilgarn Block and representative of an extensional tectonic regime with brief periods of compression. The Wiluna deposits themselves are hosted within recent to Holocene sedimentation that sit in the upper reaches of a large southeast to south flowing drainage system that began forming in the Mesozoic within Permian glacial formed tunnel valleys. Satellite radiometric images clearly show this drainage system, now a dry largely ephemeral system of salt lakes.
		Mineralisation The principal ore mineral is the uranium vanadate, Carnotite (K ₂ [UO ₂] ₂ [VO ₄]2.3H ₂ O). This is the main ore mineral for U as well as V. Carnotite has been found as micro to crypto-crystalline coatings on bedding planes in sediments, in the interstices between sand and silt grains, in voids and fissures within calcrete, dolomitic calcrete, and calcareous



Criteria JORC Code explanation

Silcrete, as well as small concentrations (or 'blotches') in silty clay and clay horizons.

Vanadium is also found in the clays within the sediments, separate from the Carnotite mineral.

The sediments hosting the Carnotite and clays are part of a small deltaic paleochannel system that once, and to an extent still, flowed into a relatively large but very shallow inland lake. The delta splays from the end of the palaeochannel, which itself is host to Carnotite mineralisation further 'up-stream' with the two deposits known as the Dawson Well

A drving climate has led to most of the delta being covered in fine silty sand-dunes which have subsequently been vegetated. Apart from a large clay pan, most of the Millipede tenements, including the ground referred to in this report (Figure 2), are covered by vegetated dune sands. The main economic concentration of Carnotite, that targeted for mining, is restricted to a zone some 1-6 metres below the surface that seems to be related to the current water table. The zone is thus not lithologically specific, rather forming a wide flat and continuous lens stretching approximately from the central delta to the current lake shoreline and inhabiting calcrete, silcrete, sandy silts and clays. This zone does however coincide with a much thicker calcareous horizon that is more prominent away from the lake shoreline and often consists of competent to hard calcrete and calcareous silcrete (possibly silicified calcrete). The calcrete zone is also definitively related to the water table, although its specific relationship with the deposition of the Carnotite remains complex and somewhat unexplained. However, it could be argued that the calcrete may help form a pH related chemical trap that pushes the oxidised uranium and vanadium complex over its solution to solid phase boundary. Locally, the Abercromby Creek straddles a boundary between highly weathered granites and greenstones, flowing from a largely granitic terrain into largely ultramafic greenstone terrain of the

Norseman-Wiluna greenstone belt, although geological maps also place it at a precise boundary

and Hinkler Well Uranium Deposits. Drainage in the channel system is towards the delta and Lake Way from the south and southwest. The current stream system flanks the delta on both sides and still flows into the lake (Lake Way) but it is now definitively ephemeral with a normally weak and limited flow restricted to the wetter summer months or a stronger flow after storm events. The lake is also thus ephemeral with evaporite precipitates dominating the surface, a product of low influx, long residence times and high evaporation rates.



Criteria	JORC Code explanation	Commentary
		closer to the lake shoreline whereby ultramafics dominate its northern flank and granites dominate its southern flanks. It has been argued that the weathered granites are a possible source for the uranium and the weathered greenstones a possible source for the vanadium in the Carnotite mineralisation. Regionally, the deposits associated with Lake Way can be included in a province of similar style calcrete associated uranium deposits all in the NE Yilgarn of Western Australia and inclusive of much larger deposits such as Yeelirrie.
Drill hole Information	 A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes: easting and northing of the drill hole collar elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar dip and azimuth of the hole down hole length and interception depth hole length. If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case. 	 All drill hole data used in U₃O₈ estimations has been previously supplied in various resource updates, notably that of 27th February 2012, 9th September, 8th October and 20th November 2013, 7th July and 2nd September 2014, 2nd September and 14th October 2015 and 1st February 2016. All drill holes within the U₃O₈ envelope that have specific V₂O₅ geochemical information have been listed in the appendix 1 of the ASX announcement of 14th December 2021. All drill holes were vertical and drilled between 3-25 m depth. The 200ppm U3O8 grade shell from which the V2O5 resource has been occurs between 0.5 (upper intersect) and 12.5m (lower intersect) depth from the surface, although more typically the lower intercept is now greater than 6m depth from the surface.
Data aggregation methods	 In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (eg cutting of high grades) and cut-off grades are usually Material and should be stated. Where aggregate intercepts incorporate short lengths of high grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail. The assumptions used for any reporting of metal equivalent values should be clearly stated. 	 No exploration results reported here. Cut-off grades are as according to estimation techniques detailed below. No aggregation of intervals was made. Metal equivalents have only been used to model U₃O₈ grade shells and not for estimating V₂O₅.
Relationship between mineralisation widths and intercept lengths	 These relationships are particularly important in the reporting of Exploration Results. If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported. If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (eg 'down 	• The mineralization lenses of all of the Wiluna Uranium deposits are horizontal in nature. Thus, given that all drill holes are vertical from the surface, and hence perpendicular to mineralization, all stated mineralization intercept thicknesses represent the TRUE thickness of the mineralization lens at the specified U ₃ O ₈ cut-off grade (in this case 500 ppm eU ₃ O ₈).



Criteria	JORC Code explanation	Commentary
	hole length, true width not known').	
Diagrams	 Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to, a plan view of drill hole collar locations and appropriate sectional views. 	All relevant maps have been included with this ASX release.
Balanced reporting	 Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results. 	No exploration results reported in this document resource drilling only
Other substantive exploration data	Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.	No exploration results reported in this document resource drilling only
Further work	 The nature and scale of planned further work (eg tests for lateral extensions or depth extensions or large-scale step-out drilling). Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive. 	No further work on the V2O5 resource is planned at this stage.

Section 3 Estimation and Reporting of Mineral Resources

(Criteria listed in section 1, and where relevant in section 2, also apply to this section.)

	All Wiluna deposits excluding Lake Maitland
transcription or keying errors, between its initial collection and its use for Mineral Resource estimation purposes. li d lc s c e a re n tt tt	Logging and sampling data is entered into a remplate with fixed formatting and fixed ithological choices (selected from fixed dropdown lists) by the geologist responsible for ogging each hole. The template is formatted so that it can be imported directly into a DataShed database. All importing and exporting into and from the database is achieved by a single point of entry/exit responsible for the database (database manager), access for such tasks is restricted to the database manager. All files are transferred from the field to the database manager using a secure commercial based



	Criteria JORC Code explanation	Commentary
	Data validation procedures used.	DropBox folder system with automatic back- up and error correction functions. Data files for resource estimation are transferred in a single zip file to the resource consultant, direct from the database manager.
		 All geological interval and gamma data is validated via a systematic check of down-hole gamma to down-hole scintillometer readings (made for each lithological unit) for every hole (both sonic and aircore). A secondary check on actual lithology logging is made by examining core and chip photographs cross- referenced to the geological logs. All historical data is validated in ISATIS against the same data used in previous estimations.
)		Lake Maitland Only
		 All post-2013 data validation has been achieved as already described above, prior to 2013 it was as follows: All geological logging and sampling is entered into a Toughbook style laptop with an offline aQuire data entry program, which contains fixed lithological codes, carry over sample ID's, fixed core lengths and recorded core loss intervals. The program does not allow errors such as overlaps, or sample miss match. At the end of each day (whether for gamma data from probing or geological logging) all data is extracted and sent to the Perth office where it is automatically entered to the sequel server database. This can only be accessed by the database manager.
		• All data has undergone a thorough 2 week long validation and integrity check by SRK in consultation with Toro Energy prior to data preparation for resource estimation of uranium, including all U ₃ O ₈ and eU ₃ O ₈ values, density values, lithology and lithology models (Vector files etc.) and geospatial information (drill hole collars etc.). All V ₂ O ₅ data have been extracted from the geochemical database and were checked for inconsistencies
	Comment on any site visits undertaken by the Competent Person and the outcome of those visits. If no site visits have been undertaken indicate why this is the case.	The competent person responsible for the resource estimate, Daniel Guibal, has not had a visit to site. It is considered that a site visit is not necessary given Mr Guibal's experience with Toro's Wiluna uranium deposits, some 10 years, including numerous estimations, as well as experience elsewhere.



Criteria	J(ORC Code explanation	Co	ommentary
Geological interpretation	•	The use of geology in guiding and controlling Mineral Resource estimation. Confidence in (or conversely, the uncertainty of) the geological interpretation of the mineral deposit.	•	The geological model is not used in the resource estimate since it has been found that mineralization is not necessarily correlated to any particular rock type, despite being often associated with carbonate or carbonated sediments. The mineralization has been found to be associated with the water table and so is more correlated to depth from the surface than any given lithology, maintaining grade across different lithology. Thus the geological model for estimation is a simple mineralization envelope based on a concentration of U that represents that concentration where the background population of U ends and the U mineralization exists (in a classic bimodal distribution). In the Wiluna deposits this is 70 ppm U ₃ O ₈ for the Centipede-Millipede deposit, 80 ppm U ₃ O ₈ for the Lake Way deposit and 100 ppm U ₃ O ₈ for the Lake Maitland deposit.
	•	Nature of the data used and of any assumptions made.	•	Examination of 3D LeapFrog models of different grade shells of the resource give a high level of confidence to the above interpretation of a ground water controlled deposit.
			•	For the U ₃ O ₈ estimation and mineralisation envelopes, all data used is based on U values from geochemistry and de-convolved gamma derived equivalents. U geochemistry is mostly F-ICPMS, 4-ICPMS and fused disc XRF. A large number of cored drill holes (diamond and sonic) have been used to test the validity of the gamma measurements (via geochemistry) – for example all of the 2011 drilling at Lake Maitland, some 201 diamond holes. Where there is geochemistry data available it is given priority over gamma derived equivalents. All de-convolved gamma derived data has been multiplied by 1.25 at Lake Maitland and 1.2 at Centipede-Millipede.
			•	For the V_2O_5 estimation all data is geochemistry data collected from diamond core, sonic core and aircore drill chips as described previously above. The geochemistry is as described above for U. The number of V_2O_5 data available is in general lower than the number of U data, in fact for the Lake Maitland deposit, there is approximately one third the data available for the V_2O_5 estimation compare to the U_3O_8 estimation due to the availability of gamma data in the more common aircore drill holes.
			•	The advantage of using a mineralization

envelope based on U₃O₈ concentrations only



Criteria	JORC Code explanation	Commentary
	 The effect, if any, of alternative interpretations on Mineral Resource estimation. The factors affecting continuity both of grade and geology. 	(both chemistry and de-convolved gamma derived equivalents) is that there are few assumptions made. Domains are based on data variability and so in effect, real changes in the behaviour of the data and data distribution. There is no forcing statistical predictions into domains based on lithology that is not necessarily correlated spatially at all times.
		 A minimum of 5% of all drill holes are required to test the validity of gamma and to introduce into the estimation except in the case of the mine block evaluation areas where 2.5% has been accepted (due to the mine block evaluation study not contributing to any update of the total resource).
		 Density values used in the resource estimates at Lake Way and Centipede-Millipede are single values representing average densities for the entire mineralization envelope. At Lake Maitland density values used in the resource estimate are derived from gamma gamma probe measurements calibrated to real wet and dry density measurements of reference sonic hole cores. The densities are averaged to the different main lithology in the geological model and applied to the block model according to the boundaries of each lithological unit (acting as density domains). Further information below under 'bulk density'.
_		 A different geological interpretation, if used in the resource estimate, may affect the results of the resource estimate slightly, however, since geology is not used in estimations a change in geological interpretations would make no difference.
		 Grade Continuity can be affected by numerous factors, including drilling density which varies from 5m x 5m to 100m x 200m, nugget effect, itself linked to the type of measurement (geochemical data are more variable than radiometric de-convolved radiometric data), uncertainties on the data themselves due to calibration problems or/and disequilibrium for the radiometric values, sampling/assaying issues for the geochemical measurements (controlled by QA/QC), and geological continuity, which is reasonably established for the Wiluna Uranium Project. Geology has been controlled by recent to Quaternary sediment deposition with overprinting calcretisation being controlled by



Criteria	J(ORC Code explanation	Co	mment	tary
				the gro	ound water flow.
Dimensions	•	The extent and variability of the Mineral Resource expressed as length (along strike or otherwise), plan width, and depth below surface to the upper and lower limits of the Mineral Resource.	•	vertical Occasi surface	Viluna deposits are surficial with a I thickness of a few meters at most. conally deeper (15 to 25m below e) mineralization exists, but its uity is not proved, because of the lack of rilling
Estimation and modeling techniques	•	The nature and appropriateness of the estimation technique(s) applied and key assumptions, including treatment of extreme grade values, domaining, interpolation parameters and maximum distance of extrapolation from data points. If a computer assisted estimation method was chosen include a description of computer software and parameters used.	•	grade s block of techniq Uniform special some Conditi visualis better (such a	lised geostatistical software, Isatis. In circumstances Localised Uniform ioning (LUC) will be used after UC to se potential variation in the orebody to evaluate proposed mining methods as is the case at Lake Maitland). The se steps of the estimation are the
				ge ge ge (2) Cr us ab the (3) Ga dis in Hi ac be co to en av from co ge sp dr Mi ha (4) C (5) Do co Mi	see of combined radiometric and cochemical data, with priority given to eochemistry. Treation of a mineralisation envelope sing Leapfrog 3D at the cut-offs detailed love were created prior to factoring of the 2013 data. The amma data corrections are made - As secussed above the 2013 gamma data the westernmost zone of Dawson linkler was corrected by a 1.2 factor to account for a systematic discrepancy between geochemical and gamma derived data and at Lake Maitland, a correction factor of 1.25 has been applied gamma data within the mineralised myelope to take into account the verage secular disequilibrium as found for research (see above), and due to consistent differences observed between eochemistry and gamma and decifically investigated in the 2015 compositing investigated in the 2015 compositing to 0.5m. Tomaining by zones of reasonably onsistent grade, or in the case of Lake aitland, essentially by the strike rientation: NS, NE and NW



Criteria JO	DRC Code explanation	Comm	entary
		(6)	Top-cuts used at the various deposits include 5000 ppm, 4500 ppm, 2000 ppm, 700 ppm and 500 ppm as well as no top-cut at all depending on the various domains. It has been found that the top-cut has very little impact on mean grade (less than 1%) and variance. No top-cuts at all applied to Lake Maitland and Lake Way.
		(7)	Panel sizes used for the estimation were 30m x 30m x 0.5m for Centipede, Millipede and Lake Way, 50m x 100m x 0.5m for Nowthanna, 200m x 100m x 0.5m for Dawson-Hinkler and 50m x 50m x 0.5m for Lake Maitland. The panel sizes are chosen from the average drilling density.
		(8)	Ordinary Kriging estimation of panels, after neighbourhood analysis to optimise quality of kriging.
		(9)	Validation of Kriging results through statistics and swath plots
•	The availability of check estimates, previous estimates and/or mine production records and whether the Mineral Resource estimate takes appropriate account of such data.	(10)	Uniform conditioning (UC) for 10m x 10m x 0.5m Selective Mining Units (SMU), which is a realistic assumption for a future operation where grade control using radiometric information will be possible.
•	The assumptions made regarding recovery of by-products.	(11)	Localised Uniform Conditioning: creation of 10m x 10m x 0.5m panels based on the results of UC at Lake Way, Dawson Hinkler and Lake Maitland. UC model
•	Estimation of deleterious elements or other non-grade variables of economic significance (eg sulphur for acid mine drainage characterisation).		maintained as official model for Centipede-Millipede due to grade differences between the UC and LUC models at higher grade cut-offs and the assumption that the UC model is the most reliable if grade differences occur.
•	In the case of block model interpolation, the block size in relation to the average	(12)	The tonnage is estimated using a constant dry density as detailed elsewhere in this table.
	sample spacing and the search employed.		
•	Any assumptions behind modelling of selective mining units.	been menvelope and the 10m x	stimation of V_2O_5 for Lake Maitland has nade using the same U_3O_8 mineralisation be as described above for Lake Maitland on estimating directly into the same 10m x 0.5m blocks as those used for the LUC actions for Lake Maitland and using the same table.
•	Any assumptions about correlation between variables.	Ordina	estimation for Lake Maitland and using ry Kriging. No UC or LUC was undertaken V2O5 estimation like it was for the U3O8



Criteria	JORC Code explanation	Commentary
	 Description of how the geological interpretation was used to control the resource estimates. Discussion of basis for using or not using 	estimation due to the lower amount of data in comparison.
	grade cutting or capping. • The process of validation, the checking	 Previous resource estimates (prepared for a number of years by SRK and Mr Daniel Guibal) are available and are considered in all
	process used, the comparison of model data to drill hole data, and use of reconciliation data if available.	current estimations. • This resource estimation is for a potential by-product, V ₂ O ₅ of the previously announced U ₃ O ₈ resources. The potential viability of V ₂ O ₅ as a by-product in the processing of the Wiluna Uranium Project's uranium ore has been outlined with the results of testing in ASX
		 announcements of 18th March, 19th July, 5th September and 10th October 2019 and 24th October 2022. There are no assumptions made to date of the exact recovery percentage, just that it is leached with the U and recoverable into a
		clean and separate processing stream from the IX circuit in amounts that make it a potentially viable by-product. Recoveries will be utilised in mining models.
		 Currently there are no geostatistical estimations made on deleterious elements, however, such elements have been included in the analysis of drill core samples in 2013 and so such estimations will be able to be accomplished in the future as more coverage across the deposits is achieved. Current analysis of drill core geochemistry and Metallurgical samples strongly suggests there are no significant economic issues related to deleterious elements.
		See detailed description of estimation process above
		See detailed description of estimation process above
		No assumptions
		 See above – no geological control in any of the 2012 JORC compliant resources.
		 See detailed description of estimation process above



Whether the tonnages are estimated on a dry basis or with natural moisture, and the method of determination of the moisture content. Cut-off parameters Mining factors or quality parameters applied. Mining factors or with matural moisture, and the method of determination of the moisture content. Mining factors or quality parameters applied. Mining factors or assumptions made regarding possible mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dittion, it is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods, but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made. **Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made. **Respense may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made. **Respense mad fine December 2018, 7**March, 18**March, 19**Mayl, 5**September and 19**September and 19**Septemb					
Moisture • Whether the tonnages are estimated on a dry basis or with natural moisture, and the method of determination of the moisture content. Cut-off parameters • The basis of the adopted cut-off grade(s) or quality parameters applied. Mining factors or quality parameters applied. • Assumptions as a sumptions and eregarding possible mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, his should be reported with an explanation of the basis of the mining assumptions made. **Assumptions made regarding possible mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, his should be reported with an explanation of the basis of the mining assumptions made. **September and 9th September 2018, 7th March, 19th March, 19th July, 5th September and 10th October 2019 and 24th October 2022. It is also important to not lat all of the engineering and mining parameters listed below will be different for a stand-alone Lake Maltland mining operation as is being suggested in this ASX release; such parameters are yet to be determined that sill of the next stage of this scoping level series of engineering studies. **Mining technique has been tested successfully on site, the main points follow.** **Mining technique has been tested successfully on site, the main points follow.** **Mining technique has been tested successfully on site, the main points follow.** **Mining technique has been tested successfully on site, the main points follow.** **Mining technique has been tested successfully on site, the main points follow.** **Mining technique has been tested successfully on site, the main points follow.** **Mining te		Criteria	JORC Code explanation	Cor	mmentary
Moisture • Whether the tonnages are estimated on a dry basis or with natural moisture, and the method of determination of the moisture content. Cut-off parameters • The basis of the adopted cut-off grade(s) or quality parameters applied. Mining factors or quality parameters applied. • Assumptions as a sumptions and eregarding possible mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, his should be reported with an explanation of the basis of the mining assumptions made. **Assumptions made regarding possible mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, his should be reported with an explanation of the basis of the mining assumptions made. **September and 9th September 2018, 7th March, 19th March, 19th July, 5th September and 10th October 2019 and 24th October 2022. It is also important to not lat all of the engineering and mining parameters listed below will be different for a stand-alone Lake Maltland mining operation as is being suggested in this ASX release; such parameters are yet to be determined that sill of the next stage of this scoping level series of engineering studies. **Mining technique has been tested successfully on site, the main points follow.** **Mining technique has been tested successfully on site, the main points follow.** **Mining technique has been tested successfully on site, the main points follow.** **Mining technique has been tested successfully on site, the main points follow.** **Mining technique has been tested successfully on site, the main points follow.** **Mining technique has been tested successfully on site, the main points follow.** **Mining te					
Moisture • Whether the tonnages are estimated on a dry basis or with natural moisture, and the method of determination of the moisture content. Cut-off parameters • The basis of the adopted cut-off grade(s) or quality parameters applied. Mining factors or quality parameters applied. • Assumptions • Assumptions made regarding possible mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made. • The proposed mining methods, will be the same as those publicly outlined by Toro for the Willians Project, however as a result of recent beneficiation and processing design studies the processing techniques activently in the processing of vanadium as a by-product at what should be no significant cost increase to processing. The new processing design and beneficiation studies have been outlined in the ASX announcements of 18th May 25th Agy					Con detailed description of actionstics process
dry basis or with natural moisture, and the method of determination of the moisture content. Cut-off parameters **The basis of the adopted cut-off grade(s) or quality parameters applied.* Mining factors or quality parameters applied. Mining factors or dimensions and internal (or, if applicable, external) mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods and parameters when estimating methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made. **Begin the mining parameters when estimating the basis of the mining assumptions made.** **Begin the mining total cut-off will be determined from the mining studies.** **The proposed mining methods, will be the same as those publicly outlined by Toro for the Wiluna Project, however as a result of recent beneficiation and processing design studies the processing design studies have been outlined in the value processing of vanadium as a by-product at what should be no significant cost increase to processing. The new processing design and beneficiation studies have been outlined in the ASX announcements of the May, 29th August, 28th September and 5th December 1016, 30th ASX announcements of 19th ASX announcements of 19th ASX announcements of 19th ASY announcements of 19th A	1				·
Mining factors Mining factors Assumptions Assumptions and internal (or, if applicable, external) mining dilution. It is always necessary as part of the process of determining methods, but the assumptions made regarding mining methods, but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made. **Repetable** Assumptions made regarding possible mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods, but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made. **Reptember** **Assumptions made clicuit design may be changing in the future. It is this change that has allowed for the potential duel processing of vanadium as a by-product at what should be no significant cost increase to processing. The new processing design and beneficiation studies have been outlined in the ASX announcements of 18th May, 29th August, 28th September and 19th September 2018, 7th March, 18th March, 19th July, 5th September and 10th October 2019 and 24th October 2022. It is also important to note that all of the engineering and mining parameters listed below will be different for a stand-alone Lake Maittand mining operation as is being suggested in this ASX release; such parameters are yet to be dearmined but is the next stage of this scoping level series of engineering studies. **Current for entire Wiluna Project is as follows:* **Minima technique has been tested successfully on site, the main points follow.** **Shallow strip mining to 15th maximum depth (approximately 8 the at Ma		Moisture	dry basis or with natural moisture, and the method of determination of the moisture	•	Tonnages are dry tonnages
assumptions mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods, but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made. September and 19th September 2018, 7th March, 18th March, 19th July, 5th September and 10th October 2019 and 24th October 2022. It is also important to note that all of the engineering and mining parameters listed below will be different for a stand-alone Lake Maitland mining operation as is being suggested in this ASX release; such parameters are yet to be determined but is the next stage of this scoping level series of engineering studies. Current for entire Wiluna Project, the main points follow. Mining technique has been tested successfully on site, the main points follow. Mining technique has been tested successfully on site, the main points follow. Mining technique has been tested successfully on site, the main points follow. Mining technique has been tested successfully on site, the main points follow. Mining technique has been tested successfully on site, the main points follow. Mining technique has been tested successfully on site, the main points follow. Shallow strip mining to 15m maximum depth (approximately 8 m at Maitland) using a combination of a Vermeer surface miner, loader and articulated trucks. 25-50cm benches De-watering of pits for process water In-pit tailings disposal below natural ground surface in lined pits, progressive compartmental mining, tailings and rehabilitation				(of cut-offs. Optimal cut-off will be determined
 Current - strip 3.8:1, using 250ppm cut-off Up to a 14 year life of mine, regional resources increase to 20+ years dependent on future))))	or	mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods, but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of		The proposed mining methods, will be the same as those publicly outlined by Toro for the Wiluna Project, however as a result of recent beneficiation and processing design studies the processing techniques and circuit design may be changing in the future. It is this change that has allowed for the potential duel processing of vanadium as a by-product at what should be no significant cost increase to processing. The new processing design and beneficiation studies have been outlined in the ASX announcements of 18th May, 29th August, 28th September and 5th December 1016, 30th January, 20th April, 20th June, 27th June, 12th September and 19th September 2018, 7th March, 18th March, 19th July, 5th September and 10th October 2019 and 24th October 2022. It is also important to note that all of the engineering and mining parameters listed below will be different for a stand-alone Lake Maitland mining operation as is being suggested in this ASX release; such parameters are yet to be determined but is the next stage of this scoping level series of engineering studies. Current for entire Wiluna Project is as follows: Mining technique has been tested successfully on site, the main points follow. Shallow strip mining to 15m maximum depth (approximately 8 m at Maitland) using a combination of a Vermeer surface miner, loader and articulated trucks. 25-50cm benches De-watering of pits for process water In-pit tailings disposal below natural ground surface in lined pits, progressive compartmental mining, tailings and rehabilitation Current - strip 3.8:1, using 250ppm cut-off Up to a 14 year life of mine, regional resources



	Cuitouio	IODC Code combination	0	
	Criteria	JORC Code explanation	C	ommentary
/			•	7 years at Centipede and Millipede followed by Lake Maitland and then Lake Way.
	Metallurgical factors or assumptions	The basis for assumptions or predictions regarding metallurgical amenability. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential metallurgical methods, but the assumptions regarding metallurgical treatment processes and parameters made when reporting Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the metallurgical assumptions made.	•	A laboratory scale pilot plant has been successfully trialled that includes all of the currently proposed process from crushing/grinding to product – actual product produced. Every part of the processing circuit has been tested and/or had research associated with it. Main factors follow. Alkaline tank leach with direct precipitation. Target production is 780 tpa U ₃ O ₈ Processing 1.3 Mtpa at a head grade of 716ppm U ₃ O ₈ Processing plant is planned to be located on the Centipede deposit related tenements. The new processing that includes IX that is currently being assessed has been described in the ASX announcements as outlined above.
	Environmental factors or assumptions	Assumptions made regarding possible waste and process residue disposal options. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider the potential environmental impacts of the mining and processing operation. While at this stage the determination of potential environmental impacts, particularly for a greenfields project, may not always be well advanced, the status of early consideration of these potential environmental impacts should be reported. Where these aspects have not been considered this should be reported with an explanation of the environmental assumptions made.	•	All of the deposits of the Wiluna Uranium Project have been approved for mining by the West Australian EPA and the federal government. Thus the project has gone through the Environmental Review and Management Programme process (The ERMP and all of the associated documents can be found on the Toro Energy website at: http://www.toroenergy.com.au/sustainability/health-safety/environmental-review-and-management-programme-ermp/ Main factors follow. Shallow open pit mining In-pit tailings disposal below natural ground surface in lined pits, progressive compartmental mining, tailings and rehabilitation – no tailings disposal planned for Dawson Hinkler deposit site. Tailings integrity modelled for 10,000 years Mining footprint returned as close as possible to natural land surface level No standing landforms remain post closure
	Bulk density	 Whether assumed or determined. If assumed, the basis for the assumptions. If determined, the method used, whether wet or dry, the frequency of the measurements, the nature, size and representativeness of the samples. The bulk density for bulk material must 	•	All Wiluna deposits excluding Lake Maitland Density has been averaged so that a single density is applied across the entire block model. The average density applied to Centipede and
		have been measured by methods that adequately account for void spaces (vugs, porosity, etc), moisture and differences	J	Millipede is 1.8 t/m³, which has been determined from averaging the density through the ore zone as measured by a



Criteria	JORC Code explanation	Co	mmentary
	 between rock and alteration zones within the deposit. Discuss assumptions for bulk density estimates used in the evaluation process of the different materials. 		calibrated dual density probe. The data used was from the 2011 drilling campaign. A duel density probe was used in the 2015 drilling program to check the earlier results in different parts of the orebody and results were proven similar, a little higher in some areas and a little lower in others, however 1.8 t/m³ is still considered appropriate. The average density applied to Lake Way is 1.72 t/m³, based on bulk samples collected from multiple resource evaluation and mining test pits in 1978, analysed by AMDEL.
			Lake Maitland only
		•	Density was determined by calibrated gamma gamma probe measurements down drill holes from across the entirety of the deposit (predominantly the 2011 drilling campaigns). Gamma gamma probe calibrated directly with reference sonic core holes whereby both dry and wet density measurements were obtained. Gamma gamma measurements were found to be matching wet density and so all measurements were re-calibrated to a dry density using both the wet and dry density determinations on the sonic core. Density was then averaged over geological units (determined as explained above) so that each geological domain within the block model had a single average dry density.
Classification	 The basis for the classification of the Mineral Resources into varying confidence categories. Whether appropriate account has been taken of all relevant factors (ie relative confidence in tonnage/grade estimations, reliability of input data, confidence in continuity of geology and metal values, quality, quantity and distribution of the data). Whether the result appropriately reflects the Competent Person's view of the deposit. 		The classification of the Uranium Resources at Wiluna was established in previous estimations, in particular see ASX announcement of 1 February 2016. The classification of the Vanadium resource for the Lake Maitland deposit is Inferred only because the number of data is generally lower (one third approximately) than for U, there has been less QA/QC performed than for U and no specific geological modelling was undertaken, the estimation being limited to the domains defined for U.
Audits or reviews	 The results of any audits or reviews of Mineral Resource estimates. 		There has been no audit of the resources reporting material change within this ASX release, other than internal SRK and Toro assessment and geological interpretation.
Discussion of relative	 Where appropriate a statement of the relative accuracy and confidence level in the Mineral Resource estimate using an approach or procedure deemed 	•	Because Vanadium is considered a by- product of the Uranium mineralisation, no detailed evaluation of the uncertainty on the



Criteria	JORC Code explanation	Commentary
accuracy/ confidence	 appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the resource within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors that could affect the relative accuracy and confidence of the estimate. The statement should specify whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used. 	 estimation was made at this stage. Factors that could affect the relative accurace of the estimations include: The correlation between U₃O₈ and V₂O₈ geochemical grades; The assaying methods used, The current V₂O₅ estimates are smooth due to the low number of data relative to the U data, and therefore probab underestimate the true grade variability. No production statistics available – not a operating mine
	These statements of relative accuracy and confidence of the estimate should be compared with production data, where available.	

Section 5 Estimation and Reporting of Diamonds and Other Gemstones

NOT APPLICABLE - URANIUM ONLY