

MANNA METALLURGICAL TESTWORK UPDATE

Optimisation testwork achieves 75% Li₂O recovery at Manna

Ongoing optimisation testwork on the Manna Lithium Project Whole-of-Ore (WOO) flotation flowsheet achieving excellent improvements in lithia recovery

Optimisation testwork focussing on magnetic separation and mica pre-flotation stages has increased Li₂O recoveries from 70% to 75% for spodumene composite ore samples.

Further optimisation testwork is pursuing improvements in recovery via reduced slimes losses, reprocessing of magnetic separation tails, and engaging with reagent suppliers to optimise spodumene flotation circuit operating conditions

Testwork results continuing to achieve >5.5% Li₂O spodumene concentrate (SC), with ongoing optimisation targeting grade increases

A total of 66 flotation tests have been completed to-date producing a SC product of 5.6 - 6.5% Li₂O and 0.4 - 0.8% Fe₂O₃

Preparations for the next phase of ore sorting testwork are well advanced with trials imminent at Steinert's industrial testwork facility in Perth

This increase in lithia recovery will have a positive impact on project economics at Manna

Metallurgical Testwork Update

Global Lithium Resources Limited (ASX: GL1, "Global Lithium" or "the Company"), is pleased to announce a progress update on the Definitive Feasibility Study (DFS) metallurgical testwork program for its 100% owned Manna Lithium Project, located 100km east of Kalgoorlie in Western Australia.

Whole of Ore Flotation Optimisation

ASX:GL1

The Whole-of-Ore (WOO) flotation process selected for the Manna Project, as presented in Figure 1, features standard SAG/Ball comminution of sorted ore, followed by two-stage desliming cyclones to remove -25 µm slimes, magnetic separation to remove iron bearing minerals, a mica pre-flotation circuit

Page 1 of 27 | ACN 626 093 150 Level 1, 16 Ventnor Ave, West Perth, WA 6005 info@globallithium.com.au | www.globallithium.com.au to remove mica minerals such as lepidolite and biotite, culminating in a high grade final spodumene concentrate product.



Figure 1. Manna Lithium Project Whole of Ore (WOO) Flotation Flowsheet





Optimisation testwork performed since GL1's last update on the DFS metallurgical testwork program (refer to ASX announcement on 16 November 2023) has focussed on the magnetic separation and mica preflotation stages.

Table 1 provides a summary update of improvements achieved from recently completed optimisation testwork performed on three composite ore samples, a high-grade and low-grade sample from the main ore zone (Zone 1) consisting of coarse to fine grain spodumene, and a third sample from the second ore type (Zone 2) consisting of fine grain spodumene with varying amounts of other lithium-bearing mica minerals.

			Zone	Zone 2			
Result	Unit	High Grade		Low Grade			
2		Updated	Prior Reported ¹	Updated	Prior Reported ¹	Updated	Prior Reported ¹
Deslime Li Loss	%	12.8	13.2	10.8	12.9	13.6	14.3
Mag. Separation Li Loss	%	5.5	3.8	5.8	4.6	5.9	5.2
Mica Float Li Loss ²	%	1.3	7.7	5.3	10.5	11.1	18.0
Spodumene Float Li Loss ²	%	3.7	3.4	4.1	3.6	5.3	2.1
Overall Li Recovery	%	76.7	71.9	74.0	68.4	64.2	60.4
9							
Spodumene Conc. Grade ²	% Li ₂ O	6.3	6.5	5.8	5.7	5.6	5.6
Spodumene Conc. Fe Grade ²	% Fe ₂ O ₃	0.5	0.4	0.4	0.6	0.4	0.8

Table 1: WOO Flotation Testwork Results | Optimisation Update

Notes:

1. Refer ASX release "Manna DFS and Metallurgical Test Work Update" dated 16 November 2023.

2. Rougher-only flotation, effectiveness of cleaning still to be investigated.

Magnetic separation and mica pre-flotation optimisation have encompassed more than 30 flotation tests exploring flotation conditions, reagent type, reagent dose and slurry chemistry, as well as the interaction between magnetic separation operating conditions and flotation performance. The results were used to identify a robust, mica-selective flotation reagent regime that is both stable and reproducible whilst reducing overall circuit spodumene losses.

Optimised magnetic separation and mica float circuit operating conditions developed as part of on-going optimisation testwork has culminated in Li₂O recoveries of 77% for the high-grade Zone 1 composite sample, 74% for the low-grade Zone 1 composite sample, and 64% for the Zone 2 composite sample.

This represents an increase of 5% Li_2O recovery for the main ore zone and 4% for the second ore type, while maintaining excellent concentrate grades from spodumene rougher-only flotation of 5.8-6.3% Li_2O and iron impurities of 0.4-0.6% Fe_2O_3 for the main ore zone. Preliminary spodumene cleaning testwork has shown considerable upgrade of the spodumene concentrate grade is possible, facilitating opportunities to further improve overall WOO flotation recoveries by relaxing operating conditions of other parts of the flowsheet to reject less gangue impurities.



The focus of the next phase of WOO flotation optimisation testwork is to further improve Li_2O recovery by investigating:

- Specifically-formulated spodumene flotation collectors to optimise spodumene flotation performance by engaging with multiple reagent suppliers
- Decreasing slimes losses by stage-wise reduction in the deslime cyclone cut point from -25µm
- Decreasing slimes losses by relaxing primary grind size from the current size of 180µm to 212µm, which is expected to necessitate coarse particle flotation (CPF) cell technology and/or a retreatment of coarse rougher flotation tailings to recovery any spodumene particles
- Re-processing of WHIMS products to recover mis-reported spodumene particles and coarse composite particles containing spodumene
- Leveraging the experience of our strategic shareholders

Ore Sorting Optimisation

Ore sorting testwork has been completed on the two main ore types and different feed grades, as previously reported (refer to ASX Announcement, 21 September 2023). Ore sorting trials have so far confirmed that 90% of iron can be rejected while maintaining a 92% Li₂O recovery, with trials showing a strong correlation between mass rejected and iron content. GL1 is currently preparing four additional bulk samples of Manna ore which are planned to be processed through Steinert's Ore Sorting testwork facility located in Bibra Lake, Perth, in the coming weeks. The aim of these additional trials is to develop a grade recovery curve for Zone 1 ore, which is expected to result in an improvement in the average lithia recovery from this zone by showing higher lithia recovery for high-grade ore, while further work will be performed on Zone 2 ore to optimise mica rejection while minimising associated spodumene ore losses.

Results of these additional ore sorting trials will be announced in due course.

A further opportunity was identified during the first round of ore sorting testwork, namely the possibility of performing magnetic separation of iron-bearing impurities from the fine ore fraction that cannot be processed by the ore sorting plant. The crushing circuit generates a -10mm fine ore fraction, which is screened and removed prior to ore sorting. Treating this fine ore fraction using a dry magnetic drum separator with a rare-earth magnetic drum (RED) at 4,000 Gauss field strength, has shown to reject magnetic waste from the fines, thereby reducing the load on the WOO flotation circuit.

Magnetic separation, or 'Cobbing' testwork has been performed on the fines fraction from the previous ore sorting trials, with the results of the work presented in Table 2. Results showed 26% and 31% magnesia waste rejection as indicated by Fe_2O_3 and MgO rejection rates with negligible Li₂O losses, with inclusion of this technology into the Manna Project flowsheet to be investigated.

		Grade			Distribution		
Result	wass	Li ₂ O	Fe ₂ O ₃	MgO	Li₂O	Fe ₂ O ₃	MgO
	%	%	%	%	%	%	%
Magnetics	6.3	0.24	12.3	21.2	1.0	26.1	31.2
Non-Magnetics	93.7	1.58	2.3	3.1	99.0	73.9	68.8
Feed	100	1.50	2.96	4.27	100	100	100

Engineering & Ancillary Testwork

Dewatering testwork has also been completed since GL1's last update, with four bulk samples generated from WOO flotation optimisation testwork sent to thickening, filtration and centrifuging vendors for equipment sizing testwork.

Vendor testwork has shown the final spodumene concentrate and tailings streams were more readily dewatered than expected, based on industry benchmarking from other lithium operations, which will provide opportunities to simplify the dewatering circuits leading to potential capital cost savings to the Manna Project.

Metallurgical Testwork Setting

Program Overview

The metallurgical testwork program is being completed on composite samples generated from approximately 12,000kg of diamond core obtained from multiple drilling programs completed at Manna during 2022/2023.

Testwork initially focussed on ore characterisation, spodumene mineralogy, comminution and liberation studies to determine the optimum beneficiation flowsheet. Coarse spodumene beneficiation adopting Dense-Media Separation (DMS) technology is not suitable for the Manna deposit. Global Lithium formed the opinion that the spodumene recovery was not high enough to warrant the additional capital cost to include a DMS circuit and added complexity. Consequently, a WOO flotation flowsheet employing a combination of magnetic separation and flotation technology was selected for DFS design and continued metallurgical studies.

The WOO flotation flowsheet encompasses four stages of gangue rejection after grinding the ore. The ground ore is de-slimed using hydrocyclones before passing over low and high intensity magnetic separators for iron mineral removal. Non-magnetics are then sent for mica flotation where lithium-bearing biotite and muscovite impurity minerals are rejected before spodumene flotation to produce a final concentrate.

Preliminary WOO flotation testwork results previously reported (refer to ASX Announcement, 16 November 2023) confirmed well liberated spodumene at a grind size of 180 µm with excellent spodumene concentrate



specifications and recovery. Ongoing metallurgical studies remain focussed on attaining optimal product specifications and maximum recoveries whilst ensuring practical scale up from laboratory to operations.

The metallurgical testwork program will culminate with an ore variability program on the calibrated laboratory procedures using targeted samples from various lithological and spatial domains within the Manna deposit.

Metallurgical testwork is being performed at Nagrom Laboratory located in Perth, Western Australia and supervised by the Global Lithium process team.

Samples

The Manna deposit has two different ore types present within the resource. The main ore zone (Zone 1), and most dominant ore type within the main central pit at Manna, consists of coarse to fine grain spodumene with quartz and feldspar as the main gangue minerals and minor amounts of mica. The second ore type (Zone 2) consists of fine grain spodumene with varying amounts of other lithium minerals. The preliminary DFS mine schedule contains approximately 78% of Zone 1 ore type and 22% of Zone 2. Both ore types contain waste rock in the form of magnetic basalt and gabbro from the foot and hanging walls. Magnetic waste rock can easily be removed via ore sorting as previously outlined (refer to ASX announcement on 21 September 2023).

Three bulk metallurgical composite samples were generated from HQ core for the initial metallurgical testwork program. Table 3 provides a summary of the head assays of the three composite samples generated. There are two samples from Zone 1 at different head grades (high-grade and low-grade) to reflect the range in grades anticipated to be processed through the plant. The third sample is a typical sample from Zone 2.

Elomont	Unit	Zone 1	Zone 2	
Liement	Onit	HG	LG	Sample
Lithium Oxide (Li ₂ O)	%	1.49	0.89	1.34
Iron Oxide (Fe ₂ O ₃)	%	1.98	1.65	2.05
Silicon (Si)	%	32.4	32.7	32.5
Aluminium (Al)	%	7.8	7.8	8.6
Potassium (K)	%	2.0	2.0	2.0
Sodium (Na)	%	2.6	3.3	2.9
Magnesium (Mg)	%	2.0	1.7	0.3
Calcium (Ca)	%	0.9	0.7	1.2

Table 3: Composite Head Assays

With ore sorting becoming an integral part of the Manna Processing Plant, a new Zone 1 "control" composite is currently being generated from crushed PQ and products from previous ore sorting testwork to simulate a sorted ore feed to the WOO flotation plant. The Zone 1 composite includes proportionally





mixed constituent of minus 12mm crushed material to represent the initial 2-3 year mine production profile. The control composite generation remains in progress and is proposed to supplement the three bulk metallurgical composite samples as Global Lithium continue to expand the metallurgical knowledge, behaviour and optimisation of the Manna deposit over the course of 2024.

Four new ore sort composite samples with variable head grades and mine dilution are currently being prepared using bulk PQ diamond drill core. Data from upcoming ore sorting testwork at Steinert on these samples is expected to establish a grade recovery curve to confirm ore sort lithia recovery across the Manna ore body, as well as provide a production tool over life-of-mine for the Manna Processing Plant.

Twenty-five ore variability samples from various lithological and spatial domains within the Manna deposit have also been selected to be generated, with these samples to undergo variability testwork on the optimised WOO flotation flowsheet. Results from this variability program will be used to develop a flotation plant grade recovery model for future mine planning, as well as inform process design requirements of the Manna Process Plant over the life-of-mine of the Project.

Global Lithium Project Director, Dr Tony Chamberlain commented,

"The metallurgical flowsheet for Manna is now well defined and the process team has been strongly focused on maximising lithia recovery. The additional 5% spodumene recovery will significantly improve the overall project economics of the Manna Project through extra spodumene concentrate production and additional revenue generated for the same plant throughput.

The team believes there is further opportunity to increase lithia recovery through reducing slimes losses within the milling circuit. This will be examined over the coming months along with additional ore sorting trials.

Global Lithium will continue to progress the DFS and examine opportunities to further enhance the project economics through higher process recoveries and optimisation of the flowsheet to reduce overall capital and operating costs."

Approved by the board of Global Lithium Resources Limited.

For more information:

Ron Mitchell Managing Director info@globallithium.com.au +61 8 6103 7488

Ben Creagh Media & Investor Relations ben@nwrcommunications.com.au +61 (0) 417 464 233



About Global Lithium

Global Lithium Resources Limited (ASX:GL1, Global Lithium) is a diversified West Australian lithium exploration and development company with multiple assets in key lithium branded jurisdictions. It's primary focus is on the 100% owned Manna Lithium Project in the Goldfields and the Marble Bar Lithium Project (MBLP) in the Pilbara region, Western Australia.

Global Lithium has now defined a total Indicated and Inferred Mineral Resource of 54Mt @ 1.09% Li₂O at its Manna and MBLP Lithium projects, confirming Global Lithium as a significant global lithium player.

Directors

Geoff Jones	Non-Executive Chair
Ron Mitchell	Managing Director
Dr Dianmin Chen	Non-Executive Director
Greg Lilleyman	Non-Executive Director
Hayley Lawrance	Non-Executive Director

Project (equity)	Category	Million Tonnes (MT)	Li₂O%	Ta₂O₅ pp
Marble Bar	Indicated	3.8	0.97	53
)	Inferred	14.2	1.01	50
	Total	18.0	1.00	51
)				
Manna	Indicated	20.2	1.12	56
	Inferred	15.8	1.14	52
\ \	Total	36.0	1.13	54
Combined Total		54.0	1.09	53

Competent Persons Statement:

Metallurgical Testwork

The information in this announcement that relates to metallurgical testwork for the Manna Lithium Project is based on, and fairly represents, information and supporting documentation reviewed by Dr Tony Chamberlain, a full-time employee of Global Lithium Resources Limited and who participates in the Company's Incentive Performance Rights and Option Plan. Dr Chamberlain is a metallurgist and member of the Australasian Institute of Mining and Metallurgy. He has sufficient experience that is relevant on matters relating to mine development, testwork methodology and flowsheet development. Dr Chamberlain considers that the information in the market announcement is an accurate

Page 8 of 27 | ACN 626 093 150 | ASX: GL1 Level 1, 16 Ventnor Ave, West Perth, WA 6005 info@globallithium.com.au | www.globallithium.com.au



representation of the available data and studies for the mining project. Dr Chamberlain consents to the inclusion in this announcement of the matters based on his information in the form and context in which it appears.

Mineral Resources

Information on historical exploration results and Mineral Resources for the Manna Lithium Project presented in this announcement, together with JORC Table 1 information, is contained in an ASX announcement released on 26 July 2023.

Information on historical exploration results and Mineral Resources for the Marble Bar Lithium Project presented in this announcement is contained in an ASX announcement released on 15 December 2022

The Company confirms that it is not aware of any new information or data that materially affects the information in the relevant market announcements, and that the form and context in which the Competent Persons findings are presented have not been materially modified from the original announcements.

Where the Company refers to Mineral Resources for the Manna Lithium Project (MLP) in this announcement (referencing previous releases made to the ASX), it confirms that it is not aware of any new information or data that materially affects the information included in that announcement and all material assumptions and technical parameters underpinning the Mineral Resource estimate in that announcement continue to apply and have not materially changed. The Company confirms that the form and context in which the Competent Persons findings are presented have not materially changed from the original announcement.



Appendix 1.

The tables below show the drilling results returned from the recent Metallurgical and Ore Sorting Diamond core drill program. This program was specifically designed to drill down dip so a bulk sample of the pegmatite could be collected for metallurgical testing requirements. These results and the high-grade intercepts are not to be interpreted as true width of the deposit and have not been added to the resource model.

The results do show that the grade within the pegmatite is consistent with depth and of a higher grade than represented in the resource model. This is due to the natural dilution of Reverse Circulation (RC) drilling and the wider drill spacing.

Further close spaced infill drilling currently being performed at the Manna Lithium Deposit, is designed to improve the classification of the resource model and to bring the overall grade of the deposit more in line with the results observed in the tables below.

2	Hole ID	Drill Type	Easting (MGA50)	Northing (MGA50)	RL (m)	Dip (degrees)	Azimuth (degrees)	Depth (m)
$ \ge$	MDD0006	HQ	455541	6584419	426	-60	322	82
	MDD0008	HQ	455745	6584172	422	-60	324	108
	MDD0011	PQ	455558	6584515	423	-60	322	112
2	MDD0013	PQ	455352	6584265	421	-72	145	78
\subseteq	MDD0014	PQ	455687	6584608	420	-62	140	150
	MDD0015A	PQ	455624	6584557	424	-65	140	211
	MDD0016	PQ	455909	6584852	413	-80	135	156
)	MDD0017	PQ	456049	6584929	413	-78	140	132
\leq	MDD0018	PQ	455748	6584652	417	-60	140	183
)	MDD0019	PQ	455298	6584334	424	-71	150	199
	MDD0020	PQ	455349	6584393	423	-68	140	106
	MDD0021	PQ	455932	6584825	415	-68	140	121
5	MRCD0038	HQ	455788	6584491	417	-54	328	345
2	MRCD0039	HQ	455750	6584410	418	-53	326	390
\mathcal{D}	MRCD0045	HQ	455665	6584263	421	-52	324	522
	MRCD0047	HQ	456171	6584782	412	-57	321	432
	MRCD0056	HQ	455617	6584066	424	-56	318	621
	MRCD0057	HQ	455867	6584271	423	-60	322	625
7	MRCD0059	HQ	455886	6584491	417	-61	320	527
J	MRCD0090	HQ	456086	6584507	419	-58	328	630
	MRCD0104	HQ	455418	6584061	426	-58	327	585
	MRCD0109	HQ	455987	6584375	422	-56	329	545
	MRCD0133	HQ	456087	6584638	416	-55	315	503

Table 4: Metallurgical Drill Core Summary





Hole ID	Northing	Easting	From (m)	To (m)	Li2O (%)
MDD000	455544	0504440	40.00	40.40	4.00
MDD006	455541	6584419	40.29	43.40	1.29
MDD008	455745	6584172	36.26	39.68	1.41
and	455745	6584172	39.68	43.04	1.73
and	455745	6584172	43.04	46.41	1.89
and	455745	6584172	46.41	48.25	1.37
and	455745	6584172	154.80	158.31	1.83
and	455745	6584172	158.31	161.74	0.91
and	455745	6584172	161.74	165.41	1.70
MDD0011	455558	6584515	55.95	59.57	1.63
and	455558	6584515	59.57	63.10	1.56
and	455558	6584515	63.10	65.50	0.74
MDD0013	455352	6584265	2.18	4.56	1.43
and	455352	6584265	4.56	7.28	1.39
and	455352	6584265	7.28	9.80	1.35
and	455352	6584265	9.80	12.00	1.77
and	455352	6584265	12.00	14.62	1.69
and	455352	6584265	14.62	16.76	1.17
and	455352	6584265	16.76	19.55	1.44
and	455352	6584265	19.55	21.73	1.47
and	455352	6584265	21.78	23.80	1.56
and	455352	6584265	23.80	26.11	2.07
and	455352	6584265	26.11	28.47	1.90
and	455352	6584265	28.47	31.21	2.32
and	455352	6584265	31.21	33.78	1.88
and	455352	6584265	33.78	36.03	1.62
and	455352	6584265	36.03	38.85	1.51
and	455352	6584265	38.85	41.57	2.14
and	455352	6584265	41.57	44.22	1.55
MDD0014	455687	6584608	26.28	29.12	2.12
and	455687	6584608	29.12	31.67	2.17
and	455687	6584608	31.67	34.22	1.66
and	455687	6584608	52.66	55.40	2.04
and	455687	6584608	55.40	58.15	1.93
and	455687	6584608	58.15	60.90	1.96
and	455687	6584608	63.73	66.38	2.54
and	455687	6584608	66.38	69.20	2.24
and	455687	6584608	69.20	71.66	1.47
and	455687	6584608	71.66	74.30	1.54

Table 5: Expanded metallurgical and ore sorting drill hole intercepts



Hole ID	Hole ID Northing		From (m)	To (m)	Li2O (%)
and	455687	6584608	74.30	76.88	2.46
and	455687	6584608	76.88	79.52	1.72
and	455687	6584608	79.52	82.11	1.89
and	455687	6584608	87.51	90.28	1.52
and	455687	6584608	90.28	92.94	1.75
and	455687	6584608	92.94	95.53	1.92
and	455687	6584608	95.53	98.25	1.77
and	455687	6584608	108.77	111.40	0.37
and	455687	6584608	114.14	116.68	0.41
and	455687	6584608	116.68	119.53	1.61
and	455687	6584608	119.53	122.30	2.07
and	455687	6584608	122.30	125.04	1.51
and	455687	6584608	125.04	127.77	2.23
and	455687	6584608	127.77	130.41	2.40
and	455687	6584608	130.41	133.17	1.00
and	455687	6584608	133.17	135.82	1.19
and	455687	6584608	135.82	138.36	1.78
and	455687	6584608	138.36	140.75	1.61
and	455687	6584608	140.75	143.41	0.18
MDD0015A	455624	6584557	36.47	39.12	2.28
and	455624	6584557	39.12	41.82	1.53
and	455624	6584557	44.47	47.07	1.61
and	455624	6584557	47.07	49.88	1.94
and	455624	6584557	49.88	52.70	1.61
and	455624	6584557	52.70	55.37	1.11
and	455624	6584557	55.37	58.07	2.28
and	455624	6584557	58.07	60.76	2.17
and	455624	6584557	63.45	66.02	1.84
and	455624	6584557	66.02	68.68	1.46
and	455624	6584557	68.68	71.27	1.25
and	455624	6584557	71.27	73.95	0.24
and	455624	6584557	97.85	100.43	2.00
and	455624	6584557	100.43	103.02	1.68
and	455624	6584557	103.02	105.46	0.44
and	455624	6584557	113.15	115.83	0.59
and	455624	6584557	115.83	118.64	1.54
and	455624	6584557	118.64	121.31	1.89
and	455624	6584557	121.31	123.86	1.72
and	455624	6584557	123.86	126.56	2.55





Hole ID	Northing	Easting	From (m)	To (m)	Li2O (%)
and	455624	6584557	126.56	129.30	2.21
and	455624	6584557	129.30	132.03	1.43
and	455624	6584557	132.03	134.89	2.13
and	455624	6584557	134.89	137.68	2.02
and	455624	6584557	137.68	140.49	1.70
and	455624	6584557	140.49	143.18	2.42
and	455624	6584557	143.18	145.92	1.05
and	455624	6584557	145.92	148.59	1.46
and	455624	6584557	148.59	151.33	1.53
and	455624	6584557	151.33	154.00	1.29
and	455624	6584557	154.00	156.64	1.80
and	455624	6584557	156.64	159.29	1.77
and	455624	6584557	159.29	162.00	1.64
and	455624	6584557	162.00	164.81	1.42
and	455624	6584557	164.81	167.50	1.69
and	455624	6584557	167.50	170.29	1.81
and	455624	6584557	170.29	173.05	1.90
and	455624	6584557	173.05	175.85	1.34
and	455624	6584557	175.85	178.60	1.62
and	455624	6584557	178.60	181.28	1.15
and	455624	6584557	181.28	183.99	2.45
and	455624	6584557	183.99	186.61	2.10
and	455624	6584557	186.61	189.44	2.14
and	455624	6584557	189.44	192.15	1.62
and	455624	6584557	192.15	194.73	2.35
and	455624	6584557	194.73	197.21	1.54
and	455624	6584557	197.21	199.83	1.51
and	455624	6584557	199.83	202.47	0.73
and	455624	6584557	202.47	205.31	0.97
and	455624	6584557	205.31	207.94	1.28
MDD0016	455909	6584852	24.84	27.43	0.17
and	455909	6584852	27.43	30.13	1.78
and	455909	6584852	30.13	32.99	1.08
and	455909	6584852	32.99	35.66	0.67
and	455909	6584852	35.66	38.40	0.45
and	455909	6584852	38.40	40.99	1.20
and	455909	6584852	40.99	43.66	1.31
and	455909	6584852	43.66	46.45	0.82
and	455909	6584852	46.45	49.15	1.05



Hole ID	ole ID Northing		From (m)	To (m)	Li2O
			(111)	(111)	(70)
and	455909	6584852	49.15	51.86	0.97
and	455909	6584852	51.86	54.51	1.83
and	455909	6584852	54.51	57.07	1.88
and	455909	6584852	57.07	59.87	1.65
and	455909	6584852	59.87	62.49	1.90
and	455909	6584852	64.93	67.63	2.07
and	455909	6584852	67.63	70.28	1.41
and	455909	6584852	70.28	73.01	1.70
and	455909	6584852	73.01	75.21	2.27
and	455909	6584852	75.21	78.41	1.59
and	455909	6584852	78.41	81.29	1.27
and	455909	6584852	81.29	84.03	0.99
and	455909	6584852	84.03	86.72	1.17
and	455909	6584852	114.52	117.13	0.10
and	455909	6584852	117.13	119.64	0.20
and	455909	6584852	119.64	122.20	2.13
and	455909	6584852	122.20	124.85	1.88
and	455909	6584852	124.85	127.57	1.49
and	455909	6584852	127.57	130.40	2.35
and	455909	6584852	130.40	133.14	2.25
and	455909	6584852	133.14	135.98	2.00
and	455909	6584852	135.98	138.52	2.54
and	455909	6584852	138.52	141.16	1.62
and	455909	6584852	141.80	143.69	1.55
and	455909	6584852	148.92	151.69	0.09
MDD0017	456049	6584929	51.76	54.40	0.99
and	456049	6584929	54.40	57.14	0.81
and	456049	6584929	57.14	59.78	1.78
and	456049	6584929	59.78	62.52	1.15
and	456049	6584929	104.35	106.95	0.09
and	456049	6584929	106.95	109.75	0.31
and	456049	6584929	109.75	112.49	1.68
and	456049	6584929	112.49	115.22	1.79
and	456049	6584929	117.92	120.57	1.76
and	456049	6584929	120.57	123.45	1.46
and	456049	6584929	123.45	126.29	1.15
and	456049	6584929	126.29	128.96	1.47
and	456049	6584929	128.96	131.77	0.12
MDD0018	455748	6584652	26.14	28.10	0.02





Hole ID	Northing	Easting	From (m)	To (m)	Li2O (%)
and	455748	6584652	28.10	30.67	0.88
and	455748	6584652	30.67	33.10	1.51
and	455748	6584652	33.10	35.75	1.80
and	455748	6584652	35.75	38.34	2.51
and	455748	6584652	41.08	43.50	1.00
and	455748	6584652	43.50	46.12	1.27
and	455748	6584652	46.12	48.66	1.07
and	455748	6584652	48.66	51.37	0.01
and	455748	6584652	63.95	66.67	0.01
and	455748	6584652	66.67	69.41	0.48
and	455748	6584652	69.41	72.23	1.36
and	455748	6584652	72.23	74.85	1.92
and	455748	6584652	74.85	77.51	2.30
and	455748	6584652	77.51	80.00	2.26
and	455748	6584652	80.00	82.55	2.60
and	455748	6584652	82.55	85.27	2.62
and	455748	6584652	85.27	88.01	1.45
and	455748	6584652	88.01	90.52	1.98
and	455748	6584652	90.52	93.22	1.10
and	455748	6584652	93.22	95.91	1.43
and	455748	6584652	129.58	132.20	0.01
and	455748	6584652	132.20	134.57	0.20
and	455748	6584652	134.57	137.06	1.27
and	455748	6584652	137.06	139.32	1.27
and	455748	6584652	139.30	141.96	0.54
and	455748	6584652	141.96	144.59	1.01
and	455748	6584652	144.59	147.29	0.43
and	455748	6584652	149.88	152.54	1.77
and	455748	6584652	152.54	155.14	2.47
and	455748	6584652	155.15	157.71	1.06
and	455748	6584652	157.71	160.42	0.77
and	455748	6584652	160.42	163.07	0.42
and	455748	6584652	163.07	165.82	1.40
and	455748	6584652	165.82	168.35	1.45
and	455748	6584652	168.35	171.09	1.26
and	455748	6584652	171.09	173.72	1.85
MDD0019	455349	6584393	22.74	24.83	1.15
and	455349	6584393	24.83	27.75	1.68
and	455349	6584393	27.75	30.06	1.88



Hole ID	Northing	Easting	From (m)	To (m)	Li2O (%)
and	455349	6584393	30.06	32.33	1.30
and	455349	6584393	32.33	34.87	1.38
and	455349	6584393	34.87	37.56	2.00
and	455349	6584393	37.56	40.25	0.93
and	455349	6584393	40.25	42.92	1.02
and	455349	6584393	53.28	56.00	2.07
and	455349	6584393	56.00	58.59	1.83
and	455349	6584393	58.59	61.29	1.80
and	455349	6584393	64.00	66.26	1.50
and	455349	6584393	66.26	69.09	1.75
and	455349	6584393	69.08	71.78	2.11
and	455349	6584393	74.25	76.85	0.98
and	455349	6584393	76.85	79.61	1.98
and	455349	6584393	79.61	82.24	1.96
and	455349	6584393	82.24	84.93	2.26
and	455349	6584393	84.93	87.61	1.52
and	455349	6584393	87.61	90.42	1.67
and	455349	6584393	90.42	93.14	1.57
and	455349	6584393	93.14	95.90	1.58
and	455349	6584393	95.90	98.52	1.60
and	455349	6584393	98.52	101.15	2.07
and	455349	6584393	101.15	103.86	1.28
and	455349	6584393	103.86	106.57	1.66
and	455349	6584393	106.57	109.31	1.18
and	455349	6584393	114.40	117.16	2.14
and	455349	6584393	117.16	120.02	1.88
and	455349	6584393	120.02	122.80	1.87
and	455349	6584393	122.80	125.47	2.06
and	455349	6584393	125.47	128.13	2.43
and	455349	6584393	128.13	130.70	3.47
and	455349	6584393	130.70	133.37	2.27
and	455349	6584393	133.37	136.04	1.61
and	455349	6584393	136.04	138.65	0.64
and	455349	6584393	138.65	141.32	1.32
and	455349	6584393	141.32	144.07	1.91
and	455349	6584393	144.07	146.98	1.82
and	455349	6584393	149.98	149.72	0.84
and	455349	6584393	149.72	152.26	1.04
and	455349	6584393	152.26	155.15	0.88



Page 16 of 27 | ACN 626 093 150 | ASX: GL1 Level 1, 16 Ventnor Ave, West Perth, WA 6005 info@globallithium.com.au | www.globallithium.com.au



Hole ID	Northing	Easting	From (m)	To (m)	Li2O (%)
and	455240	6594202	155 15	157.80	1.03
and	455349	0004393	157.80	160 50	0.68
and	455349	0504393	160.50	163.16	1.53
and	455349	0004393	163.16	165.89	0.96
and	400349	0004393	165.89	168.22	1 15
and	455349	6584393	168.22	171.09	1.13
and	455349	6584393	171.00	173.70	1.04
and	455349	6584393	171.09	176.43	1.00
and	455349	6584393	175.70	170.43	1.00
and	455349	6584393	170.43	179.23	1.00
and	455349	6584393	179.23	102.00	1.02
and	455349	6584393	182.00	184.76	1.25
and	455349	6584393	184.76	187.44	0.70
and	455349	6584393	187.44	190.22	1.54
and	455349	6584393	190.22	192.70	0.70
and	455349	6584393	192.70	195.38	0.97
MDD0020	455349	6584393	15.46	17.74	0.78
and	455349	6584393	17.74	19.90	1.13
and	455349	6584393	19.90	22.01	1.70
and	455349	6584393	22.01	24.40	1.57
and	455349	6584393	24.40	26.66	2.11
and	455349	6584393	26.66	29.51	1.51
and	455349	6584393	29.51	32.49	0.89
and	455349	6584393	32.49	34.92	0.01
and	455349	6584393	66.53	69.19	1.00
and	455349	6584393	69.19	71.78	1.55
and	455349	6584393	71.78	74.29	1.62
and	455349	6584393	74.29	76.85	1.76
and	455349	6584393	76.85	79.58	2.11
and	455349	6584393	82.28	84.98	1.65
and	455349	6584393	84.98	87.47	1.72
and	455349	6584393	87.47	90.09	1.47
and	455349	6584393	92.79	95.25	0.01
MDD0021	455932	6584825	37.06	39.62	0.80
and	455932	6584825	39.62	42.19	1.45
and	455932	6584825	42.19	44.86	0.65
and	455932	6584825	44.86	47.91	0.59
and	455932	6584825	47.91	49.90	1.39
and	455932	6584825	71.14	72.80	0.16
and	455932	6584825	72.80	76.21	0.16





Hole ID	Northing	Easting	From (m)	To (m)	Li2O (%)
and	455932	6584825	76.21	78.39	0.20
and	455932	6584825	78.39	80.94	0.65
and	455932	6584825	80.94	83.52	0.74
and	455932	6584825	85.91	88.19	0.27
and	455932	6584825	88.19	90.48	0.15
MRCD0038	6584490.76	455787.63	136.73	143.93	1.48
and	6584490.76	455787.63	148.96	152.81	1.72
and	6584490.76	455787.63	160.38	167.10	1.73
and	6584490.76	455787.63	176.00	178.00	0.51
and	6584490.76	455787.63	292.45	297.95	0.60
and	6584490.76	455787.63	313.2	320.08	1.50
MRCD0039	6584410.26	455750.47	133.00	136.00	0.84
and	6584410.26	455750.47	163.78	167.78	1.47
and	6584410.26	455750.47	169.97	171.13	1.52
and	6584410.26	455750.47	175.58	177.00	0.46
and	6584410.26	455750.47	196.46	209.68	1.52
and	6584410.26	455750.47	284.89	291.58	1.72
and	6584410.26	455750.47	351.91	366.27	1.03
MRCD0045	6584262.77	455664.68	227.57	229.19	1.46
and	6584262.77	455664.68	232.12	234.00	0.67
and	6584262.77	455664.68	237.00	239.48	1.09
and	6584262.77	455664.68	241.82	242.88	1.30
and	6584262.77	455664.68	250.00	253.96	0.69
and	6584262.77	455664.68	285.38	286.92	0.64
MRCD0047	6584781.67	456171.04	278.96	280.61	1.04
and	6584781.67	456171.04	287.62	289.95	0.55
and	6584781.67	456171.04	308.00	309.80	0.70
and	6584781.67	456171.04	312.56	317.07	1.14
and	6584781.67	456171.04	333.61	339.15	1.21
MRCD0056	6584066.25	455617.14	43.00	52.00	0.55
and	6584066.25	455617.14	60.00	65.00	0.99
and	6584066.25	455617.14	451.78	453.00	0.56
MRCD0057	6584271.23	455866.79	87.00	89.00	1.33
and	6584271.23	455866.79	106.00	107.00	0.83
and	6584271.23	455866.79	111.00	112.00	1.23
and	6584271.23	455866.79	391.20	393.00	0.78
and	6584271.23	455866.79	410.68	412.00	0.43
and	6584271.23	455866.79	427.00	428.20	0.42
and	6584271.23	455866.79	601.02	602.04	0.41



Hole ID	Northing	Easting	From (m)	To (m)	Li2O (%)
MRCD0059	6584491.3	455886.38	187.22	192.80	1.40
and	6584491.3	455886.38	207.57	210.00	1.52
and	6584491.3	455886.38	227.76	235.97	1.51
and	6584491.3	455886.38	252.49	256.75	1.79
and	6584491.3	455886.38	283.68	293.11	1.18
and	6584491.3	455886.38	302.00	303.17	0.66
MRCD0090	6584507.29	456086.28	114.00	115.00	0.53
and	6584507.29	456086.28	462.23	471.24	1.00
MRCD0104	6584060.52	455417.77	276.56	279.61	0.48
and	6584060.52	455417.77	354.00	355.99	0.58
and	6584060.52	455417.77	385.00	386.00	0.79
MRCD0109	6584375.01	455987.43	97.00	99.00	0.55
and	6584375.01	455987.43	111.00	112.00	1.08
and	6584375.01	455987.43	512.91	514.8	1.11
MRCD0133	6584637.69	456086.94	188.00	192.00	0.44
and	6584637.69	456086.94	306.15	312.58	1.50
and	6584637.69	456086.94	341.59	351.00	1.69



Page 19 of 27 | ACN 626 093 150 | ASX: GL1 Level 1, 16 Ventnor Ave, West Perth, WA 6005 info@globallithium.com.au | www.globallithium.com.au

JORC Code, 2012 Edition – Table 1 Report

Section 1 Sampling Techniques and Data (Criteria in this section apply to all succeeding sections)

Criteria	JORC Code explanation	Commentary	,			
Sampling techniques	 Nature and quality of sampling (eg cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling. Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used. Aspects of the determination of mineralisation that are Material to the Public Report. In cases where 'industry standard' work has been done this would be relatively simple (eg 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information. 	 Diamond of for metallution Selected of Perth whe sampled, of Select intercrushed and to 80% particles of the sentence of the sample of the sentence of the sentence	drilling was urgical test core was su- re it was et crushed an ervals of cu- nd riffle spl ssing 75 m sodium per ric acid. Th by ICP by a y in Perth. y technique d used offe ad is useful digestions cal Compo 0-350 kg me erated from arse graine low-grade, G) sample, one 2). les consist six Manna , 39, 45, 47 d in pallets Perth. composite na diamon f through th tions at the , Western / Zone 1 – From	undertaker work and o ubmitted to xamined an id assayed. t 1/4 core s it to 2 to 2.8 icrons. Pre- eroxide and he resultant linning Test is consider ers total diss for mineral site Sample etallurgical HQ core, r d spodume fine graine and a fine ed of repress Lithium Pro- 7, 59 and 13 and consig samples ge d cores we he proposed Nagrom te Australia. High Grad	n to produce co re sorting testv laboratories in id then cut, amples were 5 kg for pulveri- epared samples digested in dil solution is ting and Inspector red to be robust solution of the matrices that n es: composite sam epresenting a ne (Zone 1 HG ad spodumene grain spodume sentative HQ fu bject diamond of 33) that was ned to the Nag enerated from re individually d WOO flowsho est facility in e Metres	ore vork. sing s are ute ction st as may high- b ene ull cores grom

MRCD38

MRCD38

MRCD38

MRCD39

MRCD39

Page 20 of 27 | ACN 626 093 150 | ASX: GL1

Level 1, 16 Ventnor Ave, West Perth, WA 6005 info@globallithium.com.au | www.globallithium.com.au



5.65

4.01

7.42

8.63

14.08

39.79

142.15

153.20

167.10

171.13

210.08

Total

136.50

149.19

159.68

162.50

196.00

TP

JORC Code explanation

Commentary

Zone 1 – Low Grade					
From	То	Metres			
292.00	297.95	5.95			
312.00	320.50	8.50			
284.40	291.70	7.30			
351.60	367.50	15.90			
232.00	239.48	7.48			
249.80	254.30	4.50			
Total 49.63					
	Zone 1 – From 292.00 312.00 284.40 351.60 232.00 249.80	Zone 1 – Low Grade From To 292.00 297.95 312.00 320.50 284.40 291.70 351.60 367.50 232.00 239.48 249.80 254.30 Total			

Zone 2				
Hole ID	From	То	Metres	
MRCD47	310.00	317.23	7.23	
MRCD47	333.20	338.28	5.08	
MRCD59	186.30	193.10	6.80	
MRCD59	207.50	212.00	4.50	
MRCD59	227.50	235.98	8.48	
MRCD59	252.49	256.75	4.26	
MRCD59	283.68	293.71	10.03	
MRCD133	305.80	313.60	7.80	
MRCD133	341.50	352.00	10.50	
Total 64.68				

Drilling • techniques	 Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face- sampling bit or other type, whether core is oriented and if so, by what method, etc). 	 Diamond drilling used PQ and HQ2 dependent upon ground conditions. All PQ diamond drill holes were angled at approximately -60 to -80 degrees and aligned to drill down dip to the pegmatite. HQ2 core was obtained from previous resource drilling and is described in the announcement title "Manna Lithium Project Resource Grows" on 26 July 2023.
Drill sample recovery	 Method of recording and assessing core and chip sample recoveries and results assessed. Measures taken to maximise sample recovery and ensure representative nature of the samples. 	 The diamond drill core recovered is physically measured by tape measure and the length recovered is recorded for every run. Core recovery is calculated as a percentage recovery. This is confirmed by Company geologists during core orientation activities on site.

There is no observable relationship between • recovery and grade, or preferential bias in the



Page 21 of 27 | ACN 626 093 150 | ASX: GL1 Level 1, 16 Ventnor Ave, West Perth, WA 6005 info@globallithium.com.au | www.globallithium.com.au

•

Whether a relationship exists

between sample recovery and grade

Criteria	JORC Code explanation	Commentary
	and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.	drilling at this stage.
Logging	 Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies. Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography. The total length and percentage of the relevant intersections logged. 	 Drillholes were logged for lithology, alteration, mineralisation, structure, weathering, wetness and obvious contamination by a geologist. Data was then captured in a database.
Sub- sampling techniques and sample preparation	 If core, whether cut or sawn and whether quarter, half or all core taken. If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry. For all sample types, the nature, quality and appropriateness of the sample preparation technique. Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples. Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling. Whether sample sizes are appropriate to the grain size of the material being sampled 	 Half core samples were taken, generally on 1 m intervals or on geological boundaries where appropriate (minimum 0.08m to maximum of 1.36m). The samples were sent to accredited laboratories for sample preparation and analysis. All samples were sorted, dried pulverised to 75 µm to produce a homogenous representative subsample for analysis. A grind quality target of 85% passing -75 µm has been established.
Quality of assay data and laboratory tests	 The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total. For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc. Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been established. 	 Exploration assaying Exploration assaying The industry standard assay techniques are considered to be robust as the methods used offers near (4-Acid) to total dissolution (Sodium Peroxide Fusion) of the samples. For lithium exploration drilling field inserted standards are utilitsed for 1 sample in every 50. For lithium exploration drilling field duplicate samples are taken for 1 sample in every 50. Metallurgical sample assays Nagrom Laboratory prepared metallurgical samples using a fusion with sodium peroxide and digested in dilute hydrochloric acid. The resultant solution is analysed by ICP. This method offers total dissolution of the sample and is useful for mineral matrices that may resist



Criter	a JORC Code explanation	Commentary
		acid digestions. Samples are fused and digested in Alumina crucibles, as a result, Al is not able to be analysed using this method. Nagrom laboratory periodically run replicates, blanks and at least 2x matrix matched standards with every submission as part of their QA/QC.
		Li2O standards used are:
		 OREAS750 STD OREAS999 STD AMIS0355 STD TAN1 STD This assay technique is considered to be robust as the method used offers total dissolution of the sample and is useful for mineral matrices that may resist acid digestions. Li, Rb and Th are measured by ICP. Multielement analysis is performed at Nagrom by fusion with lithium borate flux with lithium nitrate additive. The resultant glass bead is analysed by XRF. XRF is suitable for the total analysis of a range of geological ores. XRF Suites are tailored to specific ore types, using predefined inter-element and matrix corrections. Loss on Ignition (LOI) is packaged with XRF suites to allow the determination of oxide totals: Si, Al, Fe, K, Na, Ca, Mg, Cu, Ni, Mn, P, Ti, Nb, Sn, Cr, Co, Ba, Zn, As, Cl, Ta, S and Pb.
Verific of sampl and assay	 The verification of significant intersections by either independent or alternative company personnel. The use of twinned holes. Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols. Discuss any adjustment to assay data. 	 Results were verified by alternative personnel at Global Lithium Twin holes have been drilled at Manna lithium project in both RC and DD to allow correlation of the assay results between drilling styles and to provide more confidence in the resource model. Primary geological and sampling data were recorded digitally and on hard copy respectively and were subsequently transferred to a digital database where it is validated by experienced database personnel assisted by the geological staff. Assay results are merged with the primary data using established database protocols. Global Lithium has not adjusted any assay data, other than to convert Li (ppm) to Li2O (%).
Locati data p	 Accuracy and quality of surveys used to locate drill holes (collar and down- hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation. Specification of the grid system used. Quality and adequacy of topographic control. 	 A handheld global positioning system (GPS) was used to initially record drillhole locations (±5 m accuracy), followed by a differential GPS surveyor pickup. Downhole survey measurements taken at 10 m intervals for RC drillholes and at an average interval of 5 m for diamond drillholes. GDA94 (MGA) Zone 50 Southern Hemisphere Topographical data provided on a 1 m by 1 m



	Criteria	JORC Code explanation	Commentary
			spatial resolution grid.
	Data spacing and distribution	 Data spacing for reporting of Exploration Results. Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied. Whether sample compositing has been applied. 	 The Manna deposit has been drilled at a spacing of around 80 m along strike by 40 m across strike and 40 m x 40 m within the main central zone. Drill spacing is appropriate for the Mineral Resource estimation and classification applied. Samples were not composited except for metallurgical test work.
	Orientation of data in relation to geological structure	 Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type. If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material. 	 No orientation data was collected as the drilling was down Dip and not used in a resource model.
U	Sample security	• The measures taken to ensure sample security.	• The diamond core samples are taken from the drilling rig by experienced personnel, stored securely and transported to the laboratory by a registered courier and handed over by signature.
	Audits or reviews	 The results of any audits or reviews of sampling techniques and data. 	 Data inputs and outputs have been reviewed and verified by Global Lithium and Steiner No audits have been undertaken to date.

Section 2 Reporting of Exploration Results

(Criteria listed in the preceding section also apply to this section.)

_	Criteria	JORC Code explanation	Commentary
	Mineral tenement and land tenure status	 Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings. The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area. 	 The Manna Lithium deposit is situated entirely within tenement WA exploration licence E28/2522 and E38/2551 All tenure is wholly owned by Global Lithium Resources Limited. The portfolio of mineral tenements, comprising two granted exploration licences are in good standing.

Page 24 of 27 | ACN 626 093 150 | ASX: GL1 Level 1, 16 Ventnor Ave, West Perth, WA 6005 info@globallithium.com.au | www.globallithium.com.au



Criteria	JORC Code explanation	Commentary
Exploration done by other parties	• Acknowledgment and appraisal of exploration by other parties.	 Mineral exploration over the Eastern Kalgoorlie project area has been undertaken for a number of commodities, including gold, base metals, diamonds, tin and tantalum by various companies since the 1960s. Breaker Resources performed a basic mapping and geochemical sampling program over the area before running a small RC drilling program of 23 holes totalling 3428m that defined the Manna Lithium deposit. After acquiring the project in 2021, GL1 has completed two large RC and Diamond drilling campaigns with the last Mineral Resource Estimate released on 26 July 2023.
Geology	• Deposit type, geological setting and style of mineralisation.	 Typical LCT pegmatite model occurring as swarms of dykes in a preferred corridor orientation. Within this area, the Company has discovered the Manna deposit, comprising a series of steeply dipping pegmatite bodies with lithium mineralisation predominantly by way of spodumene hosted pegmatites. These pegmatites have been the focus of exploration by the Company.
Drill hole Information	 A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes: easting and northing of the drill hole collar elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar dip and azimuth of the hole down hole length and interception depth hole length. If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case. 	 Collar locations (easting and northing) for the metallurgical holes is provided in Appendix 1 of this announcement.
Data aggregation methods	 In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (eg cutting of high grades) and cut-off grades are usually Material and should be stated. Where aggregate intercepts 	 Not relevant – exploration results are not being reported; a Mineral Resource has been defined.



Criteria	JORC Code explanation	Commentary
	 incorporate short lengths of high grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail. The assumptions used for any reporting of metal equivalent values should be clearly stated. 	
Relationship between mineralisation widths and intercept lengths	 These relationships are particularly important in the reporting of Exploration Results. If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported. If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (eg 'down hole length, true width not known'). 	 Not relevant – exploration results are not being reported; a Mineral Resource has been defined.
Diagrams	 Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views. 	 Not relevant – exploration results are not being reported; a Mineral Resource has been defined
Balanced reporting	Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.	 Not relevant – exploration results are not being reported; a Mineral Resource has been defined.
Other substantive exploration data	Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.	 Metallurgical data compiled and presented in this release is based on testwork performed predominately at Nagrom, on metallurgical domain composite samples as described in this release, with individual HQ and PQ core samples also utilised to generate comminution circuit design data. The following metallurgical testing has been performed: Comminution – UCS, UCS-E, CWi, SMC, Ai, BBWi and BRWi Magnetic separation via LIMS and WHIMS, utilising a range of Gauss settings from 1200 to 10,000G Desliming via 2-stage cycloning utilising 2 inch stub cyclones Mica Prefloat utilising 2.5L laboratorv-scale

 Mica Prefloat utilising 2.5L laboratory-scale Denver cells, using a range of reagents and

Criteria	JORC Code explanation	Commentary
		 operating conditions. Spodumene flotation utilising 2.5L laboratory-scale Denver cells, using a range of reagents and operating conditions. It is important to note that testwork is ongoing, and that the results presented in this release have not yet been fully optimised, and that no variability testwork has as yet been completed to establish the impact, if any, of ore variability within the Manna deposit on the findings of testwork results to date.
Further work	 The nature and scale of planned further work (eg tests for lateral extensions or depth extensions or large-scale step-out drilling). Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive. 	 An ore variability testwork program is planned to determine the impact of lateral and depth extensions of the Manna lithium deposit on process design, lithia recovery and impurity deportment.



Page 27 of 27 | ACN 626 093 150 | ASX: GL1 Level 1, 16 Ventnor Ave, West Perth, WA 6005 info@globallithium.com.au | www.globallithium.com.au